

No.	Wid.	As	As	Fe	Zn
H116	3.0	.05	0.20	2.5	1.3

No.	Wid.	As	As	Fe	Zn
H120	2.0	.24	2.35	3.0	.78
H121	2.5	.12	1.0	1.4	5.0
H122	4.0	.28	3.2	3.6	5.3
H123	3.0	.08	1.7	4.3	2.4
H124	2.5	.14	1.5	3.3	5.1
H125	2.0	.12	3.1	5.4	0.8
H126	3.3	.22	2.7	3.9	10.4

No.	Wid.	As	As	Fe	Zn
H127	2.0	.02	0.5	0.55	0.4
H128	3.0	.15	0.6	0.3	0.4
H129	3.0	.10	0.35	0.3	0.4
H130	3.0	.12	7.6	12.3	9.3
H131	3.0	.06	0.75	0.9	0.25

C.M.S. Co. Sampling

Wid.	As	As	Fe	Zn
3.0	.23	.71	2	2.2
4.0	.26	2.34	8.6	1.26
6.0	.26	.44	0	0.6
6.0	.12	.42	0	3.0
7.5	.37	.33	0	1.70
6.0	.16	.170	0	1.02
7.0	.10	.08	0	0.7
7.0	.06	.08	0	0.50
6.5	.08	.05	0	12.3
7.0	.08	.118	0	6.7
6.5	.22	3.67	0	6.7
2.0	.05	.30	0	2.2
3.0	.06	.7	0	4.2
4.0	.43	1.76	0	4.4
7.0	.23	.47	0	3.8
9.0	.33	.07	0	6.6
6.0	.27	.68	0	9.0
3.5	.55	0.43	7.3	15.1
5.0	.20	.28	0	3.7
11.0	.18	.76	0	6.5
8.0	.54	2.86	5.0	3.0
2.5	.74	0.16	12.0	7.5
6.0	.41	0.05	10.3	6.6
6.5	.29	0.00	0	6.5
6.5	.70	0.10	2.0	6.8
5.5	1.0	1.00	1.0	6.0
5.0	.10	1.59	0	5.5
7.0	.34	1.25	0	3.0
7.0	.20	3.32	2.3	5.6
4.0	.40	2.40	0	4.0
4.0	.00	.97	0	9.0
4.5	.16	.00	0	9.5
6.0	.12	.77	0	6.0
7.0	.05	.00	0	7.0
8.0	.09	.47	0	8.0
15.0	.00	.21	0	15.0
9.5	.08	.31	0	9.0
5.0	.18	1.44	0	5.0
5.0	.21	1.80	0	5.0
6.0	.37	3.70	0.5	6.0
6.2	2.74	1.46	1.4	8.4

NO. 1 TUNNEL

No. 1 Tunnel moved 20' from its correct position with reference to No. 2 Tunnel.

Upper Tunnel Average  
Wid. As Fe Zn  
4.5 .25 .23 3.0 7.4

NO. 2 TUNNEL

No. 2 Tunnel moved 100' from its correct position with reference to No. 3 Tunnel.

Wid. As Fe Zn

3.5	.09	2.24	0	2.1
3.5	.31	2.74	0	3.7
3.5	.29	4.33	7.0	8.9
5.0	.09	4.02	9.5	15.0
6.0	.04	.65	0	11.5
6.0	.10	.56	0	2.7
5.0	.14	2.05	0	3.1
5.0	.16	1.60	0	4.0
3.5	.139	4.13	0	4.0

C.M.S. Co. Sampling  
Avg. 4.5 .187 1.92 2.9 7.0

SEPARATE LEVEL MAP  
HOWARD MINE

Y.M.R., B.C.

SCALE: 1" = 30'



LEGEND:

- GRANITE
- QUARTZITE & ARGILLITE
- LAMPROPHYRE
- ORE
- FAULT

NO. 3 TUNNEL

Property File  
82FSW199