

A

PUREX LIME (LOT 9056 - 1.25 MILES NORTHEAST 4
NELSON)

OFFICE OF THE CHIEF ANALYST AND ASSAYER



COPY
001928
Y

Property File

082 FSW 253

DEPARTMENT OF MINES
VICTORIA

cc: Mr. Hughes.

SAMPLE RECEIVED FROM..... Mr. J. W. Peck,
Inspector of Mines,
105 Medical Arts Building,
Nelson, B.C.
ADDRESS.....

LABORATORY No.	SUBMITTER'S MARK	LABORATORY REPORT		
		ASSAYS		
		<u>Acid-soluble Calcium Oxide Per Cent</u>	<u>Acid-soluble Magnesium Oxide Per Cent</u>	<u>Acid-Insoluble Matter Per Cent</u>
6320M	Hole 1 Sample 1	49.2	1.2	8.6
6321M	Hole 1 Sample 2	28.2	2.8	38.2
6322M	Hole 1 Sample 3	47.1	1.1	12.2
6323M	Hole 1 Sample 4	46.1	1.6	12.8
6324M	Hole 1 Sample 5	34.2	2.8	28.7
6325M	Hole 1 Sample 6	55.6	0.4	0.6
6326M	Hole 1 Sample 7	52.6	0.9	4.1
6327M	Hole 1 Sample 8	31.0	21.4	0.8
6328M	Hole 2 Sample 9	50.6	2.8	3.5
6329M	Hole 2 Sample 10	14.7	2.8	56.3
6330M	Hole 2 Sample 11	47.2	4.8	4.1
6331M	Hole 2 Sample 12	10.3	3.0	60.1
6332M	Hole 2 Sample 13	30.1	2.5	35.9
(cont'd.)				

THIS DOCUMENT, OR ANY PART THEREOF, MAY NOT BE REPRODUCED
FOR PROMOTIONAL OR ADVERTISING PURPOSES.

DATE..... March 1, 1955.

cc: March 26, 1956.

GCB Lam

CHIEF ANALYST AND ASSAYER.

OF THE CHIEF ANALYST AND ASSAYER

c
o
p
y

DEPARTMENT OF MINES
VICTORIA

2.

SAMPLE RECEIVED FROM.....
Mr. J. W. Peck,

ADDRESS.....
Nelson, B.C.

LABORATORY No.	SUBMITTER'S MARK	LABORATORY REPORT		
		Acid-soluble Calcium Oxide Per Cent	Acid-soluble Magnesium Oxide Per Cent	Acid-insoluble Matter Per Cent
6333M	Hole 2 Sample 14	6.8	1.5	79.5
6334M	Hole 2 Sample 15	20.2	3.3	50.4
		<u>Conversion Factors</u> 1% Calcium Oxide is equivalent to 1.785% Calcium Carbonate. 1% Magnesium Oxide is equivalent to 2.092% Magnesium Carbonate.		

THIS DOCUMENT, OR ANY PART THEREOF, MAY NOT BE REPRODUCED
FOR PROMOTIONAL OR ADVERTISING PURPOSES.

DATE.....
March 1, 1955.

G. B. Lane

CHIEF ANALYST AND ASSAYER.