

NOTES on PLAN showing ORE SHOOTS with places sampled, No. 6 Tunnel,  
GIANT MINE, Spillimachene, B.C.

Oct. 6/29

Nov. 4/29.

Scale 10 Feet - One Inch

82K/16W  
82K/15-18

SAMPLING RECORD (all measurements from H.W.)  
Samples taken every 5 ft. except 248,  
258

On Right side at 7'9" stringer of Chalcopyrite.

Samples 170-176 - Not worth assaying, Practically barren of values,  
30' width.

ASSAYS			Sample	Interval	Description
oz.	%	%			
Silver	Lead	Copper			
1.0	1.5	0.4	236	31' to 36'	Discarded sample.
			237	36' to 41'	" "
			238	41' to 46'	Barytes & small % galena. Discarded.
			239	46' to 51'	" " " " " "
2.0	2.6	1.0	240	51' to 56'	Quartz, diorite, iron pyrite, little galena.
1.4	1.3	1.1	241	56' to 61'	Quartz, diorite, iron pyrite, little galena.
1.1	0.4	1.5	242	61' to 66'	Quartz, diorite, iron pyrite, chalcopyrite.
1.0	21.1	0.2	243	66' to 71'	Quartz, iron sulphide, chalcopyrite
	discarded		244	71' to 76'	Quartz, barytes, galena
	"		245	76' to 81'	Barytes, small % galena. Discarded.
			246	81' to 86'	" " " " " "
0.7	15.6	Trace	247	86' - 96'10"	Blocky Slate
1.0	11.1	0.2	248	96'10" - 101'6"	Barytes, quartz, galena.
				101'6" - 104'	Barytes, quartz, galena.

On Left side of tunnel -

The first 30' was sampled and discarded.

				30' to 41'	Sampled and discarded.
discarded			249	41' to 46'	Mostly lime. Discarded.
"			250	46' to 51'	quartz & lime, small % galena.
.05	5.4	0.1	251	51' to 56'	" " ", barytes, some galena.
discarded			252	56' to 61'	Slate, & a very small % galena.
"			253	61' to 66'	Crushed slate
1.4	0.3	1.1	254	66' to 71'	Iron sulphide, barytes, chalcopyrite.
1.2	2.1	1.0	255	71' to 76'	Quartz, iron sulphide, small % galena
1.0	5.2	0.5	256	76' to 81'	" " chalcopyrite, galena.
0.7	6.5	0.1	257	81' to 86'	Quartz, iron sulphide, galena, barytes
0.8	5.5	0.3	258	86' to 88'6"	Barytes, iron sulphide, galena
				88'6" to 106'	Blocky slate, mostly barren of ore
1.2	0.8	0.5 in	(259	61' to 66'	In roof, iron sulphide, crushed slate, and galena.
		roof			
1.8	1.0	2.1	(260	66.0 to 71'	In roof, iron sulphide, and some chalcopyrite
0.8	3.1	0.3	(261	71.0 to 76'	In roof, barites & galena.

NOTE: The Width of 6'0" in the 10' lens carrying 1% copper.  
This is the average of 254, 255, 256, 259, 260, 261,  
241, 242, 243.

"J.L.Parker"  
Mining Engineer.

