

PLAN No 4


ASSAY PLAN OF THE 2ND & 3RD LEVELS OF THE TRUE FISSURE MINE

Scale 1"=40' April 21st 1949

To accompany report of David A. Sloan.

David A. Sloan

NOTE: The widths of horizontal and vertical samples have been adjusted to represent true vein widths.



SAMPLE No	W FT.	Au. Oz.	Ag. Oz.	Pb %	Zn %
C2743	6.4	0.06	10.89	7.02	4.30
R2602	3.0	0.01	0.28	TR	0.30
R2603	4.5	0.015	1.35	0.80	1.60
R2604	3.5	TR	0.35	TR	TR
C2747	4.1	0.08	0.32	3.45	0.50
C2746	3.5	0.10	21.60	16.00	11.60
C2745	2.1	0.10	32.40	40.50	9.80
C2744	3.5	0.04	10.00	2.05	17.00
R2617	5.3	0.06	5.20	6.58	9.50
R2618	4.6	0.10	4.72	4.42	4.90
R2622	4.8	0.08	12.00	9.72	10.50
R2620	3.0	0.08	3.84	6.80	10.50
R2621	5.7	0.01	1.44	1.18	0.40
R2619	6.0	0.00	4.80	2.26	0.70

W FT.	Au. Oz.	Ag. Oz.	Pb %	Zn %	Cu %	SAMPLE No
4.2	TR	0.08	TR	TR	0.10	C2701
4.2	TR	TR	0.11	TR	0.10	C2702
3.5	0.005	TR	TR	TR	0.10	C2703
3.5	TR	TR	TR	TR	0.05	C2704
3.2	0.01	0.04	TR	TR		D2922
3.1	0.03	5.20	2.20	10.00		D2923
3.8	0.04	1.04	0.70	0.30		C2742
3.1	0.02	0.08	TR	TR		D2924
3.8	0.01	0.60	TR	TR		D2925
2.5	0.01	0.32	TR	TR		D2926
2.8	0.01	0.40	TR	TR		D2927
2.8	0.005	0.92	TR	TR		D2918
3.1	0.01	0.40	TR	TR		D2917
3.8	TR	0.16	TR	TR		D2916
6.0	0.02	14.00	9.07	10.30	0.45	I2805
2.0	0.10	5.60	2.64	2.20	0.40	I2801
2.4	0.06	3.76	4.42	0.80	0.40	C2710
3.5	0.02	2.60	2.16	4.30	0.20	C2709
4.1	0.04	6.00	3.02	4.10	0.30	C2708
5.2	0.12	13.90	8.74	3.50	1.20	C2707
2.6	0.10	2.48	2.59	0.80	0.15	C2706
3.5	0.005	0.08	TR	TR	0.05	C2705
6.3	0.02	4.46	1.62	2.20		R2605
6.2	0.03	12.00	12.36	5.00	0.90	R2606
6.8	0.03	2.96	2.48	1.50	0.15	I2802
3.5	0.02	1.60	1.08	1.20		D2946
4.2	TR	0.80	0.54	0.40		D2947
3.0	0.005	0.10	TR	TR	0.05	C2716
3.2	0.005	0.20	0.65	0.70	0.10	C2715
3.0	0.005	0.95	0.86	0.80	0.10	C2714
3.0	0.01	1.20	0.79	2.50	0.0	C2713
3.0	0.06	2.20	2.05	8.00	0.20	C2712
3.5	0.06	2.80	2.37	6.70	0.30	D2927
3.5	0.005	0.40	TR	TR	0.25	D2926
4.4	TR	0.45	TR	0.50	0.20	C2721
3.5	TR	0.25	TR	TR	0.20	C2720
3.6	0.01	0.40	TR	TR	0.60	C2719
3.5	0.02	0.50	TR	TR	0.05	C2718
5.0	0.005	0.15	TR	TR	0.05	C2717
5.6	0.02	0.60	0.16	TR		I2803
5.5	0.01	0.96	TR	TR	0.05	D2924
7.0	TR	0.40	TR	TR		D2925
1.8	0.06	9.60	8.20	9.20		I2800
4.5	0.01	0.16	TR	4.30	TR	C2722
3.8	0.04	1.00	TR	9.40		C2711
3.3	TR	1.68	1.51	1.70		I2807

SAMPLE No	W FT.	Au. Oz.	Ag. Oz.	Pb %	Zn %
D2944	7.5	TR	0.32	TR	0.10
D2945	2.8	0.01	1.12	0.75	2.70
D2943	7.7	0.01	2.40	2.75	1.60
D2941	5.4	TR	0.32	TR	0.40
D2942	3.0	0.04	14.00	5.45	11.70
D2939	5.0	0.02	3.12	0.75	1.20
D2938	3.0	0.04	13.60	4.75	29.50
D2940	7.6	0.02	2.80	2.32	14.60

SAMPLE No	W FT.	Au. Oz.	Ag. Oz.	Pb %	Zn %
R2616	4.5	TR	0.24	TR	TR
R2615	4.5	0.08	0.56	TR	TR
R2614	6.6	0.15	14.60	8.31	10.10
R2613	7.3	0.04	0.80	0.80	2.90
R2612	5.7	0.14	4.80	3.67	4.60
R2611	5.2	0.12	3.80	3.56	3.50
R2610	4.3	0.14	4.92	3.34	4.40
R2609	4.7	0.08	3.00	4.75	1.90
R2608	3.7	0.10	2.62	2.05	3.00
R2607	3.5	0.02	2.00	1.40	0.80

W FT.	Au. Oz.	Ag. Oz.	Pb %	Zn %	Cu %	SAMPLE No
5.4	0.02	0.45	TR	TR		C2724
6.7	0.005	0.20	TR	TR		C2723
5.0	TR	TR	TR	TR		C2725
5.0	0.01	0.16	TR	TR		C2726
6.3	0.01	2.15	3.24	5.20	0.15	C2731
5.0	0.04	0.55	0.32	4.20		C2730
7.3	TR	1.40	2.42	6.60		C2729
7.7	0.005	0.40	TR	TR		C2728
4.7	0.005	TR	TR	TR		C2727
4.7	0.04	4.48	3.67	4.50	0.30	C2734
5.7	0.005	1.00	0.75	0.90		C2733
6.5	0.005	0.35	TR	0.20		C2732
4.3	0.01	0.80	5.34	4.30	0.40	C2737
4.5	0.04	0.30	TR	0.3	0.15	C2736
4.0	0.03	1.10	1.13	2.30		C2735
5.1	TR	0.25	TR	TR		C2740
5.7	0.10	11.36	2.70	4.20	0.10	C2739
3.6	TR	0.40	0.16	TR		C2738
6.4	0.01	0.96	0.78	0.90		C2744
7.2	0.03	2.80	7.50	3.20	0.20	C2741
3.5	TR	0.30	TR	TR		I2802 SHIP

All samples in this block are normal samples.