

OXIDIZED SAMPLES


Width	oz. per ton		%	
	Gold	Silver	Copper	Arsenic
4'	tr	tr	7.2	5.1
3'	0.24	tr	2.5	3.0
2'	0.24	1.6	12.1	8.1
3'	0.9	2.4	14.1	8.0

Width	oz. per ton		%	
	Gold	Silver	Copper	Arsenic
3'	0.30	0.5	3.5	2.5
22"	0.20	0.4		2.4

Width	oz. per ton		%	
	Gold	Silver	Copper	Arsenic
3' (gauge)	0.08	0.6	1.7	1.2
1'	0.70	0.6	9.0	8.0
4'	0.40	0.8		nil.

**LEGEND**  
 Sheared greenstone  
 Quartz-Sulphide vein matter  
 Fault  
 Locality described in text.

Profile up cliff-face above adit-portal, this constitutes a longitudinal section along the vein-shear  
 Horizontal & Vertical Scales 1" = 20'



92F/1E

WORKINGS ON  
SILVER LEAF GROUP  
 NANAIMO M.D.  
 Scale 1" = 20'  
 Chain-compass-aneroid Survey

005898

B.C. Department of Mines  
 April, 1938