

TRENCH No's & STATIONS	J.E.R. WOOD. WIDTH	J.E.R. WOOD. OZ. AU.	G. DIROM. WIDTH	G. DIROM. OZ. AU	S. McCLAY. WIDTH	S. McCLAY. OZ. AU
14	0.4'	0.08	0.35'	0.03	0.50'	0.01
	0.3'	0.65	1.10'	0.17	0.40'	0.22
	0.45	1.54	0.30'	1.28	0.40'	2.50
			0.40'	3.85	0.75'	2.12
			0.15'	25.70	0.30'	2.44
13	0.35'	10.61	0.40"	8.05	0.20'	21.62
12	0.40'	0.20	0.30'	0.22	0.30'	0.38
11	0.75'	3.08	0.55'	11.26	0.70'	12.48
10	0.35'	0.61	0.60'	1.02	0.60'	1.00
			0.25'	0.59	0.30'	0.30
			0.80'	4.06	0.75'	2.96
			0.25'	5.24	0.70'	2.02
9	0.35'	4.28	0.20'	1.36	0.30'	0.94
8	0.35'	2.78	0.25'	10.20	0.25'	7.32
7						
6						
5	0.35'	10.32	0.30'	5.69	0.30'	2.48
4	0.4'	3.96	0.45'	2.49	0.50'	2.66
3	0.3'	1.70	0.20'	1.08	0.30'	1.76
2	0.1'	1.32	0.10'	2.10	0.10'	2.32
Face "UNCUT"	0.87'	0.95	0.80'	3.90		
	0.60'	6.04				
WEIGHTED AVERAGES	0.432'	3.49	0.38'	4.93'	0.4'	4.29
3' MINING WIDTH	0.52 oz.	$18.20	0.62	$21.70	0.57 oz.	$19.95

33.5' - South ⊙ 14
17.5' - " ⊙ 14

440'

280' South ⊙ 14 the following results were obtained:-

WOOD	DIROM	McCLAY.
0.4' - 2.32 oz.	0.3' - 0.87 oz	0.6' - 0.50 oz. 0.9' - 1.09 oz.

NOTE:- Wood bulk sampled therefore, in order to arrive at comparative average with Wood; McClay & Dirom, assays from trenches 9 & 14 were grouped separately & averaged; the results being included in final weighted averages.

AVERAGE of All SAMPLING 3' MINING WIDTH — 0.57 oz. $19.95

PROPERTY FILE
92F061(5E)

ASSAY PLAN and PROFILE MAP
BUCCANEER MINES LTD
BEDWELL RIVER, B.C.
Showing Wood, McClay & Dirom Sampling
Scale 1" - 30'
Aug 7, 1939 J.J. McClay.

006788