007909



Province of British Columbia

Energy, Mines and Petroleum Resources LAND MANAGEMENT AND POLICY BRANCH

Ministry of

## MEMORANDUM

Suite 301, 865 Hornby Street, Vancouver, B.C. V6Z 2G3

Memo To: File

From: Robert Pinsent

Date: December 15th, 1993

Subject: Ashgrove Cement

Telephone: (604) 660-0223 BRITISH COLUMBIA GEOLOGICAL SURVEY

ORIGINAL

Notes on a telephone conversation:

- The company conducted minor exploration programmes in 1992 and 1993.

- They consisted of 200 - 300 foot reverse circulation holes around the pit.

- Chips were sampled every 10 feet. They were tested for sulphur, pyrite, Magnesium content.

- Generally the magnesium content is towards the top of the section. It is somewhat erratically distributed.

- Generally, pure calcium limestone is at the base.

- The quarry has increased production somewhat. It produced 1.3 million tonnes in 1993.

It produced 800,000 tonnes of cement grade, 300,000 tonnes of chemical grade, 150,000 of agricultural grade limestone.
It also produced 200,000 tonnes of aggregate.

Robert