

## ASSAYS FOR ORE &amp; WASTE

ORE ZONE	HOLE NUMBER	FOOTAGE SAMPLE	MOLYBDENUM (Mo) ASSAYS.		
			Average for hole ore & waste	Average for ore	Average for waste.
<u>IONA</u>	B-27	896'	.031	.036	.020
	B-9	950'	.012	.013	.012
	Cut-off=0.4% Cu. B-2	453'	.023	.027	.007
	B-7	422	.023	.029	.015
	TOTAL FOOTAGE	2221			
	Average		.022	.026	.013

<u>HUESTIS</u>	B-122	254	.021	.025	.018
Cut-off=0.4% Cu.	TOTAL	254			
<u>SPUD LAKE</u>	B-127	400	.025	-	.025
Cut off=0.4% Cu	B-128	400	.047	-	.047
TOTAL FOR ZONE		800			
	Average		.036	-	.036

<u>EAST JERSEY</u>	B-110	332	.022	.019	.024
	B-119	248	.023	.021	.035
	B-112	40	.002	.002	-
	B-104	254	.013	.013	.015
	Cut off=0.4% Cu. B-102	130	.029	.029	-
	B-93	63	.020	.020	.021
	B-89	195	.044	.050	.023
	B-87	65	.032	.033	.026
	B-118	124	.008	.008	.008
	CD-51	90	.003	.003	.003
		1537			
	Average		.020	.020	.019

<u>JERSEY</u>	B-43	820	.009	.009	-
Cut off	B-36	990	.011	.011	-
0.4% Cu.	B-10	578	.016	.018	.015
	B-35	951	.017	.018	.013
	B-3	716	.017	.025	.014
	Average	3695	.014		.015

ORE ZONE	HOLE NUMBER <small>FOOTAGE SAMPLE</small>	MOLYBDENUM (Mo) ASSAYS		
		Average for hole ore & waste	Average for ore	Average for waste
<u>EAST</u>	B-123 218'	.027	.027	.027
<u>JERSEY</u>	B-124 387	.019	.020	.019
<u>EXTENSION</u>	B-125 442	.035	.040	.030
CUT off = 0.6% Cu	B-126 345	.019	.022	.017
TOTAL FOR ZONE	1092			
	Average	.025%	.027	.023
TOTAL FOOTAGE	9599			
	TOTAL 254			