

018559



BUREAU OF MINES,

Certificate No. 1378, &c.

THE GOVERNMENT OF
THE PROVINCE OF BRITISH COLUMBIA

VICTORIA, Jan., 28, 1925.

GOVERNMENT ASSAY OFFICE.

N. W. Mineral Survey District
RESIDENT ENGINEER

Rec'd JAN 26 1925

Ans'd _____

103P/6W
1030-P-126

Assay Certificate.

I HEREBY CERTIFY that I have assayed the following sample.....

handed me by G. A. Clothier, Esq., Res.Mng.Engineer, Prince Rupert, B.C.and said to represent samples from "Esperanza".

Character of sample.....

I find the same to contain, in dried sample:—

Depositor's Mark.	DESCRIPTION OF SAMPLE.	GOLD. Oz. per Ton	SILVER. Oz. per Ton.	COPPER. % Wet Assay.	LEAD. % Wet Assay.	ZINC. %
1378.	Esperanza No.1		0.4		trace	1.5%
1379.	No.2		0.2		trace	1.0
1380.	No.3		5.2		trace	1.2
1381.	No.4		3.2		trace	1.0
1382.	No.5		6.0		trace	1.0
1383.	6		353.0		6.0	6.0
1384.	7		22.5		trace	1.5
1385.	8		10.0		trace	1.5
1386.	9		23.0		trace	2.0
1387.	10		84.0		trace	3.5
1388.	11.		62.0		trace	2.0
1389.	12.		100.0		trace	2.5
1390.	13		129.0		1.5	2.5
1391.	14		46.0		trace	2.5
1392.	15		12.0		trace	2.0
1393.	16		32.0		trace	1.5
1394.	17		4.0		trace	1.5
1395.	18		49.0		0.5	1.7
1396.	19.		4.0		trace	1.0

CHARGES \$.....

1M-923-3436


 Asst. Provincial Government Assayer.



BUREAU OF MINES.

THE GOVERNMENT OF
THE PROVINCE OF BRITISH COLUMBIA

VICTORIA. Jan'y. 22, 1925.

Certificate No. 1397, &c.

GOVERNMENT ASSAY OFFICE.

N. W. Mineral Survey District
RESIDENT ENGINEER

Rec'd JAN 26 1925

Ans'd _____

Assay Certificate.

I HEREBY CERTIFY that I have assayed the following sample.....

handed me by..... **Geo.A.Clothier, Esq.,**

and said to represent

Character of sample.....

I find the same to contain, in dried sample :—

Depositor's Mark.	DESCRIPTION OF SAMPLE.	GOLD. Oz. per Ton	SILVER. Oz. per Ton.	COPPER. % Wet Assay.	LEAD. % Wet Assay.	ZINC. %
1397.	Esperanza, No.20		5.0		trace	1.0
1398.	21		1.0		trace	1.0
1399.	22		1.0		trace	0.7
1400	23		2.5		trace	1.0
1401	24		1.5		trace	1.0
1402	25		15.0		trace	1.5
1403.	26		1.5		trace	1.0
1404.	27		15.5		trace	2.0
1405.	28		5.0		trace	1.0
1406.	29		5.0		trace	1.0
1407.	30		trace		trace	1.5
1408.	31		4.0		trace	2.0
1409	32		4.5		0.2	1.5
1410	33		5.0		trace	1.5
1411.	34		7.5			
1411.	Tungsten (WO ₃) 20.0%					

CHARGES \$

H. E. Whittaker

Asst. Provincial Government Assayer.

