

103P/6W
103 O-P-126



Folio No. 401.

DEPARTMENT OF MINES
VICTORIA

Sample received from W.H. Mathews, Esq.,Address Associate Mining Engineer, Mines Dept.

Certificate No.	DESCRIPTION OF SAMPLE.	GOLD.	SILVER.	COPPER.	LEAD.	ZINC.	WO ₃
		Oz. per Ton.	Oz. per Ton.	%	%	%	
✓ 32-J		0.08	2.3				trace
✓ 33-J		0.01	1.1				1.82%
✓ 34-J		0.04	20.5				0.89%
✓ 35-J		0.01	4.4				trace
✓ 36-J		0.23	56.4				0.24%
✓ 37-J		0.01	2.2				0.30%
✓ 38-J		0.1	8.9				trace
✓ 39-J		0.01	0.5				0.32%

Date September 23rd, 1942.

J. Cass. Brown. Cass
Chief Analyst and Assayer.



DEPARTMENT OF MINES
VICTORIA

Sample received from W.H. Mathews, Esq.,

Address Associate Mining Engineer, Mines Dept.

Certificate No.	DESCRIPTION OF SAMPLE.	GOLD.	SILVER.	COPPER.	LEAD.	ZINC.	Tin	WO ₃
		Oz. per Ton.	Oz. per Ton.	%	%	%		
21-J	Silver Bell Ore					8.1	0.01	
22-J	Tam O'Shanter Ore				3.5	2.3	0.05	
23-J	Noble 5 - sphalerite						0.01	
24-J	Rambler Cariboo Ore					27.1	0.01	
25-J		0.01	nil					0.14%

Date September 23rd, 1942.

J. Cass. Brown. Cass
Chief Analyst and Assayer.