



SILVERLEAF
L 4039

MAY P. J.
L 4038

GOOD HOPE
L 4037



No.	In.	Au.	Ag.	Pb.	Zn.
476	30	0.01	0.80	Tr.	Tr.
477	13	0.02	2.25	Tr.	Tr.
478	2.5	0.015	2.15	0.20	0.15
479	24	Tr.	0.07	0.55	0.30
480	99	0.005	0.80	Tr.	Tr.
481	65	0.01	0.95	Tr.	Tr.
482	62	0.01	0.45	Tr.	Tr.
483	62	0.01	0.45	Tr.	Tr.
484	48	0.02	3.15	0.40	Tr.
485	18	0.02	5.35	0.90	Tr.
486	20	0.02	5.35	0.90	Tr.
487	20	0.02	5.35	0.90	Tr.

No.	In.	Au.	Ag.	Pb.	Zn.
488	20	0.09	2.05	Tr.	Tr.
489	45	0.01	0.95	Tr.	Tr.
490	45	Tr.	Tr.	Tr.	Tr.
491	60	Tr.	0.10	Tr.	Tr.
492	30	Tr.	0.10	Tr.	Tr.
493	25	Tr.	Tr.	Tr.	Tr.

SILVER TIP GOLD MINES LTD.
Stewart, B. C.
ASSAY PLAN
OF MAIN WORKINGS
1 INCH = 40 FEET

Assay sequence: Number; Ore width in inches; Gold oz./ton;
Ag oz./ton; Pb %/ton; Zn %/ton.

July, 1957
1042043
PROPERTY FILE

019129

FIG 4