

5000-2 LEVEL  
 selected grab samples  
 from dump 20.1oz Ag.  
 5.02 oz Ag.  
 29.2 oz Ag.

3.3' 9.75oz Ag

5000-2 LEVEL  
 3.3' 9.75oz Ag

5000

5100

5200

5300

5400

5500

5600

5700

1.85'  
 36.40oz Ag  
 7.38% Pb

5150-4 LEVEL  
 grab 26.25 Ag.  
 11.50 Pb.  
 7.43 Zn.  
 30.00 Ag.  
 24.09 Pb.  
 7.6 Zn.  
 4.04'  
 13.20 Ag  
 8.1% Zn  
 1.15'  
 25.03 Ag  
 4.22% Pb  
 8.75% Zn

.73'  
 113.73 Ag  
 25.46 Pb  
 4.54% Zn

5300-4 LEVEL  
 surface slope

4.0'  
 dump - galena  
 malachite  
 arsenopyrite

10' 2.84oz Ag.  
 quartz - dyke breccia

5' qtz. vein  
 arsenopyrite

5600-2 LEVEL

2C  
 selected grab samples  
 from dump 251.80oz Ag. 70% Pb  
 22.10oz Ag.  
 galena  
 sphalerite  
 arsenopyrite  
 chalcopyrite



5700-4 LEVEL  
 selected grab samples  
 from dump 42.20 Ag 39.80 Pb  
 40.70 Ag 19.10 Pb  
 13.7 Zn  
 1.56 Cu

diss. galena  
 in quartz  
 float  
 1.98 Au

diss. galena  
 in quartz  
 selected grab  
 58.10 oz Ag.  
 34.80% Pb

2"-3" galena  
 30" qtz. vein

48 TRENCH  
 2.5' - .22 Au  
 40.50 Ag.  
 20.40 Pb  
 5.4 Zn  
 3.3 Cu


ATLIN SILVER CORPORATION

MAP 10 SURFACE SAMPLE PLAN

SCALE - HOR. 1" = 100'

DATE - APRIL 1975

DRAWN BY - *James Smith*



020059