## SAMPLES

293 Individual, massive zincblende stringers; no pyrite:

Aug. - 0.72 ozs. Ag. - 8.30 ozs. Pb. - 0.65% Zn. - 21.00%

294 Grab samples taken at random in oldest tunnel:

Au. - 1.32 ozs. Ag. - 10.70 ozs. Pb. - 4.70% Zn. - 7.50%.

(Samples taken by G.M. Radisics as per attached letter dated October 23, 1951.)

1.