

GEOCHEMICAL ANALYSIS CERTIFICATE

AVARRE RESOURCES CORP.

Project: Rox Claims

Sample Type: Rocks & Stream Sed.

Multi-element ICP Analysis - .500 gram sample is digested with 3 ml of aqua regia, diluted to 10 ml with Water. This leach is partial for Mn, Fe, Ca, P, La, Cr, Mg, Ba, Ti, B, W and limited for Na, K and Al. Detection Limit for Au is 3 ppm. Au Analysis - 10 gram sample is digested with aqua regia, MIBK extracted, graphite furnace AA finished to 1 ppb detection.

Analyst White Channel
 Report No. 9120143
 Date: October 17, 1991

520350

92K/1

ELEMENT SAMPLE	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Hg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au ² ppt
1 0+38W	2	707	6	139	5.7	169	59	103	43.32	48	5	14	3	6	.2	34	2	2	.23	.006	2	25	.04	19	.01	24	.25	.01	.02	1	
2 0+44W	7	185	68	11229	6.0	28	15	183	5.41	476	5	3	1	10	143.1	11	15	9	.51	.009	2	85	.12	24	.02	4	.50	.01	.05	1	
3 0+60W	6	21	19	36	.3	5	4	113	1.14	4	5	ND	9	10	.5	2	2	21	.20	.008	13	77	.16	91	.09	3	.41	.04	.13	1	15
4 1+00W	11	3002	89	14649	125.4	6	5	58	3.11	405	5	425	1	1	220.5	56	141	14	.01	.007	2	151	.03	4	.01	3	.10	.01	.01	1	
5 1+03W	12	2451	81	22893	65.0	5	14	154	3.51	3129	5	171	1	11	350.0	43	119	31	.08	.008	2	169	.27	10	.01	4	.54	.01	.01	1	
6 1+10W	9	2016	64	13268	50.9	8	12	237	4.21	4104	5	163	1	2	212.5	34	73	65	.03	.010	2	128	.58	7	.01	3	.79	.01	.01	1	
7 1+55W	7	33490	132	30640	198.6	7	33	66	16.30	3233	5	66	1	2	453.5	47	262	5	.16	.028	2	124	.04	10	.01	5	.33	.01	.01	1	
8 1+57W	11	1806	403	31640	395.4	9	17	73	3.36	3419	5	13831	1	1	449.3	37	494	4	.04	.009	2	191	.07	31	.01	2	.20	.01	.04	1	
9 1+60W	12	540	39	8942	18.0	10	7	63	1.87	2152	5	22	1	1	169.4	14	43	5	.09	.010	2	148	.06	39	.01	2	.25	.01	.04	1	
8 1+60W	15	756	291	44423	249.5	9	20	66	3.34	1013	5	822	1	1	770.3	31	341	2	.02	.005	2	241	.01	21	.01	3	.09	.01	.03	1	
0 4+75W	13	417	32	7210	5.8	23	29	199	3.53	57	5	10	1	8	110.1	2	19	36	2.11	.023	2	134	.34	9	.06	4	1.72	.01	.01	1	
0 0+40W 0+25W	10	162	4	42	.5	5	43	95	1.85	21	5	ND	1	12	.5	2	2	11	.32	.029	2	125	.07	9	.10	2	.16	.01	.01	1	260
1 0+60W 0+10W	6	229	6	47	.8	51	34	321	4.15	14	5	ND	1	104	.7	2	2	74	3.20	.040	2	111	.83	73	.18	6	2.16	.10	.29	2	18000
2 0+38W	8	85	15	90	.8	28	9	403	5.06	134	5	ND	2	58	.8	3	2	32	1.25	.063	5	64	.37	72	.09	8	1.24	.05	.13	1	7200
3 1+10W	2	72	30	1022	.5	5	10	245	1.91	12	5	ND	1	130	10.2	3	3	64	1.84	.148	6	22	.38	34	.22	3	1.64	.10	.04	1	3900
4 1+57W	5	65	6	54	.4	18	9	420	3.95	9	5	ND	3	49	.2	2	3	63	.68	.067	7	64	.75	119	.17	2	1.14	.04	.48	1	60
5 1+57W	5	284	10	388	2.2	21	8	103	1.73	44	5	ND	2	54	18.2	2	4	20	.65	.077	11	39	.09	30	.10	2	.45	.05	.04	1	360
6 3+40W VV	1	429	23	220	4.1	16	70	3560	20.11	3	5	ND	1	8	.2	2	3	50	1.00	.005	2	16	.18	23	.11	3	.66	.05	.03	1	400
7 2+50W 2+25W	21	487	2	31	2.9	183	94	85	17.05	2	5	ND	2	234	.2	2	3	9	3.16	.177	8	14	.04	39	.09	2	4.42	.35	.02	1	9500
8 2+35W 2+25W	6	502	2	69	.7	12	12	191	9.71	20	5	ND	3	21	.2	2	3	139	.05	.005	2	69	.26	48	.10	6	2.14	.01	.12	1	18
IT-1 0+00W	1	43	51	101	.3	9	18	544	3.65	55	5	ND	1	30	.3	2	2	109	.61	.026	2	13	.70	106	.21	4	1.52	.06	.09	3	22
IT-2 0+40W	3	43	10	188	1.8	22	14	1400	3.22	672	5	4	1	21	1.8	2	2	29	2.25	.043	4	5	.41	35	.05	2	3.46	.01	.06	1	900
IT-3 0+60W	3	35	22	59	.1	5	11	283	3.47	62	5	ND	1	29	.2	2	2	77	.72	.068	4	10	.51	62	.16	2	1.42	.06	.10	2	8
IT-4 1+19W	4	48	16	270	.8	7	6	243	4.09	208	5	ND	1	22	4.5	3	4	86	.40	.035	4	14	.55	90	.19	2	1.54	.05	.15	1	5100
IT-5 1+60W	5	10124	239	14953	185.8	7	37	590	15.81	6968	5	126	2	11	219.7	51	459	31	.59	.032	9	33	.26	41	.04	2	1.50	.01	.06	1	133000
IT-6 2+35W	1	210	11	321	3.9	11	16	249	3.45	101	5	8	1	28	4.4	2	6	96	.45	.041	3	13	.66	130	.21	2	1.62	.07	.23	1	1780
IT-7 4+75W	2	232	2	615	6.1	55	24	337	3.43	47	5	37	1	62	7.3	2	9	67	2.13	.076	4	29	.64	132	.13	4	2.71	.04	.11	1	12000
IT-8 2+50W 2+25	2	36	23	81	.2	11	16	300	3.87	16	5	ND	1	31	1.3	2	3	109	.33	.038	2	14	.74	188	.21	2	1.98	.05	.24	1	18