

## SHANGRI-LA MINERALS PROJECT-BLUE GROUSE FILE # 87-2039

521060 Blue Grouse  
92c/16  
Page 22

SAMPLE#	MO	CU	PB	ZN	AG	NI	CO	MN	FE	AS	U	AU	TH	SR	CD	SB	BI	V	CA	P	LA	CR	MG	BA	TI	B	AL	NA	K	W	AU#	
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM	
1340 Add " " Blue Grouse pit	B6-1	gb	2 36023	10	773	40.9	17	53	956	9.34	14	5	ND	1	5	4	2	2	43	3.61	.006	2	3	.22	5	.02	4	.30	.01	.01	1	7
	B6-2	1m	2 633	24	209	.5	317	71	1334	7.05	32	5	ND	1	106	1	2	2	125	1.39	.024	2	361	2.93	12	.21	4	3.84	.01	.03	1	3
	B6-3	1m	1 609	2	22	.4	105	33	468	2.59	10	5	ND	1	58	1	2	2	76	2.59	.055	2	108	.35	74	.02	10	1.52	.01	.16	2	1
	B6-4	1m	5 5322	12	54	3.3	14	13	2004	13.85	8	5	ND	1	10	1	2	2	29	18.04	.010	2	3	.14	28	.01	2	.27	.24	.01	4	1
	B6-5	1m	4 50181	12	259	17.6	61	37	1338	14.02	70	5	ND	1	28	3	4	2	164	8.86	.045	2	18	.31	37	.06	2	.83	.19	.03	1	3
	B6-6	1.5m	4 239	8	16	.2	1	3	2148	13.08	12	5	ND	1	4	1	2	2	22	16.85	.001	2	1	.05	10	.01	2	.18	.23	.01	8	1
	B6-7	7m	5 12766	8	233	9.1	15	24	2106	13.93	34	5	ND	1	5	1	2	2	25	14.80	.007	2	4	.10	7	.01	2	.22	.22	.01	16	8
	B6-10	.5m	3 9613	6	373	2.4	25	38	1154	6.72	14	5	ND	1	17	1	4	2	129	.46	.052	4	115	2.45	1	.12	2	2.36	.02	.01	1	1
	B6-11	.5m	6 1700	10	20	.5	18	8	2464	12.14	8	5	ND	1	2	1	2	2	12	15.28	.027	2	1	.09	4	.01	2	.36	.23	.01	3	2
	B6-12	1m	6 5895	10	44	1.0	25	9	2636	13.02	6	5	ND	1	7	1	2	2	29	13.63	.032	2	7	.40	5	.02	2	.64	.22	.01	3	7
	B6-13	1m	3 6955	12	74	2.3	9	18	1348	4.79	4	5	ND	2	102	1	2	2	53	3.29	.084	8	2	1.27	9	.23	4	2.28	.01	.04	1	6
	B6-14	.5m	10 12894	4	93	1.7	5	19	1750	5.82	16	5	ND	1	6	1	2	2	22	5.20	.007	2	1	.21	1	.01	2	.09	.01	.01	1	1
	B6-15	.5m	4 11013	34	11766	8.9	3	43	978	15.19	74	5	ND	2	5	64	4	2	23	1.45	.025	2	1	.22	2	.02	4	.11	.01	.01	1	26
	B6-16	2m	9 8677	6	130	.1	52	12	1350	7.03	6	5	ND	1	67	1	2	2	49	5.86	.018	2	31	.74	2	.07	2	1.00	.04	.01	1	2
	B6-17	gb	12 25863	8	382	.8	87	33	2584	11.48	8	5	ND	2	34	1	4	2	151	3.10	.020	2	56	1.74	7	.10	2	1.82	.01	.01	1	4
	B6-18	gb	3 22510	6	141	.4	4	13	3514	9.52	4	5	ND	2	7	1	2	2	28	3.40	.016	2	3	.31	3	.01	2	.23	.01	.01	2	2
	B6-19	gb	2 1377	8	69	.3	2	8	2448	10.36	6	5	ND	1	5	1	2	2	27	12.43	.014	2	1	.10	1	.01	2	.15	.20	.01	8	1
	B6-20	gb	4 274	8	35	.1	1	13	2280	14.01	8	5	ND	1	3	1	2	2	34	16.22	.008	2	1	.09	4	.01	2	.11	.23	.01	6	1
	B6-21	1m	4 2972	8	45	.1	2	20	2676	13.85	6	5	ND	1	7	1	2	2	19	18.13	.003	2	1	.05	1	.01	2	.13	.23	.01	5	1
	STD C/AU-R		20 57	38	132	6.9	67	27	972	3.83	42	20	7	33	47	17	14	20	62	.45	.082	34	56	.85	175	.08	32	1.68	.06	.12	12	510

ASSAY REQUIRED FOR for Cu &gt; 10,000 ppm