



REPRESENTATIVES IN
EASTERN CANADA, UNITED
STATES, EUROPE & JAPAN

G. S. ELDRIDGE & CO. LTD.
STANDARD TESTING LABORATORIES
CHEMICAL, INSPECTING AND TESTING ENGINEERS, ANALYTICAL CHEMISTS
PROVINCIAL ASSAYERS & METALLURGISTS
VANCOUVER - VICTORIA - PRINCE GEORGE
633 HORNBY STREET - VANCOUVER 1 - CANADA

FILE No. 30713

521322
Amai Inlet

PHONE MUTUAL 4-1267
CABLE ADDRESS "ELDRICO"

February 16, 1960

Mr. A.B. Thomson,
Kyuquot,
B.C.

Dear Sir:

WE HEREBY CERTIFY that the following are the results of
assays made by us upon submitted ORE sample.

Marks	Gold (Au)	
	ounces	value
	<u>per ton</u>	<u>per ton</u>
Wt. of sample 5.30 lbs.	5.91	\$206.85

Total gold in sample recovered by amalgamation

Value

Gold

487.12 milligrams

54.80 cents

~~206.78~~
206.78

Respectfully submitted,
G.S. ELDRIDGE & CO.LTD.

H. Sharples

H. Sharples
Chief Assayer

HS*j1



REPRESENTATIVES IN
EASTERN CANADA, UNITED
STATES, EUROPE & JAPAN

G. S. ELDRIDGE & CO. LTD.
STANDARD TESTING LABORATORIES
CHEMICAL, INSPECTING AND TESTING ENGINEERS, ANALYTICAL CHEMISTS
PROVINCIAL ASSAYERS & METALLURGISTS
VANCOUVER - VICTORIA - PRINCE GEORGE
•
633 HORNBY STREET - VANCOUVER 1 - CANADA

FILE No.

PHONE MUTUAL 4-1267
CABLE ADDRESS "ELDRICO"

February 16, 1960

Mr. A.B. Thomson,
Kyuquot,
B. C.

Dear Sir:

We have tested the sample of ore submitted by you for an amalgamation assay. Please find enclosed our assay certificate.

The small sample of ore that you enclosed is certainly rich in telluride. Gold telluride does not amalgamate. As suggested by you in your letter, this telluride material was added to the main sample.

Yours very truly,
G.S. ELDRIDGE & CO.LTD.

H. Sharples
Chief Assayer

HS*jl