

R E P O R TON THE FERNIER GROUP OF GOLD MINING CLAIMS,
PORCUPINE MOUNTAIN, Near CLINTON, B.C.LOCATION:

This group of mineral claims is situated on the Western slope of Porcupine Mountain, locally known as the Black Dome, at the head of the North fork of Lone Cabin Creek, and can be reached by a good road from Clinton, B.C. to Gang Ranch, and from Gang Ranch through Empire Valley to the claims. This would involve approximately 10 miles of new road of easy construction through glacial drift.

These eight claims, known as the FERNIER GROUP are indicated and named on the accompanying map, along with the other fifty claims and fractions, making in all a total of fifty-eight claims and fractions, or approximately 3000 acres of mineral ground purchased or in process of being purchased by the Company. The Fernier Group is, I believe, typical of the whole mountain and the other groups purchased. The peak of Porcupine Mountain being on the Ptarmigan claim, one of Fernier's group.

GEOLOGY:

Porcupine Mountain, or the Black Dome as it is known locally, has an altitude of approximately 7500 feet and rises from the plateau about 10 miles west of the Fraser River.

The ground covered by the claims is open, with talus or grassy covered slopes, and consists of porphyritic andesitic rocks, some tuffs and rhyolites.

ORE DEPOSITS AND VEINS:

I have indicated on the accompanying map some of the numerous leads I observed while on the property. The leads are sheeted and brecciated zones in slightly altered porphyritic andesite, and most leads contain more or less quartz in lenses and veinlets. Some of these veins have width of 10 to 20 feet. Grains of pyrite can be found in the quartz and in the altered andesite within the leads. Visible gold can be seen in most of these leads. The strike of the leads is from 15 to 60 degrees North East and dip very steeply to the North West, some to the South East.

I found from assays which I took across the main leads (where pits were dug) that the results were very low in gold in some places, and in others sufficiently high to give one hopes of a good grade throughout. (A certificate of assays from G.S. Eldridge is enclosed. These pits were not dug at regular intervals, but just at any irregular distance apart, hence the assay results do not record a true value of the leads investigated. None of the pits were deep enough to expose the leads below the surface weathering which is very thick. I chipped off rock across leads, had it washed carefully to remove any accumulated concentration of metal, by doing this some of the samples may have been robbed of original specks of gold in the

original pyrites, now eaten away.

On panning the loose material above the leads fine gold was left abundantly on the pan from some of the leads and less from others, but always some colors from every lead I examined in this way. I have indicated the results of assays on the accompanying map, and also the leads. A study of the enclosed map will give the reader a good idea of the enormous tonnage to be expected from the thick bed of porphyritic andesite, with its numerous shear zones.

CONCLUSION:

There could be an enormous tonnage of gold bearing vein material, the value of which is not yet determined definitely. For example, take the No.4 shear on the Bonanza Claim, the pits are spaced approximately at 0 feet 40, 20, 40 and 50 feet apart and assay \$1.75, \$25.70, \$4.55, \$1.75 and \$13.80 per ton respectively, an average of \$9.47 per ton over an average width of samples taken 5'2 $\frac{1}{2}$ ". If the pits were spaced 10 feet or even 20 feet apart and sampled accordingly and carried on much further along the vein a truer picture of values would be possible. Also depth must be established by diamond drilling.

I therefore recommend the expenditure of roughly \$50,000.00 for stripping and trenching below weathered surfaces at regular intervals, and approximately 10,000 feet of diamond drilling, as there is the possibility of an enormous tonnage of good grade gold ore available over this large area, and indications are that it will turn out to be a large producer of gold and considerable silver.

Yours respectfully,

J.E. HANLON, R.P.E.

REPRESENTATIVES IN
LONDON, ENG., UNITED STATES AND EUROPE

CABLE NO.
FILE NO.

G. ELDRIDGE & CO. LTD.
AND
STANDARD TESTING LABORATORIES

MONTREAL, TORONTO, WINNIPEG, VICTORIA, VANCOUVER

TESTING
INDUSTRIAL
REGISTERED METALLURGICAL
PROVINCIAL ASSAYERS
AND
ENGINEERS

WE TEST ALL ARTICLES OF COMMERCE

OFFICE AND LABORATORIES
633 HORNBY STREET

VANCOUVER 1, B.C.

MEMBERS OF
CANADIAN INSTITUTE CHEMISTRY
CANADIAN INSTITUTE MINING AND METALLURGY
AMERICAN SOCIETY TESTING MATERIALS
AMERICAN SOCIETY FOR METALS
AMERICAN CHEMICAL SOCIETY

January 31st, 1953.

Mr. H. F. Stuart-Woolverton,
423 Hamilton Street,
Vancouver, B. C.

Dear Sir:

We have made a jig test on the sample of OXIDIZED QUARTZ
ORE, crushed through 20 mesh and report the following results:

	Weight Percent	Gold oz. per ton	Distribution percent
Concentrates	9.8%	5.67	30.0%
Middles	17.3%	2.04	19.4%
Coarse Tails	54.2%	1.06	30.4%
Slimes	18.7%	1.95	20.2%

It would appear from the above figures that the ore would
have to be ground much finer to free the gold.

Respectfully submitted,

G. S. ELDRIDGE & CO. LTD.

per

G. S. Eldridge

FILE No. 534

CABLE ADDRESS: "ELDRICO"

HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B.C.

PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We Hereby Certify that the following are the results of assays made by us upon samples of SIEVE TEST ON PRE-CRUSHED THROUGH 4 MESH
herein described and received from MR. H. F. STUART-WOOLVERTON JANUARY 28th 1953

MARKED	GOLD		SILVER		PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	VALUE PER TON	TOTAL VALUE PER TON (2000 LBS)
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON						
+ 10 mesh Weight 40.9%	1.52	\$ 53.20				\$		\$		\$
+ 20 mesh Weight 20.3%	1.48	\$ 51.80				\$		\$		\$
-20 mesh Weight 38.8	2.64	\$ 92.40				\$		\$		\$
Head Sample Weight 100%	1.84	\$ 64.40				\$		\$		\$

3M. 3-52. C. & W.

Gold calculated at \$ 35.00 per ounce.

Silver calculated at per ounce.

Calculated at cents per lb.

Calculated at cents per lb.

Paid 2

NOTE.—Samples only retained 3 months unless otherwise specified.

G. S. Eldridge Provincial Assayer

FILE No 75

CABLE ADDRESS: "ELDRICO"

HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B.C.

PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We Hereby Certify that the following are the results of assays made by us upon samples of ORE

herein described and received from H. F. STUART-WOOLVERTON

JANUARY 22nd. 1953

MARKED	GOLD		SILVER								TOTAL VA
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON	PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON		VALUE PER TON	PER TON (2000 LBS)
		\$		\$		\$		\$		\$	\$
	1.81	64.40									

SM. 3-52. C. & W.

Gold calculated at \$ 35.00 per ounce.

Silver calculated at per ounce.

Calculated at cents per lb.

Calculated at cents per lb.

Paid 2

NOTE.—Samples only retained 3 months unless otherwise specified.

G. S. Eldridge Provincial Assayer

FILE NO. 4

CABLE ADDRESS: "ELDRICO"

HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B.C.

PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We Hereby Certify that the following are the results of assays made by us upon samples of ORE
herein described and received from H. F. STUART-WOOLVERTON JANUARY 22nd. 1953

MARKED	GOLD		SILVER								TOTAL VALUE
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON	PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON		VALUE PER TON	PER TON (2000 LBS)
	1.84	\$ 64.40		\$		\$		\$		\$	\$

3M. 3-52. C. & W.

Gold calculated at \$35.00 per ounce.

Silver calculated at per ounce.

Calculated at cents per lb.

Calculated at cents per lb.

NOTE.—Samples only retained 3 months unless otherwise specified.

G. S. Eldridge Provincial Assayer

FILE NO. 7194

MAILING ADDRESS: "ELDRICO"

HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B.C.

PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We Hereby Certify that the following are the results of assays made by us upon samples of ORES
herein described and received from BRETT'S LIMITED NOVEMBER 21, 1952

MARKED	GOLD		SILVER		PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	TOTAL VALUE PER TON (2000 LB)
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON							
SUGAR BOWL 10' Wide	0.76	\$ 26.60				\$				\$	
GIANT VEIN 24' Wide	0.08	2.80									
MONEY CONTACT VEIN 2"-6" Wide	7.40	259.00									
RED BIRD 4' Wide Upper Vein Channel Sample	0.56	19.60									
#3-A VEIN 2' Wide	0.16	5.60									
#4-VEIN 3' Wide	0.56	54.60									

SM. 3-22. C. & W.

Gold calculated at \$ 35.00 per ounce.

Silver calculated at _____ per ounce.

Calculated at _____ cents per lb.

Calculated at _____ cents per lb.

NOTE:—Samples only retained 3 months unless otherwise specified

G. S. Eldridge Provincial Assayer

FILE No. 7194

CABLE ADDRESS: "ELDRICO"

HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B. C.

PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We Hereby Certify that the following are the results of assays made by us upon samples of ORES
herein described and received from BRETT'S LIMITED NOVEMBER 21, 1952.

MARKED	GOLD		SILVER						TOTAL VALUE	
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON	PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	VALUE PER TON	PER CENT. (2000)
#5 LOWER REDBIRD 2' Wide	0.12	\$ 4.20		\$		\$		\$		\$
RIBBON VEIN 4' Wide	3.44	\$ 120.40								

3M. 3-52. C. S. W.

Gold calculated at \$ 35.00 per ounce.

Calculated at _____ cents per lb.

Silver calculated at _____ per ounce.

Calculated at _____ cents per lb.

NOTE.—Samples only retained 3 months unless otherwise specified.

G. S. Eldridge Provincial Assayer

FILE NO. 7138
1170

Certificate of Assay

ABLE ADDRESS: "ELDRICO"
HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B.C.

PHONE TATLOW 1267

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We Hereby Certify that the following are the results of assays made by us upon samples of ORE
herein described and received from Brett's Ltd. November 15, 1952.

MARKED	GOLD		SILVER						TOTAL VALUE	
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON	PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	VALUE PER TON	PER TON (2000 LBS.)
Sugar Bowl Vein 10' wide	4.16	\$ 145.60		\$		\$		\$		\$

DM. 3-52. C. & W.

Gold calculated at \$ 35.00 per ounce.

Calculated at _____ cents per lb.

Silver calculated at _____ per ounce.

Calculated at _____ cents per lb.

NOTE.—Samples only retained 3 months unless otherwise specified.

G. S. Eldridge Provincial Assayer

FILE NO. #7718
1548

CABLE ADDRESS: "ELDRICO"
HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B.C.
PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We Hereby Certify that the following are the results of assays made by us upon samples of ORES
herein described and received from MR. EDGAR TRETHEWAY DECEMBER 12 1952

MARKED	GOLD		SILVER		PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	TOTAL VALUE PER TON (2000 LB.)
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON							
HONEY CONTACT QUARTZ SEAM	5.16	\$ 180.60		\$		\$		\$		\$	
HONEY CONTACT COUNTRY ROCK	0.02	.70									
RIBBON VEIN	0.36	12.60									
SUGAR BOWL QUARTZ	0.16	5.60									
RED BIRD	0.72	25.20									

3M. 3-52. C. & W.

Gold calculated at \$35.00 per ounce.
Silver calculated at per ounce.

Calculated at cents per lb.
Calculated at cents per lb.

NOTE:—Samples only retained 3 months unless otherwise specified.

R. S. M. Intosh

Provincial Assayer

FILE NO. 016

CABLE ADDRESS: "ELDRICO"

HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B. C.

PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We hereby Certify that the following are the results of assays made by us upon samples of ORE
herein described and received from Brett's Limited _____ September 23, 1955

MARKED	GOLD		SILVER		COPPER (Cu)		PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	TOTAL VALUE PER TON (200)
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON	PER CENT.	VALUE PER TON					
		\$		\$		\$		\$		\$	\$
#1 Red Bird North Wall	0.02	0.70	Trace		Trace						
#2 Red Bird South Wall	0.02	0.70	Trace		Trace						
#3 - 8" Across	0.14	4.90	2.6		2.9						
#4 - 28" Wide	0.03	1.05	0.2		Trace						
#5 - Decomposed Rock	0.08	2.80	0.4		0.2						
#6 - 6' Wide on hanging wall on north cut of granite	Trace		Trace								

3M-MP

Gold calculated at \$ 35.00 per ounce.

Silver calculated at _____ per ounce.

Calculated at _____ cents per lb.

Calculated at _____ cents per lb.

NOTE.—Samples only retained 3 months unless otherwise specified

G. S. Eldridge Provincial Assayer

G. S. ELDRIDGE & CO. LTD.

AND

STANDARD TESTING LABORATORIES

MONTREAL, TORONTO, WINNIPEG, VICTORIA, VANCOUVER

INSPECTING AND TESTING
ENGINEERS

INDUSTRIAL CHEMISTS

REGISTERED CHEMICAL AND
METALLURGICAL ENGINEERS

PROVINCIAL ASSAYERS

WE TEST ALL ARTICLES OF COMMERCE

OFFICE AND LABORATORIES
633 HORNBY STREET

VANCOUVER 1, B.C.

MEMBERS OF
CANADIAN INSTITUTE CHEMISTRY
CANADIAN INSTITUTE MINING AND METALLURGY
AMERICAN SOCIETY TESTING MATERIALS
AMERICAN SOCIETY FOR METALS
AMERICAN CHEMICAL SOCIETY

February 9th, 1953.

Mr. H. F. Stuart-Woolverton,
423 Hamilton Street,
Vancouver, B. C.

Dear Sir:


We have made a table test on the sample of ORE, crushed through 60 mesh and report the following results:

	WEIGHT PERCENT	GOLD OZ./PER TON	GOLD DISTRIBUTION PERCENT
HEADS	100.00	1.64	100.00
Concentrate	.80	98.80	48.20
Middlings 1	6.85	2.06	8.70
" 2	4.75	2.76	2.23
" 3	5.50	.42	1.42
Tailings	54.5	.16	5.38
Slimes	27.6	2.01	34.07
			<u>100.00</u>

Respectfully submitted,

G. S. ELDRIDGE & CO. LTD.

per



FILE NO.

1843

CABLE ADDRESS: "ELDRICO"

HEAD OFFICE AND LABORATORIES:
633 HORNBY STREET
VANCOUVER 1, B.C.

PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORSG. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALSWe hereby Certify that the following are the results of assays made by us upon samples of ORE
herein described and received from Bretts Limited October 5, 1953

MARKED	GOLD		SILVER		PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	TOTAL VALUE PER TON (2000)
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON					
1. #4 Red Bird - new cut	.04	\$ 1.40		\$		\$		\$	
2. #4 New Cut - north end	.02	.70							
3. #5 Red Bird Vein	.04	1.40							
4. Vein between 485 Red Bird	Trace	-							
5. Shrader Vein	1.04	36.40							
6. 25 feet dyke near No.1 R.B. at cross- cut road	.04	1.40							
7. Vein along road above old camp	.02	.70							

3M-MP-153

Gold calculated at \$ _____ per ounce.

Calculated at _____ cents per lb.

Silver calculated at _____ per ounce.

Calculated at _____ cents per lb.

NOTE.—Samples only retained 3 months unless otherwise specified

G. S. Eldridge Provincial Assayer

FILE NO. 1058

CABLE ADDRESS: "ELDRICO"

HEAD OFFICE AND LABORATORY

633 HORNBY STREET
VANCOUVER 1, B.C.

PHONE TATLOW 1267

Certificate of Assay

G. S. ELDRIDGE & CO. LTD.

PROVINCIAL ASSAYERS, ANALYTICAL AND CONSULTING CHEMISTS
METALLURGICAL AND CEMENT INSPECTORS

G. S. ELDRIDGE, B.Sc.
MEMBER OF
CHEMICAL INSTITUTE OF CANADA
CANADIAN INSTITUTE OF MINING AND
METALLURGY
AMERICAN SOCIETY FOR TESTING
MATERIALS
AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY OF METALS

We Hereby Certify that the following are the results of assays made by us upon samples of O.R.E.

herein described and received from BRETT'S LIMITED NOVEMBER 5, 1952

MARKED	GOLD		SILVER		PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	PER CENT.	VALUE PER TON	TOTAL VALUE PER TON (2000 LB)
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	VALUE PER TON							
#1 Across 4'	2.28	\$ 79.80		\$							\$
#2 Grab Sample Vein 16'	4.16	145.60									

3M. 3-52. C. & W.

Gold calculated at \$35.00 per ounce.

Calculated at _____ cents per lb.

Silver calculated at _____ per ounce.

Calculated at _____ cents per lb.

NOTE.—Samples only retained 3 months unless otherwise specified.

G. S. Eldridge Provincial Assayer

CERTIFICATE OF ASSAY

J. R. WILLIAMS & SON LTD.

File #158156

PROVINCIAL ASSAYERS AND CHEMISTS

Office and Laboratory:

580 Nelson Street, Vancouver 2, B. C.

I Hereby Certify that the following are the results of assays made by me upon samples of O. R. E. herein described and received from M. R. S. W. Wright. July 5, 1957

MARKED	GOLD		SILVER						GROSS TOTAL VALUE (2000 lbs.) Per Ton
	Ounces Per Ton	Value Per Ton	Ounces Per Ton	Value Per Ton	Per Cent.	Value Per Ton	Per Cent.	Value Per Ton	
# 011	0.36	\$		\$		\$		\$	\$

*Specimen of Heavy Arsenic
sulphides - Earl Brett
Chilliwack*

Gold calculated at \$..... per ounce.

Silver calculated at..... cents per ounce.

Calculated at..... cents per lb.

Calculated at..... cents per lb.

Calculated at..... cents per lb.

NOTE—Pulps of Samples retained 2 months from date of Receipt.
Rejects 1 week unless otherwise instructed.

J. R. Williams
Provincial Assayer.

J. R. WILLIAMS & SON LTD.

PROVINCIAL ASSAYERS

580 NELSON STREET

per D. Cannon

VANCOUVER 2, B. C., October 8th 1953.

RESULTS of Assays made on samples of ore submitted by: Messrs. Berens River Mines Ltd.

MARK	Gold Ozs.p/t	Silver Ozs.p/t			
No. 1.	0.01	0.48	Silver Standard.	1.2'	
2.	0.12	1.00	Schraeder	1.7'	
3.	0.03	0.10	Fenton	2.5'	
4.	0.58	0.35	Grant	2'	Most westerly trench.
5.	0.04	0.25	Red Bird	3.5'	Most easterly sample
6.	0.02	0.10	" "	4.7'	Wall rock adjoining # 5
7.	0.44	0.30	" "	3.4'	
8.	0.03	0.10	" "	2.0	Adjoining # 7
9.	0.72	0.80	Grant	3.6'	last trench push in.
10.	0.02	0.10	"	2.9'	Wall rock adj # 9 to north
11.	0.04	0.15	"	2.0'	" " " # 9 to south
12.	0.03	1.35	Sugar Bowl	6.0'	West side of vein
13.	0.02	0.40	" "	2.0'	Vein
14.	0.06	0.10	" "	3.0'	East side of vein
15.	0.06	0.20	# 13 vein	3.0'	

Assays made by

William

CERTIFICATE OF ASSAY

File #125221/223

J. R. WILLIAMS & SON LTD.

PROVINCIAL ASSAYERS AND CHEMISTS

Office and Laboratory:

580 Nelson Street, Vancouver 2, B. C.

I **Hereby Certify** that the following are the results of assays made by me upon samples of ORE herein described and received from Messrs. Empire Valley Mines, Sept. 19, 1955.

MARKED	GOLD		SILVER		Copper		GROSS TOTAL VALUE		
	Ounces Per Ton	Value Per Ton	Ounces Per Ton	Value Per Ton	Per Cent.	Value Per Ton	Per Cent.	Value Per Ton	(2000 lbs.) Per Ton
#1 - 105' R-4	0.04	\$	0.70	\$					
#2	0.02		0.40						
#3	0.16	\$	6.35	\$	3.50	36.80			41.80

Gold calculated at \$ _____ per ounce.

Silver calculated at _____ cents per ounce.

Calculated at _____ cents per lb.

Calculated at _____ cents per lb.

Calculated at _____ cents per lb.

NOTE—Pulps of Samples retained 2 months from date of Receipt.
Rejects 1 week unless otherwise instructed.

J. R. Williams
Provincial Assayer.

CERTIFICATE OF ASSAY

File #110544/551

J. R. WILLIAMS & SON LTD.

PROVINCIAL ASSAYERS AND CHEMISTS

Office and Laboratory:

580 Nelson Street, Vancouver 2, B. C.

I Hereby Certify that the following are the results of assays made by me upon samples of ORE herein described and received from M. W.E. Brett, Esq. November 27th, 1952.

MARKED	GOLD		SILVER		Per Cent.	Value Per Ton	Per Cent.	Value Per Ton	GROSS TOTAL VALUE (2000 lbs.) Per Ton
	Ounces Per Ton	Value Per Ton	Ounces Per Ton	Value Per Ton					
Red Bird - 4' wide	0.52	\$ 18.20		\$		\$		\$	
Per Red Bird - wide	0.055	1.92							
Ant Vein - 24' wide	0.055	1.92							
Carbon Vein - 3' wide	1.68	58.80							
Gar Bowl - 10' wide	0.13	6.30							
Sample #2 of Sugar	1.76	61.60							
- A. Vein 2' wide	1.02	35.70							
- 2nd Assay, loss 3'	2.12	74.20							

Gold calculated at \$ 35.00 per ounce.

Silver calculated at _____ cents per ounce.

Calculated at _____ cents per lb.

Calculated at _____ cents per lb.

Calculated at _____ cents per lb.

NOTE—Pulps of Samples retained 2 months from date of Receipt.
Rejects 1 week unless otherwise instructed.

J. R. Williams
Provincial Assayer.

Green

Boria Cr.

Hill in bottom


Porcupine

Cr.

CABIA

21304	21307	21308	21309
ARC	ARC	ARC	ARC
70	71	72	

30252A	30252B		
ARC	ARC		
37	35		
2255A	30253A	30227A	30228A
ARC	ARC	ARC	ARC
59	50	29	
30253B	30225A	30226A	
ARC	ARC	ARC	
L 7871	L 7872	28	27
		ARC	
L 7873	L 7874	22	23
		ARC	
L 7875	L 7876	21	
		ARC	
L 7877	L 7878	20	
		ARC	
L 7879	L 7880	19	
		ARC	
L 7881	L 7882	18	
		ARC	
L 7883	L 7884	17	
		ARC	
L 7885	L 7886	16	
		ARC	
L 7887	L 7888	15	
		ARC	
L 7889	L 7890	14	
		ARC	
L 7891	L 7892	13	
		ARC	
L 7893	L 7894	12	
		ARC	
L 7895	L 7896	11	
		ARC	
L 7897	L 7898	10	
		ARC	
L 7899	L 7900	9	
		ARC	
L 7901	L 7902	8	
		ARC	
L 7903	L 7904	7	
		ARC	
L 7905	L 7906	6	
		ARC	
L 7907	L 7908	5	
		ARC	
L 7909	L 7910	4	
		ARC	
L 7911	L 7912	3	
		ARC	
L 7913	L 7914	2	
		ARC	
L 7915	L 7916	1	
		ARC	



787E	787G
C	C
787H	787I
C	C

21357G	MINE
21356G	MINE

787F
C
787J
C

2101D	2101E
ARC	ARC
11	12
2102D	2102E
ARC	ARC
3	4
2103D	2103E
ARC	ARC
5	6
2104D	2104E
ARC	ARC
7	8
2105D	2105E
ARC	ARC
9	10
2106D	2106E
ARC	ARC
11	12

122° 30' CLINTON MINING DIVISION

TO SOUTH SEE MAP 920/1W

For up-to-date information on claims in any area you should apply to the Mining Recorder for the Mining Division concerned

DEPARTMENT OF MINES AND PETROLEUM VICTORIA, B.C.

MINERAL CLAIM MAP 920/8