

WEIGHTED AVERAGE - ALL SAMPLES SAWN ON VERTICAL PROJECTION # 1 VEM - (WBM - JULY 1961)

A) SILVER & ANTIMONY - SURFACE

(1) O'GRADY - IGNORE FOR PRESENT.

(2) PIONEER - IGNORE IN FAVOUR OF (3) below.

(3) RUTHERFORD.

(a) - 3.8' @ 1.23 Ag + 3.8' @ 8.45 Sb.

(b) - 4.4' @ 4.31 Ag + 4.4' @ 9.89 Sb.

WxG.      WxG.  
Ag.      Sb.

4.674      32.110

181.764      43.516.

(4) PIONEER.

(a) - 5.1 @ 12.92 Ag + 5.1 @ 2.55 Sb.

65.892      13.005

(b) - 3.4 @ 13.40 Ag + 3.4' @ 1.30 Sb.

45.560      4.420

16.7

16.7

297.890      93.051

Avg 4.2' @ 17.84 Ag + 4.2' @ 5.57 Sb. Total of 230' length.

B) 6500 ADIT - BACON.

SILVER

ANTIMONY

1.9' @ 16.60 Ag = 31.54

1.9 @ 3.34 Sb = 6.346.

35 3.0 @ 9.23      27.69

3.0 @ 0.45 Sb      1.350.

20 3.4 @ 1.59      5.41

3.4 @ 5.36 Sb.      18.224.

45 2.5' @ 2.51      6.28.

2.5 @ 1.78      4.450.

35 2.2 @ 4.87      10.71

2.2 @ 0.41.      0.902

~~1.4 @ 0.12      0.17~~

~~1.4 @ 0.17~~

35 2.2 @ 3.35      7.37

2.2 @ 0.23      0.506.

80. 3.8 @ 3.74      14.21.

3.8 @ 1.54      5.852

~~1.3 @ 0.82~~

~~1.3 @ 0.10~~

34 3.4 @ 7.30      24.82

3.4 @ 0.32      1.088.

2.9 @ 12.04      34.92

2.9 @ 0.39.      1.131.

25.3      162.95

Avg. 2.8' @ 6.44 Ag. + 2.8' @ 1.58 Sb 39.849

Total of 284' length.