



No. 2 TUNNEL
Ei. 6192'

No. 1 TUNNEL
Ei. 6250'

No. 3 TUNNEL

Schelte here!

SURFACE SAMPLES				
SAMPLE NO	WIDTH INCHES	GOLD OZ PER TON	U ₃ O ₈ PER CENT	COBALT PER CENT
1	24	1.04	0.0055	3.6
2	30	0.41	0.0300	7.3
3	72	0.52	0.0220	5.1
4	84	0.32	0.0025	5.1
5	24	0.24	0.0200	0.3
6	25	0.27	0.0035	4.4
7	24	0.35	0.0200	3.9
8	18	1.60	0.0070	4.3
9	60	0.27	0.0100	0.9
10	96	0.27	0.0030	0.8
UNDERGROUND SAMPLES				
11	60	0.22	0.0100	0.3
12	24	0.02	0.0140	0.5
13	13	1.24	0.0080	6.0
14	36	0.53	0.0380	3.5
15	12	0.61	0.0050	3.7
16	33	0.62	0.0220	4.1
17	36	0.51	0.0320	2.5
18	39	0.15	0.2100	1.5
19	36	1.09	0.0260	6.6
20	36	0.23	1.0100	1.3
21	38	0.48	1.5400	2.2
22	40	0.38	0.2400	3.0
23	53	0.84	0.6100	4.0
24	49	0.01	0.2300	0.7
25	52	0.51	0.2100	3.5
26	34	1.21	1.0400	5.3
27	23	1.78	0.5300	7.2
28	60	0.76	1.8900	5.4
29	39	1.58	0.0095	3.2
30	39	1.82	0.0100	1.3
31	38	0.58	0.0030	0.6
32	24	0.83	0.0030	0.5
33	48	1.00	0.0030	1.4
34	33	1.26	0.0025	1.1
35	26	1.40	0.0015	1.2
36	12	0.34	0.0020	0.4
37	60	0.12	0.0040	2.0
38	80	2.21	0.8700	3.1
39	72	2.14	0.0180	4.4
40	46	0.86	N.A.	3.69
41	72	1.04	N.A.	0.72
42	72	0.24	N.A.	0.40
43	60	0.06	N.A.	0.29
44	22	0.58	0.50	1.32
45	108	0.30	0.03	0.40
46	48	1.25	0.073	2.04
47	74	1.75	0.062	2.60
48	96	2.40	0.118	3.30
49	84	1.08	0.002	0.52



LEGEND

- No. 1 Level Ore (Probable)
- No. 2 Level Ore (Probable)
- No. 3 Level Ore (Probable)

After :
B.C. DEPARTMENT OF MINES
J.S. STEVENSON, 1948

T. R. TOUGH & ASSOCIATES LTD.
MAJOR RESOURCES LTD.
NORTHERN GEM PROPERTY
LILLOOET M.D.
**COMPOSITE OF LEVELS
ASSAY PLAN**

92J/15 675571

