


DH 1, 2, 3 - Taseko Prop, New Pyramid.

DH-1



DH 1 - 5'

DH 2 - 6'

DH 3 - 4'

DH 1. 0-2' Mod by ^{stalline qtz} qtz - minor dk gray sil patches trending || core length. Coarse pyrite dod up to $\frac{1}{4}$ and some fg ms py. Occ. coarse blobs of cpy up to $\frac{1}{2}$ " Prop. av. 30% pyrite 3% cpy over length.

2-3.3 less qtz some dk fg chl incl. Very coarse heavy py up to 50% py. 15% cpy

3.3-5.0 Similar to 1st sect Pyrite more evenly dist.

DH#2 - 45'

0-2.0 Very heavy sulph. sect. - up to 70% evenly distrib. - minor ^{cryst white} qtz in breccia veinlets. Est 25% cpy in very coarse silky cpy

2.0-4.0 DK grey quartz with strong br and sulph. reheating. 30% pyrite - heavily dissem. and in stringers. Some moderate banding || core. 5% coarse cpy in erratic.

4.0-6.0 As above but somewhat heavier coarse white quartz.

DH#3 - 0-0.9 Coarse xtal qtz with fine dk grey py. bands. - 10% pyrite.

Wall rock

0.8-3.0 - 50% sulph as coarse xt. Sulph. 10% cpy as very coarse blebs mainly volc. chl. material. Some veining obviously parallel core.

3.0-4.0 Similar to above but less sulphides - 25%.

Prelim Dec 29/75

		Au	Ag
528	.11	1.1	10.3
	5.50	3.6	13.4
	.18	1.7	2.9
31	9.95	over #50g	very high
	.96	3.5	5.8
	.97	3.8	3.6
34	.49	3.95	7.8
	1.70	2.99	.2
36	.06	.256	3.7

NPY Vic 75-1,2,3.

Dec 29 1975

New Pyramid - Taseko
 Assays as received by phone from GTL
 4:20 PM Dec 29

Interval	Length	Sample No	LA			LA		
			Cu	Au	Ag	Cu	Au	Ag
0-2.0	2.0	528	.11	1.093	10.28	.22	2.186	20.56
2.0-3.3	1.3	529	5.50	3.642	13.38	7.15	4.735	17.39
3.3-5.0	1.7	530	0.18	1.843	3.10	.31	3.133	5.27
						<u>7.68</u>	<u>10.054</u>	<u>43.22</u>

$$\begin{aligned}
 \text{Cu} &= \frac{7.68}{5.0} = 1.54\% \\
 \text{Au} &= \frac{10.054}{5.0} = 2.01\% \text{ oz} \\
 \text{Ag} &= \frac{43.22}{5.0} = 8.64 \text{ oz}
 \end{aligned}
 \left. \vphantom{\begin{aligned} \text{Cu} \\ \text{Au} \\ \text{Ag} \end{aligned}} \right\} \text{over } 5.0$$

Hole 2

0-2.0	2.0	531	9.95	14.516	12.26
2.0-4.0	2.0	532	.96	3.526	5.75
4.0-6.0	2.0	533	.97	3.889	3.57
			<u>11.88</u>	<u>21.931</u>	<u>21.58</u>

$$\begin{aligned}
 \text{Cu} &= \frac{11.88}{3} = 3.96\% \quad \text{Au} = \frac{21.931}{3} = 7.31\% \text{ oz} \quad \text{Ag} = \frac{21.58}{3} = 7.19\% \text{ oz} \\
 & \hspace{15em} \text{over } 6.0
 \end{aligned}$$

Hole 3

0-0.8	0.8	534	.49	3.655	7.81	.392	2.924	6.248
0.8-3.0	2.2	535	1.70	3.312	4.08	3.74	7.286	8.976
3.0-4.0	1.0	536	.06	0.256	3.73	.06	.256	3.730
						<u>4.192</u>	<u>10.466</u>	<u>18.954</u>

$$\begin{aligned}
 \text{Cu} &= \frac{4.192}{4} = 1.05\% \\
 \text{Au} &= \frac{10.466}{4} = 2.62\% \text{ oz} \\
 \text{Ag} &= \frac{18.954}{4} = 4.74\% \text{ oz}
 \end{aligned}
 \left. \vphantom{\begin{aligned} \text{Cu} \\ \text{Au} \\ \text{Ag} \end{aligned}} \right\} \text{over } 4.0$$

Weighted averages phone to Carl 4:50 PM Dec 29/75



GENERAL TESTING LABORATORIES

DIVISION SUPERINTENDENCE COMPANY (CANADA) LTD.

1001 EAST PENDER ST. VANCOUVER, B.C. CANADA V6A 1W2
 PHONE (604) 254-1647 TELEX 04-507514 CABLE SUPERVISE

TO: **NEW PYRAMID GOLD MINES**
 Suite 300
 890 West Pender Street
 Vancouver, B.C.

CERTIFICATE OF ASSAY

No: **7512-225LB** DATE: **Dec. 30/75**

We hereby certify that the following are the results of assays on: **Drill Core**

MARKED	GOLD	SILVER	Copper	XXX	XXX	XXX	XXX	XXX
	OZ/ST GR/MT	OZ/ST GR/MT	Cu (%)					
0531	14.516	12.26	9.95					
0532	3.526	5.75	0.96					
0533	3.889	3.57	0.97					
0534	3.655	7.81	0.49					
0535	3.312	4.08	1.70					
0536	0.256	3.73	0.06					

cc. Mr. R.D. Westewelt, R. Eng ✓

NOT REJECTS RETAINED ONE MONTH. PULPS RETAINED THREE MONTHS. ON REQUEST PULPS AND REJECTS WILL BE STORED FOR A MAXIMUM OF ONE YEAR.

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSION OR EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

(Handwritten signature)

PROVINCIAL ASSAYER

L. WONG

COPY

Analytical and Consulting Chemists, Bulk Cargo Specialists, Surveyors, Inspectors, Samplers, Weighers

MEMBER: American Society For Testing Materials • The American Oil Chemists' Society • Canadian Testing Association
 REFEREE AND/OR OFFICIAL CHEMISTS FOR: Vancouver Merchants Exchange • National Institute Of Oilseed Products • The American Oil Chemists' Society
 OFFICIAL WEIGHMASTERS FOR: Vancouver Board Of Trade • Vancouver Merchants Exchange



GENERAL TESTING LABORATORIES

DIVISION SUPERINTENDENCE COMPANY (CANADA) LTD.

1001 EAST PENDER ST., VANCOUVER, B.C., CANADA, V6A 1W2
 PHONE (604) 254-1647 TELEX 04-507514 CABLE SUPERVISE

TO:
NEW PYRAMID GOLD MINES
 Suite 300
 890 West Pender Street
 Vancouver, B.C.

CERTIFICATE OF ASSAY

No.: 7512-2254A DATE: Dec. 29/75

We hereby certify that the following are the results of assays on: **Drill Core**

MARKED	GOLD	SILVER	Copper	XXX	XXX	XXX	XXX	XXX
	OZ/ST GR/MT	OZ/ST GR/MT	Cu (%)					
0528	1.093	10.28	0.11					
0529	3.642	13.38	5.50					
0530	1.843	3.10	0.18					

cc. Mr. R.D. Westewelt, P. Eng

NOTE: REJECTS RETAINED ONE MONTH. PULPS RETAINED THREE MONTHS. ON REQUEST PULPS AND REJECTS WILL BE STORED FOR A MAXIMUM OF ONE YEAR.

REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSION OR EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.


L. WONG PROVINCIAL ASSAYER

Analytical and Consulting Chemists, Bulk Cargo Specialists, Surveyors, Inspectors, Samplers, Weighers

MEMBER: American Society For Testing Materials • The American Oil Chemists' Society • Canadian Testing Association
 REFEREE AND OR OFFICIAL CHEMISTS FOR: Vancouver Merchants Exchange • National Institute Of Oilseed Products • The American Oil Chemists' Society
 OFFICIAL WEIGHMASTERS FOR: Vancouver Board Of Trade • Vancouver Merchants Exchange

	Cu	Au Ag	Ag
2.0 28	.11	1.093	10.28
1.3 29	5.50	3.642	13.38
1.7 30	0.18	1.843	5.56 3.10
2.0 31	9.95	14.516	12.26
2.0 32	.96	3.526	5.75
2.0 33	.97	3.889	3.57
0.8 34	.49	3.655	7.81
2.2 35	1.70	3.312	4.08
1.0 36	.06	0.256	3.73

Rec'd by phone from
Wong 4.20 PM
Dec 29/75



GENERAL TESTING LABORATORY

DIVISION SUPERINTENDENCE COMPANY (CANADA) LTD

1001 EAST PENDER ST., VANCOUVER, B.C., CANADA V6A 5S4
 PHONE (604) 254-1647 TELEX 04-507514 CABLE SUPER 32

TO:
Mr. Ray Saadien
 c/o **Canarim Investment Corp. Ltd**
 424 Burrard Street
 Vancouver, B.C.

CERTIFICATE OF ASSAY

No.: **7509-0551** DATE: **Sept. 10/75**

We hereby certify that the following are the results of assays on:

Ore

MARKED	GOLD	SILVER	Lead	Zinc	Copper	XXXXXXXXXXXXXXXXXXXX		
	OZ/ST GR/MT	OZ/ST GR/MT	Pb (%)	Zn (%)	Cu (%)			
Vic # 1	1.430	7.52	0.01	0.06	6.78	<i>grab sample</i>		
Vic #2	2.958	16.52	0.02	0.06	1.55	" "		
Vic #3	2.408	2.14	0.01	0.02	2.27	<i>channel sample across 36"</i>		
LW/wk								

NOTE: REJECTS RETAINED ONE MONTH. PULPS RETAINED THREE MONTHS. ON REQUEST PULPS AND REJECTS WILL BE STORED FOR A MAXIMUM OF ONE YEAR.

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSION OR EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

L. WONG PROVINCIAL ASSAY

COPY

Analytical and Consulting Chemists, Bulk Cargo Specialists, Surveyors, Inspectors, Samplers, We

MEMBER: American Society For Testing Materials • The American Oil Chemists' Society • Canadian Testing Association
 REFEREE AND/OR OFFICIAL CHEMISTS FOR: Vancouver Merchants Exchange • National Institute Of Oilseed Products • The American Oil Chemist
 OFFICIAL WEIGHMASTERS FOR: Vancouver Board Of Trade • Vancouver Merchants



GENERAL TESTING LABORATORIES

DIVISION SUPERINTENDENCE COMPANY (CANADA) LTD.

1001 EAST PENDER ST., VANCOUVER, B.C., CANADA, V6A 1W2
 PHONE (604) 254-1647 TELEX 04-507514 CABLE SUPERVISE

TO:
L. J. MANNING & ASSOCIATES
 #310 - 890 West Pender Street
 Vancouver, B.C.

CERTIFICATE OF ASSAY

No.: 7410-0250 DATE: Oct. 9, 1974

We hereby certify that the following are the results of assays on: **ORE**

MARKED	GOLD	SILVER	COPPER					
	OZ/ST GR/MT	OZ/ST GR/MT	(Cu%)					
"VIC GROUP"								
81	1.04	1.15	0.05	NO VISIBLE Sulphides				
82	0.069	0.03	0.01	Barred R _x /S _{id}				
83	0.147	0.08	0.01	NO VISIBLE				

✓ 1 cc: Mr. Carl Zuber, 5-309 2nd Ave. N., Williams Lake, B.C.

LW/kl

NOTE: REJECTS RETAINED ONE MONTH. PULPS RETAINED THREE MONTHS. ON REQUEST PULPS AND REJECTS WILL BE STORED FOR A MAXIMUM OF ONE YEAR.

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSION OR EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

L. Wong

PROVINCIAL ASSAYER


Analytical and Consulting Chemists, Bulk Cargo Specialists, Surveyors, Inspectors, Samplers, Weighers

MEMBER American Society For Testing Materials • The American Oil Chemists' Society • Canadian Testing Association
 REFEREE AND OR OFFICIAL CHEMISTS FOR: Vancouver Merchants Exchange • National Institute Of Oilseed Products • The American Oil Chemists' Society
 OFFICIAL WEIGHMASTERS FOR: Vancouver Board Of Trade • Vancouver Merchants Exchange

COPY

Assays Rec'd Aug 27/74 4:00pm GENERAL TESTING PAT
HAR

	Au	Ag	Cu	
b1	.269	.24	.13	8" Vein - 6085' EL. Vol. Breccia Qtz, Py, Gpy
b2	.241	.55	.12	12" - Center of 27" width 7' to R. of #61 6085' EL. 5-6% Sulphides Qtz. w/ Py, Gpy
b3	2.124 3.54	2.68	(7%)	30" Vein Material - 100' above v. Alt 5810' 12% Sulphides Bottom of gully Qtz, Vol, Py, Gpy
b4	5.35	5.17	2.9%	6" W x 24" Long Selected Sample Massive Sulphides to 70% 10' below #63 Py, Gpy R. Wall of gully
b5	2.86	8.10	5%	6" W x 36" Long Selected Sample Massive Sulphides to 70% 10' below #64 Py, Gpy, R. Wall of gully





Sample Plan
Vic Claims
Taseko Lake
1" = 100'

August 26, 1974
GMR Johnston

Sample No	Description	Sample length	Oz Au/ton	Oz Ag/ton	% Cu
1	weakly sheared volcanics minor pyrite - foot wall	24"	0.001	0.07	0.01
2	Quartz vein 10-20% Pyrite some chalcopyrite - 40 feet long vein	27"	0.362	0.34	0.13
3	Shear Zone bleached 1% pyrite	96"	0.001	0.04	0.05
4	Quartz vein 20% pyrite 1/2% chalcopyrite 25 feet long vein	6"	0.335	0.31	0.09
5	Hanging wall Volcanics minor pyrite	24"	0.002	0.06	0.11
6	Quartz vein - 30 feet long vein 10-20% pyrite minor chalcopyrite	30"	0.001	0.02	0.01
7	Quartz vein - 20 feet long vein 5-15% pyrite	12"	0.008	0.01	0.01
8	foot wall Volcanics	24"	0.109	0.02	0.03
9	Quartz vein - 20 feet long vein 5-30% pyrite 1-2% chalcopyrite	16"	1.855	5.24	0.10
10	bleached and silicified shear zone containing two 4" Quartz veinlets sampled full width of shear 1-5% pyrite 1/2% chalcopyrite	45"	1.142	1.16	3.38
11	bleached shear zone in back of adit 2% Pyrite	36"	0.014	0.03	0.03
12	Quartz vein - 30 feet From end of adit 10% pyrite lies beneath sample 9 - 35 feet long vein	12"	0.280	0.52	0.57

August 26, 1974

W. M. Roberts



All
Assay Plan
Vic Claims
Taseko Lake

1" = 20'

August 26, 1974
L. M. Kellogg