

681409  
Bednesti  
Lake  
936/14

ACME ANALYTICAL LABORATORIES LTD. 852 E. HASTINGS ST. VANCOUVER B.C. V6A 1R6 PHONE 253-3158 DATA LINE 251-1011

GEOCHEMICAL ICP ANALYSIS

.500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.  
THIS LEACH IS PARTIAL FOR MN.FE.CA.P.CR.MG.BA.TI.B.AL.NA.K.W.SI.ZR.CE.SN.Y.NB AND TA. AU DETECTION LIMIT BY ICP IS 3 PPM.  
- SAMPLE TYPE: ROCK CHIPS AU\* ANALYSIS BY AA FROM 10 GRAM SAMPLE. HG ANALYSIS BY FLAMELESS AA. BA\* NAOH FUSION. EDTA LEACH AND ICP ANALYSIS.

DATE RECEIVED: MAY 16 1985 DATE REPORT MAILED: *May 28/85* ASSAYER: *T. Saundry* DEAN TOYE OR TOM SAUNDRY. CERTIFIED B.C. ASSAYER

LARAMIDE RESOURCES FILE # 85-0617

PAGE 1

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au†	Hg	Ba†
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm	%	ppm	%	ppm	%	%	%	ppm	ppb	ppb	ppm	
3506	1	65	4	74	.1	44	23	1638	5.97	51	7	ND	4	112	1	2	2	39	6.22	.08	3	30	1.92	27	.01	10	.40	.03	.06	1	52	130	72
3507	5	220	19	399	.3	87	19	542	6.71	28	5	ND	3	15	5	3	2	7	.14	.07	6	7	.07	59	.01	31	.37	.01	.06	1	26	230	264
3508	1	53	8	153	.1	29	29	1337	10.40	2	5	ND	4	102	1	2	2	137	4.56	.17	7	40	2.10	43	.01	28	2.09	.02	.11	1	7	140	83
3509	1	110	5	56	.1	43	28	1214	5.62	104	5	ND	5	190	1	2	2	31	8.90	.06	3	45	2.79	39	.01	12	.92	.02	.15	1	75	50	193

ACME ANALYTICAL LABORATORIES LTD.

852 E. HASTINGS ST. VANCOUVER B.C. V6A 1R6

PHONE 253-3158

DATA LINE 251-1011

## GEOCHEMICAL ICP ANALYSIS

.500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.

THIS LEACH IS PARTIAL FOR MN, FE, CA, P, CR, MG, BA, TI, B, AL, NA, K, W, SI, ZR, CE, SN, Y, NB AND TA. AU DETECTION LIMIT BY ICP IS 3 PPM.

- SAMPLE TYPE: ROCK CHIPS AU\* ANALYSIS BY AA FROM 10 GRAM SAMPLE. HG ANALYSIS BY FLAMELESS AA. BA\* NAOH FUSION. EDTA LEACH AND ICP ANALYSIS.

DATE RECEIVED: MAY 16 1985 DATE REPORT MAILED: *May 20/85* ASSAYER: *T. Saundry* DEAN TOYE OR TOM SAUNDRY. CERTIFIED B.C. ASSAYER

LARAMIDE RESOURCES FILE # 85-0617

PAGE 1

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Aut ppb	Hg ppb	Ba# ppm
3506	1	65	4	74	.1	44	23	1638	5.97	51	7	ND	4	112	1	2	2	39	6.22	.08	3	30	1.92	27	.01	10	.40	.03	.06	1	52	130	72
3507	5	220	19	399	.3	87	19	542	6.71	28	5	ND	3	15	5	3	2	7	.14	.07	6	7	.07	59	.01	31	.37	.01	.06	1	26	230	264
3508	1	53	8	153	.1	29	29	1337	10.40	2	5	ND	4	102	1	2	2	137	4.56	.17	7	40	2.10	43	.01	28	2.09	.02	.11	1	7	140	83
3509	1	110	5	56	.1	43	28	1214	5.62	104	5	ND	5	190	1	2	2	31	8.90	.06	3	45	2.79	39	.01	12	.92	.02	.15	1	75	50	193

ACME ANALYTICAL LABORATORIES LTD.

852 E. HASTINGS ST. VANCOUVER B.C. V6A 1R6

PHONE 253-3158

DATA LINE 251-1011

**GEOCHEMICAL ICP ANALYSIS**

.500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.

THIS LEACH IS PARTIAL FOR MN.FE.CA.P.CR.MG.BA.TI.B.AL.NA.K.W.SI.ZR.CE.SN.Y.NB AND TA. AU DETECTION LIMIT BY ICP IS 3 PPM.

- SAMPLE TYPE: ROCK CHIPS AU\* ANALYSIS BY AA FROM 10 GRAM SAMPLE. UG ANALYSIS BY FLAMELESS AA. BA\* NAOH FUSION. EDTA LEACH AND ICP ANALYSIS.

DATE RECEIVED: MAY 16 1985

DATE REPORT MAILED: *May 28/85*

ASSAYER: *T. Saundry* DEAN TOYE OR TOM SAUNDRY. CERTIFIED B.C. ASSAYER

LARAMIDE RESOURCES FILE # 85-0617

PAGE 1

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm	Au† ppb	Hg ppb	Ba† ppm
3506	1	65	4	74	.1	44	23	1638	5.97	51	7	ND	4	112	1	2	2	39	6.22	.08	3	30	1.92	27	.01	10	.40	.03	.06	1	52	130	72
3507	5	220	19	399	.3	87	19	542	6.71	28	5	ND	3	15	5	3	2	7	.14	.07	6	7	.07	59	.01	31	.37	.01	.06	1	26	230	264
3508	1	53	8	153	.1	29	29	1337	10.40	2	5	ND	4	102	1	2	2	137	4.56	.17	7	40	2.10	43	.01	28	2.09	.02	.11	1	7	140	83
3509	1	110	5	56	.1	43	28	1214	5.62	104	5	ND	5	190	1	2	2	31	8.90	.06	3	45	2.79	39	.01	12	.92	.02	.15	1	75	50	193