


PLAN 35-51 TO ACCOMPANY
A SUMMARY REPORT ON THE
J & L MINERAL OPTION
LEAD-ZINC-GOLD-SILVER PROSPECT
BRITISH COLUMBIA
NTS: 82M/8E

R. Pegg, P. Eng
Geological Engineer

B. Grant

For: Selco - A division of BP Exploration Canada Limited
Vancouver, B.C.

March, 1984



Sample No.	Cu	Pb	Zn	As	Au	g/t	g/t	m
30963	0.01	1.10	14.40	0.013	54.8	0.7		0.24
30964	0.01	0.02	0.15	0.173	3.9	0.2		0.21
30965	0.01	0.01	0.04	0.081	2.6	0.1		0.29
30966	0.01	0.07	0.06	1.360	5.2	1.0		0.29
30967	0.01	0.06	0.04	1.010	6.2	0.6		0.14
30968	0.01	0.04	0.01	5.050	11.2	1.1		0.36
30969	0.01	0.01	0.01	0.055	0.3	0.1		0.15
30970	0.01	0.03	0.01	0.418	3.9	0.2		0.16
30971	0.01	0.06	0.01	0.342	4.8	0.7		0.26

Sample No.	Cu	Pb	Zn	As	Au	g/t	g/t	m
31007	0.03	3.29	7.94	0.999	78.8	1.9	0.20	
31008	0.02	0.87	0.84	0.972	22.6	0.5	0.50	
31009	0.03	0.12	0.03	8.350	13.0	2.2	0.22	
31010	0.01	0.06	0.10	0.837	2.7	0.3	1.00	
31011	0.09	12.20	18.98	0.888	310.5	4.0	0.10	
31012	0.01	0.17	0.23	0.086	2.1	0.1	0.57	

Sample No.	Cu	Pb	Zn	As	Au	g/t	g/t	m
30990	0.01	2.90	1.72	2.680	64.1	5.0	0.35	
30991	0.01	0.18	0.22	1.360	8.2	1.2	0.77	
30992	0.01	0.06	0.01	15.200	15.1	3.8	0.12	
30993	0.01	0.02	0.01	0.168	2.1	0.1	0.38	
30994	0.01	0.12	0.38	1.260	7.0	1.6	0.20	
30995	0.01	0.28	0.96	0.242	10.3	0.2	0.31	
30996	0.24	3.32	0.86	10.500	199.8	12.8	0.11	

Sample No.	Cu	Pb	Zn	As	Au	g/t	g/t	m
31013	0.01	0.02	0.02	1.360	3.4	0.1	0.29	
31012	0.13	1.78	4.26	6.180	52.8	11.2	0.07	
31013	0.01	0.05	0.07	1.360	2.7	0.3	0.11	
31014	0.01	0.09	0.03	3.990	10.6	1.8	0.55	
31015	0.01	0.66	0.69	0.685	19.9	0.7	0.91	
31016	0.20	4.34	16.30	0.202	330.8	1.6	0.09	
31017	0.01	0.56	0.43	0.014	14.4	0.2	0.46	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31067	0.01	0.01	0.271	4.8	0.1	0.57	
31068	0.16	0.21	4.640	6.5	4.1	0.15	
31069	0.06	0.05	0.123	1.4	0.2	0.74	
31070	2.34	11.90	4.170	68.9	7.2	0.26	
31071	0.74	1.41	0.313	19.9	0.6	0.10	
31072	7.07	9.03	0.618	109.1	1.4	0.09	
31073	0.08	0.09	0.009	2.7	0.1	0.21	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31111	1.66	5.40	8.450	92.2	17.1	0.28	
31112	0.06	0.13	0.219	3.4	0.3	0.60	
31113	0.01	0.02	0.039	2.0	0.1	1.00	
31114	2.90	4.11	2.600	98.7	5.8	0.53	
31115	0.10	0.13	0.231	5.5	0.2	0.29	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31500	0.17	0.13	0.643	14.4	1.3	0.70	
31501	0.04	0.03	0.239	3.4	0.3	0.87	
31502	0.04	0.04	0.307	3.4	0.3	0.30	
31503	0.01	0.01	0.010	3.1	0.1	0.98	
31504	0.03	0.07	0.032	2.7	0.1	0.68	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31136	0.13	0.03	0.224	11.6	0.7	0.80	
31137	0.04	1.43	0.572	4.1	0.8	0.04	
31138	0.06	0.12	0.809	3.4	1.2	0.62	
31139	0.01	0.01	0.014	3.4	0.1	0.86	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31883	0.01	0.01	0.002	1.4	0.1	1.20	
31885	0.01	0.01	0.005	4.1	0.1	0.90	
31887	0.01	0.02	0.002	2.4	0.1	0.60	
31889	0.01	0.01	0.001	1.4	0.1	0.70	
31891	0.01	0.01	0.002	1.0	0.1	0.40	
31893	0.04	0.01	0.009	5.5	0.1	1.10	
31895	0.01	0.01	0.015	3.4	0.1	1.00	
31897	0.78	1.26	0.109	31.2	0.2	0.10	
31899	0.14	0.09	1.290	2.7	1.2	0.40	
31901	1.78	5.40	0.195	32.9	0.2	0.80	
31903	0.52	3.28	0.005	11.7	0.2	1.30	
31905	0.10	0.08	0.502	5.1	0.2	0.90	
31907	1.02	11.70	12.000	103.8	22.2	0.26	
31909	0.33	0.40	0.945	13.6	0.9	0.60	
31911	3.56	7.94	17.100	134.0	14.8	0.56	
31913	0.11	0.04	1.150	3.1	1.3	0.90	
31915	0.13	3.15	8.090	9.9	10.6	0.70	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31160	1.72	0.13	0.960	145.0	17.9	0.20	
31149	0.17	0.01	0.170	7.5	0.7	0.20	
31150	0.59	0.01	0.066	14.4	0.1	0.87	
31151	0.02	0.01	0.000	2.1	0.1	0.40	
31152	0.01	0.01	0.020	2.7	0.1	0.25	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31162	0.97	1.64	1.190	33.9	0.9	0.36	
31163	0.34	0.17	0.299	30.2	0.3	0.44	
31164	0.81	0.38	0.772	21.9	0.7	0.37	
31165	0.69	0.04	0.208	220.6	2.1	0.20	
31166	0.21	0.07	0.887	17.5	1.0	0.64	
31167	0.44	6.52	7.990	13.7	12.0	0.15	
31168	0.47	21.70	0.113	6.8	0.1	0.38	
31169	0.01	0.20	0.019	2.7	0.1	0.23	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31205	0.06	0.01	0.362	5.9	0.3	0.67	
31206	7.14	12.00	6.570	162.5	10.8	0.36	
31207	1.30	0.46	0.152	36.1	0.2	0.24	
31208	2.34	1.43	2.980	207.0	4.1	0.70	
31209	1.37	1.20	2.650	160.6	2.9	0.34	
31210	2.68	4.23	9.450	203.1	7.4	0.04	
31211	0.13	0.18	0.014	5.2	1.2	0.10	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31244	0.43	0.43	1.180	16.2	1.0	0.68	
31245	1.08	1.05	17.000	115.7	34.2	0.57	
31246	0.57	0.37	2.270	15.4	3.1	0.18	
31247	5.80	16.30	2.870	274.3	4.7	0.89	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31260	1.84	1.04	25.400	457.8	0.8	0.19	
31261	0.24	0.09	10.400	24.1	4.3	0.36	
31262	0.21	0.03	8.600	26.5	1.6	0.27	
31263	0.05	0.02	6.490	10.9	1.1	0.29	
31264	1.78	2.40	11.000	33.1	20.1	0.27	
31265	3.50	10.30	12.200	285.1	12.0	0.55	
31266	3.14	4.79	5.210	221.1	12.3	0.24	
31267	0.19	0.64	2.190	9.4	1.6	0.41	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31229	0.08	0.06	0.318	6.2	0.2	0.34	
31230	6.17	3.15	2.450	234.7	4.6	0.89	
31231	12.80	13.50	0.930	259.8	2.1	0.34	
31232	1.03	4.26	7.700	34.9	12.3	0.31	
31233	16.70	9.93	4.280	598.1	6.6	0.21	
31234	2.56	1.72	3.330	148.2	4.0	0.20	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31248	0.43	0.43	1.180	16.2	1.0	0.68	
31249	1.08	1.05	17.000	115.7	34.2	0.57	
31250	0.57	0.37	2.270	15.4	3.1	0.18	
31251	5.80	16.30	2.870	274.3	4.7	0.89	


Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31252	0.06	0.01	0.362	5.9	0.3	0.67	
31253	7.14	12.00	6.570	162.5	10.8	0.36	
31254	1.30	0.46	0.152	36.1	0.2	0.24	
31255	2.34	1.43	2.980	207.0	4.1	0.70	
31256	1.37	1.20	2.650	160.6	2.9	0.34	
31257	2.68	4.23	9.450	203.1	7.4	0.04	
31258	0.13	0.18	0.014	5.2	1.2	0.10	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31259	0.43	0.43	1.180	16.2	1.0	0.68	
31260	1.08	1.05	17.000	115.7	34.2	0.57	
31261	0.57	0.37	2.270	15.4	3.1	0.18	
31262	5.80	16.30	2.870	274.3	4.7	0.89	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31263	0.08	0.06	0.318	6.2	0.2	0.34	
31264	6.17	3.15	2.450	234.7	4.6	0.89	
31265	12.80	13.50	0.930	259.8	2.1	0.34	
31266	1.03	4.26	7.700	34.9	12.3	0.31	
31267	16.70	9.93	4.280	598.1	6.6	0.21	
31268	2.56	1.72	3.330	148.2	4.0	0.20	

Sample No.	Pb	Zn	As	Au	g/t	g/t	m
31269	0.43	0.43	1.180	16.2	1.0	0.68	
31270	1.08	1.05	17.000	115.7	34.2	0.57	
31271	0.57	0.37	2.270	15.4	3.1	0.18	
31272	5.80	16.30	2.870	274.3	4.7	0.89	

Sample No.	Pb	Zn	As
------------	----	----	----



LEGEND


○ SURVEY STATION

○ CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)

WEIGHTED AVERAGE GRADE ACROSS A HORIZONTAL DISTANCE

m HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION



SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 7C
ASSAYS (MIDDLE SECTION)

DRAWN BY T. O. GARROW	DATE SEPT 20, 1983	N.T.S.	PLAN
TRACED BY J. S.	DATE OCT. 1983	82 M/BE	36



LEGEND


○ SURVEY STATION

○ CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)

— WEIGHTED AVERAGE

— HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.




SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 7C
ASSAYS (LOWER SECTION)

DRAWN BY T. O. GARROW	DATE SEPT 20, 1983	N.T.S.	PLAN 37
TRACED BY J. S.	DATE OCT. 1983	82 M / BE	

MINE GRID NORTH



Ag	Au	Cu	g/t	g/t	g/t	g/t	g/t
<0.01	0.01	0.010	0.7	<0.1	0.70	31646	
<0.01	<0.01	0.001	1.4	<0.1	0.55	31645	
<0.01	<0.01	0.001	1.4	<0.1	0.55	31644	
<0.01	0.01	0.003	1.4	<0.1	1.00	31643	
<0.01	<0.01	0.001	2.1	<0.1	0.20	31642	
<0.01	<0.01	0.001	1.4	<0.1	0.80	31641	
<0.01	<0.01	0.001	1.4	<0.1	1.10	31640	
<0.01	<0.01	<0.001	1.4	<0.1	0.30	31639	
<0.01	0.01	0.001	0.7	<0.1	0.25	31638	
<0.01	<0.01	0.003	1.4	<0.1	0.50	31637	
<0.01	<0.01	0.001	0.7	<0.1	0.80	31636	
<0.01	<0.01	0.001	0.7	<0.1	0.40	31635	
<0.01	<0.01	0.001	1.4	<0.1	0.30	31634	
<0.01	<0.01	0.001	0.7	<0.1	0.60	31633	
<0.02	<0.01	0.001	0.7	<0.1	0.80	31632	
<0.01	<0.01	0.001	2.1	<0.1	0.35	31631	
<0.01	<0.01	0.001	0.3	<0.1	0.45	31630	
<0.01	<0.01	0.001	0.7	<0.1	0.90	31629	
<0.01	<0.01	0.001	0.7	<0.1	0.45	31628	
<0.01	<0.01	0.002	1.4	<0.1	1.00	31627	
<0.01	<0.01	0.001	1.4	0.1	0.70	31626	
<0.01	0.01	0.002	1.4	0.1	1.20	31625	
<0.01	<0.01	0.001	1.7	0.1	0.90	31624	
<0.01	<0.01	0.002	1.4	<0.1	0.15	31623	
<0.01	0.01	0.002	1.0	<0.1	1.00	31622	
<0.01	<0.01	0.003	1.0	<0.1	0.40	31621	
<0.01	0.01	0.002	1.4	<0.1	0.50	31620	
<0.01	0.01	0.051	1.4	<0.1	0.90	31619	
<0.01	0.01	0.005	1.0	<0.1	0.90	31618	
<0.01	0.01	0.130	1.7	0.1	1.00	31617	
<0.01	0.01	0.015	1.4	0.1	1.00	31616	
<0.01	0.01	0.012	0.7	<0.1	1.00	31615	
<0.01	0.01	0.001	4.1	0.1	1.00	31614	
<0.01	0.01	0.002	5.5	0.1	1.00	31613	
<0.01	<0.01	0.004	3.4	<0.1	0.95	31612	
<0.01	0.01	0.002	2.4	<0.1	1.00	31611	
<0.01	0.01	0.002	1.4	<0.1	0.95	31610	
<0.01	0.01	0.004	1.4	<0.1	1.10	31609	
<0.01	0.01	0.002	1.0	<0.1	1.00	31608	
0.01	0.01	0.010	2.7	0.1	1.00	31607	
<0.01	0.01	0.002	4.5	<0.1	1.00	31606	
<0.01	0.01	0.001	2.7	0.1	1.00	31605	
<0.01	0.01	0.002	2.0	<0.1	0.80	31604	
<0.01	0.01	0.001	5.5	<0.1	1.20	31603	
<0.01	0.01	0.004	4.4	<0.1	0.90	31602	
0.02	0.02	0.022	4.4	<0.1	0.80	31601	
<0.01	0.01	0.002	1.4	<0.1	0.40	31599	
<0.01	<0.01	0.002	1.7	<0.1	0.70	31598	
<0.01	<0.01	0.002	5.1	<0.1	0.60	31597	
<0.01	0.01	0.001	4.4	<0.1	0.80	31596	
<0.01	<0.01	0.003	3.4	<0.1	0.80	31595	
<0.01	<0.01	0.005	4.4	<0.1	1.00	31594	
0.02	0.01	0.005	2.7	<0.1	1.00	31593	
0.01	0.01	0.005	2.0	<0.1	1.00	31592	
<0.01	0.01	0.003	2.0	<0.1	0.90	31591	

LEGEND


○ SURVEY STATION

○ CH.P. SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)

WEIGHTED AVERAGE WEIGHTED AVERAGE GRADE ACROSS A HORIZONTAL DISTANCE.

m L HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.



SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 7 B
ASSAYS

DRAWN BY T.D. GARROW	DATE SEPT. 30, 1983.	N.T.S.	PLAN
TRACED BY J.S.	DATE OCT. 1983.	82 M/8E	38

10,320 E

10,335 E

10,350 E

10,365 E

10,030 N

10,030 N

10,015 N

10,015 N


10,000 N

10,320 E


10,335 E

10,350 E

10,365 E



% Pb	% Zn	% Au	g/t Ag	g/t Au	m L
<0.01	0.01	0.004	2.7	<0.1	0.60
<0.01	0.01	0.009	3.4	<0.1	1.00
<0.01	0.01	0.003	4.8	<0.1	1.00
<0.01	<0.01	0.012	2.0	<0.1	0.10
<0.01	0.01	0.008	2.0	<0.1	0.40
<0.01	0.01	0.009	4.1	<0.1	0.70
<0.01	0.01	0.019	2.7	<0.1	0.80
<0.01	0.03	0.015	2.7	<0.1	0.75
<0.01	0.04	0.018	4.1	<0.1	1.00
0.02	0.20	0.042	1.4	<0.1	0.15



LEGEND

○ SURVEY STATION

○ CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)

W WEIGHTED AVERAGE GRADE ACROSS A HORIZONTAL DISTANCE


L HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.

SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 7 A
ASSAYS


DRAWN BY T. O. GARROW	DATE OCT. 23, 1983	N.T.S.	PLAN 39
TRACED BY J. S.	DATE NOV. 1983	82 M / 8 E	



SELCO INC. EXPLORATION WESTERN CANADA

**J & L PROJECT
PLAN 8C
ASSAYS (UPPER SECTION)**

DRAWN BY T.O. GARROW	DATE SEPT. 1983	NTS	PLAN
TRACED BY J.S.	DATE OCT. 1983	82 M / 8 E	40



LEGEND

○ SURVEY STATION

○ CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)

— WEIGHTED AVERAGE GRADE CROSS SECTION (HORIZONTAL DISTANCE)


m L HORIZONTAL LENGTH (METRES)


NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.

SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 8 C
ASSAYS (MIDDLE SECTION)

DRAWN BY T.O. GORROW	DATE SEPT. 1983	N.T.S.	PLAN
TRACED BY J.S.	DATE OCT. 1983	82 M / E	41





LEGEND

○ SURVEY STATION

CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)

WEIGHTED AVERAGE

HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION

SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 8 C
ASSAYS (LOWER SECTION)


DRAWN BY T.O. GROW	DATE SEPT. 1983	N.T.S.	PLAN
TRACED BY J.S.	DATE OCT. 1983	82 M / 8 E	42

10,423 E

10,445 E

10,455 E

10,470 E



WEIGHTED AVERAGE = 1.01% Pb, 2.54% Zn,
15.09% As, 80.7g/t Ag, 23.4g/t Au
Over 0.97m

	Pb	Zn	As	Ag	Au	L
31661	0.15	0.03	2,320	23.6	1.1	0.77
31662	0.04	0.01	6,340	4.7	0.0	0.76
31663	0.39	0.10	15,400	42.6	16.4	0.55
31664	1.57	5.74	14,700	130.6	34.6	0.42

WEIGHTED AVERAGE = 2.25% Pb, 2.50% Zn,
8.46% As, 52.7g/t Ag, 9.7g/t Au
Over 0.94m

	Pb	Zn	As	Ag	Au	L
31716	<0.01	0.02	0.016	6.0	0.1	0.15
31717	<0.01	<0.01	0.010	3.4	<0.1	1.12
31718	<0.01	0.01	0.169	1.3	0.1	0.35
31719	0.10	0.03	0.140	24.0	2.0	0.53
31720	0.09	3.15	4.820	19.4	4.6	0.10
31721	6.48	6.52	10,200	112.5	24.6	0.31

WEIGHTED AVERAGE = 0.26% Pb, 0.26% Zn,
2.26% As, 49.4g/t Ag, 0.3g/t Au
Over 1.00m

	Pb	Zn	As	Ag	Au	L
31751	0.05	0.03	0.130	0.3	<0.1	1.00
31752	0.26	0.26	2,260	49.4	0.3	1.00
31753	0.27	0.34	1,300	7.5	0.6	0.24

WEIGHTED AVERAGE = 1.64% Pb, 7.01% Zn,
0.81% As, 111.3g/t Ag, 5.9g/t Au
Over 1.93m

	Pb	Zn	As	Ag	Au	L
31776	0.04	0.07	1,030	0.5	0.2	0.49
31777	0.31	0.04	3,200	28.4	1.7	0.15
31778	0.51	1.04	11,400	65.5	5.8	0.13
31779	1.31	10.20	8,430	61.7	8.2	0.20
31780	0.16	0.46	1,240	7.5	1.2	0.16
31781	3.34	10.00	2,620	237.2	8.7	0.74
31782	0.54	7.05	2,860	23.6	3.9	0.55

WEIGHTED AVERAGE = 1.75% Pb, 2.32% Zn,
2.66% As, 48.1g/t Ag, 4.8g/t Au
Over 2.37m

	Pb	Zn	As	Ag	Au	L
31807	1.72	4.52	4,600	44.2	7.9	0.70
31808	0.79	0.98	1,700	19.8	2.1	0.85
31809	1.51	1.46	1,720	56.8	1.9	0.20
31810	1.37	0.37	2,220	78.8	6.7	0.40
31811	10.50	7.94	0,092	162.5	1.9	0.12

WEIGHTED AVERAGE = 1.30% Pb, 2.16% Zn,
0.94% As, 70.7g/t Ag, 3.3g/t Au
Over 2.01m

	Pb	Zn	As	Ag	Au	L
31839	1.45	0.72	0,606	174.8	7.4	0.48
31840	0.28	2.39	0,702	20.6	4.9	0.32
31841	0.28	0.39	0,140	11.3	0.3	0.22
31842	1.93	0.42	1,690	54.2	1.4	0.35
31843	9.49	1.34	6,580	242.0	8.9	0.11
31844	0.32	0.08	0,324	8.9	0.2	0.09
31845	0.53	1.99	0,142	15.1	0.2	0.51
31846	0.23	0.01	0,020	4.8	<0.1	0.48

WEIGHTED AVERAGE = 1.06% Pb, 5.56% Zn,
0.80% As, 17.7g/t Ag, 0.2g/t Au
Over 2.46m

	Pb	Zn	As	Ag	Au	L
31910	1.31	6.10	0,004	14.8	0.2	1.23
31919	0.87	2.77	<0.001	17.6	0.2	0.62
31920	0.76	7.30	0,005	23.8	0.2	0.61

	Pb	Zn	As	Ag	Au	L
31647	0.01	0.01	0.160	0.3	0.1	0.54
31648	1.28	0.31	14,900	92.5	13.1	0.34
31649	0.39	0.25	2,230	27.9	2.3	0.60
31650	0.69	1.34	11,600	25.0	18.2	0.66

WEIGHTED AVERAGE = 1.67% Pb, 0.71% Zn,
8.78% As, 40.4g/t Ag, 11.2g/t Au
Over 1.60m

	Pb	Zn	As	Ag	Au	L
31686	0.02	0.02	0,048	2.6	0.1	0.70
31687	0.01	0.01	0,051	2.0	<0.1	0.87
31688	0.06	0.02	1,350	15.7	0.7	0.34
31689	0.10	0.02	19,700	15.0	5.6	0.54
31690	0.16	0.01	9,450	1.4	<0.1	0.15

WEIGHTED AVERAGE = 0.10% Pb, 0.02% Zn,
12.15% As, 13.3g/t Ag, 3.2g/t Au
Over 1.03m

	Pb	Zn	As	Ag	Au	L
31736	<0.01	0.01	0,086	0.3	0.1	0.54
31737	<0.01	<0.01	0,145	1.4	<0.1	0.60
31738	0.02	0.02	4,250	12.3	1.3	0.41
31739	0.09	0.01	7,910	35.0	4.0	0.60
31740	0.32	0.26	6,790	58.3	5.1	0.47

WEIGHTED AVERAGE = 0.19% Pb, 0.12% Zn,
7.41% As, 45.2g/t Ag, 4.5g/t Au
Over 1.07m

	Pb	Zn	As	Ag	Au	L
31761	0.05	0.08	0,182	2.0	0.8	0.53
31762	0.50	0.17	14,500	58.3	2.1	0.44
31763	0.05	0.02	1,090	6.2	0.2	0.20
31764	0.09	0.52	2,640	61.7	3.4	0.18
31765	0.22	0.13	0,334	13.7	0.8	0.24
31766	2.89	4.79	1,520	74.4	4.6	0.52

WEIGHTED AVERAGE = 1.23% Pb, 1.71% Zn,
5.02% As, 59.6g/t Ag, 2.6g/t Au
Over 1.50m

	Pb	Zn	As	Ag	Au	L
31792	0.26	0.26	2,020	40.8	0.5	0.17
31793	0.29	0.10	2,710	23.6	1.1	0.46
31794	2.50	3.05	2,310	127.0	5.6	0.16
31795	6.39	18,600	2,230	125.5	7.0	0.65
31796	4.56	7.16	2,760	122.4	5.1	0.71
31797	0.48	0.17	2,630	14.7	2.5	0.78

WEIGHTED AVERAGE = 4.36% Pb, 0.50% Zn,
2.46% As, 108.5g/t Ag, 5.0g/t Au
Over 1.85m

	Pb	Zn	As	Ag	Au	L
31822	1.06	1.11	2,880	74.7	4.3	0.80
31823	0.62	0.32	0,916	41.1	3.6	0.60
31824	5.74	5.40	0,545	197.4	1.4	0.40
31825	0.31	0.21	0,126	7.9	0.2	0.30

WEIGHTED AVERAGE = 2.13% Pb, 1.97% Zn,
1.65% As, 93.3g/t Ag, 3.3g/t Au
Over 1.09m

	Pb	Zn	As	Ag	Au	L
31855	0.28	1.02	0,125	4.8	0.2	0.26
31856	1.75	9.20	0,243	96.3	0.8	0.75
31857	0.36	0.33	0,068	5.5	0.1	1.25

WEIGHTED AVERAGE = 1.37% Pb, 7.09% Zn,
0.21% As, 72.7g/t Ag, 0.6g/t Au
Over 1.01m


	Pb	Zn	As	Ag	Au	L
31875	0.40	3.47	0,141	8.9	0.1	0.57
31876	0.87	3.26	0,007	13.7	<0.1	1.09
31877	0.38	4.26	0,003	8.2	0.1	0.83

WEIGHTED AVERAGE = 0.60% Pb, 3.64% Zn,
0.09% As, 10.8g/t Ag, 0.1g/t Au
Over 2.49m

LEGEND

- SURVEY STATION
- CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)
- WEIGHTED AVERAGE GRADE ACROSS A HORIZONTAL DISTANCE.
- m L HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.



SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 9 C
ASSAYS (UPPER SECTION)


DRAWN BY T. D. GARRROW	DATE SEPT. 14, 1983.	N.T.S.	PLAN 43
TRACED BY J.S.	DATE NOV. 1983.	82 M/8E	

10,425 E

10,440 E

10,455 E

10,470 E



WEIGHTED AVERAGE = 0.74% Pb, 0.61% Zn,
11.59% As, 42.9g/t Ag, 11.5g/t Au,
Over 1.97m

	Pb	Zn	As	Ag	Au	L
31651	1.08	0.75	20,900	89.2	16.7	0.55
31652	0.28	0.02	7,340	18.3	3.6	0.23
31653	0.68	0.66	3,220	34.2	3.5	0.41
31654	0.66	0.66	10,600	25.4	14.4	0.78
31655	0.03	0.18	0.204	1.8	0.2	0.49

WEIGHTED AVERAGE = 0.44% Pb, 1.98% Zn,
9.77% As, 14.4g/t Ag, 2.1g/t Au,
Over 1.31m

	Pb	Zn	As	Ag	Au	L
31691	0.01	0.02	0.136	2.0	0.1	0.34
31692	<0.01	0.01	0.104	2.6	0.1	0.29
31693	<0.01	0.01	0.089	4.8	<0.1	0.50
31694	0.07	<0.01	2,940	15.7	0.7	0.36
31695	0.03	0.01	10,400	1.4	0.1	0.42
31696	0.11	0.01	17,200	11.7	5.4	0.25
31697	0.11	0.01	12,700	4.5	0.3	0.25
31698	1.31	6.62	2,460	36.5	3.1	0.39

WEIGHTED AVERAGE = 0.17% Pb, 0.08% Zn,
5.13% As, 43.1g/t Ag, 2.7g/t Au,
Over 1.47m

	Pb	Zn	As	Ag	Au	L
31741	0.01	0.01	0.713	4.1	0.1	0.75
31742	0.05	0.03	13,700	13.0	1.4	0.23
31743	0.06	0.07	3,470	33.6	1.4	0.67
31744	0.27	0.08	6,520	51.1	3.8	0.60

WEIGHTED AVERAGE = 1.35% Pb, 4.08% Zn,
3.71% As, 64.0g/t Ag, 3.8g/t Au,
Over 2.43m

	Pb	Zn	As	Ag	Au	L
31767	1.31	3.26	7,600	182.7	2.1	0.26
31768	0.55	0.20	3,580	27.8	3.9	0.47
31769	0.17	0.12	8,104	0.3	0.2	0.37
31770	1.06	6.72	4,030	71.3	5.1	1.33

WEIGHTED AVERAGE = 1.63% Pb, 4.93% Zn,
2.12% As, 75.5g/t Ag, 4.2g/t Au,
Over 2.01m

	Pb	Zn	As	Ag	Au	L
31790	0.41	0.70	0.997	37.4	0.3	0.08
31799	3.34	4.90	4,210	93.6	7.1	0.15
31800	6.72	22.70	1,370	235.2	8.2	0.31
31801	0.19	0.42	1,580	9.2	1.8	0.80
31802	0.04	3.15	3,990	91.2	5.4	0.59
31803	0.14	0.26	0.446	8.6	0.4	0.93

WEIGHTED AVERAGE = 1.87% Pb, 2.71% Zn,
1.80% As, 59.0g/t Ag, 2.5g/t Au,
Over 1.13m

	Pb	Zn	As	Ag	Au	L
31826	4.28	5.92	2,940	139.7	5.6	0.35
31827	0.29	0.90	1,630	14.4	1.4	0.41
31828	1.24	1.67	1,120	29.1	0.9	0.37
31829	0.37	0.63	0.094	4.8	0.1	0.71
31830	0.14	0.01	0.009	2.7	<0.1	0.23

WEIGHTED AVERAGE = 0.40% Pb, 12.50% Zn,
0.097% As, 11.7g/t Ag, 0.6g/t Au,
Over 0.56m

	Pb	Zn	As	Ag	Au	L
31859	0.40	12.50	0.097	11.7	0.6	0.56
31859	0.20	0.16	0.308	6.5	0.4	1.30
31860	0.41	0.70	0.015	8.2	0.1	0.25
31861	0.13	0.04	0.003	3.4	0.1	0.33

J-37

J-38

J-39

WEIGHTED AVERAGE = 4.31% Pb, 6.25% Zn,
9.05% As, 108.6g/t Ag, 16.7g/t Au,
Over 1.81m

	Pb	Zn	As	Ag	Au	L
31665	0.24	0.06	3,690	29.2	2.3	0.61
31666	0.03	0.02	2,370	6.2	0.5	0.60
31667	0.79	0.72	11,400	69.5	8.1	0.57
31668	3.56	6.01	12,400	108.3	30.2	0.61
31669	0.22	11.50	3,590	302.2	11.3	0.63

WEIGHTED AVERAGE = 5.16% Pb, 3.68% Zn,
6.95% As, 127.6g/t Ag, 7.1 g/t Au,
Over 1.31m

	Pb	Zn	As	Ag	Au	L
31722	0.08	0.06	0.137	3.8	0.2	0.25
31723	0.03	0.04	0.158	5.0	0.4	0.56
31724	0.06	0.02	9,700	18.7	1.2	0.77
31725	2.17	6.10	2,610	62.8	7.1	0.27
31726	22.70	11.70	3,290	593.2	24.0	0.27
31727	0.79	0.31	0.295	10.9	3.5	0.33
31728	0.12	0.32	0.414	16.5	1.3	0.24

WEIGHTED AVERAGE = 0.29% Pb, 0.31% Zn,
2.79% As, 9.9g/t Ag, 1.6g/t Au,
Over 1.93m

	Pb	Zn	As	Ag	Au	L
31754	0.02	0.02	0.047	3.4	0.2	0.38
31755	0.17	0.13	2,070	3.4	1.1	1.15
31756	0.23	0.15	4,710	15.4	1.1	0.24
31757	0.59	0.62	3,490	20.9	2.3	0.54

WEIGHTED AVERAGE = 1.20% Pb, 5.78% Zn,
3.81% As, 53.2g/t Ag, 4.9g/t Au,
Over 2.59m

	Pb	Zn	As	Ag	Au	L
31783	0.47	0.16	4,300	60.3	2.8	0.17
31784	1.57	8.52	8,330	54.2	13.6	0.17
31785	0.07	0.19	0.641	1.4	0.6	0.19
31786	4.56	10.00	1,900	187.3	3.7	0.40
31787	0.78	6.10	2,720	28.4	2.5	0.48
31788	0.47	0.62	4,890	36.3	6.7	0.98

WEIGHTED AVERAGE = 1.82% Pb, 2.81% Zn,
1.89% As, 52.3g/t Ag, 2.9g/t Au,
Over 2.63m

	Pb	Zn	As	Ag	Au	L
31812	2.45	5.92	4,190	86.7	7.7	0.31
31813	0.74	1.02	1,060	19.5	1.2	0.66
31814	1.06	0.74	2,110	39.7	2.8	0.89
31815	4.68	13.70	0.096	74.7	0.6	0.24
31816	2.74	1.74	2,040	84.6	3.6	0.54

WEIGHTED AVERAGE = 1.45% Pb, 2.09% Zn,
0.77% As, 32.3g/t Ag, 1.1g/t Au,
Over 1.76m

	Pb	Zn	As	Ag	Au	L
31847	0.43	7.05	0.637	13.0	1.4	0.32
31848	3.62	1.04	2,220	82.3	2.7	0.46
31849	0.77	0.96	0.143	15.1	0.3	0.98
31850	0.31	0.50	0.014	6.0	0.2	0.43

WEIGHTED AVERAGE = 1.56% Pb, 6.83% Zn,
0.002% As, 25.0g/t Ag, 0.2g/t Au,
Over 2.14m

	Pb	Zn	As	Ag	Au	L
31868	0.23	0.26	0.008	4.1	0.1	1.08
31869	0.40	0.86	0.002	6.2	0.2	0.53
31870	0.29	3.36	0.003	6.2	0.1	0.45
31921	1.68	6.83	0.002	36.1	0.2	1.08
31922	0.58	3.36	0.001	12.3	<0.1	0.62
31923	0.71	11.70	<0.001	15.7	0.1	0.48
31924	0.07	0.27	0.004	6.3	<0.1	0.40

WEIGHTED AVERAGE = 1.16% Pb, 6.83% Zn,
0.002% As, 25.0g/t Ag, 0.2g/t Au,
Over 2.14m

	Pb	Zn	As	Ag	Au	L
31878	0.78	2.60	0.004	17.0	0.1	0.96
31879	0.28	6.52	<0.001	9.9	0.2	1.05
31880	0.28	2.60	0.004	17.0	0.1	0.96
31881	0.28	6.52	<0.001	9.9	0.2	1.05

J-35

J-36

J-37

9,970 N

9,970 N


9,955 N

9,955 N

LEGEND

- SURVEY STATION
- CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)
- WEIGHTED AVERAGE GRADE ACROSS
- HORIZONTAL DISTANCE
- m HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.



SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 9 C
ASSAYS (MIDDLE SECTION)

DRAWN BY T. D. GARROW	DATE SEPT 14, 1983	N.T.S. 82 M / 8 E	PLAN 44
TRACED BY J.S.	DATE NOV 1983		

10,425 E

10,440 E

10,455 E


10,470 E

10,425 E

10,440 E

10,455 E

10,470 E



WEIGHTED AVERAGE = 1.31% Pb, 1.66% Zn,
8.81% As, 41.4g/t Ag, 14.8g/t Au,
Over 1.55m

	Pb	Zn	As	Ag	Au	L
31656	1.75	1.76	12.100	69.7	16.6	0.25
31657	0.54	0.25	3.360	37.5	3.6	0.30
31658	0.13	0.06	4.080	14.7	2.4	0.30
31659	1.90	2.92	12.000	44.3	24.3	0.70
31660	0.06	0.32	0.264	2.0	0.7	0.90

WEIGHTED AVERAGE = 0.55% Pb, 10.58% Zn,
8.49% As, 30.9g/t Ag, 2.6g/t Au,
Over 1.70m

	Pb	Zn	As	Ag	Au	L
31699	0.03	0.07	0.122	3.3	0.1	0.46
31700	0.02	0.01	0.665	4.0	0.1	0.58
31701	0.04	0.01	11.700	10.0	1.6	0.36
31702	0.24	0.02	20.200	25.9	4.3	0.24
31703	0.11	0.01	12.500	0.4	<0.1	0.31
31704	1.14	20.90	3.060	62.0	3.8	0.57
31705	0.77	23.00	1.490	32.6	2.1	0.30

WEIGHTED AVERAGE = 5.01% Pb, 3.62% Zn,
5.46% As, 128.0g/t Ag, 6.8g/t Au,
Over 1.56m

	Pb	Zn	As	Ag	Au	L
31745	0.01	0.01	2.510	1.7	0.4	0.13
31746	0.06	0.02	18.300	12.0	1.9	0.25
31747	0.22	0.10	5.800	66.8	3.7	0.56
31748	2.45	1.54	6.970	63.4	5.8	0.63
31749	16.50	12.50	2.990	330.8	13.4	0.37
31750	0.26	0.30	0.350	4.1	0.7	0.43

WEIGHTED AVERAGE = 0.99% Pb, 4.14% Zn,
3.56% As, 48.3g/t Ag, 3.5g/t Au,
Over 2.55m

	Pb	Zn	As	Ag	Au	L
31771	0.24	0.10	3.760	106.3	1.4	0.30
31772	1.22	0.18	13.800	27.8	17.6	0.80
31773	1.51	5.22	2.500	57.6	4.2	0.40
31774	1.31	4.60	2.020	48.3	3.8	1.05
31775	0.51	5.00	4.510	21.2	2.1	0.72

WEIGHTED AVERAGE = 1.58% Pb, 3.37% Zn,
1.67% As, 30.1g/t Ag, 2.3g/t Au,
Over 2.47m

	Pb	Zn	As	Ag	Au	L
31804	0.89	1.15	1.920	15.8	2.1	0.81
31805	0.30	0.62	0.289	14.4	1.2	0.74
31806	3.26	7.68	2.600	56.2	3.4	0.90

WEIGHTED AVERAGE = 1.10% Pb, 1.90% Zn,
1.61% As, 31.6g/t Ag, 1.6g/t Au,
Over 0.72m

	Pb	Zn	As	Ag	Au	L
31831	1.22	3.05	1.780	37.7	1.9	0.43
31832	0.91	0.20	1.730	22.6	1.2	0.29
31833	0.31	0.04	2.550	4.8	2.2	0.91
31834	0.46	0.01	0.025	11.7	0.1	0.68

WEIGHTED AVERAGE = 2.17% Pb, 4.35% Zn,
10.73% As, 118.7g/t Ag, 20.3g/t Au,
Over 1.63m

	Pb	Zn	As	Ag	Au	L
31671	1.86	3.72	10.400	217.8	23.1	0.26
31672	1.17	3.97	12.500	59.3	23.0	0.82
31673	1.80	5.20	8.260	160.5	15.0	0.55
31674	0.07	0.13	0.340	7.1	0.6	0.32

WEIGHTED AVERAGE = 4.59% Pb, 2.67% Zn,
14.13% As, 98.6g/t Ag, 5.4g/t Au,
Over 1.43m

	Pb	Zn	As	Ag	Au	L
31729	0.03	0.02	0.380	0.3	0.0	0.20
31730	0.05	0.03	23.400	1.2	0.1	0.69
31731	0.10	0.03	11.400	541.6	25.1	0.23
31732	1.25	2.61	2.470	25.0	3.1	0.24
31733	21.00	11.70	3.430	35.3	3.5	0.27
31734	0.37	0.20	0.303	10.5	0.5	0.27
31735	0.10	0.30	0.040	2.0	<0.1	0.44

WEIGHTED AVERAGE = 0.90% Pb, 1.83% Zn,
2.91% As, 43.4g/t Ag, 4.8g/t Au,
Over 1.98m

	Pb	Zn	As	Ag	Au	L
31758	0.34	0.07	1.930	27.1	0.3	1.10
31759	1.87	3.26	2.090	33.2	4.5	0.30
31760	1.45	4.43	5.210	79.5	13.6	0.58

WEIGHTED AVERAGE = 1.37% Pb, 4.46% Zn,
145.2% As, 74.2g/t Ag, 2.6g/t Au,
Over 2.20m

	Pb	Zn	As	Ag	Au	L
31789	4.00	0.86	2.110	127.9	4.1	0.55
31790	1.03	5.14	0.887	131.3	1.0	0.60
31791	0.10	1.77	1.810	13.4	2.5	1.05

WEIGHTED AVERAGE = 1.60% Pb, 1.46% Zn,
1.36% As, 51.1g/t Ag, 3.0g/t Au,
Over 2.59m

	Pb	Zn	As	Ag	Au	L
31817	0.47	0.43	0.759	13.4	2.3	0.35
31818	0.71	1.00	1.930	50.7	4.3	0.88
31819	6.52	9.20	0.254	88.8	0.7	0.23
31820	0.16	0.14	0.155	3.4	0.7	0.51
31821	2.88	0.90	2.320	96.4	3.7	0.62

WEIGHTED AVERAGE = 1.39% Pb, 2.74% Zn,
0.43% As, 41.8g/t Ag, 0.8g/t Au,
Over 1.44m


	Pb	Zn	As	Ag	Au	L
31851	1.39	19.70	0.471	57.9	0.3	0.33
31852	1.39	0.37	0.424	37.0	0.5	1.11
31853	0.12	0.02	0.010	1.4	0.1	0.50
31854	0.08	0.01	0.009	1.0	<0.1	0.37

WEIGHTED AVERAGE = 0.77% Pb, 6.03% Zn,
0.002% As, 13.2g/t Ag, 0.1g/t Au,
Over 2.05m

	Pb	Zn	As	Ag	Au	L
31871	1.22	0.92	0.102	14.7	0.2	0.42
31872	0.31	0.80	0.859	7.5	0.8	0.73
31873	0.35	0.27	0.015	0.9	<0.1	0.36
31874	0.10	0.52	0.093	1.4	<0.1	0.66

WEIGHTED AVERAGE = 0.67% Pb, 4.03% Zn,
0.007% As, 10.0g/t Ag, 0.1g/t Au,
Over 2.24m

	Pb	Zn	As	Ag	Au	L
31880	1.12	4.79	0.007	10.1	0.2	1.11
31881	0.12	5.40	0.001	0.7	<0.1	0.67
31882	0.40	4.11	0.014	8.8	0.1	0.40



LEGEND


○ SURVEY STATION

○ CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)

— WEIGHTED AVERAGE GRADE ACROSS A HORIZONTAL DISTANCE

— HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION



SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN 9 C
ASSAYS (LOWER SECTION)

DRAWN BY T. D. GARROW	DATE SEPT. 14, 1983	N.T.S.	PLAN
TRACED BY J.S.	DATE NOV. 1983	82 M / 8 E	45

10,425 E

10,440 E



10,455 E

10,470 E

9,955 N

9,955 N

9,970 N




Weighted Average = 1.06% Pb, 5.56% Zn, 0.003% As, 17.7 g/t Ag, 0.2 g/t Au over 2.46 m.

Weighted Average = 2.46% Pb, 4.86% Zn, 1.062% As, 43.2 g/t Ag, 2.2 g/t Au over 1.21 m.

Weighted Average = 0.57% Pb, 2.51% Zn, 0.003% As, 11.6 g/t Ag, 0.2 g/t Au over 1.77 m.

Weighted Average = 3.60% Pb, 6.36% Zn, 0.973% As, 47.4 g/t Ag, 1.7 g/t Au over 2.27 m.

- LEGEND**
- SURVEY STATION
 - CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)
 - WEIGHTED AVERAGE GRADE ACROSS A HORIZONTAL DISTANCE
 - HORIZONTAL LENGTH (METRES)
- NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.



SELCO INC. EXPLORATION WESTERN CANADA


J & L PROJECT
PLAN IOC
ASSAYS (UPPER SECTION)

DRAWN BY P. M. S.	DATE NOV. 19, 1983	N.T.S.	PLAN 46
TRACED BY J. S.	DATE NOV. 1983.	82 M/8E	

10,485 E.

10,530 E.

10,530 E.



9,970 N.

9,970 N.

9,955 N.

9,955 N.



9,940 N.

9,940 N.

10,485 E.

10,500 E.

10,515 E.



Weighted Average = 1.16% Pb, 6.83% Zn, 0.002% As, 25.0 g/t Ag, 0.2 g/t Au over 2.14m.

Weighted Average = 1.90% Pb, 3.60% Zn, 1.240% As, 57.3 g/t Ag, 2.6 g/t Au over 1.52m.

Weighted Average = 0.45% Pb, 3.00% Zn, 0.002% As, 9.5 g/t Ag, 0.1 g/t Au over 1.77m.



Weighted Average = 5.21% Pb, 4.89% Zn, 2.724% As, 99.4 g/t Ag, 4.6 g/t Au over 1.57m.

- LEGEND**
- SURVEY STATION
 - CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)
 - WEIGHTED AVERAGE GRADE ACROSS A HORIZONTAL DISTANCE.
 - HORIZONTAL LENGTH (METRES)
- NOTE:** DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.

SELCO INC. EXPLORATION WESTERN CANADA


J & L PROJECT
PLAN IOC
ASSAYS (MIDDLE SECTION)

DRAWN BY P.M.B.	DATE NOV 19, 1983	N.T.S.	PLAN 47
TRACED BY J.S.	DATE NOV. 1983.	82 M/8E	



LEGEND


- SURVEY STATION
- CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)
- WEIGHTED AVERAGE
- HORIZONTAL LENGTH (METRES)
- NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.




SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
PLAN IOC
ASSAYS (LOWER SECTION)

DRAWN BY P. M. S.	DATE NOV 19, 1983	N.T.S.	PLAN
TRACED BY J. S.	DATE NOV 1983	82 M/8E	48



Pb	Zn	Ag	g/t Ag	g/t Au	m
+0.01	0.01	+0.001	0.7	+0.1	0.60
+0.01	+0.01	0.004	0.7	+0.1	1.20
+0.01	+0.01	0.225	2.7	+0.1	0.90
+0.01	0.01	+0.001	1.4	+0.1	1.00
+0.01	0.01	+0.001	0.3	+0.1	0.40
+0.01	0.01	+0.001	2.0	+0.1	0.40
+0.01	0.01	+0.001	0.3	+0.1	1.00
+0.01	0.01	+0.001	1.4	+0.1	0.92
+0.01	+0.01	0.001	1.4	+0.1	0.53
+0.01	0.01	0.001	1.4	+0.1	1.15
+0.01	0.01	0.007	1.4	+0.1	1.00
+0.01	0.01	0.002	0.7	+0.1	0.99
+0.01	0.01	0.001	0.7	+0.1	0.94
+0.01	0.01	+0.001	0.3	+0.1	1.11
+0.01	0.01	0.003	1.4	+0.1	0.94
+0.01	0.01	0.001	1.4	+0.1	1.03
+0.01	0.01	+0.001	0.7	+0.1	1.03
+0.01	0.01	+0.001	0.3	+0.1	0.97
+0.01	0.01	+0.001	0.7	+0.1	0.98
+0.01	0.01	+0.001	0.3	+0.1	1.01
+0.01	0.01	+0.001	0.7	+0.1	0.93
+0.01	0.01	0.002	0.3	+0.1	1.00
+0.01	0.01	0.002	0.7	+0.1	0.83
+0.01	0.01	0.032	1.4	+0.1	1.20
+0.01	0.01	0.001	1.4	+0.1	0.75
+0.01	0.01	+0.001	2.0	+0.1	0.95
+0.01	0.01	0.001	0.7	+0.1	0.97
+0.01	0.01	0.001	2.0	+0.1	0.48
+0.01	0.01	0.001	1.4	+0.1	0.23
+0.01	0.01	0.001	1.4	+0.1	0.86
+0.01	0.02	0.001	1.3	0.1	0.79
+0.01	0.01	0.003	0.7	+0.1	0.95
+0.01	+0.01	0.016	0.7	+0.1	0.41
+0.01	0.01	0.016	1.4	+0.1	0.68
+0.01	0.01	0.002	1.4	+0.1	0.83
+0.01	0.01	0.002	1.4	+0.1	1.03
+0.01	0.01	+0.001	1.4	+0.1	1.00
+0.01	+0.01	0.003	1.4	+0.1	0.58
+0.01	+0.01	0.001	1.4	+0.1	1.03
+0.01	+0.01	0.001	2.7	+0.1	0.81
+0.01	+0.01	0.002	2.7	+0.1	0.53
+0.01	0.01	0.010	0.3	+0.1	0.32
+0.01	0.01	0.018	2.7	+0.1	0.35
0.03	0.01	0.047	4.1	+0.1	0.17
+0.01	0.01	0.003	1.4	+0.1	0.93
0.01	+0.01	0.016	1.4	+0.1	0.75
+0.01	+0.01	0.007	0.3	+0.1	0.70



LEGEND


○ SURVEY STATION

○ CHIP SAMPLE SECTION LOCATION (ASSAY SAMPLE NUMBERS)

— WEIGHTED AVERAGE GRADE ACROSS A HORIZONTAL DISTANCE

— HORIZONTAL LENGTH (METRES)

NOTE: DEVELOPMENT OUTLINE SURVEYED TO SHOULDER ELEVATION.



SELCO INC.		EXPLORATION WESTERN CANADA	
J & L PROJECT			
PLAN 10B			
ASSAYS			
DRAWN BY P. M. B.	DATE NOV. 5, 1983.	N.T.S.	PLAN
TRACED BY J. S.	DATE NOV. 1983.	82 M / 8 E	49

11,020 N

10,030 N

10,060 N

10,030 N

10,000 N

860 m elev

860 m elev

840 m elev

840 m elev

820 m elev

820 m elev

800 m elev

800 m elev

780 m elev

780 m elev

760 m elev

760 m elev

740 m elev

740 m elev

720 m elev

720 m elev


700 m elev

700 m elev

J&L Road


J&L Road

Ground Elevation



LEGEND

- 0 GRAPHITE SCHIST
 - 0A CARBONACEOUS LIMESTONE (BLACK, WELL BANDED), ± GRAPHITE
 - 0B CARBONACEOUS LIMESTONE (CARBONATE 'SWEAT DOTS', ± GRAPHITE)
 - 0C CARBONACEOUS CHERT (LIMESTONE, ± GRAPHITE)
 - 0D LIMESTONE (GREY BANDED)
 - 1 LIMESTONE (SILICEOUS, BANDED)
 - 1A LIMESTONE (SILICEOUS, BANDED)
 - 2 MUSCOVITE (SERICITE) PHYLLITE
 - 2A MUSCOVITE (SERICITE) - QUARTZ SCHIST (± CHLORITE)
 - 2B CALCAREOUS MUSCOVITE (SERICITE) PHYLLITE
 - 3 CHLORITE SCHIST
 - 3A CHLORITE - MUSCOVITE (SERICITE) SCHIST
 - 3B CHLORITE - QUARTZ SCHIST (± MUSCOVITE)
 - 3C CALCAREOUS CHLORITE SCHIST
 - 4 QUARTZITE
 - 4A QUARTZ - MUSCOVITE (SERICITE) SCHIST (± CHLORITE)
 - 4B QUARTZ - CHLORITE SCHIST
 - 4C CALCAREOUS QUARTZITE
 - 5 CHERT
 - 6 INJECTED QUARTZ BRECCIA
 - 7 MYLONITE (± SHEARED SCHIST P)
 - 8 CALCITE / SOULMITE
 - 9 MASSIVE SULPHIDES (SILICEOUS MATRIX)
 - 9A MASSIVE SULPHIDES (CALCAREOUS MATRIX)
 - 9B MASSIVE SULPHIDES (SECONDARY WHITE QUARTZ MATRIX)
 - 10 QUARTZ VEIN
 - 11 PORPHYRY DYKE (SHEARED)
- FAULT
- DIAMOND DRILL HOLE
- 83-4 (82.91m) DIAMOND DRILL HOLE NUMBER (LENGTH OF HOLE)
- SURVEY STATION
- GEOLOGICAL CONTACTS (INTERPRETED)
- L.C. LOST CORE



SELCO INC. EXPLORATION
WESTERN CANADA

J & L PROJECT
SECTION 9, 970 E
LOOKING SOUTH-EAST
GEOLOGY

DRAWN BY R. PEGG	DATE JAN. 1984	N.T.S.	PLAN 50
TRACED BY J. S.	DATE JAN. 1984	B2 M / 8 E	


11,020 N

10,030 N

10,060 N

10,030 N


10,000 N



Sample No.	Pb	Zn	As	Au	Weighted Avg Pb	Weighted Avg Zn	Weighted Avg As	Weighted Avg Au
28001	0.06	0.14	0.095	4.8	0.1	1.05		
28002	0.02	0.01	0.007	5.5	0.5	1.00		
28003	0.03	0.01	0.007	5.5	<0.1	1.01		
28004	2.40	8.37	0.369	87.1	0.2	0.55		
28005	0.04	0.07	0.004	6.2	<0.1	1.00		
28006	0.01	0.01	0.001	0.1	<0.1	1.00		
28007	<0.01	<0.01	0.001	0.1	<0.1	1.00		
28008	<0.01	0.05	0.004	0.3	<0.1	0.57		
28009	2.03	7.60	0.202	49.4	0.1	0.58		
28010	0.56	4.11	0.091	13.0	<0.1	0.58		
28011	0.51	0.50	0.017	11.0	<0.1	0.40		
28012	4.12	2.22	0.430	76.8	0.8	0.36		
28013	0.14	0.09	0.026	2.7	<0.1	0.71		
28014	0.12	0.14	0.031	4.3	<0.1	0.71		
28015	0.03	2.46	0.002	0.3	<0.1	0.30		
28016	2.74	24.50	0.046	14.7	1.0	0.35		
28017	1.03	15.10	0.075	16.1	1.0	0.52		
28018	0.37	0.54	0.006	14.7	0.4	0.80		
28019	0.08	0.03	1.600	6.7	0.2	0.70		
28020	0.05	0.02	1.010	2.1	<0.1	0.65		
28021	0.05	0.03	0.280	3.4	<0.1	0.47		
28022	0.01	0.02	0.079	1.0	0.3	0.90		
28023	0.01	0.01	0.682	9.6	0.6	0.98		
28024	0.01	0.01	0.025	1.4	<0.1	1.00		
28025	2.50	1.10	12.500	35.7	13.2	0.15		
28026	0.03	0.03	0.260	2.4	0.2	1.00		

LEGEND

- SURVEY STATION
 - 83-4 (82.91m) DIAMOND DRILL HOLE NUMBER (LENGTH OF HOLE)
 - DIAMOND DRILL HOLE
 - ASSAY SAMPLE (WITHIN 1 ROCK UNIT, BETWEEN ROCK CONTACTS)
 - N.A. NOT ASSAYED
 - L.C. LOST CORE
- Sample number, % Lead, % Zinc, % Arsenic, g/t Silver, g/t Gold, Sample length (metres).



SELCO INC. EXPLORATION WESTERN CANADA

J & L PROJECT
SECTION 9, 970E
LOOKING SOUTH-EAST
ASSAY RESULTS

DRAWN BY P. PEGG	DATE JAN. 1984	N.T.S.	PLAN
TRACED BY J.S.	DATE JAN. 1984	82M/8E	51