

SHEET No. 1
FILE No. 277758/766

J. R. WILLIAMS & SON LTD.

PROVINCIAL ASSAYERS

580 NELSON STREET

MUTUAL 5-5821

Kleanza
800807

VANCOUVER 2, B.C., November 14, 1966

RESULTS of Assays made on samples of ore submitted by: MR. W. M. SHARP

MARK	Gold Oz/Ton	Silver Oz/Ton	Copper %	Lead %	Zinc %
Silver Bow. 5939 C <i>1/4 step</i> <i>2.0'</i>	0.04	4.00		2.25	2.50
" 5940 C <i>ota. @ 1.5'</i> <i>5825H; 5930E.</i>	0.04	5.15	2.30	<i>est. - 5% - combined</i>	
Blue- Bird 5941 C <i>3.0' @</i> <i>face of tunnel</i>	0.02	1.20			
" 5942 C <i>3.0' combined</i> <i>chip on surf. cut</i>	0.005	0.80		0.50	
No. 2 Gem 5943 C <i>4.0' true</i> <i>sum ota.</i>	0.015	1.00		1.60	3.25
upper Gem Dr. 5944 C <i>1.5'</i> <i>ota - 17'</i>	0.80	2.25			
" 5945 C <i>1.5'</i> <i>ota - 44'</i>	0.40	1.10			
upper 5946 C <i>10.0'</i> <i>(X-sect. 01-10')</i>	0.08	0.30	0.15		
" 5947 C <i>12.0'</i> <i>(X-sect 10-22')</i>	0.04	0.30	0.20		

8. 31. 50

Assays made by:

J. Moore