

800890

W.M. SHARP. P. ENG.

PROPERTY BOUNTY - Expo  
DIAMOND DRILL LOG - KENNEDY SILVER

SHEET No. \_\_\_\_\_  
LOC. COLLAR @ Portal of 880 Adit \_\_\_\_\_  
ELEV. COLLAR 880' EL \_\_\_\_\_  
BEARING N 05° E \_\_\_\_\_  
INCLIN. -35° \_\_\_\_\_

DDH No. 6 \_\_\_\_\_  
STARTED Oct. 169 \_\_\_\_\_  
COMPLETED Nov/69 \_\_\_\_\_  
END/DATE \_\_\_\_\_

CORE ← FEET RECOV.	DESCRIPTION OF CORE	SAMPLING					
		No.	FT.	COR. SL.	Au	Ag	Cu
0-54' (30')	Broken, weath. hbd. diorite, no vis. min in.						
-58' 3'	Hbd di; broken w freq. shear slips; Gen dark green chlorite atth w. freq. cherty spots. minor py i tr. cp	B-C					
-62' 4'	Hbd di; all chlor w. coarse py as banded & random repl. Fair cp w gr @ 58-58.3', @ 57.2'-58' i rem. as obscure dissem. w py - pyrth. avg 30°	#2535	4'		0.015	0.32	0.49
-66' 3.7'	Hbd di, dark chlor atth only slightly broken; sp py. tr cp min in.	(58-62')					
-70'	Hbd di; gen dark chla, w occ cherty bands, shearing & silic replace @ 40°; sp disc pyrite only.						

No 2535 OFFICE COPY

TO: BONDAR-CLEGG & COMPANY LTD.  
1500 Pemberton Ave., North Vancouver, B.C.  
GEOCHEMISTS - ASSAYERS - CHEMISTS  
GEOCHEMICAL KIT SUPPLIES

Date Nov 13/69  
Project BOUNTY - Expo  
Description DDH # 880 Adit: Banded (30°) py w appreciable cp  
Assayed for: Au -  
Ag -  
Au Ag Cu Pb Zn Ni MoS<sub>2</sub> Cu -

REMARKS: Very good pct of core recovery.  
DRILLED BY: S. Fegan.  
LOGGED BY: WINK.  
Nov 13/69



# BONDAR-CLEGG & COMPANY LTD.

geologists • geochemists • analysts • assayers

1500 PEMBERTON AVENUE, NORTH VANCOUVER, B.C.

Phone 988-5315

## CERTIFICATE OF ASSAY

TO Mr. Wm. Sharp  
171 W. Esplanade  
North Vancouver, B.C.

Report Number: A29-500  
 Sample Received: November 14, 1969  
 Results Completed: November 20, 1969

I hereby certify that the following are the results of assays made by us upon the herein described core samples.

MARKED	GOLD		SILVER	Copper							TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent	
2535	.015	.53	.32	.49							

NOTE:  
 Rejects retained two weeks  
 Pulps retained three months  
 unless otherwise arranged.

Gold & Silver values reported on these sheets  
 have not been adjusted to compensate losses and  
 gains inherent in fire assay methods.

Gold calculated at \$ 35.00 per ounce

*Peter Kemp*

Registered Assayer, Province of British Columbia



**BONDAR-CLEGG & COMPANY LTD.**

geologists • geochemists • analysts • assayers

1500 PEMBERTON AVENUE, NORTH VANCOUVER. B.C.

Phone 988-5315

**CERTIFICATE OF ASSAY**

TO Mr. Wm. Sharp  
171 W. Esplanade  
North Vancouver, B.C.

Report Number: A29-500  
Sample Received: November 14, 1969  
Results Completed: November 20, 1969

I hereby certify that the following are the results of assays made by us upon the herein described core samples.

MARKED	GOLD		SILVER	Copper							TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
2535	.015	.53	.32	.49							

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

Gold & Silver values reported on these sheets  
have not been adjusted to compensate losses and  
gains inherent in fire assay methods.

Gold calculated at \$ 35.00 per ounce

*Peter Kempe*  
Registered Assayer, Province of British Columbia