

PHONE: 685-5821  
File #299517/520

CERTIFICATE OF ASSAY

KENNEDY SILVER,

BOUNTY-EXPO. PITT. L.

J. R. WILLIAMS & SON LTD.

PROVINCIAL ASSAYERS AND CHEMISTS

Office and Laboratory:

580 Nelson Street, Vancouver 2, B. C.

800892

I **Hereby Certify** that the following are the results of assays made by me upon samples of Ore  
herein described and received from Mr. Wm. Sharp Nov. 30, 197

MARKED	GOLD		SILVER		Copper		GROSS TOTAL VALUE		
	Ounces Per Ton	Value Per Ton	Ounces Per Ton	Value Per Ton	Per Cent.	Value Per Ton	Per Cent.	Value Per Ton	(2000 lbs.) Per Ton
		\$		\$		\$		\$	\$
15620	0.01		0.90		0.30		- - - 2.5' ON A 25E. Q.C. : ASSAY-CP. MARCASITE.		
15621	0.015		0.60		0.27		- - - 0.5' " A 26E Q.C. ASSY. QZ. CP.		
15622	0.02		0.75		0.77		- - - GRAB. PILE # 17-N300 ADIT.		
15623	0.005		0.10		Trace		- - - 3.5' MARCASITE REPL. OF F.G.R. DI. DWKE; No Vis. CP. THIS LOCALITY		

Gold calculated at \$ \_\_\_\_\_ per ounce.

Silver calculated at \_\_\_\_\_ cents per ounce.

NOTE—Pulps of Samples retained 2 months from date of Receipt.  
Rejects 1 week unless otherwise instructed.

Calculated at \_\_\_\_\_ cents per lb.

Calculated at \_\_\_\_\_ cents per lb.

Calculated at \_\_\_\_\_ cents per lb.

*J. R. Williams*

Provincial Assayer.

PHONE: 685-5821

CERTIFICATE OF ASSAY

File # 294423/428

*SCOTT CREEK, PITT LAKE  
(KENNEDY SILVER PROSPECT.)*

**J. R. WILLIAMS & SON LTD.**

PROVINCIAL ASSAYERS AND CHEMISTS

Office and Laboratory:

580 Nelson Street, Vancouver 2, B. C.

**I Hereby Certify** that the following are the results of assays made by me upon samples of ORE  
herein described and received from Mr. W. M. SHARP August 15 19 67.

MARKED	GOLD		SILVER		Copper		GROSS TOTAL VALUE		
	Ounces Per Ton	Value Per Ton	Ounces Per Ton	Value Per Ton	Per Cent.	Value Per Ton	Per Cent.	Value Per Ton	(2000 lbs.) Per Ton
<i>925' Q/CUT</i>		\$		\$		\$		\$	\$
15612 C @ 10'-15' = 5'	0.01		0.20		0.32				
15613 C @ 15'-20' = 5'	0.015		0.40		0.70				
15614 C @ 20'-24' = 4'	0.02		0.35		0.60				
<i>TUNNEL BELOW 925' Q/C</i>									
15615 C N. WALL OF STUB <i>X-CUT, ACROSS 2.0'</i>	0.015		0.20		Trace				
15616 C @ 1500 Q/C <i>@ 16'-18' = 2.0'</i>	Trace		0.25		0.14				
<i>TUNNEL BELOW 925' Q/C</i>									
15617 C <i>RANDOM GRAB OF AVERAGE TUNNEL VEIN SULFIDES.</i>	0.045		1.55		1.00				

Gold calculated at \$ \_\_\_\_\_ per ounce.

Silver calculated at \_\_\_\_\_ cents per ounce.

NOTE—Pulps of Samples retained 2 months from date of Receipt.  
Rejects 1 week unless otherwise instructed.

Calculated at \_\_\_\_\_ cents per lb.

Calculated at \_\_\_\_\_ cents per lb.

Calculated at \_\_\_\_\_ cents per lb.

*J. R. Williams*

Provincial Assayer.

TO:

*Copies delivered directly to Kennedy.*  
Kennedy Silver Mines Ltd.

826 - 470 Granville Street

VANCOUVER, B. C.

CC: Mr. W. M. Sharp, P. Eng.

#1 - 425 Howe Street

VANCOUVER 1, B. C.



**Certificate of Assay**  
**COAST ELDRIDGE**

PROFESSIONAL SERVICES DIVISION

WARNOCK HERSEY INTERNATIONAL LIMITED

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

*Kennedy, Pitt Lake*



Member  
Canadian Testing  
Association

PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

FILE NO. A.3-K-68-1911

DATE October 2, 1968

We Hereby Certify that the following are the results of assays made by us upon submitted Drill Core samples

MARKED	GOLD		SILVER	Copper (Cu)	PER CENT.	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.					
<i>DDA #2</i> 61245 @ 51' - 53.7' -	0.03	\$ 1.05	0.1	0.68					
61246 @ 107.5' - 110.5' -				0.39					

/bg

Gold calculated at \$ ----- per ounce

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gains inherent in the fire assay process.

*H. Sharp*

Provincial Assayer