

(Aug. 1975 Rees)

801066

(75-2)

Stoping

Note essential to keep waste waste-dilution to a minimum + prob. a min. mining width of 3.5'

Probably an average 4' minimum mining width can be attained. As this will lead to considerable dilution by h.w. & f.w. granites, it will be essential to construct an ore bin with a cover-grizzly (6" x 8") & air-water washing jet - permitting bulk of coarse slabby waste to be sorted out before trucking ore to mill. This practice successfully employed at other Alcon properties where considerable unavoidable dilution occurs.