

Copies sent to:

To: Mr. R.J. Dealy & Mr. W.M. Sharp



801340



PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

Silver Star Mines Ltd.,

### Certificate of Assay

704 - 626 West Pender Street

**WARNOCK HERSEY INTERNATIONAL LIMITED**

FILE NO. 468-A-9228

Vancouver, B.C.

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

DATE November 6, 1969

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

We Hereby Certify that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
		\$							
5700 ✓ 1003 Δ 13 + 25', 2.7'	0.02	0.70	1.9	3.82	1.11				
✓ 1004 " + 35', 2.5'	0.01	0.35	2.1	2.23	0.61				
✓ 1005 " + 45', 2.3'	Trace	-	6.0	10.86	2.30				
✓ 1006 " + 55', 3.2'	0.04	1.40	3.4	4.83	0.71				
✓ 1007 " + 65', 3.4'	0.07	2.45	1.1	0.83	0.56				
✓ 1008 Δ 13 + 75', 3.1	0.04	1.40	0.6	0.54	0.33				
✓ 1009 Δ 14 + 10', 4.1	0.08	2.80	1.6	1.67	1.32				
✓ 1010 " + 20', 2.6	0.26	9.10	11.4	13.13	15.61				
✓ 1011 " + 30', 2.1	0.15	5.25	5.2	1.76	1.16				
✓ 1012 " + 40', 2.2	0.44	15.40	3.0	2.06	1.82				
✓ 1013 Δ 14 + 50', 1.5'	0.09	3.15	2.1	1.10	0.51				
✓ 1014 " + 60', 2.0'	0.67	23.45	3.4	2.62	5.11				
✓ 1015 " + 70', 2.3'	0.04	1.40	1.7	0.81	0.05				
✓ 1016 Δ 8 + 80', 2.4'	0.26	9.10	0.9	0.78	0.28				
✓ 1017 Δ 9 + 00', 2.0	0.07	2.45	0.2	0.86	0.35				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Sharp*

Provincial Assayer

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSIONS OF EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

TO:

Silver Star Mines Ltd. (2)



Certificate of Assay



PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

WARNOCK HERSEY INTERNATIONAL LIMITED  
COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

FILE NO. 450-A-9228

DATE November 6, 1969

We Hereby Certify that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
		\$							
✓ 1018 Δ 9+10', 4.7'	0.04	1.40	0.3	0.71	0.53				
✓ " 1019 " + 20' 4.3	0.08	2.80	0.4	0.42	0.35				
✓ " 1020 " + 30' 3.1	0.05	1.75	0.2	0.29	0.28				
✓ " 1021 " + 40' 2.2	0.03	1.05	0.1	0.32	0.15				
✓ " 1022 " + 50' 2.0	0.15	5.25	0.7	0.69	0.18				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Stanley*

Provincial Assayer

SEYMOUR LABORATORY LTD.

147 Riverside Drive, North Vancouver, B.C. Tel. (604) 929-2228

Nº 622

CERTIFICATE OF ANALYSIS

TO SILVER STAR MINES  
Rm. 704 - 626 WEST PENDER ST.  
VANCOUVER 1, B.C.

TYPE OF SAMPLES ROCK

No. of SAMPLES 2

FILE No. 622 Our Inv. 1437

SAMPLE No.	OZ. PER TON GOLD	OZ. PER TON SILVER	% Pb	% Zn	%	%			
1001	0.28	2.2	2.78	0.39					5700 DR @ Δ 14+10'; 2.3' WIDE CHIP ON FACE
1002	0.06	0.9	0.50	0.07					5700 DR CHIP ON FACE @ Δ 14+56'; 1.6' WIDE

CC: Mr. Ed. Borup, c/o Home Hotel, Nelson, B.C.  
 Mr. W.M. Sharp, 171 W. Esplanade. North Vanc. ✓

*J. Chatter*

PROVINCIAL ASSAYER

DATE OCTOBER 30, 1969

SEYMOUR LABORATORY LTD.

147 Riverside Drive, North Vancouver, B.C. Tel. (604) 929-2228

N<sup>o</sup> 593

CERTIFICATE OF ANALYSIS

TO SILVER STAR MINES  
ROOM 704 - 626 W. PENDER ST.  
VANCOUVER 2, B.C.

TYPE OF SAMPLES SLUDGE

No. of SAMPLES 30

FILE No. 593 Our Inv. 1411

SAMPLE No.	OZ. PER TON GOLD	OZ. PER TON SILVER	% Pb	% Zn	%	%		
11287	tr	tr	0.004	0.010	0-5'		5900 T.H. @	Δ 12+100', H.W.
11288	tr	tr	tr	0.006	- 10'			
11289	tr	tr	tr	0.008	- 15'			
11290	tr	tr	tr	0.010	- 20'			
11291	tr	tr	tr	0.010	- 25'			
11292	tr	tr	tr	0.014	- 30'			
11293	tr	tr	0.004	0.014	- 35'			
11294	tr	tr	0.004	0.008	- 40'			
11295	tr	tr	tr	0.008	- 45'			
11296	tr	tr	tr	0.004	- 50'			
11297	tr	0.1	0.004	0.012	0-5'		5900 T.H. @	Δ 12+125', H.W.
11298	tr	tr	tr	0.002	- 10'			
11299	tr	tr	tr	0.004	- 15'			
11300	tr	0.1	tr	0.002	- 20'			
14501	tr	tr	tr	0.006	- 25'			
14502	tr	tr	tr	0.004	- 30'			
14503	tr	tr	0.004	0.004	- 35'			
14504	tr	tr	tr	0.006	- 40'			
14505	tr	tr	0.004	0.014	- 45'			
14506	tr	tr	tr	0.004	- 50'			
14507	0.02	0.1	0.004	0.018	0-5'		5900 T.H. @	Δ 12+100', F.W.
14508	tr	0.1	tr	0.010	- 10'			
14509	tr	0.1	0.004	0.010	- 15'			
14510	tr	0.1	0.020	0.036	- 20'			
14511	tr	tr	0.004	0.016	- 25'			
14512	tr	0.1	tr	0.004	- 30'			
14513	tr	0.1	0.004	0.014	- 35'			
14514	tr	tr	tr	0.008	- 40'			
14515	0.01	tr	tr	0.016	- 45'			
14516	tr	0.1	tr	0.012	- 50'			

CC: Mr. Ed. Borup c/o Hume Hotel, Nelson, B.C.  
Mr. W.M. Sharp, 171 W. Esplanade Ave., N. Van.

*J. Chatter*

PROVINCIAL ASSAYER

DATE OCTOBER 20, 1969



*Rec'd Nov 6/69*

SEYMOUR LABORATORY LTD.

147 Riverside Drive, North Vancouver, B.C. Tel. (604) 929-2228

CERTIFICATE OF ANALYSIS

TO SILVER STAR MINES  
ROOM 704 - 626 WEST PENDER ST.  
VANCOUVER, B.C.

DRILL SLUDGE  
TYPE OF SAMPLES

No. of SAMPLES 40

FILE No. 634 Our Inv. 1451

SAMPLE No.	OZ. PER TON GOLD	OZ. PER TON SILVER	% Pb	% Zn	SAMPLE NO.	% Au	% Ag	% Pb	% Zn
<i>T.H. 5900</i> 14517 0-5' tr		tr	tr	tr	14552-30' tr		0.1	tr	tr
<i>A 12+50'</i> 14518 -10' tr		tr	tr	tr	14553-35' tr		tr	tr	tr
<i>HW</i> 14519 -15' tr		tr	tr	tr	14554-40' tr		tr	tr	tr
14520 -20' tr		tr	tr	tr	14555-45' tr		gr	tr	tr
14521 -25' tr		tr	tr	tr	14556-50' tr		tr	tr	tr
14522 -30' tr		tr	tr	tr					
14523 -35' tr		tr	tr	tr					
14524 -40' tr		tr	tr	tr					
14525 -45' tr		tr	tr	tr					
14526 -50' tr		tr	yr	0.01					
<i>T.H.</i> 14527 0-5' tr		tr	tr	0.01					
<i>5900</i> 14528 -10' tr		tr	tr	0.01					
<i>A 12</i> 14529 -15' tr		tr	tr	tr					
<i>+25'</i> 14530 -20' tr		tr	tr	tr					
<i>HW</i> 14531 -25' tr		tr	tr	tr					
14532 -30' tr		tr	tr	tr					
14533 -35' tr		tr	tr	0.01					
14534 -40' tr		tr	tr	tr					
14535 -45' tr		tr	tr	0.01					
14536 -50' tr		tr	tr	0.01					
<i>T.H.</i> 14537 0-5' 0.01		tr	tr	0.01					
<i>5900</i> 14538 -10' tr		tr	tr	0.01					
<i>A 12</i> 14539 -15' tr		tr	tr	0.01					
<i>75'</i> 14540 -20' tr		tr	tr	0.01					
<i>HW</i> 14541 -25' tr		tr	tr	tr					
14542 -30' tr		tr	tr	0.01					
14543 -35' tr		tr	tr	0.01					
14544 -40' tr		tr	tr	tr					
14545 -45' tr		tr	tr	tr					
14546 -50' tr		tr	tr	tr					
<i>T.H.</i> 14547 0-5' tr		0.1	tr	0.01					
<i>5900</i> 14548 -10' tr		tr	tr	tr					
<i>A 12</i> 14549 -15' tr		tr	tr	tr					
<i>+145'</i> 14550 -20' tr		0.1	tr	tr					
<i>HW</i> 14551 -25' tr		tr	tr	tr					

CC: Mr. Ed. Borup c/o Hume Hotel, Nelson, B.C.  
Mr. W.M. Sharp, ✓  
171 W. Esplanade, N. Van

*J. Chatter*

PROVINCIAL ASSAYER

DATE OCTOBER 31, 1969

(In Duplicate)

Rec'd Nov 13/69  
Plattell



PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

TO:

Silver Star Mines Ltd.

704 - 626 West Pender Street

Vancouver, B.C.

# Certificate of Assay

**WARNOCK HERSEY INTERNATIONAL LIMITED**

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

FILE NO. **469-A-9230**

DATE **November 10, 1969**

(12-11-69)

Copies forwarded to: **Mr. R.J. Dealy**  
**Mr. W.M. Sharp**

**We Hereby Certify** that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
		\$							
✓ 5700 low 1023 - Δ11 + 5', 2.3'	0.04	1.40	0.6	2.25	0.68	✓			
✓ 1024 " + 15', 2.8'	0.35	12.25	8.2	7.79	12.45	✓			
✓ 1025 " + 25', 2.2'	0.54	18.90	5.4	5.98	5.79	✓			
✓ 1026 " + 35', 2.0'	0.73	25.55	2.1	1.98	1.06	✓			
✓ 1027 " + 45', 2.0'	0.16	5.60	0.8	1.32	0.48	✓			
✓ 5700 low 1028 Δ5 + 40', 1.2'	0.11	3.85	0.2	0.34	0.20				
✓ 1029 Δ6 + 0', 1.0'	0.23	8.05	1.9	1.76	0.18				
✓ 1030 " + 10', 2.9'	0.05	1.75	0.4	0.24	0.46				
✓ 1031 " + 20', 2.5'	0.11	3.85	0.3	0.15	0.18				
✓ 1032 " + 30', 1.0'	0.09	3.15	2.1	1.15	0.46				
✓ 1033 " + 40', 2.2'	0.02	0.70	0.6	0.47	0.25				
✓ 1034 " + 50', 3.7'	0.04	1.40	0.3	0.12	0.25				
✓ 1035 " + 60', 2.5'	0.01	0.35	0.2	0.10	0.23				
✓ 1036 " + 70', 3.1'	0.02	0.70	0.2	0.29	0.13				
✓ 1037 " + 80', 1.4'	0.05	1.75	1.8	1.94	0.28				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ ----- per ounce

*H. Sharpe*

Provincial Assayer

TO:



PHONE: (604) 876-4111  
 TELEX: 04-50353  
 CABLE ADDRESS:  
 ELDRICO

Silver Star Mines Ltd. (2)

# Certificate of Assay

**WARNOCK HERSEY INTERNATIONAL LIMITED**

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

FILE NO.

460-A-9230

DATE

November 10, 1969

We Hereby Certify that the following are the results of assays made by us upon submitted \_\_\_\_\_ samples

MARKED	GOLD		SILVER	Lead (Pb) PER CENT.	Zinc (Zn) CENT.	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON						
5700 lens		\$							
✓ 1038 A 7+0'; 0.8'	0.02	0.70	0.2	0.15	0.30	✓			3 pending @ rail + --- 25'
✓ 1039 A 7+10'; 0.7'	0.16	5.60	0.3	0.15	0.23	✓			
57-59 1040 Rail + 30' + 35'; 3.1'	0.05	1.75	2.9	4.70	3.54				
1041 " + 40' + 45'; 2.7'	0.15	5.25	3.0	5.24	4.50				
1042 " + 50' + 55'; 2.0'	0.63	22.05	9.2	11.96	12.45				
(55' - 105') Keen in H.W. - not sampled									3 pending above sect.
105' - on pending (6)									

Note. Rejects retained one week.  
 Pulps retained one month.  
 Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Hayles*

Provincial Assayer

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSIONS OF EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.



TO:

Silver Star Mines Ltd.,

704 - 626 West Pender Street

Vancouver, B.C.



## Certificate of Assay

WARNOCK HERSEY INTERNATIONAL LIMITED

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA



PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

FILE NO. 460-A-9476

DATE November 24, 1969

Copies sent to: (28-11-69)

Mr. R.J. Dealy &amp; Mr. W.M. Sharp

We Hereby Certify that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
5700 Transfers		\$							
1051 - split 35+40'	0.22	7.70	0.2	0.17	0.05	} fraction of vein exposed in each of raise - do not plot, as not rep. of full width of vein - plotting - pending completion of staking, timbering & final sampling -			
1052 " + 45+50'	0.01	0.35	0.2	0.44	0.13				
1053 " + 55+60' 2.5'	0.13	4.55	4.5	1.62	10.98				
1054 " + 65+70' 2.5'	0.05	1.75	6.6	6.81	3.69				
1055 " + 75+80 1.5'	0.16	5.60	3.1	5.32	5.19				
1056 " + 85' only - 1.5'	0.07	2.45	0.7	0.24	0.81				
(1057 - grab 5700 stockpile 1058 - selected chips 59+43 + 15' in sill - B.S. sample)									

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

Provincial Assayer

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSIONS OR EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.



TO:

Silver Star Mines Ltd.,  
704 - 626 West Pender Street  
Vancouver, B.C.



# Certificate of Assay

**WARNOCK HERSEY INTERNATIONAL LIMITED**  
COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA



Member  
Canadian Testing  
Association

Rec'd. Dec 31/69  
PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

FILE NO. 460-A-9857

DATE December 16, 1969

Copies sent to:

Messrs. R.J. Dealy & W.M. Sharp

<sup>18-12-69</sup>  
We ~~Herby~~ Certify that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
57-5900 Trans. raise		\$							
✓ 1043 RL+185' - 3.1'	0.98	34.30	4.0	5.45	2.33				
✓ 1044 RL+190' - 2.8'	0.09	3.15	1.4	2.40	0.40				
✓ 1045 RL+196' - 2.8'	0.25	8.75	1.8	5.25	0.30				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Sharp*

Provincial Assayer

TO:

Silver Star Mines Ltd.,

704 - 626 West Pender Street

Vancouver, B.C.

Copies forwarded to:  
Messrs. R.J. Dealy & W.M. Sharp 29-12-69

## Certificate of Assay

WARNOCK HERSEY INTERNATIONAL LIMITED  
COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

FILE NO. 460-A-9905

DATE December 23, 1969

We Hereby Certify that the following are the results of assays made by us upon submitted \_\_\_\_\_ samples

MARKED	GOLD		SILVER	Lead (Pb) CENT.	Zinc (Zn) CENT.	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON						
57-5900 Transf raise		\$							
✓ 1046 R.L.+202' - 3.0'	0.12	4.20	3.8	4.63	4.01				
✓ 1047 R.L.+208' - 2.7'	0.07	2.45	2.7	8.69	1.16				
✓ 1048 R.L.+214' - 2.6'	0.11	3.85	3.5	8.62	2.71				
✓ 1049 R.L.+220' - 2.7'	0.10	3.50	5.7	6.79	17.81				
✓ 1050 R.L.+225' - 2.4'	Trace	-	10.3	17.92	6.45				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum  
of one year by special arrangement.

Unless it is specifically stated otherwise, gold  
and silver values reported on these sheets have  
not been adjusted to compensate for losses and  
gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

Provincial Assayer

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSIONS OF EXTRACTS FROM OR REGARDING  
OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

TO:

Silver Star Mines Ltd.,

704 - 626 West Pender Street

Vancouver, B.C.



## Certificate of Assay

WARNOCK HERSEY INTERNATIONAL LIMITED

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

Member  
Canadian Testing  
AssociationPHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

FILE NO. 460-A-99888

DATE December 22, 1969

Copies forwarded to:

Messrs. R.J. Dealy &amp; W.M. Sharp 29-12-69

We Hereby Certify that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	Cadmium (Cd)	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.	PER CENT.			
57-5900 Tranchee									
✓ 1059 RL+230' - 2.7'	0.17	\$ 5.95	5.9	8.59	4.73				
✓ 1060 RL+236' - 2.7'	0.08	2.80	9.1	9.08	16.07				
✓ 1061 RL+241' - 2.4'	0.09	3.15	22.0	14.01	28.20				
✓ 1062 RL+246' - 3.0'	0.10	3.50	12.7	25.13	12.50				
✓ 6089	0.44	15.40	13.4	21.73	16.90				
6090	0.14	4.90	10.5	14.27	17.91				
6091	0.09	3.15	5.1	7.46	17.05				
6092	0.13	4.55	18.7	26.05	16.90				
6093	0.10	3.50	11.0	22.65	10.25				
6094	0.18	6.30	12.6	15.67	14.83				
6095	0.13	4.55	12.5	12.44	2.50				
6096	0.16	5.60	1.9	1.98	1.04				
6097	0.41	14.35	5.8	7.03	6.07				
Composite 1059 - 1062 + 6089 - 6097						0.32			

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

Provincial Assayer

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSIONS OF EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

TO:



PHONE: (604) 876-4111  
 TELEX: 04-50353  
 CABLE ADDRESS:  
 ELDRICO

Silver Star Mines Ltd.,  
 704 - 626 West Pender Street  
 Vancouver, B.C.

# Certificate of Assay

**WARNOCK HERSEY INTERNATIONAL LIMITED**  
 COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

FILE NO. 460-A-10011

DATE December 23, 1969

Copies forwarded to:  
 Messrs. R.J. Dealy & W.M. Sharp 29-12-69

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

**We Hereby Certify** that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
57-5900 from Rec.		\$							
✓ 1063 RL + 251' - 3.1'	0.10	3.50	5.0	10.65	6.20				
✓ 1064 RL + 256' - 3.1'	0.13	4.55	5.7	6.06	10.47				
1065 5900 Slupe + 45'	0.33	11.55	1.2	1.37	0.46				
1066 5900 Slupe S. eldridge	0.64	22.40	1.9	2.78	0.99				

Note. Rejects retained one week.  
 Pulps retained one month.  
 Pulps and rejects may be stored for a maximum of one year by special arrangement.

Gold calculated at \$ \_\_\_\_\_ per ounce

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

*H. Sharp*

Provincial Assayer



TO:

Silver Star Mines Ltd.,

704 - 626 West Pender Street,

Vancouver, B. C.



## Certificate of Assay

WARNOCK HERSEY INTERNATIONAL LIMITED

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA



PHONE: (604) 876-4111

TELEX: 04-50353

CABLE ADDRESS: *minl.*

ELDRICO

FILE NO. 460-A-9757

DATE Dec. 5, 1969

Copies forwarded to: .....

Messrs. R.J. Dealy &amp; W.M. Sharp

8-12-69

We Hereby Certify that the following are the results of assays made by us upon submitted PULPS samples

MARKED	GOLD		SILVER	Lead	Zinc	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	(Pb) PER CENT.	(Zn) PER CENT.				
		\$							
Heads	0.15	5.25	3.1	5.12	4.84				
Tails	0.04	1.40	0.74	0.87	1.34				
Pb Con	1.35	47.25	24.7	63.23	10.63				
Zn Con	0.57	19.95	17.1	3.55	54.91				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ ..... per ounce

Provincial Assayer

TO:

Silver Star Mines Ltd.,

704 - 626 West Pender Street

Vancouver, B.C.



## Certificate of Assay

WARNOCK HERSEY INTERNATIONAL LIMITED  
COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA



PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

FILE NO. 460-A-9645

DATE December 2, 1969

Copies sent to:

Messrs. R. J. Dealy &amp; W.M. Sharp

We Hereby Certify that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
		\$							
1058 - <sup>(Boh D.)</sup> Selected' chips Sample c Δ 13+15' @ Track level (5700 lev.) from Sample Rough (Dec. 9.) R. Dealy Samples 1059 - 5700 Trans. Ave @ Rail + 230' Width? 1060 - " " " " " + 236' - " ? 1061 - " " " " " + 241' - " ?	0.02	0.70	50.6	51.25	9.56				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

Provincial Assayer

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSIONS OF EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

TO:



PHONE: (604) 876-4111  
 TELEX: 04-50353  
 CABLE ADDRESS:  
 ELDRICO

Silver Star Mines Ltd.,  
 704 - 626 West Pender Street  
 Vancouver, B.C.

## Certificate of Assay

**WARNOCK HERSEY INTERNATIONAL LIMITED**

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

FILE NO. 460-A-9989

DATE December 22, 1969

Copies forwarded to:  
 Messrs. R.J. Dealy & W.M. Sharp

*We Hereby Certify* that the following are the results of assays made by us upon submitted PULPS samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	Cadmium (Cd)	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.	PER CENT.			
Pb Con 16 - 12 - 69	1.22	\$ 42.70	26.4	65.08	8.50				
Zn Con 16 - 12 - 69	0.64	22.40	16.2	3.62	53.80	1.18			

Note. Rejects retained one week.  
 Pulps retained one month.  
 Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Dealy*

Provincial Assayer



PHONE: (604) 876-4111  
 TELEX: 04-50353  
 CABLE ADDRESS:  
 ELDRICO

# Certificate of Assay

## WARNOCK HERSEY INTERNATIONAL LIMITED

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

FILE NO. 461 - 11196

DATE April 6, 1970

TO: Silver Star Mines Ltd.,  
 704 - 626 West Pender Street  
 Vancouver B.C.  
 Copies to: Mr. R. J. Dealy  
 Mr. W. M. Sharp  
 7-4-70

We Hereby Certify that the following are the results of assays made by us upon submitted ORE AND CONCENTRATES samples

MARKED	GOLD		SILVER	Lead (Pb) CENT.	Zinc (Zn) CENT.	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON						
1079 57-4 base rail + 55'	0.32	\$ 11.20	7.1	7.01	19.40	<i>4.7' true, mixed of siliceous R.O</i> <i>4.4' " " " " " "</i>			
1080 " " " + 61'	0.05	1.75	23.7	43.73	3.02				
Zn Con	0.515	18.03	14.8	4.28	50.94				
Pb Con	1.44	50.40	40.1	71.19	6.06				

Note. Rejects retained one week.  
 Pulps retained one month.  
 Pulps and rejects may be stored for a maximum  
 of one year by special arrangement.

Unless it is specifically stated otherwise, gold  
 and silver values reported on these sheets have  
 not been adjusted to compensate for losses and  
 gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Hayes*

Provincial Assayer



Rec'd April 6/70

Silver Star Mines

Mr. W. SHARPE.

Samples

5900 Service Raise to 6040.

# 1079 Rail + 55' - Chip - 4.7' Mixed - Oxidized.

1080 " + 61' - Chip - 4.4' " "

R. Dealy



PHONE: (604) 876-4111  
 TELEX: 04-50353  
 CABLE ADDRESS:  
 ELDRICO

# Certificate of Assay

TO:  
 Silver Star Mines Ltd.,  
 626 West Pender Street  
 Vancouver, B.C.

**WARNOCK HERSEY INTERNATIONAL LIMITED**  
 COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION  
 125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

FILE NO. 460-A-9410

DATE November 13, 1969

Copies forwarded to: (14-11-69)  
 Messrs. R.J. Dealy & W.M. Sharp

*To plot pending survey extension*

**We Hereby Certify** that the following are the results of assays made by us upon submitted \_\_\_\_\_ ORE \_\_\_\_\_ samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
1076 - g2 vein @ Wharf of 5700 drift-current Dec. 8/69 face - 2.4'	0.09	\$ 3.15	0.8	0.15	0.30				

Note. Rejects retained one week.  
 Pulps retained one month.  
 Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Sharp*

Provincial Assayer

TO:

Silver Star Mines Ltd.,

704 - 626 West Pender Street

Vancouver, B.C.

COPY SENT TO: Mr. R.J. Dealy  
4-3-70



# Certificate of Assay

**WARNOCK HERSEY INTERNATIONAL LIMITED**

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA



Member  
Canadian Testing  
Association

PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

*Rec'd March 4/70*  
*From E.B.*

FILE NO. 461 - 10700

DATE March 3, 1970

We Hereby Certify that the following are the results of assays made by us upon submitted ORE samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
1078 <i>P. Assayed Dug 69-2A</i>	0.11	\$ 3.95	19.0	23.85	15.47				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Hayes*

Provincial Assayer



WARNOCK HERSEY  
INTERNATIONAL LIMITED

PROFESSIONAL SERVICES DIVISION

125 East 4th Ave., Vancouver 10, B. C. Phone 876-4111 — Telex 04-50353

*Rec'd March 4/70  
from E.B.*

REPORT OF: **Chemical Analysis**  
AT **Vancouver Laboratory**  
PROJECT: **Water Sample**  
REPORTED TO: **Silver Star Mines Ltd.,  
704 - 626 West Pender Street  
Vancouver, B.C.**

FILE NO: **466 - 10620**  
DATE **March 2, 1970**  
REPORT NO:  
ORDER NO:

We have analyzed one water sample submitted to us on February 11 and report as hereunder:

SAMPLE IDENTIFICATION

Mill Tailings

TEST RESULTS

pH	-	8.1
Colour	-	15.0 ppm
Colour with Charcoal	-	Not detected
Turbidity (SiO <sub>2</sub> scale)	-	54.0 ppm
Suspended Matter	-	16.5 ppm
Alkalinity: Carbonated	-	Not detected
Bicarbonatd	-	98.0 ppm
Total Hardness (Soap Method)	-	220.0 ppm
Chlorides	-	Not detected
Sulphates	-	180.0 ppm
Total Dissolved Solids	-	392.0 ppm
Volatile Solids	-	46.0 ppm
Fixed Solids	-	246.0 ppm
Calcium	-	58.0 ppm
Magnesium	-	17.0 ppm
Sodium	-	13.0 ppm
Potassium	-	23.0 ppm
Manganese	-	Not detected
Total Iron	-	0.68 ppm
Dissolved Iron	-	0.20 ppm
Total Aluminum	-	1.9 ppm
Dissolved Aluminum	-	1.4 ppm
Dissolved Silicon	-	0.4 ppm

WARNOCK HERSEY

*B.K. Morse*

B.K. Morse  
LABORATORY SUPERVISOR



*Rec'd Oct 27/69  
from Miss Burup*

# J. R. WILLIAMS & SON LTD.

PROVINCIAL ASSAYERS AND CHEMISTS

Office and Laboratory:

580 Nelson Street, Vancouver 2, B. C.

**I Hereby Certify** that the following are the results of assays made by me upon samples of ORE  
herein described and received from Messrs. SILVER STAR MINES LTD. September 18th 1969

MARKED	GOLD		SILVER		Lead		Zinc		Per Cent.
	Ounces Per Ton	Value Per Ton	Ounces Per Ton	Value Per Ton	Per Cent.	Value Per Ton	Per Cent.	Value Per Ton	
11276	0.03	\$	0.40	\$	1.25	\$	0.20	\$	
11277	0.08		1.00		3.50		1.25		
11278	0.14		4.70		4.10		9.60		
11279	0.41		13.50		6.75		14.70		
11280	0.28		4.90		5.80		5.30		
11281	0.38		4.35		4.35		3.95		
11282	0.22		2.15		2.15		1.70		
11283	0.25		6.55		3.75		0.25		

Gold calculated at \$ \_\_\_\_\_ per ounce.

Silver calculated at \_\_\_\_\_ cents per ounce.

NOTE—Pulps of Samples retained 2 months from date of Receipt.  
Rejects 1 week unless otherwise instructed.

Calculated at \_\_\_\_\_ cents per lb.

Calculated at \_\_\_\_\_ cents per lb.

Calculated at \_\_\_\_\_ cents per lb.

*J. Moore*  
Provincial Assayer.

SHEET NO. 1  
318808/843  
FILE NO. \_\_\_\_\_

# J. R. WILLIAMS & SON LTD.

*Rec'd Oct. 27/69*  
*from Min Comp.*  
MUTUAL 5-5821

## PROVINCIAL ASSAYERS

580 NELSON STREET

This copy for: *W. Sharp. 27-10-69*  
~~Mr. C. Lind: 12-8-69~~ VANCOUVER 2, B. C., August 5th 19 69

RESULTS of Assays made on samples of ore submitted by: **Messrs. SILVER STAR MINES LTD.**

MARK	Gold Oz/Ton	Silver Oz/Ton	Lead %	Zinc %
11240 F	0.38	19.95	17.50	18.50
11241 F	0.09	5.25	5.90	4.80
11242 F	0.26	2.95	1.46	0.20
11243 F	0.17	0.30	0.34	Trace
11244 F	0.35	5.40	11.90	7.30
11245 F	0.10	1.40	1.05	1.05
11246 F	0.40	5.75	16.60	13.80
11247 F	0.11	1.80	2.55	1.20
11248 F	0.44	7.00	13.50	11.80
11249 F	0.07	0.35	0.25	0.02
11250 F	0.04	0.30	0.22	0.10
11251 F	0.05	1.15	0.95	1.40
11252 F	0.52	9.10	11.60	10.20
11253 F	0.08	3.10	3.34	2.70
11254 F	0.04	0.20	0.33	0.15
11255 F	0.06	0.15	0.20	Trace
11256 F	0.07	0.40	0.80	0.20
11257 F	0.14	1.45	0.88	0.75

Assays made by:  
*J. Howard*

SHEET No. 2  
FILE No. 318808/843

# J. R. WILLIAMS & SON LTD.

MUTUAL 5-5821

## PROVINCIAL ASSAYERS


580 NELSON STREET

VANCOUVER 2, B. C., August 5th 1969

RESULTS of Assays made on samples of ore submitted by: Messrs. SILVER STAR MINES LTD.

MARK	Gold Oz/Ton	Silver Oz/Ton	Lead %	Zinc %
11258 F	0.16	6.45	6.70	5.40
11259 F	0.05	0.95	1.70	1.40
11260 F	0.09	0.20	0.48	0.10
11261 F	0.22	13.55	24.20	17.60
11262 F	0.11	0.15	0.10	0.10
11263 F	0.19	0.25	0.70	0.75
11264 F	0.20	6.60	7.05	
11265 F	0.45	4.50	7.75	10.45
11266 F	0.09	1.35	4.75	0.90
11267 F	0.15	0.50	0.50	0.30
11268 F	0.04	0.10	0.10	0.05
11269 F	0.48	4.75	4.80	6.15
11270 F	0.12	0.50	0.62	0.10
11271 F	0.05	0.30	1.10	1.35
11272 F	0.07	0.15	2.55	1.85
11273 F	0.33	1.05	0.25	0.10
11274 F	0.14	4.80	10.80	7.05
11275 F	0.42	14.45	14.40	21.20

Assays made by:





# Sample Record

Received from Ed Kemp  
Sep. 29/69

Sample No.	Working Place	Sample Width	Location	Assay			
				Au	Ag	Pb	Zn
11201F	5900 Level Drift	0.84	Rt. wall, 40' past Sta. 12	0.10	2.60	4.10	6.70
11202F	✓ ✓ ✓	1.00	Left wall, 5' back from Sta. 13	0.02	0.10	0.10	0.10
11203F	✓ ✓ ✓	1.00	✓ ✓ , 15' past Sta. 13	0.02	0.10	0.05	0.05
11204F	✓ ✓ ✓	0.58	Face, 26' past Sta. 13	0.05	0.15	0.10	Tr.
11205F	✓ ✓ ✓	0.42	Face, 45' ✓ - -	0.16	0.10	Tr.	Tr.
11206F	✓ - -	1.00	Face, 56' - - -	0.02	1.00	0.20	Tr.
11207F	✓ ✓ ✓	0.67	Face of stub Raise, 3' above Dr. back, 46' p. Sta. 12	0.03	2.25	3.55	Tr.
11208F	5900 Level #1 Rse.	1.33	Face, 9' above drift back	0.25	12.00	42.20	12.15
11209F	✓ ✓ ✓	2.25	Face, 14½' ✓ ✓ ✓	0.23	9.15	14.60	29.10
11210F	✓ ✓ ✓	0.84	✓ , 19' ✓ ✓ ✓	0.22	6.65	10.05	15.20
11211F	✓ ✓ ✓	2.00	✓ , 26½' - - -	0.45	8.10	11.80	13.10
11212F	5700 Level X-Cut	2.33	Left wall, 55½' past Sta. 4	0.32	1.80	2.30	6.50
11213F	✓ ✓ ✓	2.17	Right wall, 63' past ✓	0.08	0.25	0.30	0.10
11214F	5900 Level #1 Rse.	1.25	Face, 32½' above drift back	0.35	10.05	11.50	9.70
11215F	✓ - -	1.75	✓ , 38½' - - -	1.06	4.65	8.10	3.80
11216F	✓ - -	0.92	✓ , 44½' - - -	0.40	10.00	14.60	8.20
11217F	- - -	1.25	✓ , 50' - - -	1.14	5.85	13.40	8.30
11218F	5700 Level Drift	2.25	Face of slash, 9' past X-Cut collar	0.26	4.55	5.30	4.70
11219F	5900 Level #1 Rse.	1.92	Face, 55' above drift back	0.73	6.00	5.50	6.80
11220F	✓ - -	2.00	✓ , 60½' - - -	0.28	9.10	8.20	4.50
11221F	✓ - -	2.08	✓ , 67½' - - -	0.14	10.25	8.10	9.90
11222F	✓ - -	3.00	✓ , 72½' - - -	0.13	2.65	0.60	0.30
11223F	5700 Level Drift	1.25	Face, 26' past Sta. 5	0.26	0.90	0.10	TR
11224F	5900 Level #1 Rse.	2.17	Face, 77½' above drift back	0.28	2.80	2.50	5.40
11225F	✓ - -	0.33	✓ , 83' - - -	0.14	1.50	1.60	0.10
11226F	✓ - -	0.17	✓ , 87½' - - -	0.02	0.05	TR	TR
11227F	5700 Level Drift		Grab sample along Rt. wall 53' to 73' past Sta. 5	0.12	0.5	0.22	0.34
11228F	✓ ✓ ✓	0.59	Face, 43½' past Sta. 6 (Center Face)	0.01	0.5	0.10	0.22
11229F	✓ - -	1.67	Right Face, 43½' past Sta. 6 <sup>2.26' e</sup>	0.032	11.6	6.8	5.0
11230F	✓ - -	2.33	Face, 49' past Sta. 6	0.04	14.80	9.19	6.64
11231F	✓ - -	2.58	✓ , 55½' ✓ ✓	0.01	1.1	2.40	0.19
11232F	✓ - -	2.83	✓ , 67½' ✓ ✓	0.01	0.3	0.37	0.24
11233F	5900 Level #2 Rse.	2.17	Face, 4' above drift back	0.65	9.5	18.62	10.82
11234F	5700 Level Drift	2.33	Face, 73' past Sta. 6	0.10	1.5	1.98	1.14
11235F	✓ - -	0.58	✓ , 85' ✓ ✓	0.03	<del>0.6</del>	0.47	0.19
11236F	5900 Level #2 Rse.	2.08	Face, 8' above drift back	0.57	8.7	12.69	18.60
11237F	✓ ✓ ✓	2.25	✓ , 14½' - - -	0.37	14.6	26.26	21.40
11238F	5900 Level #1 Rse.	1.33	Along Foot wall of Rse. from 81' to 87' above <sup>Drift Back</sup>	0.47	4.8	0.20	0.22



Sample Record

Sample No.	Working Place	Sample Width	Location	Assay			
				Pb	Ag	Pb	Zn
11239 F	5700 Level Drift	0.33	Face, 96' past Sta. 6	-	-	-	-
11240 F	5900 Level #2 Rse	1.75	Face, 21' above drift back	0.38	19.95	17.50	18.50
11241 F	5900 Level #1 Rse.	1.67	Face of slash, start of dogleg Rse. off main	0.09	5.25	5.90	4.80
11242 F	5700 Level Drift	1.17	Face, 26 1/2' past Sta. 7	0.26	2.95	1.46	0.20
11243 F	✓ ✓ ✓	2.00	✓, 38 1/2' ✓	0.17	0.30	0.34	TR
11244 F	5900 Level #2 Rse	1.08	Face, 27' above drift back	0.35	5.40	11.90	7.30
11245 F	5900 Level #1 Rse.	1.08	Face, 6' above dogleg collar	0.10	1.40	1.05	1.05
11246 F	5900 Level #2 Rse.	0.50	Face, 33 1/2' above drift back	0.40	5.75	16.60	13.80
11247 F	5900 Level #1 Rse	2.33	Face, 12 1/2' above dogleg collar	0.11	1.80	2.55	1.20
11248 F	5900 Level #2 Rse	1.08	Face, 40' above drift back	0.44	7.00	13.50	11.80
11249 F	5700 Level Drift	0.75	Face, 73' past Sta. 7	0.07	0.35	0.25	0.02
11250 F	✓ ✓ ✓	1.33	✓, 79' ✓	0.04	0.30	0.22	0.10
11251 F	5900 Level #1 Rse	1.25	Face, 18' above dogleg collar	0.05	1.15	0.95	1.40
11252 F	5900 Level #2 Rse	1.25	Face, 46' above drift back	0.52	9.10	11.60	10.20
11253 F	5900 Level #1 Rse	2.00	Face, 23 1/2' above dogleg collar	0.08	3.10	3.34	2.70
11254 F	5700 Level Drift	1.00	Face, 90' past Sta. 7	0.04	0.20	0.33	0.15
11255 F	✓ ✓ ✓	1.00	✓, 90' ✓ F.W. sect.	0.05 0.06	0.18 0.15	0.26 0.20	0.07 TR
11256 F	5900 Level #2 Rse	0.50	Face, 50 1/2' above drift back	0.07	0.40	0.80	0.20
11257 F	5900 Level #1 Rse	2.17	Face, 29' above dogleg collar	0.14	1.45	0.88	0.75
11258 F	✓ ✓ ✓	1.67	✓, 35' ✓	0.16	6.45	6.70	5.40
11259 F	5900 Level #2 Rse	0.50	Face, 62' above drift back	0.05	0.95	1.70	1.40

~~Missing Assays (Silver Star) - J.R. Wms sample books~~  
 1st request E. Romp attempt to find them. Silver Star  
704-626 W. Pender  
685-1745.

2nd " w/ Els O.K., ask Pete Williams to provide them.

Sample No	Origin	Location	Sampler's Notes	Width	As	Ag	Pb	Zn
11261	5900-#1 Rec.	Dogleg coll + 40 1/2"	well-min g2; Pb-Zn-py.	1.6'	0.22	13.55	24.20	17.60
11264 ✓	"	" " + 46 1/2"	Q2 + Oronto well min w Pb, Zn, + py.	4.0'	0.20	6.60	7.05	-
11269	"	" " + 52'	12" g2, Schist + gauge. Fair pot. Pb-py.	1.0'	0.48	4.75	4.80	6.15
11260 ✓	5700 Dn.	A8 + 53 1/2'	See Samplebook py.	1.5'	0.09	0.20	0.48	0.10
11262 ✓	"	A8 + 59 1/2'	" py.	0.4'	0.11	0.15	0.10	0.10
11263 ✓	"	A8 + 71 1/2'	" py. + Pb S.	0.4'	0.19	0.25	0.70	0.75
11265 ✓	"	A8 + 76'	" Q2 + Oronto Pb-Zn-py	0.7'	0.45	4.50	7.75	10.45
11266 ✓	"	A8 + 94 1/2'	" Q2 + pot. py. Pb-Zn-py	0.5'	0.09	1.35	4.75	0.90
11267 ✓	"	A9 + 18'	" sp Pb-Zn py.	1.3'	0.15	0.50	0.50	0.30
11268 ✓	"	A9 + 30'	" Q2-grown + cement py	1.2'	0.04	0.10	0.10	0.05
11270 ✓	"	A9 + 42'	" fair py. scant Pb.	1.0'	0.12	0.50	0.62	0.10
11271 ✓	"	A9 + 59'	" "	0.8'	0.05	0.30	1.10	1.35
11272 ✓	"	A9 + 71'	" py. bc pot. Pb.	0.4'	0.07	0.15	2.55	1.85
11273 ✓	"	A9 + 84'	"	1.0'	0.33	1.05	0.25	0.10
11274 ✓	"	A9 + 156'	" quartz w good Pb-Zn Pb	?	0.14	4.80	10.80	7.05
11275 ✓	"	A10 + 62'	?	1.7'	0.42	14.45	14.40	21.20
11276 ✓	"	A10 + 38'-44'	"ore"	0.8'	0.03	0.40	1.25	0.20
11277 ✓	"	A10 + 44'-50'	"ore"	?	0.08	1.00	3.50	1.25
11278 ✓	"	A10 + 50'-56'	"ore"	?	0.14	4.70	4.10	9.60
11279 ✓	"	A10 + 56'-62'	"ore"	?	0.41	13.50	6.75	14.70
11280 ✓	"	A10 + 62'-68'	"ore"	?	0.28	4.90	5.80	5.30
11281 ✓	"	A10 + 68'-74'	"ore"	1.5' ? Per multiplying	0.38	4.35	4.35	3.95
11282 ✓	"	A10 + 74'-80'	?	?	0.22	2.15	2.15	1.70
11283 ✓	"	A10 + 98'	"ore"	0.5'	0.25	6.55	3.75	0.25



Silver Star - 5700 level, Sept. 28/69

\* Following analyzed by "Atomic Absorption" -

Seymour Lab. 147 Riverside, N. Van phone 929-2228.

Mr. Chatterin - Planned below Oct. 14, 1969

No.	Location	Width	Remarks	* Requested checks by edridge redbeck	As	Ag	Pb	Zn
6069	<sup>ore shot</sup> Δ12+10' from sta. 121+08'	3.0'	Good qz-Pb-Zn	.15 <del>.09</del> .18	14.4 <del>12.1</del> 14.4	21.78 <del>21.2</del> 11.98	10.02 <del>10.46</del> 15.55	
6070	" +15'	3.2'	" "	* .12 0.18	<del>13.1</del> 21.8	<del>11.95</del> 18.81	<del>15.24</del> 21.00	
6071	" +20'	3.2'	High grade Pb-Zn	<del>.13</del> 0.22	<del>23.4</del> 16.10	<del>18.9</del> 16.59	<del>22.15</del> 18.04	
6072	" +25'	3.0'	ditto	<del>.12</del> 0.31	<del>15.32</del> 15.80	<del>16.9</del> 17.24	<del>17.6</del> 16.47	
6073	" +30'	2.3	ditto	* <del>.21</del> 0.02	<del>8.70</del> 1.70	<del>16.9</del> 3.38	<del>15.95</del> 1.98	
6074	" +35'	2.3	2 fair run or-py	<del>.03</del> 0.02	<del>1.88</del> 2.30	<del>3.72</del> 3.85	<del>1.30</del> 2.73	
6075	" +40'	2.0	3 scant 3 sp.	<del>.03</del> 0.02	<del>2.17</del> 1.70	<del>4.42</del> 4.19	<del>3.00</del> 1.42	
6076	" +45'	2.2	Fair	* <del>.02</del> 0.01	<del>1.74</del> 1.90	<del>4.70</del> 3.74	<del>1.20</del> 0.46	
6077	" +50'	3.6	lean / qz-bx	<del>.02</del> 0.02	<del>2.32</del> 2.30	<del>3.35</del> 2.67	<del>2.05</del> 0.96	
6078	" +55'	3.8	qz bx / scant	<del>.04</del> 0.03	<del>2.17</del> 0.60	<del>3.45</del> 2.11	<del>7.49</del> 0.52	
6079	" +60'	3.0	sp. Pb-Zn fair py	* <del>.03</del> 0.06	<del>0.73</del> 14.50	<del>2.45</del> 10.59	<del>0.27</del> 3.82	
6080	" +65'	3.4	scant Pb-Zn	<del>.03</del> 0.05	<del>13.40</del> 5.60	<del>12.40</del> 6.59	<del>2.96</del> 2.43	
"	" +70'	3.4	" " "	"	"	"	"	
6081	" +75'	4.7	Pb-Zn. Br. sil. scant patchy	<del>.04</del> 0.13	<del>5.80</del> 2.30	<del>8.00</del> 2.82	<del>2.05</del> 1.54	
6082	" +80'	2.0	Fair patchy + 9" band	* <del>.10</del> 0.04	<del>2.75</del> 11.90	<del>3.00</del> 11.03	<del>1.37</del> 3.49	
6083	" +85'	1.7	Referred patches	<del>.01</del> 0.06	<del>11.10</del> 3.00	<del>14.60</del> 7.42	<del>2.58</del> 4.10	
6084	Δ13+00 85.87'	3.0	Qz - good patches	<del>.03</del> 0.21	<del>3.32</del> 9.00	<del>8.25</del> 8.59	<del>3.50</del> 7.69	
6085	Δ13+05'	4.0	sp. patchy, unnumbered	* <del>.19</del> 0.03	<del>8.10</del> 1.90	<del>9.07</del> 2.05	<del>7.42</del> 5.95	
6086	Δ13+10' 95.87'	4.3	qz in good patches	<del>.10</del> 0.04	<del>2.00</del> .45	<del>2.30</del> 1.77	<del>5.80</del> 0.64	
6087	Δ13+15 100.87' ≈ 101'	2.5	60.6 ÷ 3.03' ditto Any width.	* <del>.04</del> Trace	<del>.043</del> 0.91	<del>0.40</del> 0.42	<del>0.38</del> 3.29	
6088	Δ13+22	1.4	qz in scant banded	* <del>.03</del> Trace	<del>.029</del> 0.91	<del>0.35</del> 0.42	<del>0.159</del> 3.29	

\* Ed Borup will be adv. by L. Jettley to pick up pulps & crusher rejects. They confirm they will mail reports as specified by wms -  
 1 copy wms  
 2 copy Silver Star office Van.  
 1 copy E. Borup, Home Hotel, Nelson.

Oct. 14. Lyle Jettley advises by phone that Olsen has sent in report that Silver Star do not have a mine & has recommended against granting \$20,000 for road work - puts some onus on wms to indicate have a starting mining operation.

SEYMOUR LABORATORY LTD.

147 Riverside Drive, North Vancouver, B.C. Tel. (604) 929-2228

Nº 579

CERTIFICATE OF ANALYSIS


TO SILVER STAR MINES  
#704 - 626 WEST PENDER ST.  
VANCOUVER 2, B.C.

TYPE OF SAMPLES ROCK  
No. of SAMPLES 20  
FILE No. 579 Our Inv. 1422

SAMPLE No.	OZ. PER TON GOLD	OZ. PER TON SILVER	% Pb	% Zn	%	%		
6069	0.09	12.1	21.20	10.46				
6070	0.12	13.1	11.95	15.24				
6071	0.13	23.4	18.90	22.15				
6072	0.12	15.32	16.90	17.60				
6073	0.21	8.7	16.90	15.95				
6074	0.03	1.88	3.72	1.30				
6075	0.03	2.17	4.42	3.00				
6076	0.02	1.74	4.70	1.20				
6077	0.02	2.32	3.35	0.205				
6078	0.04	2.17	3.45	0.749				
6079	0.03	0.73	2.45	0.270				
6080	0.03	13.4	12.40	2.96				
6081	0.04	5.8	8.00	2.05				
6082	0.10	2.75	3.00	1.31				
6083	0.01	11.1	11.60	2.58				
6084	0.03	3.32	8.25	3.50				
6085	0.19	8.10	9.07	7.42				
6086	0.10	2.00	2.30	5.80				
6087	0.04	0.043	0.40	0.380				
6088	0.03	0.029	0.35	0.159				

CC: Mr. Ed. Borup, c/o Hume Hotel, Nelson, B.C.  
Mr. W.M. Sharp, 171 W. Esplanade, N. Van.

(In Duplicate)



PROVINCIAL ASSAYER

DATE OCTOBER 22, 1969



TO:

Silver Star Mines Ltd.,

704 - 626 West Pender Street,

Vancouver, B. C.



## Certificate of Assay

WARNOCK HERSEY INTERNATIONAL LIMITED

COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

Member  
Canadian Testing  
AssociationPHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

FILE NO. 460-A-9078

DATE October 27, 1969

We Hereby Certify that the following are the results of assays made by us upon submitted Pulps samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
		\$							
Silver Star Mines									
6070	0.18	6.30	14.4	11.98	15.53				
6073	0.31	10.85	15.8	17.24	16.47				
6076	0.02	0.70	1.7	4.19	1.42				
6079	0.03	1.05	0.60	2.11	0.52				
6082	0.13	4.55	2.3	2.82	1.54				
6085	0.21	7.35	9.0	8.59	7.69				
6087	0.04	1.40	0.45	1.77	0.64				
6088	Trace		0.91	0.42	3.29				

*Checked OK against  
planned results.*

/ex

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum  
of one year by special arrangement.

Unless it is specifically stated otherwise, gold  
and silver values reported on these sheets have  
not been adjusted to compensate for losses and  
gain inherent in the fire assay process.

Gold calculated at \$ ..... per ounce

*H. Sheyde*

Provincial Assayer

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSIONS OF EXTRACTS FROM OR REGARDING  
OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

Copies sent to: Mr. R.J. Dealy and W.M. Sharp. 28-10-69 by ECB

TO:

Silver Star Mines Limited,  
704 - 626 West Pender Street,  
Vancouver, B. C.



## Certificate of Assay

**WARNOCK HERSEY INTERNATIONAL LIMITED**  
COAST ELDRIDGE PROFESSIONAL SERVICES DIVISION

125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA



Member  
Canadian Testing  
Association

PHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

FILE NO. 460-A-9145

DATE October 28, 1969

We Hereby Certify that the following are the results of assays made by us upon submitted Pulps samples

MARKED	GOLD		SILVER	Lead (Pb)	Zinc (Zn)				
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.				
6069 - 579	0.13	\$ 4.55	14.4	21.78	10.02	<i>Checked O.K. against phoned results.</i>			
6071	0.18	6.30	21.8	18.81	21.66				
6072	0.22	7.70	16.1	16.59	18.04				
6074	0.02	0.70	1.7	3.38	1.48				
6075	0.02	0.70	2.3	3.85	2.73				
6077	0.01	0.35	1.9	3.04	0.46				
6078	0.02	0.70	2.3	2.67	0.96				
6080	0.06	2.10	14.5	10.59	3.82				
6081	0.03	1.75	5.6	6.59	2.43				
6083	0.04	1.40	11.9	11.03	3.49				
6084	0.06	2.10	3.0	7.42	4.10				
6086	0.03	1.05	1.9	2.05	5.95				

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gain inherent in the fire assay process.

/er

ALL REPORTS ARE THE CONFIDENTIAL PROPERTY OF CLIENTS. PUBLICATION OF STATEMENTS, CONCLUSIONS OF EXTRACTS FROM OR REGARDING OUR REPORTS IS NOT PERMITTED WITHOUT OUR WRITTEN APPROVAL. ANY LIABILITY ATTACHED THERETO IS LIMITED TO THE FEE CHARGED.

Copies sent to: Mr. R.J. Dealy & Mr. W.M. Sharp 29-10-69 ECB

Gold calculated at \$ \_\_\_\_\_ per ounce

*H. Hayles*

Provincial Assayer