

Date August 16, 1969

MANEX MINING LTD. (NPL)

TSL ASSAYS

Driftwood 934/15

802279

Form #100

Property L.W. - Driftwood Cr.

Sample Record

E.I.C.

W.M. Sharp

Sample No.	Location	Description	ASSAYED FOR			Date Shipped
			Au	Ag	Cu	
2530	Sta 15	5.0' incl. 3 distinct Robert-cut well mineral stringers & interveining sp. mineralized siliceous rock. Cp. Tetrah. bn.	" 0.01	" 11.50	" 2.40	
2531	Key # 19-19A	Random chip of wide panel of sp. mineralized silicified volcanics w. frequent dispersed minor gash v. lts. pess. (exp. 15'-20' width)	" 0.01	" 0.35 0.35	" 0.06	
2532	Sta 19+54'	2.5' continuous chip across above zone.	" 0.01	" 0.67	" 0.12	
2533	Sta 11-B.	7.5' across sect. of siliceous Exposure: volcanics w. dispersed gash veinlets etc. of sp. bn. Tetrahedralite, incl 2 sects w. good Cu stain.	" 0.07	" 0.90	" 0.53	
2534	Sta 11-A.	6.0' across sect. of sheared Exposure: (stony) volcanics and silicified massive vics w. pods & sp. dissems of cp. bn. Tetrahedralite.	" 0.03	" 0.55	" 0.09	
19464	SHEAR ZONE	Located along road to top of mtn. Sampled across 6'-8' in bleached silicified zone w. a Trace of malachite.		✓ 0.92	✓ 0.17	



Certificate of Assay

COAST ELDRIDGE
PROFESSIONAL SERVICES DIVISION
WARNOCK HERSEY INTERNATIONAL LIMITED
125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

To
Manex Mining Ltd.,
200 - 535 Taurlaw Street
Vancouver, B.C.

We Hereby Certify that the following are the results of assays made by us upon submitted

MARKED	GOLD		SILVER	Zinc (Zn)	Copper (Cu)	PER CENT
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT	PER CENT	
# 1	0.08	2.80	145.9	3.57	15.24	
2	0.07	2.45	31.0	0.91	4.11	
3	0.67	23.45	115.4	1.91	13.88	

Gold calculated at \$ _____ per ounce

Note. Rejects retained one week.
Pulps retained one month.
Pulps and rejects may be stored for a maximum of one year by special arrangement.
Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gains inherent in the fire assay process.

H. Hays

181-P-15645

The Anaconda Company, Anaconda Sampler

RECEIVED FROM **JOHN P. MILLHOUSE**
 ADDRESS **BOX 2694**
SMITHERS, BRITISH COLUMBIA
CANADA
 MINE **DRIFTWOOD ORE**

ANACONDA, MONTANA, 59711 **JANUARY 6, 1969**

SMELTER LOT NO. **B-306 (DECEMBER a/c)**

CAR NUMBER	WEIGHTS			ASSAYS			TREATMENT CHARGE Dollars	PRICE PER TON Dollars	VALUE Dollars	Draft No.
	Pounds Gross	Per Cent Water	Pounds Dry	Per Cent Copper	Ounces Silver	Ounces Gold				
CP 341195	29,940	2.68	29,130	9.55	50.08	.106	5.25	154.71	2,253.97	
BAP By Freight									1,946.00	
									307.97	
<p>SILICA 38.2 ALUMINA 3.6 IRON 15.1 CaO 1.7</p>										
PAYMENT FOR METALS						TREATMENT				
Copper	less .5%	@ 41.7154	Less 3 1/2c	67.17	BASE	5.25				
Silver	100%	@ 173.6434	Less 6c	86.96	Add - 12c for each 1% Iron					
Gold	91%	@ 339.86	XXXI	3.83	Add - 10% of sum of metal payments in excess of \$15.00					
Silica		@			Deduct - 2.5c for each 1% Silica in excess of Alumina					
Date of Quotations					NET TREATMENT	+ Iron 5.25				

An extra charge of \$5.00 made for sampling all lots under ten tons.

Rates subject to change without notice.

Extensions and footings correct.

The Anaconda Co., Anaconda Sampler

By *[Signature]*

