


SAMPLE NUMBER	WIDTH FEET	GOLD OZ/T	SILVER OZ/T	LEAD %	ZINC %
F 14	1.0	0.05	12.83	13.2	9.0
F 11	1.5	0.02	10.60	19.6	17.9
F 8	2.2	0.04	10.36	8.1	22.4
F 9	2.5	0.10	79.94	66.57	7.9
F 10	8.6	0.04	28.76	24.3	19.8
F 12	3.8	0.02	5.07	3.3	6.9
F 13	3.0	0.02	14.29	14.6	15.6
F 16	4.2		13.6	10.0	10.2
F 17	0.5		6.28	4.4	11.6
F 18	5.0		5.40	1.2	7.2

$$\frac{130 \times 12}{9.5 \text{ cu ft/ton}} = \frac{1560}{9.5} = 164 \text{ tons per ft. of inclined depth}$$

Total length 130'
Av. width 12'

4750 E

POSSIBLE SHAPE OF ORE BODY




SAMPLE NUMBER	WIDTH FEET	GOLD OZ/T	SILVER OZ/T	LEAD %	ZINC %
F 1	2.0	0.03	10.24	8.7	41.2
F 2	3.4	0.02	9.58	3.8	7.4
F 3	2.5	0.10	12.06	11.0	8.8
F 4	1.3	0.06	4.54	3.6	45.4
F 5	1.5	0.16	11.44	8.8	21.2

4700 E

5400 N

N 05E5



SUNSHINE LARDEAU MINES LTD.

CAMBORNE, B. C.

ASSAY PLAN OF 814 DRIFT
No 8 LEVEL

DATE: Oct. 28, 1952

SCALE: 1" = 10'

8216

811203