

PROPERTY Salamet Mines Limited

812132

DIAMOND DRILL RECORD

HOLE NUMBER S 72

82E-2 Greenwood

LAT. 12,802.93.

LOCATION: DEP. 11,787.21

ELEVATION OF COLLAR 2775.63

DATUM

DIRECTION AT START: BEARING Vertical

LOGGED BY J. W. M. HOR. COMP.

PURPOSE OF HOLE VER. COMP.

TESTS

Ft.	Dip.	Ast. Bearing	Ft.	Dip.	Ast. Bearing	Core	
						Ft. Received	p.c. Recovery

SHEET NO. 1

SECTION FROM TO

STARTED October 22, 1956

COMPLETED Nov. 1, 1956.

ULTIMATE DEPTH 247

PROPOSED DEPTH

DRILLED BY National Diamond Drilling Co. Limited

HONEY PRINTING SERVICE, TORONTO—4604

Distance		ROCK	DESCRIPTION	Sample No.	Length Ft.	ANALYSIS					
From	To					Am.	Ag.	Pb.	Zn.	Cu.	Ave.
0	13	OVERBURDEN									
13	49	ACTINOLITE	Littel epidote at 29, 28' core recovered.								
49	55	DIKE	White phenocrysts in grey ground mass, 1' core								
55	128	ACTINOLITE	34' core recovered								
128	200	ACTINOLITE EPIDOTE	* Indistinct banding at 30° to core, 35' core								
200	247	ACTINOLITE	Pale grey to white, chert or silicious sections, 25' core recovered								
	247		End of hole								

RECEIVED
NOV 9 1956
NEWARK MASS CORP.

DIAMOND DRILL RECORD

PROPERTY..... Mines Limited
 LOCATION: LAT..... 10
 DEP..... 59
 ELEVATION OF COLL..... 002.33
 DATUM.....
 DIRECTION AT STAR..... N 87° 41' W
 LOGGED BY..... M. - 45°
 PURPOSE OF HOLE..... HOR. COMP.
 VER. COMP.

TESTS

ft.	Dip.	Ast. Bearing	ft.	Dip.	Ast. Bearing	Core	
						Ft. Received	p.c. Recovery

HOLE NUMBER..... 873
 SHEET NO.....
 SECTION FROM..... TO.....
 STARTED..... Oct. 24, 1956
 COMPLETED..... October 31, 1956
 ULTIMATE DEPTH..... 265
 PROPOSED DEPTH.....

DRILLED BY..... Boyles Bros.

HONEY PRINTING SERVICE, TORONTO—4504

Distance		LITHOLOGY	DESCRIPTION	Sample No.	Length Ft.	ANALYSIS												
From	To					Au.	Ag.	Pb.	Zn.	Cu.			Ave.					
0	13	RDEN																
13	114		Medium grained, few narrow section with coarse fragments															
114	134	LITE	Fine grained finely bedded 90° to core															
134	186		Interbedded with argillite															
186	197		White phenocrysts in green ground mass															
197	232	LITE	Fine grained black beds interbanded with sandstone tops up.															
232	259		White to grey medium grained															
259	265		(no core) few pcs. hematite.															
	265		End of hole															

RECEIVED
 NOV 9 1956
 WYRE & CO.

PROPERTY Salamat Mines Limited
 LOCATION: LAT. 12,400.36
 DEP. 12,003.05
 ELEVATION OF COLLAR 2757.94
 DATUM _____
 DIRECTION AT START: BEARING _____
 DIP Vertical
 LOGGED BY J. W. M. HOR. COMP. _____
 PURPOSE OF HOLE _____ VER. COMP. _____

DIAMOND DRILL RECORD

TESTS

Ft.	Dip.	Ast. Bearing	Ft.	Dip.	Ast. Bearing	Core	
						Ft. Received	p.c. Recovery

HOLE NUMBER S74
 SHEET NO. _____
 SECTION FROM _____ TO _____
 STARTED Nov. 1, 1956
 COMPLETED Nov. 8, 1956
 ULTIMATE DEPTH 334
 PROPOSED DEPTH _____

DRILLED BY National Diamond Drilling Co. Limited

HONEY PRINTING SERVICE, TORONTO—4804

Distance		ROCK	DESCRIPTION	Sample No.	Length Ft.	ANALYSIS								
From	To					Au.	Ag.	Pb.	Zn.	Cu.		Ave.		
0	19	OVERBURDEN												
19	142	EPIDOTE	Scattered pyrite throughout also scattered garnet, numerous hematite slips, small amount of chalcopryrite from 122 to end of section.											
			122.0 - 132.0 little chalco., 4% py.	12223	10(2)	Tr.	0.1				0.20			
			132.0 - 142.0 little chalco., 4% py.	12224	10(7)	Tr.	0.1				0.15			
142	222	ACTINOLITE	Minor epidote, brecciated, pyrite throughout, scattered specs chalcopryrite.											
			142.0 - 156.0 .5% chalco., 6% py.	12225	10(10)	Tr.	0.1				0.10			
			156.0 - 158.0 4% chalco., 4% py.	12226	2(1.5)	0.005	0.3				0.90			
			158.0 - 170.0 little chalco., 5% py.	12227	12(10)	Tr.	0.1				0.10			
			170.0 - 180.0 little chalco., 8% py.	12228	10(10)	Tr.	0.1				0.05			
			180.0 - 190.0 .5% chalco., 3% py.	12229	10(8)	Tr.	0.1				0.35			
			190.0 - 200.0 little chalco., 5% py.	12230	10(6)	Tr.	0.1				0.20			
			200.0 - 209.0 4% py.	12231	9(4)	Tr.	0.1				Tr.			
222	251	ACTINOLITE EPIDOTE	* Pale green epidote, 3% pyrite, considerable hematite from 245.											
251	315	ACTINOLITE	Pale green, few patches epidote, approximately 5% pyrite.											
315	334	CHERT	Brecciated, 2" core Recovered											
	334		End of hole											

RECEIVED
 NOV 27 1956
 NEWKIRK MINING CO.

DIAMOND DRILL RECORD

PROPERTY Mines Limited
 LOCATION: LAT. 49° 51.98
 DEP. 1.60
 ELEVATION OF COLLAR 2996.63
 DATUM
 DIRECTION AT START: BEARING Due West
 DIP - 45°
 LOGGED BY J. W. M. HOR. COMP.
 PURPOSE OF HOLE VER. COMP.

TESTS

Ft.	Dip.	Ast. Bearing	Ft.	Dip.	Ast. Bearing	Core	
						Ft. Received	p.c. Recovery

HOLE NUMBER 875
 SHEET NO.
 SECTION FROM TO
 STARTED Nov. 1, 1956
 COMPLETED Nov. 21, 1956
 ULTIMATE DEPTH 551
 PROPOSED DEPTH

DRILLED BY Boyles Bros.

HONEY PRINTING SERVICE, TORONTO—4604

Distance		ROCK	DESCRIPTION	Sample No.	Length Ft.	ANALYSIS							
From	To					Au.	Ag.	Pb.	Zn.	Cu.		Ave.	
0	14	OVERBURDEN											
14	59	ARKOSE	White, medium grained, few coarse fragments										
59	118	ARGILLITE	Interbedded argillite with sandstone, fine grained black argillite bedded 90° to core										
118	133	ARKOSE	Grey massive, maybe intrusive										
133	136	ARGILLITE											
136	150		No Core										
150	256	CONGLOMERATE	Angular Fragments in bluish matrix to 236, hematite cementing to 256										
256	284	SANDSTONE	Grey, bedding 90° to core, narrow lenses of conglomerate										
284	290	DIKE	White phenocrysts in dark green ground mass.										
290	483	CONGLOMERATE	Much hematite										
483	550	DIKE	Grey green with white and black phenocrysts										
550	551	CHERT	Bluish, fractured, few xls. pyrite										
	551		End of hole										

RECEIVED
 NOV 21 1956
 HONEY PRINTING SERVICE

PROPERTY Salamet Mines Limited
 LAT. 9202.79
 LOCATION: DEP. 10,807.18
 ELEVATION OF COLLAR 2938.66
 DATUM
 DIRECTION AT START: BEARING Due West
 DIP - 45°
 LOGGED BY J.W.M. HOR. COMP.
 PURPOSE OF HOLE VER. COMP.

DIAMOND DRILL RECORD

TESTS

Ft.	Dip.	Ast. Bearing	Ft.	Dip.	Ast. Bearing	Core	
						Ft. Received	p.c. Recovery

HOLE NUMBER S 78
 SHEET NO. 1
 SECTION FROM TO
 STARTED
 COMPLETED
 ULTIMATE DEPTH 2.5
 PROPOSED DEPTH

DRILLED BY Boyles Bros.

HONEY PRINTING SERVICE, TORONTO—4604

Distance		ROCK	DESCRIPTION	Sample No.	Length Ft.	ANALYSIS									
From	To					Au.	Ag.	Pb.	Zn.	Cu.			Avg.		
0	12	OVERBURDEN													
12	358.5	DIORITE	Fine and medium grained												
358.5	369	DIORITE DIKE	Fine grained, tan coloured, one foot diorite at 363 to 364												
3			358.5 - 360.0 little chalco.	12243	1.5(1.5)	0.03	0.2								
369	519.5	DIORITE	Fine and medium grained												
	519.5		End of hole												

0.65

Distance		LOG	DESCRIPTION	Sample No.	Length Ft.	ANALYSIS						
From	To					Au.	Ag.	Pb.	Zn.	Cu.	Ava.	
323	345	CHERT	Light grey and brown, pyrite throughout. Rec. 13'									
345	350	CHERT ?	Fine grained, medium green, hard. Rec. 4'									
350	447	JASPERED	Chert and quartz breccia cemented in chlorite and carbonates, fine pyrite; 360-368 leached and wuggy, 380-385 15% hematite, 392-405 leached and wuggy, 421-444 5% pyrite. Rec. 65'									
447	464	SKITE	Dark green, basaltic texture, feldspar phenocrysts. Rec. 11'									
	464		End of Hole.									

R

