

TO:

Copper Horn Mining - Ymir  
Samples chipped from Adit Feb 9/69  
335'82F-6  
Copper HornMember  
Canadian Testing  
AssociationPHONE: (604) 876-4111  
TELEX: 04-50353  
CABLE ADDRESS:  
ELDRICO

Cyprus Exploration Corporation Ltd.,

822 - 510 West Hastings Street,

Vancouver. B.C.

**Certificate of Assay**  
**COAST ELDRIDGE**  
**PROFESSIONAL SERVICES DIVISION**  
**WARNOCK HERSEY INTERNATIONAL LIMITED**  
125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

**812395**

FILE NO. A.3-C.4-69-4455

DATE February 14, 1969

We Hereby Certify that the following are the results of assays made by us upon submitted \_\_\_\_\_ ORE \_\_\_\_\_ samples

MARKED	GOLD		SILVER	Total Molybdenum (Mo)	PER CENT.	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.					
		\$							
2455 A	0.01	0.35	Trace	0.01					
B	Trace	--	Trace	0.01					
2456 A	0.01	0.35	0.3	0.005					
B	Trace	--	Trace	0.005					
2457 A	0.02	0.70	Trace	0.01					
B	Trace	--	Trace	0.005					
2458 A	Trace	--	Trace	0.01					
B	Trace	--	Trace	0.005					
2459 A	Trace	--	Trace	0.02					
B	Trace	--	0.1	0.02					
2460 A	Trace	--	0.1	0.02					
B	Trace	--	Trace	0.02					
2461 A	Trace	--	Trace	0.015					
B	Trace	--	0.2	0.01					
2462 A	Trace	--	Trace	0.01					

/hc

Gold calculated at \$ ----- per ounce

Note. Rejects retained one week.  
Pulps retained one month.  
Pulps and rejects may be stored for a maximum  
of one year by special arrangement.

Unless it is specifically stated otherwise, gold  
and silver values reported on these sheets have  
not been adjusted to compensate for losses and  
gains inherent in the fire assay process.

*H. Stages*

Provincial Assayer

TO:

Cyprus Exploration Corporation Ltd. (2)



PHONE: (604) 876-4111  
 TELEX: 04-50353  
 CABLE ADDRESS:  
 ELDRICO

**Certificate of Assay**  
**COAST ELDRIDGE**  
 PROFESSIONAL SERVICES DIVISION  
 WARNOCK HERSEY INTERNATIONAL LIMITED  
 125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

FILE NO. A.3-C.4-69-4455

DATE February 14, 1969

*We Hereby Certify* that the following are the results of assays made by us upon submitted \_\_\_\_\_ ORE \_\_\_\_\_ samples

MARKED	GOLD		SILVER	Total Molybdenum (Mo)	PER CENT.	PER CENT.	PER CENT.	PER CENT.	PER CENT.
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.					
		\$							
2462 B	Trace	--	0.1	0.01					
2463 A	0.06	2.10	0.3	0.01					
B	Trace	--	0.2	0.01					
2464 A	0.01	0.35	0.1	0.01					
B	Trace	--	Trace	0.01					
2465 A	Trace	--	0.2	0.01					
B	Trace	--	0.1	0.01					
2466 A	Trace	--	Trace	0.01					
B	Trace	--	Trace	0.005					
2467 A	Trace	--	Trace	0.005					
B	0.08	2.80	0.1	0.01					
2468 A	Trace	--	0.1	0.01					
B	Trace	--	0.1	0.005					
2469 A	Trace	--	0.1	0.01					
B	Trace	--	Trace	0.01					

/hc Gold calculated at \$ \_\_\_\_\_ per ounce

Note. Rejects retained one week.  
 Pulps retained one month.  
 Pulps and rejects may be stored for a maximum of one year by special arrangement.

Unless it is specifically stated otherwise, gold and silver values reported on these sheets have not been adjusted to compensate for losses and gains inherent in the fire assay process.

*H. Stages*

Provincial Assayer

TO:

Cyprus Exploration Corporation Ltd. (3)



PHONE: (604) 876-4111  
 TELEX: 04-50353  
 CABLE ADDRESS:  
 ELDRICO

**Certificate of Assay**  
**COAST ELDRIDGE**  
 PROFESSIONAL SERVICES DIVISION  
 WARNOCK HERSEY INTERNATIONAL LIMITED  
 125 EAST 4TH AVE. VANCOUVER 10, B.C., CANADA

FILE NO. A.3-C.4-69-4455

DATE February 14, 1969

*We Hereby Certify* that the following are the results of assays made by us upon submitted \_\_\_\_\_ ORE \_\_\_\_\_ samples

MARKED	GOLD		SILVER	Total Molybdenum (Mo)					
	OUNCES PER TON	VALUE PER TON	OUNCES PER TON	PER CENT.	PER CENT.	PER CENT.	PER CENT.	PER CENT.	PER CENT.
		\$							
2470 A	Trace	--	0.1	0.01					
B	Trace	--	0.1	0.01					

/hc

Gold calculated at \$ \_\_\_\_\_ per ounce

Note. Rejects retained one week.  
 Pulps retained one month.  
 Pulps and rejects may be stored for a maximum  
 of one year by special arrangement.

Unless it is specifically stated otherwise, gold  
 and silver values reported on these sheets have  
 not been adjusted to compensate for losses and  
 gains inherent in the fire assay process.

Provincial Assayer