

COMPARISON OF KERR ADDISON / MORRIS / BISHOP ANALYSES

1982

093L/12

TRENCH	SAMPLE No.	WIDTH (Feet)	Au oz/ST	Ag oz/ST	Pb %	Zn %	Cu %	Sb ppm	Hg ppm
A	Kerr C 101	2.5	0.062	0.52	0.33	0.22			
	Morris 793 D	2.5	0.136	0.85	0.66	0.38			2.5
	C 102	1.0	0.190	0.90	0.41	0.33			
	794 D	1.0	0.274	1.08	1.40	1.25			1.0
	C 103	2.5	0.460	1.24	2.45	2.45			
	795 D	3.0	0.772	1.44	4.65	2.97			3.2
	C 104	1.0	1.750	5.41	17.87	5.56			
	796 D	2.0	0.962	4.48	9.85	0.57			1.5
Bishop	C 105	2.0	0.270	0.50	0.74	0.14			
	793-96	8.5	0.571	1.94	4.32	1.44			
	C 101-05	9.0	0.420	1.30	2.97	1.55			
	28901	5.0	0.274	2.20	9.26	4.88	0.19		
F	C 107	15.0	0.005	0.01	0.03	0.0003			
	799 D	15.0	0.030	0.10	0.03	0.04			1.0
	28903	Grab	0.011	-	-	-	0.4		
G	C 108	2.0	0.260	1.86	5.45	10.75			
	797 D (?)	1.5	0.444	1.75	5.37	5.98			5.8
	28902	0.5	0.140	2.38	6.28	13.50	0.8		
I	C 109	3.0 ll to strike	0.005	0.03	0.0063	0.0010			
J	C 110	20"	0.001	0.01	0.0003	0.0003			
K	C 111	2.0	0.057	0.24	0.0086	0.2400			
	798 D	Grab	0.080	0.24	0.09	0.35			1.0
L	C 112	2.5	0.004	0.02	0.0023	0.0058			
	28905 ?	Grab	0.232	0.56	0.03	2.78	0.82	0.001	
M	28906 ?	2.5	0.112	0.30	0.01	0.54	0.08	0.001	
	C 114	3.0	0.004	0.01	0.0004	0.0092			
H	C 115	2.0	0.077	0.06	0.0025	0.0071			
	28904	Grab	0.109	0.45	0.74	3.85	0.10		
E	C 116	8"	0.358	2.30	4.80	2.40			
	C 117	5.0	0.241	2.54	11.20	2.26			
	C 118	Grab	0.548	4.74	20.50	16.25			
	800 D	X Grab	0.772	3.19	8.83	7.29			5.8

Bishop samples 28901 - 28906, Aug. 82  
 Tompson/Morris samples 793 D - 800 D, Aug. 82  
 Clendenan/Kerr Addison samples C101-105, C107-112, C114 - 118, Sept. 82

**821389**