

Kena 823052

RECEIVED

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

NOV 05 1981
KERR ADDISON MINES LTD.

PER _____

ANALYTICAL REPORT

Project Date of report Nov. 4/81.

File No. 1-861, 1-838R, 1-855R Date samples received Oct. 28/81.

Samples submitted by:

Company: Kerr Addison Mines

Report on: Geochem samples

..... 16 Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.
2.
3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu-Acid digestion-chemical analysis.

Au-Fire Assay.


Remarks:

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PROJECT No. _____
DATE: Nov. 4/81.
1-838R
File No. 1-861, 1-855R

SAMPLE No.	Cu %	Au oz/ton.				
3858 ✓ DH 4	.023	.001				
3868 ✓ " 4	.045	.001				
3878 ✓ " 4	.220	.001				
3892 ✓ 5	.136	.002				
3894 ✓ 5	.082	.001				
3990 ✓ 6	.326	.009				
3996 ✓ 6	.213	.002				
3998 ✓ 6	.224	.002				
4000 ✓ 6	.180	.002				
64590 ✓ 5	.094	.001				
64592 ✓ 5	.240	.002				
64616 ✓ 6	.142	.002				
64652 ✓ 6	.088	.003				
3852 ✓ DH 4	.110	.001				
3854 ✓ " 4	.195	.001				
3989 ✓ 6	.150	.001				


MINE-EN Laboratories Ltd.
CERTIFIED BY: 

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PROJECT No. _____
 DATE: Nov. 4/81.
- 1-838R
 File No. 1-861, 1-855R

SAMPLE No.	Cu %	Au			
		oz/ton			
3858	.023	.001			
3868	.045	.001			
3878	.220	.001			
3892	.136	.002			
3894	.082	.001			
3990	.326	.009			
3996	.213	.002			
3998	.224	.002			
4000	.180	.002			
64590	.094	.001			
64592	.240	.002			
64616	.142	.002			
64652	.088	.003			
3852	.110	.001			
3854	.195	.001			
3989	.150	.001			

MINE-EN Laboratories Ltd.
 CERTIFIED BY: 

REC'D
 SEP 10 1981
 KERR ADDISON MINES LTD.

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PER Nelson
 PROJECT No. _____
 DATE: Setp. 9/81.
 File No. 1-855

SAMPLE No.	Cu %	Ag	Au			
		oz/ton	oz/ton			
64655 ✓	.076	.02	.009	✓	↑ K-6 ↓	
57 ✓	.067	.02	.003	✓		
59 ✓	.028	.01	.002	✓		
64661 ✓	.014	.01	.004	✓		
64617	.045	.01	.001	✓		
19	.042	.02	.001	✓		
21	.062	.02	.001	✓		
23	.051	.03	.001	✓		
64625	.055	.02	.001	✓		
3834 ✓		.23	.048	✓		↑ K-3 ↓
36 ✓		.09	.012	✓		
40 ✓		.03	.011	✓		
42 ✓		no sample				
44 ✓		no sample				
46 ✓		no sample				
48 ✓		no sample				
52 ✓		.01	.002	✓	↑ K-4 ↓	
54 ✓		.01	.001	✓		
3856 ✓		no sample				
3800 ✓		.01	.009		↑ K-3 ↓	
22 ✓		.01	.008	✓		
24 ✓		.01	.007	✓		
26 ✓		.08	.009	✓		
28 ✓		.11	.023	✓		
30 ✓		.09	.006	✓		
32 ✓		.08	.014	✓		
3838 ✓		.01	.010	✓		
64663 ✓	.081	.09	.002	✓		

MINE-EN Laboratories Ltd.

CERTIFIED BY: _____

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

ANALYTICAL REPORT

Project Nelson Date of report Sept/9/81.

File No. 1-855 Date samples received Sept.3/81.

Samples submitted by:

Company: Kerr Addison Mines

Report on: Geochem samples

..... 23 Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu, Ag-Acid digestion-chemical analysis.

Au-Fire Assay.

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

ANALYTICAL REPORT

Project **Nelson** Date of report **Sept. 14/81.**

File No. **1-861** Date samples received **Sept. 8/81.**

Samples submitted by:

Company: **Kerr Addison Mines**

Report on: Geochem samples

..... **8** Assay samples

Copies sent to:

1. **Kerr Addison Mines, Vancouver, B.C.**

2. **H. Jones, Nelson, B.C.**

3.

Samples: Sieved to mesh Ground to mesh **-100**

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: **Cu, Ag-Acid digestion-chemical analysis.**

Au-Fire Assay.

Remarks:

RECEIVED

AUG 31 1981

KERR ADDISON MINES LTD.

PER _____

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

ANALYTICAL REPORT

Project Nelson Date of report Aug. 28/81.

File No. 1-781 Date samples received Aug. 24/81.

Samples submitted by: _____

Company: Kerr Addison Mines

Report on: _____ Geochem samples

_____ 54 _____ Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.
2. H. Jones, Nelson, B.C.
3. _____

Samples: Sieved to mesh _____ Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu, Ag-Acid digestion-chemical analysis.

Au-Fire Assay.

Remarks: _____


Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PROJECT No. Nelson
 DATE: Aug. 28/81.
 File No. 1-781

K.K. 81-2 + 81-4

SAMPLE No.	Cu %	Ag	Au		
		oz/ton	oz/ton		
↑ 3658 ✓		.13	.038	52-53.5	
60 ✓		.03	.002	35-36.5	
70 ✓		.11	.021	68.5-70	
72 ✓		.06	.010	71.5-73	
K2 74 ✓		.12	.035	74.5-76	
76 ✓		.08	.010	77.5-79	
88 ✓		.07	.003	95.5-97.0	
90 ✓		.13	.010	98.5-100	
92 ✓		.10	.024	101.5-103	
↓ 3694 ✓		.17	.134	104.5-106	
3851 ✓	.441	.09	.005	30-33	Hole #4
53 ✓	.076	.03	.002	36-39	
55 ✓	.156	.03	.002	42-45	
57 ✓	.243	.11	.003	48-51	
3859 ✓	.100	.03	.002	54-57	
3850 ✓	.306	.10	.003	# 27-30-30	

MINE-EN Laboratories Ltd.
 CERTIFIED BY: 

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C. *KK 81-3 + 81-4*

PROJECT No. Nelson
 DATE: Aug. 28/81.
 File No. 1-781

SAMPLE No.	Cu %	Ag	Au		
		oz/ton	oz/ton		
↑ 3901 ✓		.05	.009		
05 ✓		.12	.008		
07 ✓		.19	.010		
09 ✓		.12	.009		
11 ✓		.10	.018		
K3 3913 ✓		.04	.012		
3823 ✓		.03	.020	<i>37.5-39.0</i>	<i>1.5mg</i>
25 ✓		.12	.020		
27 ✓		.10	.013		
29 ✓		.18	.020		
31 ✓		.17	.010		
33 ✓		.22	.032		
35 ✓		<u>2.81</u>	<u>.343</u>	<i>46.3</i>	<i>54.6-54.75</i>
↓ 3837 ✓		.13	<u>.033</u>		
↑ 3915 ✓	.017	.02	.001		
K4 17 ✓	.039	.02	.002		
19 ✓	.045	.01	.002		
↓ 3921 ✓	.053	.02	.003	<i>D.D.H.#4</i>	
K3 3839 ✓	.014	.01	.010	<i>0-3</i>	
↑ 41 ✓	<u>.394</u>	.07	.007	<i>6-9</i>	
43 ✓	<u>.297</u>	.08	.008	<i>12-15</i>	
K4 45 ✓	<u>.416</u>	.10	.008	<i>18-21</i>	
47 ✓	<u>.271</u>	.05	.002	<i>24-27</i>	
↓ 3849 ✓	<u>.208</u>	.06	.002	<i>30-33</i>	
K3 3906 ✓		.31	.041		
3914 ✓	.024	.04	.011		

0-33 m AV = 0.320% Cu

MINE-EN Laboratories Ltd.

CERTIFIED BY: 

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

RECEIVED
AUG 31 1981
KERR ADDISON MINES LTD.
BER

ANALYTICAL REPORT

Project Date of report Aug. 26/81.

File No. 1-766 Date samples received Aug. 23/81.

Samples submitted by:

Company: Kerr Addison Mines

Report on: Geochem samples

..... 8 Assay samples

Copies sent to:

1. Kerr Addison, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Fire Assay.

Remarks:

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

ANALYTICAL REPORT

Project Date of report **Aug. 26/81.**

File No. **1-766** Date samples received **Aug. 23/81.**

Samples submitted by:

Company: **Kerr Addison Mines**

Report on: Geochem samples

..... **8** Assay samples

Copies sent to:

1. **Kerr Addison, Vancouver, B.C.**

2. **H. Jones, Nelson, B.C.**

3.

Samples: Sieved to mesh Ground to mesh **-100**

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: **Fire Assay.**

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

ANALYTICAL REPORT

Project Nelson Date of report Aug. 21/81.

File No. 1-726 Date samples received Aug. 17/81.

Samples submitted by: H. Jones

Company: Kerr Addison Mines

Report on: Geochem samples

..... 24 Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu, Ag-Acid digestion-chemical analysis.

..... Au-Fire Assay.

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

ANALYTICAL REPORT

Project Date of report **Aug. 19/81.**.....

File No. **1-711** Date samples received **Aug. 15/81.**.....

Samples submitted by:

Company: **Kerr Addison Mines**

Report on: **Geochem samples**

..... **68** **Assay samples**

Copies sent to:

1. **Kerr Addison Mines, Vancouver, B.C.**.....

2. **H. Jones, Nelson, B.C.**.....

3.

Samples: Sieved to mesh Ground to mesh **-100**.....

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: **Au-Fire assay.**.....

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

Sheet KK 81-2

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PROJECT No. Nelson
 DATE: Aug. 21/81
 File No. 1-726

SAMPLE No.	Cu	Ag	Au	Depth (m)
	%	oz/ton	oz/ton	
3649	.035	.11	.007	38.5-40 <i>#49</i> 41.5-43 <i>#51</i>
51	.032	.10	.006	
53	.011	.10	.012	44.5-46
55	.014	.04	.009	47.5-49
57	.079	.08	.011	50.5-52
59	.032	.08	.038	53.5-55
61	.040	.09	.018	56.5-57.8
62	.043	.18	.031	57.8-58.8
63	.057	.12	.023	58.8-59.6
65	.005	.03	.002	61.0-62.5
67	.017	.06	.010	64.0-65.5
69	.014	.08	.008	67.0-68.5
71	.079	.09	.024	70.0-71.5
73	.080	.08	.011	73.0-74.5
75	.057	.10	.084	76.0-77.5
77	.003	.01	.003	79.0-80.5
79	.003	.01	.002	82.0-83.5
81	No Sample			85.0-86.5
83	.003	.01	.002	88.0-89.5
85	.004	.02	.001	91.0-92.5
87	.050	.09	.017	94.0-95.5
89	.058	.09	.059	97.0-98.5
91	.128	.10	.030	100.0-101.5
93	.038	.09	.091	103.0-104.5
3664	.039	.03	.008	59.6-61.0
<i>3695</i>		<i>.12</i>	<i>.045</i>	<i>106-107.5</i>
<i>97</i>		<i>.04</i>	<i>.048</i>	<i>109-110.5</i>

99

.10

.171

MINE-EN Laboratories Ltd.

-112-113.5

CERTIFIED BY: 

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C. V6E 2S1.


PROJECT No. _____
 DATE: Aug. 19/81.
 File No. 1-711

R.K 81-1

SAMPLE No. <i>0-20 = 0.13,</i>	Au oz/ton	<u>Depth</u>		
3402 ✓	.001	64.5-66.0 25-30		
04 ✓	.002	67.5-69.0 40.		
06 ✓	.003	70.5-72 50		
08 ✓	.002	73.5-75.0 60		
10 ✓	.001	76.5-78.0 70	3411	.008
12 ✓	<u>.047</u>	79.5-81.0 70-80	3413	.010
14 ✓	.009	82.5-84.0		
16 ✓	.001	85.5-87.0		
18 ✓	.001	88.5-90 91.5-93.0		
20 ✓	.001	93.0-94.5 94.5-96.0	91.5-93.0	
22 ✓	.011	94.5-96.0		
24 ✓	.001	97.5-99.0		
26 ✓	.002	100.5-102.0		
28 ✓	.001	103.5-105.0		
30 ✓	.002	106.5-108.0		
32 ✓	.002	109.5-111.0		
34 ✓	.003	112.5-114.0		
36 ✓	.015	115.5-117.0 115-120		
38 ✓	.001	118.5-120		
40 ✓	.001	121.5-123		
42 ✓	.001	124.5-126.		
44 ✓	.002	127.5-129.0		
46 ✓	.009	130.5-132.0		
48 ✓	.003	133.5-135.0		
50 ✓	.002	136.5-138.0		
52 ✓	.001	139.5-141.0		
54 ✓	.001	142.5-144.0		
56 ✓	.001	145.5-147.0 145-150		
58 ✓	.001	148.5-150.0		
3460 ✓	.001	151.5-153.0		

MINE-EN Laboratories Ltd.

CERTIFIED BY: _____



MIN-EN LABORATORIES LTD.

705 WEST 15TH STREET, NORTH VANCOUVER, B.C. V7M 1T2

PHONE: (604) 980-5814 OR (604) 988-4524

Hold at K K 81-1

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C. V6E 2S1.

K-1

PROJECT No. _____
 DATE: Aug. 19/81.
 File No. 1-711

SAMPLE No.	Au					
	oz/ton					
3462 ✓	.001	154.5-156.7				
64 ✓	.002	157.5-159.05				
66 ✓	.003	160.5-162.0				
68 ✓	.001	163.5-165				
70 ✓	.002	166.5-168.0				
72 ✓	.002	169.5-171.0				
74 ✓	.001	172.5-174				
76 ✓	.001	175.5-177 375-400				
78 ✓	.001	178.5-180				
80 ✓	.001	181.5-182.3				
82	.002	5.5-7.0				
84	.010	8.5-10.0				
86	.006	11.5-13.0				
88	.001	14.5-16.0			3489	.005
90	.071	17.5-19.0 465-470			3491	.003
92	.002	20.5-22.0				
94	.002	25.0-26.5	23.5-25.0			
96	.001	26.5-28.0 495-500				
98	.002	28.0-29.5	29.5-31.0			
3500	.002	32.5-34.0			3601	.048
3602	.031	35.5-37.0 525-530			3603	.071
04	.002	38.5-40.0				
06	.010	41.5-43.0	41.2-41.42		AV 3601-3603 =	.0496/1.5M = 14.76'
08	.002	44.5-46.0	43.0-44.5			
10	.011	47.5-49.0	46.0-47.5			
12	.016	50.5-52.0	48.6-49.0			
14	.002	53.5-55.0	50.5-52.0			
3616	.001	56.5-58.0	53.5-55.0		3617	.005
18	.040	56.5-58.0	56.5-58.0		3619	.029
3620	.008	59.5-61.0				

MINE-EN Laboratories Ltd.

CERTIFIED BY: _____

[Handwritten Signature]

RECEIVED

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

AUG 31 1981
KERR ADDISON MINES LTD.

PER

ANALYTICAL REPORT

Project Date of report Aug. 26/81.

File No. 1-753 Date samples received Aug. 21/81.

Samples submitted by:

Company: Kerr Addison Mines

Report on: Geochem samples

..... 58 Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Ag-Acid digestion-chemical analysis.

Au-Fire Assay.

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PROJECT No. _____
 DATE: Aug. 26/81.
 File No. 1-753

KK 81-2

SAMPLE No.	Ag	Au		
	oz/ton	oz/ton		
3695 ✓	.12	.045	106-107.5	↑
97 ✓	.04	.048	109-110.5	
99 ✓	.10	.171	118-118.5	
3701 ✓	.10	.018	115-116.5	
03 ✓	.05	.014	118-119.5	
05 ✓	.11	.049	121-122.5	
07 ✓	.07	.013		
09 ✓	.01	.006		
11 ✓	.01	.010		
13 ✓	.05	.006		
15 ✓	.07	.019		
17 ✓	.02	.008		
19 ✓	.02	.008		
21 ✓	.05	.002	145-146.5	
23 ✓	.07	.002		
25 ✓	.02	.002		
27 ✓	.02	.003		
29 ✓	.03	.018		
31 ✓	.16	.011		
3733 ✓	.12	.016		
3734 ✓	.10	.009	164.5-167	↑
3735 ✓	.11	.010	177.0-179.2	
3737 ✓	.02	.006		
39 ✓	.03	.003		
41 ✓	.03	.009		
43 ✓	.07	.021		
45 ✓	.03	.007		
47 ✓	.07	.010		
49 ✓	.03	.007		
3751 ✓	.05	.027	153.-154.5	↓

KK 81-2

KK 81-3

MINE-EN Laboratories Ltd.

CERTIFIED BY: _____

MIN-EN LABORATORIES LTD.

705 WEST 15TH STREET, NORTH VANCOUVER, B.C. V7M 1T2

PHONE: (604) 980-5814 OR (604) 988-4524

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PROJECT No. _____
 DATE: Aug. 26/81.
 File No. 1-753

SAMPLE No.	Ag	Au			
	oz/ton	oz/ton			
3753 ✓	.03	.002			
55 ✓	.03	.009			
57 ✓	.05	.010			
59 ✓	.05	.009			
61 ✓	.02	.009			
63 ✓	.02	.009			
65 ✓	.03	.019			
67 ✓	.03	.019			
69 ✓	.06	.020			
71 ✓	.07	.010			
73 ✓	.03	.013			
75 ✓	.02	.003			
77 ✓	.06	.004		KK81-3	
79 ✓	.06	.010			
81 ✓	.05	.003			
83 ✓	.07	.002			
3785 ✓	.02	.001			
3805 ✓	.01	.001			
07 ✓	.01	.001			
09 ✓	.02	.001			
11 ✓	.02	.002			
13 ✓	.02	.004			
15 ✓	.02	.003			
17 ✓	.02	.011			
19 ✓	.04	.010			
3821 ✓	.02	.003			
3801 ✓	.02	.001			
3803 ✓	.02	.010			

MINE-EN Laboratories Ltd.

CERTIFIED BY: _____

RECEIVED

SEP-8 1981

KERR ADDISON MINES LTD.

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PROJECT No. _____

DATE: Sept. 5/81.

File No. 1-838

SAMPLE No.	Cu %	Ag oz/ton	Au oz/ton			
	3696 ✓		.10	.023	↑ K-2 ↓ K-6 ↓	
3698 ✓		.06	.027			
3700 ✓		.08	.047			
3702 ✓		.09	.027			
3704 ✓		.08	.015			
3706 ✓		.02	.011			
3742 ✓		.15	.076			
3744 ✓		.01	.003			
3750 ✓		.04	.005			
3752 ✓		.01	.004			
3768 ✓		.03	.028			
3770 ✓		.08	.025			
3989 ✓	.133	.09	.002			
3991 ✓	.125	.03	.002			
3993 ✓	.167	.03	.001			
3995 ✓	.185	.06	.005			
3997 ✓	.134	.03	.002			
3999 ✓	.122	.02	.001			
64651 ✓	.182	.07	.002			
64653 ✓	.056	.02	.001			
64603 ✓	.059	.06	.002			
64605 ✓	.051	.03	.005			
64607 ✓	.063	.06	.001			
64609 ✓	.090	.06	.001			
64611 ✓	.092	.09	.002			
64613 ✓	.124	.03	.001			
64615 ✓	.088	.09	.003			

MINE-EN Laboratories Ltd.

CERTIFIED BY: 

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

RECEIVED

KERR ADDISON MINES LTD.

FER

ANALYTICAL REPORT

Project Nelson Date of report Sept. 5/81.

File No. 1-838 Date samples received Sept. 1/81.

Samples submitted by:

Company: Kerr Addison Mines,

Report on: Geochem samples

27

Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu, Ag-Acid digestion-chemical analysis.

Au-Fire Assay.

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

RECEIVED

SEP 15 1981

KERR ADDISON MINES LTD.

ANALYTICAL REPORT

PER _____

Project Nelson Date of report Sept. 14/81.

File No. 1-861 Date samples received Sept. 8/81.

Samples submitted by: _____

Company: Kerr Addison Mines

Report on: _____ Geochem samples

_____ 8 _____ Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3. _____

Samples: Sieved to mesh _____ Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu, Ag-Acid digestion-chemical analysis.

Au-Fire Assay.

Remarks: _____

SPECIALISTS IN MINERAL ENVIRONMENTS

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

RECEIVED

SEP-8 1981
KERR ADDISON MINES LTD.

PER

ANALYTICAL REPORT

Project Nelson Date of report Sept. 3/81.

File No. 1-821 Date samples received Aug. 31/81.

Samples submitted by:

Company: Kerr Addison Mines

Report on: Geochem samples

..... 15 Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu, Ag-Acid digestion-chemical analysis.

Au-Fire Assay.

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

ANALYTICAL REPORT

Project Nelson Date of report Sept. 2/81.

File No. 1-809 Date samples received Aug. 27/81.

Samples submitted by: H. Jones

Company: Kerr Addison Mines

Report on: Geochem samples

40 Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu, Ag-Acid digestion-chemical analysis.

Au-Fire Assay.

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

MIN-EN LABORATORIES LTD.

705 WEST 15TH STREET, NORTH VANCOUVER, B.C. V7M 1T2

PHONE: (604) 980-5814 OR (604) 988-4524


Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C. KK 81-4 & KK 81-5

PROJECT No. Nelson
 DATE: Sept. 2/81.
 File No. 1-809

SAMPLE No.	Cu %	Ag	Au			
		oz/ton	oz/ton			
3935 ✓ <i>K-4</i>	.072	.02	.001	162-165		
37 ✓	.025	.01	.002	156-159		
39 ✓	.023	.02	.001	150-153		
41 ✓	.018	.01	.001	144-147		
3943 ✓ <i>K-4</i>	.077	.01	.010	138-141		
3873 ✓	.269	.02	.008	96-99 ✓		
75 ✓	.212	.03	.003	102-105 ✓		
77 ✓	.201	.01	.003	108-111 ✓		
79 ✓	.128	.01	.002	114-117 ✓		
81 ✓	.084	.01	.002	121-124 ✓		
3883 ✓ <i>K-4</i>	.152	.01	.002	127-130 ✓		
3872 ✓	.225	.03	.003	93-96 ✓		
74 ✓	.240	.01	.002	99-102 ✓		
3876 ✓	.265	.01	.003	105-108 ✓		
3945 ✓ <i>K-4</i>	.122	.01	.002	133-135 ✓		
47 ✓ <i>K-5</i>	.109	.01	.002	96-99		
49 ✓	.090	.01	.001	102-105		
51 ✓	.124	.01	.002	108-111	Send in	111-114
53 ✓	.200	.01	.002	114-117	9 mo. 202	117-120 123-126
55 ✓	.204	.02	.003	120-123		
3885 ✓ <i>K-5</i>	.056	.01	.002	0-9		
87 ✓	.102	.01	.002	15-16		
89 ✓	.079	.01	.001	18-21		
91 ✓	.138	.04	.008	24-27		
93 ✓	.288	.02	.009	30-33		
3895 ✓	.033	.27	.003	36-39		
3888 ✓ <i>K-5</i>	.204	.01	.003	16-18		
3861 ✓ <i>K-4</i>	.120	.02	.011	60-63 ✓		
63 ✓	.158	.01	.007	66-69 ✓		
3865 ✓	.159	.01	.006	72-75		

MINE-EN Laboratories Ltd.

CERTIFIED BY: 

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C. KK 81-5 + K-L 81-2

PROJECT No. Nelson
 DATE: Sept. 2/81.
 File No. 1-817

SAMPLE No.	Cu %	Ag	Au		
		oz/ton	oz/ton		
3957 ✓	.034	.22	.001	126-129.0	
59 ✓	.024	.02	.002	132-133.0	
61 ✓	.030	.01	.001	138-141.0	
63 ✓	.046	.02	.001	144-147	
65 ✓	.043	.01	.001	150-153	
67 ✓	.062	.03	.001	156-159	
69 ✓	.106	.02	.001	162-165	
3971 ✓	.051	.01	.001	167-170	
3897 ✓	.086	.01	.002	42-45	
3899 ✓	.009	.01	.002	48-51	
64577 ✓	.031	.01	.002	57 60-57	
79 ✓	.014	.02	.001	60-63	
81 ✓	.029	.01	.002	66-69	
83 ✓	.035	.01	.002	72-75	
64585 ^{K5} ↓	.053	.01	.001	78-81	
3648 ^{K2} ✓	no sample			37-38.5	
50 ✓	no sample			40-41.5	
52 ✓	no sample			43-44.5	
56 ✓	no sample			49-50.5	
3686 ✓	no sample			92.5-94	

MINE-EN Laboratories Ltd.
 CERTIFIED BY: 

MIN-EN Laboratories Ltd.

705 WEST 15th STREET,
NORTH VANCOUVER, B.C., CANADA V7M 1T2
TELEPHONE (604) 980-5814

ANALYTICAL REPORT

Project Nelson Date of report Sept. 2/81.

File No. 1-817 Date samples received Aug. 28/81.

Samples submitted by: H. Jones

Company: Kerr Addison Mines

Report on: Geochem samples

15 Assay samples

Copies sent to:

1. Kerr Addison Mines, Vancouver, B.C.

2. H. Jones, Nelson, B.C.

3.

Samples: Sieved to mesh Ground to mesh -100

Prepared samples stored discarded

rejects stored discarded

Methods of analysis: Cu, Ag-Acid digestion-chemical analysis.

Au-Fire Assay.

Remarks:

SPECIALISTS IN MINERAL ENVIRONMENTS

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C. V6E 2S1.

PROJECT No. _____
 DATE: Aug. 19/81.
 File No. 1-711

SAMPLE No.	Au				
	oz/ton				
		<i>Ho/ke K 81-1</i>			
3402	.001	<i>64.5-66.0</i>			
04	.002	<i>67.5-69.0</i>			
06	.003	<i>70.5-72.0</i>			
08	.002	<i>73.5-75.0</i>			
10	.001	<i>76.5-78.0</i>			
12	.047	<i>79.5-81.0</i>			
14	.009	<i>82.5-84.0</i>			
16	.001	<i>85.5-87.0</i>			
18	.001	<i>88.5-90.0</i>			
20	.001	<i>91.5-93.0</i>			
22	.011	<i>94.5-96.0</i>			
24	.001	<i>97.5-99.0</i>			
26	.002	<i>100.5-102.0</i>			
28	.001	<i>103.5-105.0</i>			
30	.002	<i>106.5-108.0</i>			
32	.002	<i>109.5-111.0</i>			
34	.003	<i>112.5-114.0</i>			
36	.015	<i>115.5-117.0</i>			
38	.001	<i>118.5-120.0</i>			
40	.001	<i>121.5-123.0</i>			
42	.001	<i>124.5-126.0</i>			
44	.002	<i>127.5-129.0</i>			
46	.009	<i>130.5-132.0</i>			
48	.003	<i>133.5-135.0</i>			
50	.002	<i>136.5-138.0</i>			
52	.001	<i>139.5-141.0</i>			
54	.001	<i>142.5-144.0</i>			
56	.001	<i>145.5-147.0</i>			
58	.001	<i>148.5-150.0</i>			
3460	.001	<i>151.5-153.0</i>			

MINE-EN Laboratories Ltd.

CERTIFIED BY: 

Certificate of Assay

Plotted on drill logs

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C. V6E 2S1.

PROJECT No. _____
 DATE: Aug. 19/81.
 File No. 1-711

SAMPLE No.	Au				
	oz/ton	<i>Hole # K 81-1</i>			
3462	.001	154.5	- 156.0		
64	.002	157.5	- 159.0		
66	.003	160.5	- 162.0		
68	.001	163.5	- 165.0		
70	.002	166.5	- 168.0		
72	.002	169.5	- 171.0		
74	.001	172.5	- 174.0		
76	.001	175.5	- 177.0		
78	.001	178.5	- 180.0		
80	.001	181.5	- 182.3		
82	.002	5.5	- 7.0		
84	.010	8.5	- 10.0		
86	.006	11.5	- 13.0		
88	.001	14.5	- 16.0		
90	.071	17.5	- 19.0		
92	.002	20.5	- 22.0		
94	.002	23.5	- 25.0		
96	.001	26.5	- 28.0		
98	.002	29.5	- 31.0		
3500	.002	32.5	- 34.0		
3602	.031	35.5	- 37.0		
04	.002	38.5	- 40.0		
06	.010	41.2	- 41.42		
08	.002	43.0	- 44.5		
10	.011	46.0	- 47.5		
12	.016	48.6	- 49.0		
14	.002	50.5	- 52.0		
16	.001	53.5	- 55.0		
18	.040	56.5	- 58.0		
3620	.008	59.5	- 61.0		

MINE-EN Laboratories Ltd.

CERTIFIED BY: 

Certificate of Assay

TO: Kerr Addison Mines,
703-1112 W. Pender St.,
Vancouver, B.C.

PROJECT No. Nelson
 DATE: Aug. 28/81.
 File No. 1-781

SAMPLE No.	Cu %	Ag oz/ton	Au oz/ton			
	3901		.05	.009		
05		.12	.008			
07		.19	.010			
09		.12	.009			
11		.10	.018			
3913		.04	.012			
3823		.03	.000			
25		.12	.020			
27		.10	.013			
29		.18	.020			
31		.17	.010			
33		.22	.032			
35		2.81	.343			
3837		.13	.033			
3915	.017	.02	.001			
17	.039	.02	.002			
19	.045	.01	.002			
3921	.053	.02	.003			
3839	.014	.01	.010			
41	.394	.07	.007			
43	.297	.08	.008			
45	.416	.10	.008			
47	.271	.05	.002			
3849	.208	.06	.002			
3906		.31	.041			
3914	.024	.04	.011			

MINE-EN Laboratories Ltd.

CERTIFIED BY: 