


Atlenian Resources Ltd.
 GREENWOOD GOLD-COPPER PROPERTY
 SURFACE PLAN
 MAIN ZONE - NEAR SURFACE SECTION
 1" = 50 ft.

ORE BLOCK No.	SECTION	THICKNESS	DIP LENGTH	STRIKE LENGTH	VOLUME ft^3	TONNAGE @ 100 lb/ton	Ave Grade (Cu/Au)	Stripping Ratio
1	20+75N	55	80	30	132000	13200	0.90/0.10	2.86:1
2	20+15N	30	105	40	126000	12600	0.38/0.05	3.06:1
3	19+90N	16.5	195	50	160875	16090	1.76/0.05	3.73:1
4	19+15N	30	50	60	90000	9000	0.93/0.094	2.6:1
5	18+85N	22	190	60	250800	25080	0.78/0.06	6.46:1
6	18+15N	24	173	90	373680	37368	0.85/0.058	2.82:1

113 340 Tons 0.92% Cu 0.064 oz/ton Au Stripping ratio 4.65:1



PLAN
 MINERAL RESERVE BOOKS
 LEXINGTON Cu-Au PROPERTY
 Greenwood, B.C. BRP-2
 Outline By: F. Chou Dec 2/80
 (in color)
 Sheet 2 of 2

823228