



CONSOLIDATED  
**COLUMBIA RIVER MINES**

LTD. (N.P.L.)

3rd Floor, 78 Water Street, Vancouver, B.C. V6B 1A1 Telephone 689-3911

823637

August 22, 1975

Vancouver Stock Exchange  
536 Howe Street  
Vancouver, B.C.

Dear Sirs:

RE: Ruth Vermont Mine Ore Reserves  
Golden, B.C.

Mr. Laurence Sookochoff , P. Eng. of T.R. Tough & Associates  
has reported the following ore reserves in the Ruth Vermont  
silver, lead & zinc Mine of which a copy is attached.

Yours very truly,

CONSOLIDATED  
COLUMBIA RIVER MINES LTD.

M.M. Pardek,  
President

MMP:rl

August 20, 1975

Board of Directors  
Consolidated Columbia River Mines  
3rd Floor - 73 Water St.  
Vancouver, B.C.

Dear Sirs:

The following is a resume of ore reserves on your Ruth Vermont Property:

NELSON OREBODY

<u>Class</u>	<u>Tonnage</u>	<u>Grade</u>		
		oz. Ag/Ton	%Pb	%Zn
Proven	242,500	4.66	3.76	5.52
Probable	350,000	3.73	2.70	3.95
Inferred	<u>450,000</u>	-	-	-
	1,042,500			

PINE TREE VEIN

<u>Class</u>	<u>Tonnage</u>	<u>Grade</u>		
		oz. Ag/Ton	%Pb	%Zn
Proven	60,000	10.00	6.61	5.80
Probable	35,000	10.00	6.61	5.80
Inferred	<u>164,400</u>	-	-	-
	259,400			

BLACKSMITH VEIN

<u>Class</u>	<u>Tonnage</u>	<u>Grade</u>		
		oz. Ag/Ton	%Pb	%Zn
Proven	4,700	9.10	4.72	2.82
Probable	8,400	9.10	4.72	2.82
Inferred	<u>94,000</u>	-	-	-
	107,100			

...../2

Board of Directors  
August 20, 1975  
Page 2

WIND LASS VEIN

<u>Class</u>	<u>Tonnage</u>	<u>Grade</u>		
		oz. Ag/ton	%Pb	%Zn
Proven	3,750	18.8	6.10	2.94
Probable	5,000	18.8	6.10	2.94
Inferred	<u>50,000</u>	-	-	-
	58,750			


Total tonnage in the proven, probable & inferred categories for the Ruth Vermont Mine is 1,467,750.

Total tonnage of proven ore is 310,950 with a weighted average grade of 5.95 oz/ton Ag; 5.03% Pb; and 5.53% Zn.

In addition to the silver, lead and zinc mineralization, tungsten in the form of scheelite occurs in a quartz vein along the footwall of the ore zone. 115 feet of the vein along the lower Nelson Tunnel has been sampled which returned an average of 3.12%  $WO_3$  over an average width of 1.18 feet. One sample returned 18%  $WO_3$ .

A circuit in the mill to recover the tungsten values is planned.

Respectfully submitted,

A circular professional engineer seal for Laurence Sookochoff, a member of the Professional Engineers of British Columbia. The seal contains the text "PROFESSIONAL ENGINEER OF BRITISH COLUMBIA" around the perimeter and "LAURENCE SOOKOCHOFF" in the center. A handwritten signature is written over the seal.  
Laurence Sookochoff, P. Eng.

LS:rl