

823969

CREST LABORATORIES (B.C.) LTD.B.C. REGISTERED ASSAYERS
GEOCHEMISTS1068 HOMER STREET,
VANCOUVER 3, B.C.

August 16, 1971

Dusty Mac Mines Ltd.,
1710 - 1177 West Hastings Street,
Vancouver, B.C.Lab No. 637GGeochemical analysis for copper & molybdenumMesh Size: - 80
Analytical Method: Atomic Absorption
Digestion Method: $\text{HClO}_4 \pm \text{HNO}_3$

Sample Marked:	Copper ppm	Sample Marked:	Copper ppm	Sample Marked:	Copper ppm
<u>C GROUP</u>		00 - 10	86	14S - 15 NE	52
00 - 1SW	43	11	94	14S - 1 <u>Moly ppm</u>	180
2	29	12	40	2 -2	240
3	18	13	22	3	55
4	22	14	15	4	24
5	19	15	14	5	36
6	17	16	30	6	19
7	13	17	22	7	24
8	35	18 <u>Moly ppm</u>	230	8	152
9	34	19 -2	150	9	64
10	29	20 -2	122	10	28
11	10	14S - 1NE	NO SAMPLE	11	57
12 <u>Moly ppm</u>	118	2	NO SAMPLE	12	32
13 -2	43	3 -2	98	13	31
14 -2	200	4	55	14	20
15 -2	220	5	46	15	33
00 - 1	24	6	32	16	19
2	15	7	100	17	17
3	24	8	18	18	35
4	30	9	22	19	15
5	30	10	14	20	20
6	28	11	48	14N - 1	25
7	20	12	34	2	90
8	30	13	24	3	90
9	29	14	43	4	25

Dusty Mac Mines Ltd.,
 Lab No. 637G,
 August 16, 1971
 Page 2 ...

Sample Marked:	Copper ppm	Sample Marked:	Copper ppm	Sample Marked:	Copper ppm
14N -5	21	28S -20	22	56S -15	225
6	35	42S -1	16	16	17
7	21	2	22	17	17
8	35	3	109	18	17
9	25	4	14	19	35
10	39	5	18'	20	18
11	24	6	20	70S -1	20
12	20	7	22	2	13
13	35	8	30	3	21
14	14	9	72	4	33
15	165	10	24	5	21
16	300	11	55	6	29
17	32	12	25	7	15
18	23	13	19	8	24
19	33	14	30'	9	15
20	17	15	38	10	23
28S - 1	17	16	36	11	25
2	14	17	71	12	22
3	19	18	15	13	4x 57
4	31	19	180	14	47
5	51	20	26	15	23
6	38	56S -1	13	16	49
7	30	2	71	17	25
8	29	3	21	18	27
9	23	4	21	19	23
10	36	5	19	20	20
11	43	6	25	84S -1	59
12	43	7	19	2	23
13	30	8	22	3	25
14	185	9	20	4	83
15	20	10	25	5	29
16	35	11	19	6	15
17	38	12	24	7	20
18	58	13	32	8	25
19	39	14	28	9	9

Dusty Mac Mines Ltd.,
 Lab No. 637G,
 August 16, 1971
 Page 3 ...

Sample Marked:	Copper ppm	Sample Marked:	Copper ppm	Sample Marked:	Copper ppm
84S - 10	78	8S - 18E	18	16S - 26W	9
11	19	20	17	28	14
12	45	22	19	30	5
13	50	24	19	16S - 2E	14
14	40	26	13	4	8
15	56	28	50	6	28
16	20	30	7	8	32
17	30	32	20	10	9
18	29	14N - 2W	23	12	19
19	35	4	18	14	13
20	50	6	25	16	12
<u>D GROVE</u>		8	11	18	16
8S - 2W	25	10	36	20	16
4	15	12	9	22	12
6	15	14	14	24	48
8	11	16	14	26	12
10	10	18	32	28	16'
12	17	20	13	30	54
14	14	22	16	32	32
16	17	24	NO SAMPLE	34	36
18	33	26	12	22N - 2W	16
20	10'	28	11	4	10
22	9	30	12	6	20
24	11	16S-00BL	8	8	18
26	11	2W	21	10	22
28	12	4	13	12	20
30	19	6	20	14	36
8S-00BL	25	8	17	16	NO SAMPLE
2E	10	10	13	18	24
4	12	12	33	20	18'
6	66	14	15	22	15
8	20	16	32	24	10
10	50	18	50	26	16
12	15	20	34	28	20
14	29	22	25	30	16
16	9	24	8	22N - 00BL	8

Dusty Mac Mines Ltd.,
 Lab No. 637G,
 August 16, 1971
 Page 4 ...

Sample Marked:	Copper ppm	Sample Marked:	Copper ppm	Sample Marked:	Copper ppm
22N - 2E	14	28S - 14E	10	24S - 8E	22
6	10	16	13	24S - 10E	12
4	12	18	12	12	32
8	8	20	20	14	20
10	19	22	18	16	16
12	16	24	12	32S - BL	54
14	14	26	16	2W	28
16	26	28	36	4	58
18	22	30	23	6	16
20	12	32	50	8	24
22	16'	34	32	10	58
24	10	36	30	32S - 2E	52
26	9	38	31	4	7
28	10	32S - 2W	66	6	13
30	9	4	15	8	21
32	14	6	21	10	14
24S - 2W	21	10	16	12	28
4	14	12	14	14	20
6	16	14	180	16	21
8	20	16	16	18	15
10	12	18	10	20	16
12	12	20	14	22	11
14	19	24	28	24	15
16	15	26	26	26	6
18	54	28	14	28	14
20	12	30	22	30	12
22	14	32	36	32	18
26	26	32S - 2E	16'	34	10
28	22	4	22	36	13
30	14	6	10	38	14
24S - 2E	22	8	18	40	11
4	14	10	28	42	28
6	73	12	12	44	14
8	16	14	16	46	12
10	46	16	19	32N - 2W	11
12	54	<u>F GROUP</u>		4	22

Dusty Mac Mines Ltd.,
 Lab No. 637G,
 August 16, 1971
 Page 5 ...

Sample Marked:	Copper ppm	Sample Marked:	Copper ppm	Sample Marked:	Copper ppm
32N - 6W	36	40S - 10E	10	40N - 34E	6
8 NO SAMPLE		12	28	36	14
10 NO SAMPLE		14	12	38	39
12	35	16	25	40	110
32N - 00 BL	8	18	9	42	20
2E	17	20	46	44	96
4	14	22	10	46	26
6	16	24	17	<u>G GROUP</u>	
8	12	28	34	8S - 32W	30
10	84	30	14	34	46
12	16	32	10	36	39
14	10	34	14	38	14
16	28	36	12	40	20
18	11	38	8	42	16
20	10	40	14	44	18
22	12	42	14	46	20
24	9	44	13	48	8
26	18	46	18	50	8
28	18	40N - BLOO	19	52	8
30	28	2E	13	54	7
32	12	4 NO SAMPLE		56	11
34	12	6	18	58	10
36	16	10	33	16S - 2W	30
38	14	12	180	4	14
40	9	14	32	6	19
42	10	16	88	8	15
44	34	18	20	10	25
46	25	20	15	12	27
40S - 00	14	22	10	14	12
2W	16	24	12	16	10
4	33	26	14	18	19
40S - 2E	20	28	22	20	34
4	13	30	152	22	NO SAMPLE
6	8	32	9	24	33
8	8				

Dusty Mac Mines Ltd.,
 Lab No. 637G,
 August 16, 1971
 Page 6 ...

Sample Marked:	Copper ppm	Sample Marked:	Copper ppm	Sample Marked:	Copper ppm
16S - 26W	12	56S -36E	30	64S - 46E	33
28	19	38	31	48	30
30	21	40	37	50	29
32	11	42	45	52	64
34	13	44	60	54	57
36	115	46	38	56	53
38	25	48	65	58	42
40	22	50	21	60	29
42	17	52	24	<u>H GROUP</u>	
44	10	54	22	L1 - 1	28
46	12	56	34	2	22
48	19	58	22	3	7
50	9	60	23	4	27
52	14	64S -00	28	5	11
54	9	2E	32	6	28
56	7	4	24	7	15
58	11	6	58	8	6
60	10	8	35	9	13
56S - 00	25	10	28	10	15
2E	19	12	27	11	10
4	22	14	34	12	17
6	29	16	20	13	14
8	61	18	16	14	46
10	59	20	21	15	24
12	35	22	21	16	24
14	35	24	42	17	42
16	58	26	15	18	14
18	31	28	44	19	28
20	47	30	48	20	9
22	35	32	43	21	30
24	48	34	44	22	33
26	100	36	31	23	18
28	64	38	33	24	13
30	43	40	30	25	12
32	30	42	46	26	22
34	42	44	46	27	10
				28	15

Dusty Mac Mines Ltd.,
 Lab No. 637G,
 August 16, 1971
 Page 7 ...

Sample Marked:	Copper ppm	Sample Marked:	Copper ppm	Sample Marked:	Copper ppm
L 1 29	13	L - Z-23	22	L 3 - 14	14
30	17	24	10	15	80
31	30	25	28	16	60
32	45	26	28	17	100
33	260	27	146	18	360
35	52	28	62	19	12
37	28	29	35	20	17
40	83	30	80	21	22
41	23	31	126	22	14
42	104	32	86	23	6
43	21	33	62	24	9
44	32	34	50	L 4 - 6	32
45	52	35	36	7	15
L1 -ROAD SEL.	11	36	40	8	29
L Z - 1	15	37	26'	9	18
2	60	38	14	10	32
3	29	29	18	11	25
4	16	40	48	12	44
5	16	41	38	13	25
6	17	42	56	14	15
7	40	43	27	15	70
8	20	44	14	16	13
9	24	45	16	17	26
10	14	L - 3-1	24	18	8
11	70	2	22	19	56
12	22	3	54	20	30
13	35	4	54	21	37
14	9	5	18	22	16
15	17	6	38	34	20
16	26	7	39	24	9
17	16	8	42	40S - 26	13
18	19	9	14		
19	25	10	80		
20	22	11	13		
21	88	12	20		
22	24	13	14		

Yours truly.

CREST LABORATORIES (B.C.) LTD.,

F.C. Burgess
 F.C. Burgess, Chief Assayer