

COMPAN

George Stewart

GEOCHEMICAL ANALYSIS DATA SHEET

MIN - EN Laboratories Ltd.

705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-5814

824742

FILE No. 9-548

DATE: Aug. 27,


1979.

PROJECT No.:

ATTENTION: George Stewart

| Sample Number | 6 Mo ppm | 10 Cu ppm | 15 Pb ppm | 20 Zn ppm | 25 Ni ppm | 30 Co ppm | 35 Ag ppm | 40 Fe ppm | 45 Hg ppb | 50 As ppm | 55 Mn ppm | 60 Au ppb | 65 | 70 | 75 | 80 |
|---------------|----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----|-----|-----|-----|
| 81 | 86 | 90 | 95 | 100 | 105 | 110 | 115 | 120 | 125 | 130 | 135 | 140 | 145 | 150 | 155 | 160 |
| 00-BL | 24 | 13 | | 68 | | | | 19 | | | | 215 | | | | |
| 1E | 5 | 12 | | 89 | | | | 07 | | | | 465 | | | | |
| 2E | 2 | 22 | | 76 | | | | 07 | | | | 520 | | | | |
| 3E | 1 | 26 | | 79 | | | | 09 | | | | 315 | | | | |
| 4E | 1 | 17 | | 56 | | | | 09 | | | | 255 | | | | |
| 5E | 1 | 9 | | 59 | | | | 05 | | | | 455 | | | | |
| 6E | 1 | 69 | | 61 | | | | 09 | | | | 395 | | | | |
| 7E | 3 | 178 | | 69 | | | | 12 | | | | 395 | | | | |
| 8E | 3 | 290 | | 45 | | | | 12 | | | | 280 | | | | |
| 9E | 6 | 174 | | 65 | | | | 08 | | | | 300 | | | | |
| 00-10E | 1 | 140 | | 52 | | | | 08 | | | | 380 | | | | |
| 1N-BL | 22 | 18 | | 126 | | | | 09 | | | | 730 | | | | |
| 1E | 7 | 16 | | 95 | | | | 07 | | | | 820 | | | | |
| 2E | 2 | 17 | | 58 | | | | 06 | | | | 480 | | | | |
| 3E | 2 | 28 | | 70 | | | | 09 | | | | 220 | | | | |
| 4E | 3 | 16 | | 68 | | | | 07 | | | | 400 | | | | |
| 5E | 1 | 14 | | 70 | | | | 08 | | | | 290 | | | | |
| 6E | 1 | 60 | | 55 | | | | 10 | | | | 385 | | | | |
| 7E | 2 | 42 | | 126 | | | | 09 | | | | 510 | | | | |
| 8E | 4 | 490 | | 84 | | | | 12 | | | | 260 | | | | |
| 9E | 3 | 440 | | 63 | | | | 16 | | | | 250 | | | | |
| 1N-10E | 4 | 145 | | 59 | | | | 10 | | | | 770 | | | | |
| 1S-BL | 8 | 16 | | 71 | | | | 09 | | | | 600 | | | | |
| 1E | 1 | 16 | | 85 | | | | 07 | | | | 540 | | | | |
| 2E | 6 | 280 | | 95 | | | | 35 | | | | 485 | | | | |
| 3E | 2 | 18 | | 105 | | | | 06 | | | | 430 | | | | |
| 4E | 1 | 11 | | 104 | | | | 09 | | | | 715 | | | | |
| 5E | 2 | 25 | | 89 | | | | 08 | | | | 580 | | | | |
| 6E | 1 | 141 | | 72 | | | | 11 | | | | 630 | | | | |
| 1S-7E | 1 | 60 | | 49 | | | | 11 | | | | 480 | | | | |

CERTIFIED BY



GEOCHEMICAL ANALYSIS DATA SHEET

PROJECT No.:


MIN - EN Laboratories Ltd.

DATE: Aug. 27, 1979.

705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-5814

ATTENTION: George Stewart

| Sample Number | 6 Mo ppm | 10 Cu ppm | 15 Pb ppm | 20 Zn ppm | 25 Ni ppm | 30 Co ppm | 35 Ag ppm | 40 Fe ppm | 45 Hg ppb | 50 As ppm | 55 Mn ppm | 60 Au ppb | 65 | 70 | 75 | 80 |
|---------------|----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----|-----|-----|-----|
| 81 | 86 | 90 | 95 | 100 | 105 | 110 | 115 | 120 | 125 | 130 | 135 | 140 | 145 | 150 | 155 | 160 |
| 1S-1W | 1 | 12 | | 56 | | | 05 | | | | 435 | | | | | |
| 1S-2W | 2 | 11 | | 49 | | | 06 | | | | 340 | | | | | |
| 2N-BL | 1 | 16 | | 72 | | | 05 | | | | 605 | | | | | |
| 1E | 3 | 14 | | 68 | | | 08 | | | | 380 | | | | | |
| 2E | 1 | 22 | | 50 | | | 05 | | | | 130 | | | | | |
| 3E | 1 | 26 | | 82 | | | 07 | | | | 305 | | | | | |
| 4E | 1 | 26 | | 51 | | | 06 | | | | 350 | | | | | |
| 5E | 1 | 19 | | 81 | | | 06 | | | | 500 | | | | | |
| 6E | 1 | 39 | | 73 | | | 07 | | | | 350 | | | | | |
| 7E | 2 | 69 | | 249 | | | 08 | | | | 340 | | | | | |
| 8E | 15 | 3000 | | 78 | | | 19 | | | | 515 | | | | | |
| 9E | 8 | 168 | | 66 | | | 12 | | | | 535 | | | | | |
| 2N-10E | 4 | 220 | | 47 | | | 08 | | | | 330 | | | | | |
| 2S-BL | 8 | 13 | | 69 | | | 08 | | | | 265 | | | | | |
| 1E | 2 | 15 | | 78 | | | 06 | | | | 705 | | | | | |
| 2E | 2 | 18 | | 55 | | | 05 | | | | 450 | | | | | |
| 3E | 5 | 20 | | 77 | | | 08 | | | | 380 | | | | | |
| 4E | 4 | 108 | | 145 | | | 07 | | | | 290 | | | | | |
| 5E | 1 | 116 | | 81 | | | 07 | | | | 610 | | | | | |
| 6E | 2 | 96 | | 59 | | | 07 | | | | 660 | | | | | |
| 7E | 2 | 104 | | 50 | | | 07 | | | | 430 | | | | | |
| 1W | 1 | 18 | | 58 | | | 06 | | | | 345 | | | | | |
| 2S-2W | 1 | 12 | | 54 | | | 06 | | | | 240 | | | | | |
| 3S-BL | 1 | 16 | | 61 | | | 06 | | | | 485 | | | | | |
| 1E | 2 | 18 | | 70 | | | 06 | | | | 635 | | | | | |
| 2E | 3 | 23 | | 98 | | | 07 | | | | 290 | | | | | |
| 3E | 2 | 31 | | 112 | | | 09 | | | | 460 | | | | | |
| 4E | 3 | 142 | | 92 | | | 10 | | | | 420 | | | | | |
| 5E | 5 | 97 | | 55 | | | 09 | | | | 385 | | | | | |
| 3S-1W | 2 | 12 | | 61 | | | 07 | | | | 410 | | | | | |



GEOCHEMICAL ANALYSIS DATA SHEET

PROJECT No.:

MIN - EN Laboratories Ltd.


DATE: Aug. 27,
1979.705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-5814

ATTENTION:

George Stewart

| Sample. Number | 6 Mo ppm | 15 Cu ppm | 20 Pb ppm | 25 Zn ppm | 30 Ni ppm | 35 Co ppm | 40 Ag ppm | 45 Fe ppm | 50 Hg ppb | 55 As ppm | 60 Mn ppm | 65 Au ppb | 70 | 75 | 80 | |
|----------------|----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----------------|-----|-----|-----|-----|
| 81 | 86 | 90 | 95 | 100 | 105 | 110 | 115 | 120 | 125 | 130 | 135 | 140 | 145 | 150 | 155 | 160 |
| 3S-2W | 2 | 14 | | 53 | | | 08 | | | | 365 | | | | | |
| 3N-1E | 1 | 16 | | 86 | | | 10 | | | | 405 | | | | | |
| 2E | 1 | 22 | | 21 | | | 06 | | | | 300 | | | | | |
| 3E | 1 | 24 | | 64 | | | 07 | | | | 295 | | | | | |
| 4E | 1 | 38 | | 61 | | | 10 | | | | 310 | | | | | |
| 5E | 1 | 25 | | 55 | | | 07 | | | | 390 | | | | | |
| 6E | 2 | 34 | | 56 | | | 08 | | | | 345 | | | | | |
| 7E | 2 | 183 | | 86 | | | 19 | | | | 410 | | | | | |
| 8E | 1 | 26 | | 49 | | | 04 | | | | 465 | | | | | |
| 9E | 4 | 168 | | 62 | | | 12 | | | | 250 | | | | | |
| 3N-10E | 2 | 123 | | 60 | | | 10 | | | | 400 | | | | | |
| 4N-1E | 1 | 12 | | 30 | | | 09 | | | | 105 | | | | | |
| 2E | 1 | 40 | | 30 | | | 12 | | | | 295 | | | | | |
| 3E | 1 | 18 | | 61 | | | 10 | | | | 345 | | | | | |
| 4E | 1 | 21 | | 58 | | | 11 | | | | 390 | | | | | |
| 5E | 2 | 42 | | 63 | | | 11 | | | | 320 | | | | | |
| 6E | 1 | 29 | | 59 | | | 08 | | | | 310 | | | | | |
| 7E | 2 | 40 | | 74 | | | 07 | | | | 480 | | | | | |
| 8E | 2 | 600 | | 184 | | | 12 | | | | 220 | | | | | |
| 9E | 2 | 260 | | 68 | | | 10 | | | | 315 | | | | | |
| 4N-10E | 10 | 280 | | 67 | | | 13 | | | | 380 | | | | | |
| 4S-BL | 1 | 19 | | 65 | | | 08 | | | | 630 | | | | | |
| 1E | 1 | 21 | | 70 | | | 08 | | | | 590 | | | | | |
| 2E | 1 | 44 | | 76 | | | 07 | | | | 530 | | | | | |
| 3E | 1 | 99 | | 62 | | | 11 | | | | 280 | | | | | |
| 4E | 4 | 100 | | 45 | | | 06 | | | | 675 | | | | | |
| 5E | 2 | 58 | | 51 | | | 08 | | | | 565 | | | | | |
| 1W | 1 | 20 | | 54 | | | 08 | | | | 325 | | | | | |
| 4S-2W | 2 | 18 | | 62 | | | 07 | | | | 460 | | | | | |
| 4N1ESS | 2 | 28 | | 72 | | | 11 | | | | 310 | | | | | |

CERTIFIED BY



GEOCHEMICAL ANALYSIS DATA SHEET

PROJECT No.:

MIN - EN Laboratories Ltd.

DATE: Aug. 27,
1979.705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-5814

ATTENTION: George Stewart

| Sample Number | Mo ppm | Cu ppm | Pb ppm | Zn ppm | Ni ppm | Co ppm | Ag ppm | Fe ppm | Hg ppb | As ppm | Mn ppm | Au ppb | | | |
|---------------|----------|----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| 6 81 | 10 90 | 15 95 | 20 100 | 25 105 | 30 110 | 35 115 | 40 120 | 45 125 | 50 130 | 55 135 | 60 140 | 65 145 | 70 150 | 75 155 | 80 160 |
| 4N-2ESS | 2 | 30 | | 58 | | | 08 | | | | 395 | | | | |
| 3NOE+ | | | | | | | | | | | | | | | |
| 340MSS | 2 | 50 | | 111 | | | 14 | | | | 530 | | | | |
| 5N-1E | 1 | 15 | | 69 | | | 06 | | | | 295 | | | | |
| 2E | 4 | 13 | | 62 | | | 05 | | | | 265 | | | | |
| 3E | 2 | 20 | | 77 | | | 07 | | | | 405 | | | | |
| 4E | 3 | 20 | | 87 | | | 08 | | | | 540 | | | | |
| 5E | 1 | 38 | | 65 | | | 08 | | | | 420 | | | | |
| 6E | 1 | 34 | | 70 | | | 09 | | | | 385 | | | | |
| 7E | 1 | 28 | | 71 | | | 08 | | | | 365 | | | | |
| 8E | 1 | 74 | | 83 | | | 08 | | | | 230 | | | | |
| 9E | 4 | 198 | | 78 | | | 12 | | | | 490 | | | | |
| 5N-10E | 5 | 720 | | 52 | | | 14 | | | | 380 | | | | |
| 5S-BL | 1 | 15 | | 72 | | | 05 | | | | 535 | | | | |
| 1E | 1 | 16 | | 93 | | | 04 | | | | 585 | | | | |
| 2E | 1 | 76 | | 101 | | | 08 | | | | 540 | | | | |
| 3E | 6 | 125 | | 55 | | | 10 | | | | 740 | | | | |
| 4E | 4 | 71 | | 53 | | | 11 | | | | 755 | | | | |
| 5E | 1 | 138 | | 65 | | | 11 | | | | 885 | | | | |
| 1W | 3 | 12 | | 84 | | | 04 | | | | 1000 | | | | |
| 5S-2W | 3 | 13 | | 53 | | | 05 | | | | 480 | | | | |
| 6S-BL | 3 | 13 | | 52 | | | 05 | | | | 750 | | | | |
| 1E | 2 | 20 | | 81 | | | 07 | | | | 390 | | | | |
| 2E | 4 | 28 | | 130 | | | 08 | | | | 545 | | | | |
| 3E | 2 | 28 | | 68 | | | 09 | | | | 775 | | | | |
| 4E | 7 | 96 | | 95 | | | 09 | | | | 1020 | | | | |
| 5E | 6 | 114 | | 76 | | | 16 | | | | 1240 | | | | |
| 1W | 1 | 26 | | 78 | | | 09 | | | | 745 | | | | |
| 6S-2W | 2 | 17 | | 63 | | | 08 | | | | 720 | | | | |
| 6N-2E | 2 | 14 | | 100 | | | 05 | | | | 335 | | | | |
| 6N-3E | 1 | 15 | | 31 | | | 06 | | | | 280 | | | | |

GEOCHEMICAL ANALYSIS DATA SHEET

PROJECT No.:

MIN - EN Laboratories Ltd.

DATE: Aug. 27,


ATTENTION:

George Stewart

705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-5814

1979.

| Sample Number | Mo ppm | Cu ppm | Pb ppm | Zn ppm | Ni ppm | Co ppm | Ag ppm | Fe ppm | Hg ppb | As ppm | Mn ppm | Au ppb | | | |
|---------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|-----|-----|-----|
| 61 | 10 | 15 | 20 | 25 | 30 | 35 | 40 | 45 | 50 | 55 | 60 | 65 | 70 | 75 | 80 |
| 86 | 90 | 95 | 100 | 105 | 110 | 115 | 120 | 125 | 130 | 135 | 140 | 145 | 150 | 155 | 160 |
| 6N-4E | 2 | 25 | | 70 | | | 09 | | | | 295 | | | | |
| 5E | 1 | 21 | | 63 | | | 09 | | | | 285 | | | | |
| 6E | 1 | 21 | | 71 | | | 11 | | | | 230 | | | | |
| 7E | 1 | 27 | | 61 | | | 08 | | | | 380 | | | | |
| 8E | 1 | 53 | | 54 | | | 10 | | | | 310 | | | | |
| 9E | 9 | 540 | | 65 | | | 15 | | | | 440 | | | | |
| 6N-10E | 4 | 440 | | 66 | | | 17 | | | | 145 | | | | |
| 7S-1E | 4 | 16 | | 64 | | | 07 | | | | 610 | | | | |
| 2E | 2 | 49 | | 71 | | | 07 | | | | 500 | | | | |
| 3E | 4 | 53 | | 69 | | | 13 | | | | 1010 | | | | |
| 4E | 4 | 56 | | 78 | | | 10 | | | | 890 | | | | |
| 5E | 4 | 88 | | 59 | | | 14 | | | | 1120 | | | | |
| 7S-BL | 4 | 22 | | 61 | | | 11 | | | | 395 | | | | |
| 1W | 1 | 13 | | 66 | | | 07 | | | | 560 | | | | |
| 2W | 1 | 120 | | 86 | | | 11 | | | | 385 | | | | |
| 7S-3W | 2 | 20 | | 76 | | | 08 | | | | 1170 | | | | |
| 7N-2E | 3 | 13 | | 12 | | | 06 | | | | 40 | | | | |
| 3E | 2 | 10 | | 32 | | | 07 | | | | 85 | | | | |
| 4E | 1 | 15 | | 39 | | | 06 | | | | 85 | | | | |
| 5E | 1 | 26 | | 53 | | | 11 | | | | 185 | | | | |
| 6E | 3 | 59 | | 65 | | | 12 | | | | 245 | | | | |
| 7E | 3 | 32 | | 47 | | | 07 | | | | 185 | | | | |
| 8E | 4 | 21 | | 68 | | | 09 | | | | 320 | | | | |
| 9E | 4 | 39 | | 56 | | | 11 | | | | 245 | | | | |
| 7N-10E | 7 | 260 | | 118 | | | 11 | | | | 195 | | | | |
| 8S-BL | 2 | 11 | | 61 | | | 04 | | | | 655 | | | | |
| 1E | 2 | 30 | | 78 | | | 09 | | | | 485 | | | | |
| 2E | 1 | 20 | | 57 | | | 08 | | | | 405 | | | | |
| 3E | 1 | 52 | | 59 | | | 08 | | | | 320 | | | | |
| 8S-4E | 1 | 46 | | 64 | | | 10 | | | | 515 | | | | |



GEOCHEMICAL ANALYSIS DATA SHEET

PROJECT No.: _____

MIN - EN Laboratories Ltd.

DATE: Aug. 27,ATTENTION: George Stewart705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-58141979.

| Sample Number | Mo ppm | Cu ppm | Pb ppm | Zn ppm | Ni ppm | Co ppm | Ag ppm | Fe ppm | Hg ppb | As ppm | Mn ppm | Au ppb | | | |
|---------------|----------|----------|----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| 6 81 | 10 86 | 15 90 | 20 95 | 25 100 | 30 105 | 35 110 | 40 115 | 45 120 | 50 125 | 55 130 | 60 135 | 65 140 | 70 145 | 75 150 | 80 155 |
| 8S-5E | 2 | 54 | | 53 | | | 08 | | | | 650 | | | | |
| 8S-5E | 2 | 360 | | 56 | | | 15 | | | | 380 | | (silt) | | |
| 1W | 1 | 14 | | 56 | | | 05 | | | | 535 | | | | |
| 2W | 2 | 13 | | 59 | | | 08 | | | | 615 | | | | |
| 8S-3W | 1 | 24 | | 67 | | | 07 | | | | 710 | | | | |
| 8N-2E | 1 | 13 | | 45 | | | 08 | | | | 130 | | | | |
| 3E | 3 | 14 | | 70 | | | 10 | | | | 220 | | | | |
| 4E | 2 | 10 | | 84 | | | 08 | | | | 235 | | | | |
| 5E | 2 | 33 | | 36 | | | 11 | | | | 415 | | | | |
| 6E | 2 | 28 | | 29 | | | 09 | | | | 215 | | | | |
| 7E | 2 | 36 | | 24 | | | 07 | | | | 220 | | | | |
| 8E | 3 | 20 | | 65 | | | 08 | | | | 300 | | | | |
| 9E | 2 | 32 | | 40 | | | 09 | | | | 195 | | | | |
| 8N-10E | 5 | 31 | | 74 | | | 06 | | | | 195 | | | | |
| 9N-2E | 4 | 21 | | 31 | | | 13 | | | | 210 | | | | |
| 3E | 2 | 7 | | 38 | | | 09 | | | | 95 | | | | |
| 4E | 1 | 8 | | 70 | | | 05 | | | | 475 | | | | |
| 5E | 2 | 24 | | 58 | | | 10 | | | | 200 | | | | |
| 6E | 2 | 24 | | 49 | | | 08 | | | | 285 | | | | |
| 7E | 4 | 28 | | 48 | | | 08 | | | | 190 | | | | |
| 8E | 4 | 28 | | 86 | | | 09 | | | | 375 | | | | |
| 9E | 2 | 49 | | 66 | | | 11 | | | | 250 | | | | |
| 9N-10E | 8 | 2600 | | 147 | | | 31 | | | | 380 | | | | |
| 9S-BL | 1 | 19 | | 62 | | | 06 | | | | 590 | | | | |
| 1E | 2 | 290 | | 58 | | | 19 | | | | 470 | | | | |
| 2E | 2 | 125 | | 53 | | | 08 | | | | 360 | | | | |
| 3E | 4 | 74 | | 64 | | | 12 | | | | 365 | | | | |
| 4E | 7 | 1090 | | 79 | | | 31 | | | | 1040 | | | | |
| 9S-5E | 4 | 107 | | 75 | | | 11 | | | | 340 | | | | |
| 9S-1W | 3 | 20 | | 64 | | | 08 | | | | 550 | | | | |

PROJECT No.: _____

MIN - EN Laboratories Ltd.


DATE: Aug. 27,

ATTENTION: George Stewart


705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-5814

1979.

| Sample Number | Mo ppm | Cu ppm | Pb ppm | Zn ppm | Ni ppm | Co ppm | Ag ppm | Fe ppm | Hg ppb | As ppm | Mn ppm | Au ppb | | | | |
|---------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|-----|-----|-----|-----|
| 6 | 10 | 15 | 20 | 25 | 30 | 35 | 40 | 45 | 50 | 55 | 60 | 65 | 70 | 75 | 80 | |
| 81 | 86 | 90 | 95 | 100 | 105 | 110 | 115 | 120 | 125 | 130 | 135 | 140 | 145 | 150 | 155 | 160 |
| 9S-2W | 2 | 14 | | 58 | | | 04 | | | | 590 | | | | | |
| 3W | 2 | 25 | | 75 | | | 08 | | | | 455 | | | | | |
| 9S-4W | 2 | 17 | | 48 | | | 06 | | | | 390 | | | | | |
| 10S-BL | 5 | 69 | | 52 | | | 09 | | | | 260 | | | | | |
| 1E | 2 | 40 | | 62 | | | 08 | | | | 305 | | | | | |
| 2E | 4 | 47 | | 66 | | | 09 | | | | 440 | | | | | |
| 3E | 2 | 17 | | 61 | | | 06 | | | | 700 | | | | | |
| 4E | 1 | 82 | | 79 | | | 13 | | | | 425 | | | | | |
| 5E | 1 | 52 | | 53 | | | 09 | | | | 340 | | | | | |
| 1W | 3 | 45 | | 71 | | | 11 | | | | 475 | | | | | |
| 2W | 3 | 65 | | 65 | | | 07 | | | | 390 | | | | | |
| 3W | 2 | 94 | | 43 | | | 07 | | | | 305 | | | | | |
| 10S4W | 1 | 19 | | 87 | | | 07 | | | | 1120 | | | | | |
| 10N-2E | 1 | 20 | | 62 | | | 09 | | | | 225 | | | | | |
| 3E | 1 | 19 | | 118 | | | 06 | | | | 780 | | | | | |
| 4E | 1 | 8 | | 86 | | | 05 | | | | 450 | | | | | |
| 5E | 2 | 38 | | 47 | | | 08 | | | | 340 | | | | | |
| 6E | 3 | 38 | | 61 | | | 08 | | | | 310 | | | | | |
| 7E | 2 | 27 | | 62 | | | 09 | | | | 360 | | | | | |
| 8E | 2 | 66 | | 55 | | | 12 | | | | 350 | | | | | |
| 9E | 4 | 42 | | 93 | | | 08 | | | | 425 | | | | | |
| 10N10E | 5 | 102 | | 126 | | | 12 | | | | 425 | | | | | |
| 11S-BL | 6 | 60 | | 76 | | | 09 | | | | 410 | | | | | |
| 1E | 5 | 50 | | 71 | | | 09 | | | | 395 | | | | | |
| 2E | 3 | 44 | | 70 | | | 10 | | | | 335 | | | | | |
| 3E | 3 | 34 | | 40 | | | 05 | | | | 295 | | | | | |
| 4E | 4 | 67 | | 52 | | | 08 | | | | 490 | | | | | |
| 5E | 4 | 114 | | 70 | | | 10 | | | | 450 | | | | | |
| 1W | 2 | 41 | | 71 | | | 10 | | | | 460 | | | | | |
| 11S-2W | 2 | 34 | | 57 | | | 09 | | | | 300 | | | | | |



| Sample Number | Mo ppm | Cu ppm | Pb ppm | Zn ppm | Ni ppm | Co ppm | Ag ppm | Fe ppm | Hg ppb | As ppm | Mn ppm | Au ppb | | | |
|---------------|----------|----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|-----------|
| 6 81 | 10 90 | 15 95 | 20 100 | 25 105 | 30 110 | 35 115 | 40 120 | 45 125 | 50 130 | 55 135 | 60 140 | 65 145 | 70 150 | 75 155 | 80 160 |
| 11S3W | 2 | 18 | | 58 | | | 04 | | | | 500 | | | | |
| 4W | 5 | 31 | | 62 | | | 06 | | | | 460 | | | | |
| 11S5W | 4 | 20 | | 74 | | | 06 | | | | 420 | | | | |
| 12SBL | 8 | 88 | | 60 | | | 05 | | | | 960 | | | | |
| 1E | 2 | 29 | | 47 | | | 04 | | | | 400 | | | | |
| 2E | 5 | 72 | | 52 | | | 08 | | | | 280 | | | | |
| 3E | 4 | 29 | | 54 | | | 05 | | | | 270 | | | | |
| 4E | 5 | 48 | | 66 | | | 09 | | | | 540 | | | | |
| 5E | 6 | 78 | | 48 | | | 05 | | | | 440 | | | | |
| 1W | 2 | 36 | | 76 | | | 08 | | | | 1100 | | | | |
| 2W | 3 | 24 | | 40 | | | 04 | | | | 310 | | | | |
| 3W | 3 | 42 | | 44 | | | 05 | | | | 260 | | | | |
| 4W | 4 | 134 | | 62 | | | 07 | | | | 480 | | | | |
| 12S5W | 4 | 22 | | 78 | | | 05 | | | | 740 | | | | |
| 13SBL | 3 | 54 | | 50 | | | 05 | | | | 280 | | | | |
| 1E | 4 | 34 | | 52 | | | 08 | | | | 300 | | | | |
| 2E | 5 | 69 | | 72 | | | 12 | | | | 1120 | | | | |
| 3E | 2 | 54 | | 74 | | | 07 | | | | 1320 | | | | |
| 1W | 4 | 46 | | 68 | | | 06 | | | | 620 | | | | |
| 2W | 2 | 42 | | 58 | | | 05 | | | | 380 | | | | |
| 3W | 3 | 21 | | 59 | | | 05 | | | | 400 | | | | |
| 4W | 2 | 31 | | 61 | | | 07 | | | | 260 | | | | |
| 5W | 4 | 39 | | 49 | | | 08 | | | | 320 | | | | |
| 13S6W | 5 | 22 | | 76 | | | 07 | | | | 1150 | | | | |
| 14SBL | 5 | 74 | | 42 | | | 04 | | | | 400 | | | | |
| 1E | 5 | 56 | | 78 | | | 07 | | | | 1750 | | | | |
| 2E | 3 | 35 | | 44 | | | 07 | | | | 800 | | | | |
| 3E | 2 | 22 | | 44 | | | 04 | | | | 1220 | | | | |
| 1W | 2 | 36 | | 62 | | | 08 | | | | 900 | | | | |
| 14S2W | 4 | 46 | | 58 | | | 07 | | | | 520 | | | | |

CERTIFIED BY 

PROJECT No.: _____

MIN - EN Laboratories Ltd.

DATE: Aug. 28,

ATTENTION: George Stewart

705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-5814

1979.

| Sample Number | Mo ppm | Cu ppm | Pb ppm | Zn ppm | Ni ppm | Co ppm | Ag ppm | Fe ppm | Hg ppb | As ppm | Mn ppm | Au ppb | | | |
|-----------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|-----|-----|-----|
| 6 | 10 | 15 | 20 | 25 | 30 | 35 | 40 | 45 | 50 | 55 | 60 | 65 | 70 | 75 | 80 |
| 81 | 86 | 90 | 95 | 100 | 105 | 110 | 115 | 120 | 125 | 130 | 135 | 140 | 145 | 150 | 160 |
| 610-20 3952 | 145 | 750 | | | | | 21 | | | | | 5 | | | |
| 53 | 5 | 355 | | | | | 17 | | | | | 5 | | | |
| 54 | 5 | 495 | | | | | 19 | | | | | 10 | | | |
| 55 | 8 | 200 | | | | | 16 | | | | | 45 | | | |
| 56 | 47 | 161 | | | | | 24 | | | | | 45 | | | |
| 57 | 8 | 220 | | | | | 18 | | | | | 45 | | | |
| 58 | 37 | 310 | | | | | 28 | | | | | 45 | | | |
| 59 | 13 | 335 | | | | | 17 | | | | | 45 | | | |
| 60 | 5 | 152 | | | | | 20 | | | | | 25 | | | |
| 61 | 5 | 275 | | | | | 16 | | | | | 5 | | | |
| 62 | 6 | 310 | | | | | 12 | | | | | 5 | | | |
| 63 | 11 | 755 | | | | | 26 | | | | | 55 | | | |
| 64 | 19 | 140 | | | | | 16 | | | | | 10 | | | |
| 65 | 8 | 775 | | | | | 27 | | | | | 15 | | | |
| 66 | 5 | 320 | | | | | 14 | | | | | 20 | | | |
| 67 | 11 | 2350 | | | | | 33 | | | | | 100 | | | |
| 68 | 12 | 171 | | | | | 15 | | | | | 50 | | | |
| 779-786.5 69 | 2 | 680 | | | | | 16 | | | | | 20 | | | |
| 800 70 | 10 | 315 | | | | | 18 | | | | | 10 | | | |
| 71 | 9 | 375 | | | | | 25 | | | | | 20 | | | |
| 72 | 22 | 455 | | | | | 22 | | | | | 20 | | | |
| 73 | 7 | 1180 | | | | | 26 | | | | | 75 | | | |
| 74 | 2 | 1690 | | | | | 40 | | | | | 70 | | | |
| 75 | 7 | 1040 | | | | | 28 | | | | | 160 | | | |
| 76 | 5 | 1570 | | | | | 28 | | | | | 80 | | | |
| 77 | 9 | 1070 | | | | | 23 | | | | | 75 | | | |
| 78 | 9 | 800 | | | | | 23 | | | | | 25 | | | |
| 79 | 8 | 1740 | | | | | 28 | | | | | 150 | | | |
| 80 | 5 | 1720 | | | | | 30 | | | | | 60 | | | |
| 900-10 3981 | 3 | 475 | | | | | 16 | | | | | 50 | | | |

610-20

779-786.5

800

Co. independent

900-10

1ST copy

[Handwritten signature]

PROJECT No.:

MIN - EN Laboratories Ltd.

DATE: **Aug. 29,**

ATTENTION: **George Stewart**

705 WEST 15th ST., NORTH VANCOUVER, B.C. V7M 1T2
PHONE (604) 980-5814

1979.

*DDH2
Footings
310-20
320-30*

*Consecutive
10'*

*590-600
600-610*

| Sample Number | Mo ppm | Cu ppm | Pb ppm | Zn ppm | Ni ppm | Co ppm | Ag ppm | Fe ppm | Hg ppb | As ppm | Mn ppm | Au ppb | Mo ppm | | |
|------------------------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|-----|-----|
| | 86 | 95 | 100 | 105 | 110 | 115 | 120 | 125 | 130 | 135 | 140 | 145 | 150 | 155 | 160 |
| <i>71</i> REC 672 | | 139 | | | | | 15 | | | | | 100 | 5 | | |
| 673 | | 104 | | | | | 14 | | | | | 35 | 16 | | |
| 340-50 674 | | 156 | | | | | 18 | | | | | 500 | 82 | | |
| 350-60 675 | | 260 | | | | | 16 | | | | | 65 | 12 | | |
| 360-70 676 | | 265 | | | | | 20 | | | | | 35 | 58 | | |
| 370-80 677 | | 230 | | | | | 20 | | | | | 10 | 39 | | |
| 380-90 678 | | 240 | | | | | 17 | | | | | 5 | 7 | | |
| 390-400 679 | | 430 | | | | | 26 | | | | | 5 | 7 | | |
| 400-10 680 | | 675 | | | | | 28 | | | | | 35 | 34 | | |
| 410-20 681 | | 390 | | | | | 23 | | | | | 40 | 6 | | |
| 420-30 682 | | 320 | | | | | 21 | | | | | 45 | 10 | | |
| 430-40 683 | | 710 | | | | | 33 | | | | | 25 | 6 | | |
| 440-50 684 | | 1120 | | | | | 40 | | | | | 15 | 3 | | |
| 450-60 685 | | 660 | | | | | 18 | | | | | 10 | 6 | | |
| 460-70 686 | | 540 | | | | | 16 | | | | | 10 | 14 | | |
| 470-80 687 | | 1550 | | | | | 34 | | | | | 5 | 14 | | |
| 480-90 688 | | 720 | | | | | 18 | | | | | <5 | 13 | | |
| 490-500 689 | | 655 | | | | | 19 | | | | | 10 | 18 | | |
| 500 690 | | 575 | | | | | 17 | | | | | 5 | 11 | | |
| 510 691 | | 715 | | | | | 22 | | | | | 10 | 12 | | |
| 520 692 | | 790 | | | | | 25 | | | | | 5 | 16 | | |
| 530 693 | | 760 | | | | | 21 | | | | | <5 | 20 | | |
| 540 694 | | 1400 | | | | | 36 | | | | | 5 | 48 | | |
| 550 695 | | 960 | | | | | 23 | | | | | 5 | 28 | | |
| 560 696 | | 1460 | | | | | 31 | | | | | 10 | 32 | | |
| 570 697 | | 2700 | | | | | 34 | | | | | 75 | 100 | | |
| 580 698 | | 2600 | | | | | 35 | | | | | 20 | 130 | | |
| 590 699 | | 5250 | | | | | 38 | | | | | 45 | 200 | | |
| <i>71</i> REC 700 | | 1550 | | | | | 12 | | | | | 120 | 25 | | |
| 3951 | | 2200 | | | | | 24 | | | | | 100 | 360 | | |

George Stewart