

RANDOM SAMPLES TAKEN DURING STAKING

826034
Nizi

GEOCHEMICAL ANALYSIS CERTIFICATE

Loring Laboratories Ltd. File # 92-0617

629 Beaverdam Road N.E., Calgary AB T2K 4W7

SAMPLE#	Mo ppm	Cu ppm	Pb ppm	Zn ppm	Ag ppm	Ni ppm	Co ppm	Mn ppm	Fe %	As ppm	U ppm	Au ppm	Th ppm	Sr ppm	Cd ppm	Sb ppm	Bi ppm	V ppm	Ca %	P %	La ppm	Cr ppm	Mg %	Ba ppm	Ti %	B ppm	Al %	Na %	K %	W ppm
34977 RW-1	7	17	29	54	.2	5	2	310	1.16	6	5	ND	37	7	.3	2	2	11	.06	.016	16	137	.03	37	.01	4	.42	.09	.16	.1
34977 RW-2	2	53	55	62	.1	13	6	432	1.87	3	5	ND	1	8	.2	4	2	15	.15	.024	2	204	.28	21	.01	2	.78	.08	.04	.1
34977 RW-3	2	30	11	43	.1	21	10	407	3.46	2	5	ND	19	14	.4	2	2	42	.19	.035	6	124	1.02	52	.04	4	1.75	.03	.20	.1
34977 RW-4	5	95	297	533	.1	30	8	763	7.38	5	5	ND	7	14	2.0	5	2	68	.12	.122	15	128	.66	13	.01	2	1.44	.01	.02	.1
34977 RW-5	2	56	42	142	.2	92	25	748	5.10	2	5	ND	14	67	1.5	4	2	75	1.13	.066	33	132	2.12	66	.30	2	3.08	.09	.23	.1

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER. THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR MG BA TI B W AND LIMITED FOR NA K AND AL. AU DETECTION LIMIT BY ICP IS 3 PPM.
- SAMPLE TYPE: PULP Samples beginning 'RE' are duplicate samples.