

CORON 7

827550

Lara
92B/13

hole #	from	to	interval	Cu	Pb	Zn	Ag _{oz}	Ag _{gt}	Au _{oz}	Au _{gt}	Ba	SG	NSL
85-70													
86-101	223.45	226.05	2.6	.03	.05	.11	.29	9.82	.004	.12			3.78
103													
104	196.24	199.22	2.98	.02	.06	.14	.32	10.88	.009	.32		2.7	5.86
107	210.72	217.65	6.93	0	0	.01	.05	1.59	.003	.11		2.7	1.36
109	181.26	201.60	20.34	.02	.02	.14	.14	4.95	.005	.17		2.7	3.30
111	109.29	114.84	5.55	.02	.01	.06	.41	14.03	.010	.33	.49	2.7	6.05
112													
113	134.83	139.02	4.19	.01	.01	.02	.28	9.75	.012	.40	.50		5.65
114	71.99	76.05		.33	1.05	3.79	1.49	51.23	.036	1.24	.42	2.99	41.92
115	127.43	137.66	10.23	0	0	.01	.03	.94	.004	.14	.13	2.70	1.51
117													
120	187.10	209.39	22.29	21	5	81 ppm		.25 ppm		6.35 ppb	890 ppm		-geochem only.
140	112.95	116.05	3.10	.49	.03	1.15	.34	11.54	.035	1.21	.15	2.91	24.46
86-99													
88-226	70.68	70.98	0.30	0.05	0.50	0.88	0.25	8.57	.052	1.78	0.34	2.80	22.9
88-227	80.40	83.21	2.81	0.15	0.34	1.56	0.60	20.59	0.060	2.05	0.47	2.91	31.34

CORONATION ZONE INTERSECTIONS

	from	to	interval	Cu	Pb	Zn	Ag _{oz}	Ag _{gr}	Au _{oz}	Au _{gr}	Ba	SG	NSR
13 ✓	107.48	120.12	12.64	.02	.04	.17	.12	4.0	.008	.29	.209	2.78	4.39
-14 ✓	109.10	113.60	4.50	.02	.05	.19	.10	3.41	.007	.23	.261	2.73	3.85
15 ✓	50.50	62.42		.40	.47	2.65	1.93	66.0	.063	2.16	.358	2.84	48.62
16 ✓	79.16	81.67	2.51	.48	.25	1.84	.91	31.20	.021	.74	.339	2.88	26.57
17 ✓	43.84	45.17	1.33	.06	.34	1.48	1.10	37.85	.010	.35	.371	2.87	17.39
18 ✓	62.84	65.10	2.26	.35	.50	2.40	.72	24.56	.055	1.87	.385	2.89	36.80
19 ✓	80.76	86.55	5.79	.30	.27	1.67	.59	20.34	.035	1.19	.450	2.88	25.78
20 ✓	66.48	69.72	3.24	.35	.36	.97	1.54	52.89	.028	.96	-	-	27.41
21 ✓	127.56	134.80	7.24	.29	.11	.54	.61	20.88	.032	1.11	.446	2.83	20.12
22 ✓	106.14	115.34		.19	.21	1.12	.82	28.09	.094	3.21	.402	2.82	41.88
23 ✓	118.11	130.72	12.61	.13	.11	.29	.45	15.56	.033	1.13	.362	2.84	16.30
24 ✓	92.37	106.96	14.59	.36	.19	1.10	1.02	35.12	.029	.99	.478	2.87	24.90
25 ✓	117.65	129.66	12.01	.44	.07	1.02	.31	10.72	.025	.87	.415	2.87	19.99
26 ✓	167.30	172.44	5.14	.37	.04	1.16	.16	5.47	.015	.52	.377	2.87	15.48
27 ✓	66.79	71.12		1.59	.48	2.83	1.73	59.42	.043	1.48	.454	2.99	57.62 -
28 ✓	118.41	135.52	17.11	.17	.11	1.48	.46	15.64	.025	.87	.353	2.84	19.26
29 ✓	83.30	105.00	21.70	.05	.12	.27	.25	8.69	.003	.11	-	-	4.51
30 ✓	107.96	113.93	5.97	.14	.13	.96	1.05	35.84	.037	1.26	.473	2.88	24.03
31 ✓	77.27	79.20	1.93	.25	.27	1.01	.57	19.57	.008	0.28	.283	2.78	13.96
32 ✓	79.40	79.68	.28	.73	1.95	5.60	6.36	218.02	.290	9.94	.490	2.80	166.10 -
33 ✓	72.65	77.97		.31	1.32	3.57	1.62	55.70	.065	2.23	.424	2.96	51.18 -
34 ✓	75.02	86.08	11.06	.50	.73	4.11	1.76	60.22	.033	1.11	.552	2.86	45.56
35 ✓	54.73	59.10	4.37	.01	.01	.01	.02	.69	.002	.07	-	-	.90
36 ✓	23.67	28.10		.87	.50	3.48	2.41	82.65	.287	9.82	.400	2.94	131.64 -
37 ✓	30.97	38.49		1.05	.28	1.82	1.41	48.23	.045	1.55	.361	2.96	44.58
38 ✓	72.21	77.44	5.23	.61	.36	2.05	.84	28.66	.028	.95	.451	2.86	30.92
39 ✓	51.19	57.40		.19	.53	1.67	.99	34.09	.052	1.79	.319	2.89	32.78
61 ✓	105.68	114.17	8.49	.05	.15	.95	.31	10.67	.018	.63	.62	2.81	12.54
62 ✓	85.24	110.05		.36	.46	2.46	1.93	66.17	.082	2.82	.50	2.92	53.34 -
63 ✓	109.75	120.21	10.46	.30	.13	2.31	.70	23.93	.025	.85	.44	2.97	25.74
64 ✓	36.49	46.90		.14	.32	.78	1.47	50.33	.057	1.96	.59	2.86	32.59
65 ✓	48.48	50.02	1.54	.10	.20	.57	.71	24.35	.166	5.67	1.15	3.04	60.45 -
122 ✓	21.02	23.86		.36	.53	2.92	2.89	99.09	.233	8.00	.33	2.84	108.89 -
125 ✓	45.12	52.18	7.06	.09	.17	1.25	.23	7.97	.022	.76	.35	2.83	14.96
126 ✓	49.21	49.99	0.78	.91	.76	3.29	1.12	38.56	.033	1.15	.46	2.80	37.50 - 2e sample
129 ✓	45.77	53.53		.15	.26	1.64	0.82	28.26	.036	1.23	.46	2.89	25.52
131 ✓	39.43	44.59	5.16	.04	.09	.38	.30	10.15	.011	.36	.39	2.95	7.45
132 ✓	25.84	36.47		.55	1.07	5.17	2.05	70.17	.046	1.57	.42	3.05	57.12 -
134 ✓	15.00	21.08	16.08	0.98	0.71	5.31	2.97	101.82	.204	6.99	.40	3.01	118.32 - no assay sheet
135 ✓	8.25	15.84		1.73	3.20	15.21	7.02	240.28	.230	7.87	.31	3.23	205.50 -
136 ✓	13.71	20.11		.32	.78	5.09	1.41	48.37	.027	.93	.50	2.96	43.50

hole#	from	to	interval	Cu	Pb	Zn	Ag oz	Ag g/t	Au oz	Au g/t	Ba	SG	NSR	
CORON.														
87-170														
171 ✓	140.92	159.63	18.71	.31	.17	1.00	.79	27.13	.029	.99	.35	2.86	22.48	
172 ✓	189.31	205.13	15.82	.09	.42	.53	.51	17.58	.01	.20	—	—	9.30	- part geochem - part assay.
179 ✓	79.88	84.19	4.31	7	29.1	85.6		.14 ppm		20 ppb	1613 ppm			- geochem.
180 ✓	93.06	95.09	2.03	.35	.37	.79	.34	11.63	.026	.89	.27	2.95	18.67	
181														
182 ✓	221.35	226.45	←											part geochem part assay.
184 ✓	355.53	367.78		1.01	.33	2.03	1.21	41.35	.085	2.93	.46	2.90	56.39	
186 ✓	198.13	209.52	11.39	116	41.6	190		.89 ppm		108 ppb	352 ppm			- geochem.
188														
189														
190														
191 ✓	395.99	397.33	1.34	2562	1467	9330		20.38 ppm		1079.4 ppb	3099 ppm			geochem.
193														
194														
196	342.57	355.90	13.33											part geochem part assay
197	66.90	72.23	5.33	0.16	0.15	0.78	0.28	16.78	0.015	0.84	0.09	—	11.85	part geochem part assay
198 ✓	134.70	140.47	5.77	32	31.4	88.1		1.86 ppm		84.1 ppb	3180 ppm			geochem.
199 ✓	121.08	134.46		.19	.18	1.50	1.63	55.78	.081	2.76	.69	3.00	44.38	
200														
201														
202 ✓	84.64	87.05	2.41	14	46.3	155.2		.35 ppm		38.1 ppb	1819 ppm			geochem.
203 ✓	34.89	37.11		.62	.54	5.28	1.38	47.38	.066	2.27	0.23	2.96	59.94	
204														
205 ✓	405.90	422.00	15.10	.50	.25	1.38	.80	27.32	.030	1.03	.42	2.92	27.02	
206 ✓	121.26	123.14	1.88	.27	.01	.30	.29	10.11	.011	.39	.13	1	10.23	

hole #	from	to	interval	Cu	Pb	Zn	Ag _{oz}	Agg _{lt}	Anoz	Aug _{lt}	Ba	SG	NSR
- CORON 86	76.73	78.00	1.27	10	5	15		0.2		opp			1 sample.
87	—	—	—										
88	—	—	—										
89	—	—	—										
90 ✓	258.17	264.56	6.39	.09	.05	.40	.17	5.98	.015	.52	—	—	8.83
91	—	—	—										
- 92	223.38	234.73		46ppm	126ppm	216ppm		8.46ppm		302ppb	3695ppm		geochem
93	—	—	—										
H.W. ZONE 94 ✓	124.09	138.80	13.99	not assayed.									
95	119.44	133.00	13.56	96	166	410	4.2	21.81	—	270ppb.			
96	—	—	—										
97	—	—	—										
98	—	—	—										

CORON 1.

87-152													
154													
157													
159													
159A													
162													
163 ✓	124.12	126.85	2.73	.25	.12	2.44	.15	5.12	.026	.88	.22		22.59
165 ✓	60.83	68.53	7.7	.11	.41	1.40	.96	32.96	.020	.69	.31	—	20.02
167 ✓	40.66	53.16	12.50	.41	.12	.84	.72	24.57	.056	1.91	.040	2.92	31.05
168 ✓	57.02	57.49	0.47	.39	.27	1.80	.34	11.66	.008	.27	.28		17.53 - only 1 sample.
174 ✓	52.25	64.40	12.15	.17	.09	1.21	.38	13.18	.013	.44	.47	2.84	13.81
175 ✓	47.96	55.22	7.26	.15	.13	1.42	.39	13.25	.008	.27	.18		12.92
176 ✓	73.45	73.94	0.49	.13	.14	1.91	.19	6.51	.007	.24	.56		13.13 - only 1 sample.
178	—	none.											
183	—	none.											
185 ✓	172.18	183.30	11.12	.01	.04	.07		7.39		.19	.57		- values in ppm's.
187	—	none.											
192	—	none.											
195	—	none.											

207.

85-40 ✓	46.00	50.80		1.14	2.47	8.94	8.46	289.89	.211	7.25	.685	3.03	174.19
42 ✓	110.20	119.50		.16	.24	1.38	.75	25.73	.056	1.93	.405	3.01	30.6
48 ✓	112.24	115.95	3.71	.02	.01	.01	.05	1.77	.012	.41	.43	2.84	4.40
49 ✓	96.00	97.32	1.32	.01	.01	.01	.02	.69	.002	.07	.11	2.8	.94 - CEZ one sample
49 ✓	122.50	128.33	5.83	.04	.02	.04	.12	4.20	.010	.33	.38	2.75	4.62 CEZ.
50 ✓	172.95	176.82	3.87	.08	.15	.86	1.35	46.37	.017	.57	.50	2.79	18.36