

Mt. Sicker
 Assay Sheets
 Hole Numbers: 86-78 to 90-272
 DATE: 17-September-1990

HOLE NUMBER: 86-78

ASSAY SHEET

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS				
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %		
13670	25.85	26.30	0.45	123	32	2130	0.6	59	1260											
10714	29.18	29.65	0.47							.00	.00	.00	.00	0.00	.000	0.00	.27	2.70	0.00	3
10715	29.65	29.94	0.29							.10	.38	.86	.29	9.94	.024	0.82	.39	3.00	14.74	5
10716	29.94	31.91	1.97							.00	.00	.06	.00	0.00	.000	0.00	.37	2.70	0.25	5
10717	31.91	32.35	0.44							.16	.01	.20	.00	0.00	.004	0.14	.16	2.90	4.21	3
10718	32.35	33.19	0.84							.07	.03	.22	.05	1.71	.004	0.14	.27	2.80	3.44	4
10719	33.19	35.39	2.20							.01	.01	.02	.00	0.00	.003	0.10	.35	2.80	1.17	4
13671	41.70	43.65	1.95	12	18	92	0.9	23	1420											
13672	43.65	44.60	0.95	995	65	2720	1.1	55	1100											
13673	44.60	45.30	0.70	372	45	125	1.2	42	1340											
13674	45.30	46.80	1.50	11	23	39	0.7	18	1080											
	207.18	207.72	0.54	142	630	2500	3.0	65										0.00		7
	207.72	210.67	2.95	33	49	181	.7	20										0.00		1
	210.67	213.44	2.77	19	8	29	.2	15										0.00		4
	213.44	214.65	1.21	22	11	23	.4	20										0.00		5
	214.65	217.71	3.06	17	5	32	.0	10										0.00		2
	226.96	229.57	2.61	13	4	16	.0	20										0.00		5
10720	238.77	240.27	1.50							.00	.00	.01	.00	0.00	.000	0.00	.11	2.70	0.04	1
10721	240.27	241.71	1.44							.00	.01	.01	.00	0.00	.002	0.07	.13	2.70	0.68	1
10722	241.71	243.27	1.56							.00	.00	.01	.00	0.00	.002	0.07	.21	2.70	0.67	1
10723	243.27	244.75	1.48							.00	.02	.04	.07	2.40	.008	0.27	.18	2.90	3.15	10
10724	244.75	245.40	0.65							.29	.09	8.30	.29	9.94	.037	1.27	.28	3.00	51.44	7
10725	245.40	246.47	1.07							.65	.06	.27	.92	31.54	.054	1.85	.34	2.90	32.48	5
10726	246.47	248.40	1.93							.00	.00	.01	.00	0.00	.002	0.07	.22	2.70	0.67	3
10727	248.40	250.33	1.93							.00	.00	.00	.00	0.00	.002	0.07	.14	2.70	0.63	3
10728	250.33	251.74	1.41							.02	.00	.01	.02	0.69	.000	0.00	.11	2.80	0.43	3
AVE.	29.65	35.39	5.74							0.03	0.03	0.12	0.02	0.75	0.003	0.11	0.33			
AVE.	41.70	46.80	5.10	244.23	31.931	570.47	0.92	30.098	1249.4											
ALT.AVG.	243.27	246.47	3.20							0.28	0.05	1.79	0.40	13.68	0.029	1.00	0.25			
ALT.AVG.	244.75	246.47	1.72							0.51	0.07	3.30	0.68	23.38	0.048	1.63	0.32			

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
13675	27.39	28.52	1.13	1500	34	1495	2.0	110									0.00	7
	28.52	29.45	0.93	1050	12	119	1.3	85									0.00	5
	29.45	30.62	1.17	760	39	895	0.8	65									0.00	7
	30.62	33.39	2.77	46	9	323	0.2	35									0.00	5
	59.55	60.90	1.35	16	35	77	1.0	21	780									
13726	60.90	62.30	1.40	38	28	67	0.7	37	1020									
13727	63.95	64.95	1.00	15	39	68	0.5	30	1040									
13728	64.95	65.95	1.00	7	18	75	0.7	19	1460									
	94.60	97.24	2.64	4200	3	89	0.6	25									0.00	30
	97.24	98.29	1.05	1500	6	35	0.3	30									0.00	30
	98.29	99.80	1.51	3000	3	56	0.4	25									0.00	20
	99.80	101.20	1.40	4300	6	73	1.0	50									0.00	40
	156.75	157.53	0.78	7590	5	173	1.1	30									0.00	2
	250.12	250.82	0.70	38	5	30	0.0	5									0.00	5
	250.82	251.80	0.98	68	4	43	0.0	0									0.00	1
	251.80	252.59	0.79	12	8	40	0.0	0									0.00	3
AVE.	27.39	30.62	3.23	1102.4	29.48	881.48	1.36	86.502										
AVE.	27.39	33.39	6.00	614.69	20.02	623.65	0.83	62.725										
AVE.	59.55	62.30	2.75	27.200	31.436	71.909	0.85	29.15	902.18									
AVE.	63.95	65.95	2.00	11.000	28.500	71.500	0.60	24.50	1250.0									
AVE.	94.60	101.20	6.60	3517.1	4.11	69.47	0.59	31.10										

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS				
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %		
14406	17.95	19.50	1.55	52	28	35	0.3	1	1820											
14407	19.50	22.20	2.70	101	22	41	0.3	2	1300											
14408	22.20	23.76	1.56	214	25	57	0.3	1	1290											
14409	23.76	26.12	2.36	53	29	48	0.5	2	1810											
14410	38.40	40.74	2.34	34	26	42	0.3	1	1480											
14411	40.74	42.20	1.46	229	24	41	0.6	2	1900											
14412	42.20	43.54	1.34	215	27	66	0.9	1	1420											
14413	43.54	44.35	0.81	233	25	68	0.5	3	1480											
14414	44.35	45.70	1.35	1002	30	78	0.9	2	1170											
14415	45.70	47.74	2.04	51	21	8	0.3	1												
14416	47.74	50.06	2.32	25	20	6	0.3	2												
14417	50.06	51.95	1.89	170	17	7	0.3	5												
14418	51.95	53.68	1.73	464	21	10	0.5	2												
14419	53.68	54.90	1.22	606	32	9	1	38												
14420	54.90	56.55	1.65	155	23	17	0.5	2												
14421	56.55	58.06	1.51	7	28	26	0.6	1												
14422	58.06	60.60	2.54	242	20	190	0.9	2												
10729	204.70	206.27	1.57							.02	.01	.01	.02	0.69	.002	0.07	.14	2.70	1.07	2
10730	206.27	207.25	0.98							.00	.02	.00	.03	1.03	.005	0.17	.25	2.80	1.79	4
10731	207.25	208.42	1.17							.00	.00	.02	.07	2.40	.016	0.55	.34	2.70	5.56	3
10732	208.42	209.58	1.16							.07	.18	.28	3.42	117.24	.031	1.06	1.13	2.80	33.29	5
10733	209.58	210.34	0.76							.13	.63	1.17	2.12	72.67	.069	2.37	1.07	2.80	42.27	6
10734	210.34	210.78	0.44							.73	5.00	11.70	6.46	221.45	.121	4.15	.40	3.50	142.77	20
10735	210.78	211.04	0.26							2.40	14.40	6.80	8.87	304.06	.622	21.32	.27	3.30	330.64	15
10736	211.04	211.60	0.56							.83	.31	.24	.70	24.00	.031	1.06	.23	2.70	26.48	
10737	211.60	212.47	0.87							.47	1.30	3.80	1.33	45.59	.028	0.96	.32	2.80	40.67	5
10738	212.47	213.27	0.80							2.60	.44	7.20	2.92	100.10	.151	5.18	.52	3.40	130.12	20
10739	213.27	213.78	0.51							.41	.84	6.00	2.47	84.67	.096	3.29	.52	2.90	76.74	5
10740	213.78	215.27	1.49							.01	.00	.02	.00	0.00	.002	0.07	.16	2.70	0.84	
10741	215.27	216.24	0.97							.00	.00	.01	.00	0.00	.002	0.07	.07	2.60	0.67	
10742	216.24	217.73	1.49							.00	.00	.00	.00	0.00	.000	0.00	.09	2.70	0.00	
AVE.	17.95	26.12	8.17	99.415	25.733	44.939	0.36	1.6193	1544.1											
AVE.	40.74	45.70	4.96	436.26	26.607	62.234	0.75	1.8931	1503.0											
AVE.	50.06	60.60	10.54	260.37	22.631	56.112		6.5617												
ALT.AVG.	204.70	215.27	10.57							0.41	0.83	1.94	1.52	51.94	0.052	1.77	0.43			
AVE.	210.34	213.78	3.44							1.19	2.33	5.57	2.99	102.58	0.124	4.25	0.39			
ALT.AVG.	210.34	213.78	3.44							1.19	2.33	5.57	2.99	102.58	0.124	4.25	0.39			

Sample	From (m)	To (m)	Length (m)	ASSAYS					GEOCHEMICAL					COMMENTS					
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T		AG G/T	AU OZ/T	AU G/T	BA %	
14382	13.90	15.80	1.90	49	32	33	0.3	8											
14383	15.80	17.30	1.50	13	29	28	0.4	2											
14384	17.30	18.70	1.40	5	29	30	0.3	2											
14385	18.70	20.60	1.90	11	30	32	0.5	2											
14386	20.60	22.25	1.65	214	28	41	1.3	2											
14387	22.25	24.90	2.65	77	25	46	1.1	56											
14388	24.90	26.00	1.10	13	31	32	0.7	2											
14389	26.00	27.28	1.28	18	30	45	0.6	2											
14390	44.70	46.30	1.60	18	31	39	0.8	10											
14391	46.30	48.32	2.02	18	28	36	0.9	23											
14392	48.32	50.10	1.78	185	24	74	1.9	2											
14393	50.10	50.90	0.80	187	29	75	1.1	2											
14394	50.90	53.77	2.87	124	23	10	0.4	23											
14395	53.77	54.91	1.14	10	17	2	0.4	22											
14396	54.91	56.70	1.79	37	19	3	0.4	10											
14397	56.70	58.42	1.72	7	22	5	0.6	11											
14398	58.42	59.40	0.98	5	23	17	0.4	5											
14399	59.40	60.70	1.30	13	27	24	0.6	10											
14400	60.70	61.98	1.28	20	30	34	0.4	2											
14401	61.98	63.70	1.72	11	28	36	0.5	6											
14402	63.70	65.16	1.46	98	29	47	0.6	10											
14403	65.16	67.60	2.44	447	27	154	1.2	32											
	190.89	190.97	0.08	8	6	34	0	0											
AVE.	20.60	27.28	6.68	88.996	27.687	42.268	0.99	23.422											
AVE.	44.70	50.90	6.20	87.752	27.755	52.716	1.19	10.906											
AVE.	50.90	67.60	16.70	104.53	24.531	38.481	0.58	15.052											

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL								COMMENTS			
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T				AU G/T	BA %	
	88.00	90.38	2.38	126	2	39	0.0	0										0.00	7		
	93.35	95.85	2.50	69	2	40	0.0	0										0.00	10		
	175.33	177.07	1.74	181	630	1280	5.8	170										0.00	5		
	185.62	188.36	2.74								.00	.00	.01	.01	0.34	.001	0.03	0.42	2		
	188.36	189.15	0.79								.01	.15	.09	.04	1.37	.013	0.45	5.05	2		
	189.15	189.43	0.28								.70	.36	8.70	2.43	83.30	.055	1.89	.24	3.20	77.80	25
	189.43	190.30	0.87								.00	.00	.01	.02	0.69	.002	0.07	0.79	1		
	190.30	191.35	1.05								.01	.00	.01	.01	0.34	.001	0.03	0.55	1		
ALT.AVG.	188.36	190.30	1.94								0.11	0.11	1.30	0.38	12.89	0.014	0.49	0.03	0.46	13.64	4.87

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS	
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T
14313	12.26	13.12	0.86	298	18	77	1.5	15									
14314	13.12	13.68	0.56	822	30	110	1.5	13									
14315	13.68	14.47	0.79	417	24	97	1.4	15									
14316	14.47	15.71	1.24	1135	12	137	2.5	10									
14317	15.71	17.30	1.59	554	22	136	1.7	4									
14318	17.30	20.40	3.10	90	25	153	1.6	16									
14319	20.40	23.40	3.00	649	31	58	0.8	9	1400								
14320	23.40	24.30	0.90	80	24	41	0.7	1	1500								
14321	24.30	26.10	1.80	636	24	69	1	34									
14322	26.50	26.72	0.22	81	25	56	1.1	5	1120								
14323	26.72	28.34	1.62	1017	26	35	1.1	3	1700								
14324	28.34	30.11	1.77	11	23	34	1	5									
14325	30.11	31.60	1.49	38	23	33	0.5	2									
14326	31.60	33.00	1.40	17	21	27	0.8	3									
14347	33.00	34.30	1.30	11	23	25	0.8	16									
14327	51.20	53.34	2.14	13	20	26	0.6	10									
14328	65.20	65.50	0.30	10	24	33	0.9	2	1570								
14329	65.50	66.50	1.00	4	26	38	0.8	1									
14330	66.50	67.03	0.53	8	29	23	1	1	1520								
14331	68.52	70.10	1.58	206	25	26	1.1	20	1880								
14332	82.50	83.09	0.59	31	26	89	0.8	1									
14333	83.09	83.73	0.64	2450	25	53	1.4	1	1500								
14334	83.73	84.10	0.37	524	27	101	1.4	23									
14335	95.35	95.80	0.45	23	30	73	0.7	1									
14336	95.80	96.60	0.80	24	27	78	0.6	2									
14337	96.60	97.70	1.10	15	35	56	0.5	6									
14338	97.70	98.64	0.94	32	30	58	0.7	4									
14339	98.64	101.18	2.54	22	24	36	0.9	5									
14341	110.50	112.30	1.80	32	27	77	0.9	2	700								
14342	112.30	113.80	1.50	21	30	43	0.8	1	570								
14340	113.80	115.00	1.20	32	25	48	0.5	2	400								
14343	122.53	124.00	1.47	22	31	44	0.7	2	1450								
14344	124.00	125.13	1.13	26	34	63	0.8	2	1370								
14345	125.13	127.10	1.97	50	34	38	0.8	17									
AVE.	12.26	28.34	16.08	525.03	23.882	91.355	1.2968	12.155	531.74								
AVE.	28.34	34.30	5.96	19.159	22.530	30.143		6.1795									
AVE.	65.20	67.03	1.83	6.1421	26.541	32.836		1.1639	697.60								

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
13730	49.68	51.69	2.01	16	7	83	0.2	0									0.00	
	144.40	145.40	1.00	36	12	53	0.6	5	1020									
13731	145.40	146.30	0.90	294	8	73	0.5	5	890									
13732	153.40	154.70	1.30	9	9	42	0.8	10	1270									
13733	154.70	156.00	1.30	8	7	58	0.5	5	800									
	161.98	163.15	1.17	1240	5	31	0.6	45									0.00	
	163.15	165.15	2.00	303	2	10	0.2	45									0.00	
	169.55	171.05	1.50	20	4	18	0.0	15									0.00	
	171.05	172.55	1.50	20	0	25	0.0	10									0.00	
13734	177.65	178.50	0.85	83	6	114	0.6	5	1140									
	292.20	293.33	1.13	10	6	104	0.0	10									0.00	
	293.33	294.45	1.12	7	4	23	0.0	0									0.00	
	294.45	295.02	0.57	10	17	6	0.0	0									0.00	
	295.02	297.44	2.42	70	5	47	0.0	0									0.00	
	297.44	299.50	2.06	29	4	67	0.0	20									0.00	
AVE.	161.98	165.15	3.17	648.83	3.11	17.75	0.35	45.00										

HOLE NUMBER: 86-88

ASSAY SHEET

DATE: 17-September-1990

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
	28.78	29.98	1.20	26	6	5	0.0	0									0.00	
	33.25	33.99	0.74	55	5	128	0.0	0									0.00	
	33.99	39.95	5.96	40	5	158	0.0	35									0.00	
	145.27	145.70	0.43	10	6	24	0.0	0									0.00	
	145.70	147.08	1.38	15	6	20	0.0	0									0.00	
	147.08	148.48	1.40	48	11	80	0.0	0									0.00	
	148.48	149.03	0.55	37	12	105	0.0	0									0.00	
	149.03	150.89	1.86	7	4	30	0.0	10									0.00	
	150.89	152.25	1.36	6	3	19	0.0	110									0.00	
	223.87	225.57	1.70	29	3	28	0.2	35									0.00	

HOLE NUMBER: 86-89

ASSAY SHEET

DATE: 17-September-1990

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
	37.86	39.80	1.94	30	3	39	0.6	0										0.00
	82.86	83.52	0.66	66	2	56	0.0	0										0.00
	159.49	161.00	1.51	8	2	33	0.0	40										0.00
	161.00	162.95	1.95	6	2	26	0.0	10										0.00
	162.95	163.78	0.83	8	2	38	0.0	20										0.00
	173.01	174.84	1.83	19	3	81	0.0	5										0.00
	174.84	175.25	0.41	44	3	154	0.0	0										0.00
	200.63	201.27	0.64	65	7	63	0.2	25										0.00

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS			
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %	
14433	14.57	16.20	1.63	505	12	41	0.5	3	1050										
14434	16.20	17.79	1.59	744	11	46	0.7	2											
14435	17.79	19.14	1.35	664	13	40	1.1	10											
	34.00	35.66	1.66							.04	.00	.00	.00	0.00	.002	0.07		1.16	2
	35.66	37.06	1.40							.17	.00	.05	.05	1.71	.002	0.07		3.39	3
	37.06	37.84	0.78							.80	.00	.01	.13	4.46	.004	0.14		12.67	7
	37.84	38.70	0.86							.04	.00	.00	.00	0.00	.000	0.00		0.53	1
14436	58.10	60.04	1.94	89	9	63	0.6	2	1670										
	223.45	223.46	0.01							.01	.01	.02	.50	17.14	.021	0.72		9.94	
	223.46	224.28	0.82							.02	.04	.09	.20	6.86	.002	0.07		2.56	2
	224.28	224.90	0.62							.02	.04	.11	.20	6.86	.002	0.07		2.64	2
	224.90	225.67	0.77							.03	.04	.08	.35	12.00	.003	0.10		3.89	7
	225.67	226.05	0.38							.06	.13	.20	.48	16.45	.010	0.34		7.92	3
	226.05	229.56	3.51							.00	.00	.00	.02	0.69	.000	0.00		0.12	3
	229.56	233.08	3.52							.00	.00	.00	.02	0.69	.000	0.00		0.12	3
AVE.	14.57	19.14	4.57	635.12	11.947	42.444	0.75	4.7199	374.51										
AVE.	34.00	38.70	4.70							0.20		0.02	0.04	1.25	0.002	0.07			
AVE.	223.45	226.05	2.60							0.03	0.05	0.11	0.29	9.82	0.004	0.12			

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS				
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %		
14438	17.80	19.69	1.89								.06	.00	.00	.15	5.14	.004	0.14	2.7	2.98	4
	19.69	20.42	0.73								.03	.00	.01	.02	0.69	.002	0.07	2.7	1.19	1
	56.84	59.03	2.19								.00	.00	.00	.01	0.34	.000	0.00	2.7	0.06	5
	59.03	61.22	2.19								.00	.00	.00	.00	0.00	.000	0.00	2.7	0.00	5
	62.65	64.43	1.78	97	6	141	1.4	15	1740											
	196.24	196.63	0.39								.01	.04	.09	.19	6.51	.008	0.27	2.7	4.25	
	196.63	197.12	0.49								.05	.04	.12	.50	17.14	.003	0.10	2.7	5.25	2
	197.12	198.12	1.00								.01	.03	.06	.18	6.17	.020	0.69	2.7	7.84	1
	198.12	198.95	0.83								.03	.10	.18	.47	16.11	.003	0.10	2.7	5.13	5
	198.95	199.22	0.27								.03	.06	.37	.21	7.20	.003	0.10	2.7	4.24	
	199.22	201.22	2.00								.00	.00	.00	.01	0.34	.007	0.24	2.7	2.27	
	201.22	203.22	2.00								.00	.00	.00	.01	0.34	.024	0.82	2.7	7.62	
AVE.	196.24	199.22	2.98								0.02	0.06	0.14	0.32	10.88	0.009	0.32	2.70	5.86	2.06

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
14363	6.70	8.55	1.85	44	30	29	0.8	11										
14364	8.55	9.70	1.15	21	30	31	1.1	20										
14365	9.70	10.96	1.26	15	31	36	0.8	10										
14366	10.96	12.00	1.04	164	31	36	0.7	12										
14368	13.77	14.56	0.79	33	34	48	0.4	1										
14369	31.08	32.53	1.45	20	33	41	1.2	1										
14370	32.53	33.69	1.16	29	29	46	1.4	2										
14371	41.45	43.90	2.45	9	30	30	0.8	10										
14372	43.90	44.60	0.70	7	30	35	0.9	1										
14373	44.60	45.76	1.16	29	37	64	1.1	5										
14374	45.76	47.70	1.94	16	33	58	0.8	12										
14375	47.70	48.71	1.01	42	28	106	0.9	36										
14376	48.71	49.91	1.20	29	41	66	1.3	17										
14377	49.91	52.87	2.96	168	36	76	1	20										
14378	52.87	54.15	1.28	36	34	41	1	57										
14379	54.15	56.06	1.91	121	34	48	0.7	3										
14380	56.06	56.90	0.84	317	33	155	1.6	35										
14381	56.90	57.85	0.95	150	27	161	1.4	26										
	210.72	211.09	0.37						.01	.00	.03	.02	0.69	.012	0.41	2.7	4.16	3
	211.09	211.59	0.50						.00	.01	.01	.44	15.08	.020	0.69	2.7	9.08	3
	211.59	213.88	2.29						.00	.00	.00	.02	0.69	.000	0.00	2.7	0.12	
	213.88	214.19	0.31						.01	.04	.06	.02	0.69	.002	0.07	2.7	1.19	1
	214.19	215.00	0.81						.01	.00	.02	.02	0.69	.006	0.21	2.7	2.23	1
	215.00	215.85	0.85						.00	.00	.00	.01	0.34	.000	0.00	2.7	0.06	2
	215.85	216.73	0.88						.01	.00	.01	.02	0.69	.000	0.00	2.7	0.30	5
	216.73	217.65	0.92						.00	.00	.00	.00	0.00	.002	0.07	2.7	0.63	2
	217.65	219.65	2.00						.00	.00	.00	.00	0.00	.000	0.00	2.7	0.00	
	219.65	221.65	2.00						.00	.00	.00	12.61	432.27	.000	0.00	2.7	78.18	
AVE.	6.70	12.00	5.30	55.662	30.434	32.472	0.85	12.911										
AVE.	41.45	57.85	16.40	82.445	33.373	68.493		18.477										
AVE.	210.72	217.65	6.93								0.01	0.05	1.59	0.003	0.11			

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS				
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %		
14352	6.92	8.22	1.30	17	22	25	0.8	2	1560											
14353	8.22	9.44	1.22	24	30	30	1	1	1940											
14354	9.44	10.40	0.96	56	25	43	0.9	4	1500											
14355	10.40	11.95	1.55	70	27	53	0.4	2	1600											
14356	16.82	17.84	1.02	253	28	54	0.4	2	820											
14357	17.84	19.00	1.16	352	22	45	0.9	3	1100											
14358	19.00	20.26	1.26	46	24	17	0.5	1												
14404	24.86	25.92	1.06	1424	29	32	0.9	4												
14405	25.92	26.37	0.45	514	24	62	1.7	11	500											
14359	42.10	43.44	1.34	34	24	56	1.2	5												
14360	43.44	44.80	1.36	77	31	29	1.1	32												
14361	44.80	46.00	1.20	201	32	70	1.3	42												
14362	46.00	47.57	1.57	570	29	118	2.2	24												
	181.26	181.96	0.70							.00	.01	.02	.15	5.14	.002	0.07		2.7	1.66	2
	181.96	182.93	0.97							.00	.00	.00	.04	1.37	.002	0.07		2.7	0.88	2
	182.93	184.39	1.46							.00	.03	.06	.12	4.11	.004	0.14		2.7	2.29	2
	184.39	185.01	0.62							.00	.02	.04	.24	8.23	.006	0.21		2.7	3.57	1
	185.01	186.03	1.02							.02	.04	.11	.67	22.97	.010	0.34		2.7	8.07	2
	186.03	187.65	1.62							.01	.01	.02	.13	4.46	.006	0.21		2.7	2.92	1
	187.65	188.93	1.28							.01	.00	.06	.08	2.74	.016	0.55		2.7	5.91	
	188.93	189.70	0.77							.03	.15	.27	.53	18.17	.009	0.31		2.7	7.83	2
	189.70	192.30	2.60							.00	.00	.01	.02	0.69	.000	0.00		2.7	0.16	
	192.30	193.26	0.96							.01	.02	.06	.03	1.03	.000	0.00		2.7	0.59	2
	193.26	194.16	0.90							.00	.00	.01	.01	0.34	.000	0.00		2.7	0.10	1
	194.16	195.10	0.94							.00	.00	.00	.02	0.69	.000	0.00		2.7	0.12	
	195.10	196.06	0.96							.00	.00	.01	.02	0.69	.000	0.00		2.7	0.16	3
	196.06	196.96	0.90							.01	.00	.09	.07	2.40	.003	0.10		2.7	1.88	5
	196.96	197.91	0.95							.26	.07	1.23	.58	19.88	.031	1.06		2.7	21.93	5
	197.91	198.43	0.52							.14	.24	1.72	.50	17.14	.012	0.41		2.7	16.12	3
	198.43	199.36	0.93							.00	.00	.03	.02	0.69	.000	0.00		2.7	0.25	2
	199.36	200.51	1.15							.00	.00	.02	.02	0.69	.000	0.00		2.7	0.21	5
	200.51	201.60	1.09							.01	.00	.01	.02	0.69	.000	0.00		2.7	0.30	
	201.60	203.60	2.00							.00	.00	.05	.01	0.34	.000	0.00		2.7	0.27	
AVE.	6.92	11.95	5.03	42.473	26.054	38.276	0.61	2.1392	1653.0											
AVE.	16.82	20.26	3.44	210.56	24.512	37.413	0.61	1.9709	614.07											
AVE.	24.86	26.37	1.51	1152.8	27.510	40.940	1.14	6.0861	149.01											
AVE.	42.10	47.57	5.47	235.17	28.931	70.154	1.48	25.283												
AVE.	181.26	201.60	20.34							0.02	0.02	0.14	0.14	4.95	0.005	0.17				

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
14348	24.89	26.50	1.61	29	30	73	0.7	2										
14349	32.61	33.80	1.19	37	30	107	0.9	1										
14350	33.80	35.76	1.96	36	30	101	0.9	1										
	161.53	162.03	0.50							.00	.00	.01	.02	0.69	.002	0.07	.11	0.79
	162.03	162.53	0.50							.00	.00	.00	.02	0.69	.001	0.03	.07	0.44
	162.53	163.03	0.50							.00	.00	.01	.02	0.69	.000	0.00	.06	0.16
	163.03	163.53	0.50							.00	.00	.00	.02	0.69	.070	2.40	.05	22.17
	163.53	164.03	0.50							.00	.00	.00	.01	0.34	.016	0.55	.07	5.10
	164.03	164.53	0.50							.00	.00	.00	.01	0.34	.000	0.00	.09	0.06
	164.53	165.03	0.50							.00	.00	.00	.01	0.34	.000	0.00	.10	0.06
	165.03	165.53	0.50							.00	.00	.00	.01	0.34	.000	0.00	.08	0.06
	165.53	166.03	0.50							.00	.00	.00	.00	0.00	.000	0.00	.08	0.00
	166.03	166.52	0.49							.00	.00	.00	.00	0.00	.000	0.00	.08	0.00
	166.52	168.52	2.00							.00	.00	.00	.00	0.00	.000	0.00	.07	0.00
	168.52	170.52	2.00							.00	.00	.00	.00	0.00	.002	0.07	.07	0.63
AVE.	32.61	35.76	3.15	36.378	30.000	103.27	0.90	1.0000										

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS			
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %	
14346	44.80	45.74	0.94	47	36	81	0.7	1.											
	123.13	123.63	0.50																0.12
	123.63	124.13	0.50																0.54
	124.13	124.63	0.50																1.04
	124.63	126.18	1.55																5.48
	126.18	126.68	0.50																0.96
	126.68	127.18	0.50																1.49
	127.18	127.68	0.50																1.45
	127.68	128.18	0.50																0.66
	128.18	128.68	0.50																0.76
	128.68	129.54	0.86																1.19
	129.54	130.04	0.50																1.02
	130.04	130.54	0.50																1.69
	130.54	131.04	0.50																0.50
	131.04	131.54	0.50																1.04
	131.54	132.04	0.50																3.34
	132.04	132.58	0.54																4.15
	132.58	134.83	2.25																2.41
	134.83	135.33	0.50																3.97
	135.33	135.83	0.50																6.51
	135.83	136.33	0.50																3.19
	136.33	136.83	0.50																5.48
	136.83	138.07	1.24																2.58
	138.07	138.57	0.50																14.21
	138.57	139.02	0.45																8.39
	139.02	141.02	2.00																1.62
AVE.	134.83	139.02	4.19																5.65
																			2.25

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
	10.97	11.99	1.02	880	2	66	.10	40	3700									0.0
	11.99	14.02	2.03	72	2	34	.10	25	3100									0.0
	14.02	15.48	1.46	25	2	65	.10	15	3400									0.0
	15.48	17.07	1.59	11	2	28	.10	10	2700									0.0
	17.07	17.94	0.87	13	2	33	.10	5	2600									0.0
	17.94	18.85	0.91	8	2	17	.10	5	2600									0.0
	18.85	19.20	0.35	420	2	2050	.10	5	2500									0.0
	19.20	20.12	0.92	20	2	148	.10	5	2200									0.0
	28.04	29.56	1.52	10	3	17	.10	5	2600									0.0
	29.56	31.08	1.52	85	2	350	.10	5	2500									0.0
	33.98	34.82	0.84	4	2	11	.10	5	3200									0.0
	34.82	35.05	0.23	2700	9	41	2.20	120	440									0.0
	35.05	36.27	1.22	179	2	13	.10	5	2400									0.0
	36.27	37.14	0.87	25	3	10	.10	5	2400									0.0
	37.14	38.10	0.96	5	2	10	.10	5	2500									0.0
	38.10	39.62	1.52	220	2	12	.10	5	2400									0.0
14423	39.62	41.74	2.12	23	12	68	0.6	5										
14424	53.30	54.25	0.95	1224	15	46	1.3	5										
14425	54.25	55.65	1.40	766	13	63	1	1										
14426	55.65	57.03	1.38	59	13	28	0.5	5										
14427	63.09	64.31	1.22	270	12	26	0.2	2										
14428	68.88	70.26	1.38	37	12	33	0.2	5										
14429	70.26	72.24	1.98	77	11	43	0.6	5										
14430	72.24	73.70	1.46	28	10	51	0.5	5										
	306.15	307.82	1.67	18	5	92	.10	95	3000									0.0
	307.82	308.72	0.90	120	310	1450	4.40	130	4000									0.0
	308.72	309.64	0.92	220	620	920	7.30	150	3200									0.0
	309.64	310.32	0.68	210	305	1050	5.90	1350	2800									0.0
	310.32	310.90	0.58	97	225	655	3.10	85	4500									0.0
AVE.	10.97	20.12	9.15	140.08	2.00	128.26	0.10	15.80	2934.5									
AVE.	33.98	41.74	7.76	161.40	5.0515	27.736	0.30	8.4085	1785.2									
AVE.	53.30	57.03	3.73	621.08	13.509	45.721		3.4987										
AVE.	68.88	73.70	4.82	50.705	10.983	42.560	0.46	5.0000										

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS			
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %	
	0.00	0.00	0.00	3300	7	45	.90	70									0.0	5	
	12.40	13.91	1.51	9	7	78	.10	15	3800								0.0	5	
	13.91	15.42	1.51	35	7	8710	.20	35	4300								0.0	5	
	15.42	15.85	0.43	500	5	4050	.50	15	3900								0.0	5	
	15.85	17.17	1.32	27	3	68	.20	30	3100								0.0	5	
	17.17	18.49	1.32	12	2	56	.10	20	2500								0.0	5	
	18.49	19.80	1.31	17	3	110	.10	10	2200								0.0	5	
	19.80	22.18	2.38	6	3	66	.10	5	2600								0.0		
	22.18	24.56	2.38	5	2	31	.10	5	2100								0.0		
	24.56	26.94	2.38	6	2	39	.10	5	2200								0.0		
	26.94	27.24	0.30	12	3	380	.10	5	1500								0.0	4	
	27.24	30.00	2.76	10	2	90	.10	5	2000								0.0		
	30.00	32.00	2.00	10	4	69	.10	5	2600								0.0	3	
	32.00	34.00	2.00	30	2	58	.10	5	1800								0.0	3	
	34.00	36.00	2.00	6	2	33	.10	5	2200								0.0	3	
AVE.	13.91	15.85	1.94	138.07	6.56	7677.1	0.27	30.57	4211.3										

Sample	From (m)	To (m)	Length (m)	ESTIMA GCU PPM	ASSAYS										GEOCHEMICAL					SUL %	COMMENTS		
					GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T	IAU OZ/T	AU G/T	BA %	SG SG	NSR NSR				
	71.99	72.88	0.89	2550	9	130	1.40	120	1600												0.00	5	
	72.88	74.17	1.29	79	4	88	.10	15	1900												0.00	3	
	74.17	75.34	1.17	3750	10	100	2.00	200	1000												0.00	10	
	75.34	76.30	0.96	116	3	56	.10	10	1300												0.00	3	
	350.17	350.47	0.30	72	2	106	.10	5	1800												0.00		
	350.47	352.60	2.13	13	5	21	.10	30	980												0.00		
	352.60	352.99	0.39	31	23	72	.10	60	800												0.00		
	352.99	355.53	2.54	51	270	780	.80	85	1600												0.00		
	355.53	356.51	0.98							.40	1.23	3.20	1.86	63.76	.186	6.38	.60	2.90	90.24		3		
	356.51	357.51	1.00							.30	1.09	6.00	1.80	61.70	.037	1.27	.31	2.90	52.90		7		
	357.51	357.97	0.46							.38	.08	.60	.58	19.88	.054	1.85	.28	3.00	28.19		7		
	357.97	358.60	0.63							.42	.36	2.32	.88	30.17	.018	0.62	.31	2.80	26.69		5		
	358.60	359.52	0.92							1.50	.38	3.30	.77	26.40	.027	0.93	.34	2.90	47.14		3		
	359.52	359.99	0.47							12.90	.13	2.08	3.81	130.61	1.081	37.06	.32	3.20	543.13		10		
	359.99	360.56	0.57							1.00	.52	6.20	.87	29.82	.023	0.79	.35	2.90	51.99		5		
	360.56	360.96	0.40							.88	.14	.74	.52	17.83	.016	0.55	.60	2.90	23.11		5		
	360.96	361.47	0.51							.18	.42	2.81	.31	10.63	.016	0.55	.52	2.90	21.45		3		
	361.47	361.88	0.41							.13	.16	1.10	.15	5.14	.019	0.65	.54	2.90	13.36		2		
	361.88	362.39	0.51							.09	.17	.25	.19	6.51	.035	1.20	.83	2.90	14.65		3		
	362.39	363.12	0.73							.36	.22	.61	.22	7.54	.021	0.72	.54	2.90	15.54		5		
	363.12	363.72	0.60							.14	.14	.40	.32	10.97	.029	0.99	.52	2.90	14.80		2		
	363.72	364.42	0.70							.31	.06	.06	.40	13.71	.033	1.13	.51	2.80	17.30		5		
	364.42	365.38	0.96							.08	.01	.01	.10	3.43	.011	0.38	.53	2.80	5.20		2		
	365.38	365.57	0.19							9.25	.16	3.40	29.36	1006.5	.485	16.63	.37	3.10	471.07		3		
	365.57	366.38	0.81							.06	.01	.24	.07	2.40	.033	1.13	.52	2.80	12.62		3		
	366.38	366.88	0.50							.04	.02	.13	.10	3.43	.013	0.45	.55	3.00	5.80		10		
	366.88	367.28	0.40							.21	.01	.76	.51	17.48	.018	0.62	.43	2.80	14.73		2		
	367.28	367.78	0.50							.30	.03	4.45	.39	13.37	.011	0.38	.26	3.00	28.13		5		
	367.78	368.56	0.78	3350	220	2000	5.30	170	2600											0.00	2		
	368.56	369.82	1.26	345	12	1500	.60	55	980											0.00	0		
	369.82	370.28	0.46	290	1150	4100	2.80	130	2900											0.00	1		
	370.28	370.63	0.35	185	10	176	.80	55	910											0.00	0		
	370.63	371.53	0.90	10	7	12	.10	15	1700											0.00	2		
	371.53	373.08	1.55	2	5	6	.10	5	1200											0.00			
	373.08	374.53	1.45	2	12	10	.10	5	850											0.00			
	374.53	375.97	1.44	2	9	10	.10	10	1200											0.00			
	387.73	388.30	0.57	14	9	40	.10	5	1200											0.00	1		
	388.30	389.23	0.93	10	9	46	.10	30	1200											0.00	5		

HOLE NUMBER: 87-184

ASSAY SHEET

DATE: 17-September-1990

Sample	From (m)	To (m)	Length (m)	GCU PPM	GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T	IAU OZ/T	AU G/T	BA %	SG SG	NSR NSR	SUL %		
	389.23	389.73	0.50	19	14	78	.30	35	1800										0.00	10		
	389.73	390.43	0.70	87	160	640	1.30	30	2100										0.00	1		
AVE.	71.99	76.30	4.31	1594.0	6.44	92.803	0.88	85.789	1460.1												5.31	
AVE.	355.53	360.96	5.43							1.75	0.61	3.45	1.41	48.28	0.149	5.10	0.39	2.92	93.67		5.27	
ALT.AVG.	355.53	357.51	1.98							0.35	1.16	4.61	1.83	62.72	0.111	3.80	0.45	2.90	71.38		5.02	
ALT.AVG.	355.53	367.78	12.25							1.01	0.33	2.03	1.21	41.35	0.085	2.93	0.46	2.90	56.53		4.41	
ALT.AVG.	358.60	360.96	2.36							3.54	0.32	3.32	1.36	46.53	0.234	8.03	0.38	2.96	143.02		5.22	

HOLE NUMBER: 87-184

ASSAY SHEET

PAGE: 2

Sample	From (m)	To (m)	Length (m)	ESTIMA GCU PPM	ASSAYS										GEOCHEMICAL					SUL %	COMMENTS						
					GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T	IAU OZ/T	AU G/T	BA %	SG SG	NSR NSR								
14464	9.95	11.36	1.41	17	34	82	0.5	7																			
14465	11.36	12.37	1.01	10	25	91	0.4	10																			
14466	12.37	12.96	0.59	12	30	93	0.2	33																			
14467	19.55	21.00	1.45	43	28	60	0.7	18	2300																		
14468	21.00	22.50	1.50	16	26	85	0.9	23	2600																		
14469	22.50	23.65	1.15	3315	26	80	2.5	38	1340																		
14470	23.65	25.00	1.35	69	18	66	0.7	9	2100																		
14471	31.40	32.61	1.21	26	21	9	0.6	18	3180																		
14472	32.61	34.14	1.53	9	30	25	0.6	5																			
14473	34.14	35.77	1.63	10	18	11	0.6	2	3200																		
14474	35.77	38.20	2.43	8	20	30	0.8	3	2600																		
14475	38.20	39.26	1.06	4	23	26	0.7	1	2500																		
14476	39.26	41.17	1.91	5	17	16	0.5	1	1800																		
14477	75.28	77.22	1.94	4	17	16	0.6	5																			
14478	89.60	90.23	0.63	2328	26	59	0.8	21																			
AVE.	9.95	12.96	3.01	13.671	30.196	87.176	0.41	13.103																			
AVE.	19.55	23.65	4.10	950.88	26.707	74.756	1.28	25.439	2140.5																		
AVE.	31.40	41.17	9.77	9.6991	21.095	20.275	0.64	4.3961	2197.5																		

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS			
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %	
	5.95	7.95	2.00	8	6	67	.60	25	2800									0.00	
	7.95	9.95	2.00	63	4	73	.40	10	2600									0.00	
	9.95	11.95	2.00	40	4	100	.40	20	2600									0.00	
	11.95	13.95	2.00	18	2	60	.10	15	2200									0.00	
	13.95	15.95	2.00	12	8	35	1.10	110	3100									0.00	
	15.95	17.95	2.00	7	2	50	.20	15	2000									0.00	
	17.95	20.00	2.05	3	2	48	.10	5	2000									0.00	
	36.00	38.00	2.00	29	3	30	.10	5	3400									0.00	
	38.00	39.97	1.97	130	2	28	.10	5	2000									0.00	
	39.97	40.57	0.60	1000	5	23	.40	25	1300									0.00	7
	40.57	41.32	0.75	143	3	41	.10	10	1400									0.00	1
	41.32	43.32	2.00	72	2	50	.10	5	1800									0.00	1
	43.32	45.32	2.00	300	3	100	.10	10	1700									0.00	
AVE.	9.95	13.95	4.00	29.00	3.00	80.000	0.25	17.50	2400.0										
AVE.	36.00	45.32	9.32	189.42	2.70	49.325	0.12	7.76	2099.8										

Sample	From (m)	To (m)	Length (m)	ESTIMA GCU PPM	ASSAYS					GEOCHEMICAL					SUL %	COMMENTS				
					GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T			IAU OZ/T	AU G/T	BA %	SG SG
	4.42	4.97	0.55	230	25	51	.20	10	3200									0.00	1	
	4.97	5.50	0.53	355	70	460	.40	20	3300									0.00	1	
	5.50	6.60	1.10	104	24	124	.10	5	3500									0.00	1	
	6.60	7.48	0.88	725	54	325	1.50	80	2700									0.00	3	
	7.48	8.64	1.16	780	39	520	1.30	60	2500									0.00	3	
	8.64	10.97	2.33	795	25	560	1.60	30	2300									0.00	3	
	10.97	11.43	0.46	2150	5	197	3.80	85	2200									0.00	5	
	11.43	12.66	1.23	575	5	235	1.00	15	2100									0.00	3	
	12.66	14.68	2.02	670	5	165	1.20	70	2100									0.00	3	
	29.38	31.11	1.73	240	260	585	.50	30	1900									0.00	3	
14439	31.90	33.46	1.56	482	6	154	1.1	2	1350											
14440	33.46	35.15	1.69	284	8	131	0.8	5	1470											
14441	35.15	36.69	1.54	72	6	111	0.3	2	1430											
14442	36.69	38.28	1.59	310	6	139	0.7	6	1000											
14443	52.19	53.19	1.00	82	8	216	0.9	4	930											
14444	53.19	54.15	0.96	149	14	72	0.8	8	2200											
14445	54.15	55.08	0.93	90	15	68	0.9	4	2900											
	55.08	56.18	1.10	27	2	32	.10	30	2400									0.00	2	
	56.18	58.31	2.13	100	3	43	.10	5	2200									0.00	2	
	58.31	59.77	1.46	44	2	31	.10	5	2000									0.00	2	
	59.77	61.23	1.46	6	2	34	.10	5	1900									0.00	2	
	61.23	63.19	1.96	3	2	35	.10	5	1800									0.00	2	
14446	76.52	78.42	1.90	153	6	119	0.9	2	1300											
14447	78.42	79.98	1.56	418	6	107	.1	7	1240											
	79.98	80.77	0.79	330	31	170	.70	150	760									0.00		
	84.14	84.65	0.51	280	31	250	.40	150	1300									0.00		
	361.55	361.85	0.30	101	2	73	.10	5	530									0.00		
	370.73	371.16	0.43	19	9	20	.10	5	700									0.00		
	371.16	371.78	0.62	14	4	138	.10	5	710									0.00		
	371.78	372.10	0.32	14	3	39	.1	5	860									0.00		
	372.10	372.88	0.78	17	15	235	.20	10	1100									0.00		
	392.10	393.17	1.07	15	15	92	.40	25	1400									0.00		
	393.17	394.41	1.24	11	12	114	.20	65	1400									0.00		
	394.41	395.28	0.87	8	15	210	1.30	1000	3200									0.00		
	395.28	395.99	0.71	12	56	485	.30	200	1300									0.00		
	395.99	396.88	0.89	925	1400	12000	14.00	260	3200									0.00	2	
	396.88	397.33	0.45	5800	1600	4050	33.00	2700	2900									0.00	3	
	397.33	398.27	0.94	22	13	48	.40	50	1300									0.00		

Sample	From (m)	To (m)	Length (m)	GCU PPM	GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T	IAU OZ/T	AU G/T	BA %	SG SG	NSR NSR	SUL %		
	398.27	399.56	1.29	29	9	16	.20	10	1300										0.00			
	399.56	401.12	1.56	75	11	19	.30	5	3400										0.00			
	401.12	402.54	1.42	21	5	41	.20	35	1100										0.00			
	410.06	411.13	1.07	18	6	42	.20	65	1100										0.00		5	
	411.13	412.09	0.96	27	4	45	.20	5	1200										0.00		5	
	412.09	413.00	0.91	19	9	32	.20	5	920										0.00		5	
	414.69	415.69	1.00	27	15	71	.20	10	1600										0.00		10	
	415.69	415.99	0.30	58	38	250	.30	10	1400										0.00			
AVE.	4.42	14.68	10.26	669.97	24.06	323.12	1.21	41.95	2517.6												2.66	
AVE. ^{CHT}	31.90	38.28	6.38	287.72	6.5298	133.79	0.73	3.7915	1313.9													
AVE. ^{CHT}	52.19	55.08	2.89	106.83	12.246	120.54	0.87	5.3287	1985.8													
AVE. ^{CHT}	76.52	80.77	4.25	283.17	10.647	124.08		31.346	1177.6													
AVE.	395.99	397.33	1.34	2562.1	1467.2	9330.2	20.38	1079.4	3099.3												2.34	

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS				
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %		
	8.02	9.52	1.50	200	8	108	.80	240	1700									0.0	2	
	9.52	11.02	1.50	125	91	200	.50	100	2100									0.0	2	
	11.02	12.52	1.50	11	20	148	.20	70	2300									0.0	2	
	12.52	14.02	1.50	48	4	515	.30	50	1900									0.0	2	
	14.02	14.66	0.64	178	42	3600	.40	50										0.0	4	
	14.66	15.94	1.28	580	189	310	1.40	120										0.0	4	
	15.94	16.95	1.01	495	25	1450	.90	110										0.0	4	
	16.95	18.55	1.60	365	74	4000	.70	90										0.0	4	
	18.55	19.04	0.49	1100	73	930	1.20	85										0.0	2	
	19.04	21.50	2.46	1250	19	1900	1.00	75										0.0	3	
	21.50	25.00	3.50	290	2	48	1.00	180	3200									0.0	4	
	25.00	26.51	1.51	260	3	63	.30	35	2700									0.0	4	
	26.51	29.26	2.75	88	3	39	.20	25	2600									0.0	4	
	29.26	30.78	1.52	270	16	50	.20	20	2400									0.0	4	
	55.80	57.30	1.50	390	3	124	.40	5	940									0.0		
	57.30	58.80	1.50	380	2	100	.40	5	1200									0.0		
	58.80	60.30	1.50	535	2	88	.40	15	1500									0.0		
	60.30	61.80	1.50	15	5	19	.20	20	2000									0.0		
	61.80	63.30	1.50	8	5	20	.10	15	2200									0.0		
	63.30	64.80	1.50	6	2	76	.10	10	1900									0.0		
	64.80	66.30	1.50	4	2	26	.10	5	1500									0.0	2	
	66.30	68.08	1.78	45	3	116	.10	5	1600									0.0	2	
	404.20	405.99	1.79				.20	5										0.0		
AVE.	12.52	21.50	8.98	626.53	55.786	1833.8	0.84	82.611	347.37											
AVE.	55.80	60.30	4.50	435.00	2.33	104.00	0.40	8.33	1213.3											

Sample	From (m)	To (m)	Length (m)	ESTIMA GCU PPM	ASSAYS										GEOCHEMICAL					COMMENTS
					GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T	IAU OZ/T	AU G/T	BA %	SG SG	NSR NSR	
	3.66	5.20	1.54	130	370	180	.80	25	2300									0.00	3	
	5.20	6.43	1.23	19	54	80	.20	5	2400									0.00	3	
	6.43	8.44	2.01	23	24	115	.10	10	2500									0.00	3	
	8.44	9.87	1.43	129	5	100	.20	10	2600									0.00	3	
	9.87	11.50	1.63	49	4	78	.10	10	2900									0.00	3	
	11.50	13.25	1.75	14	3	79	.10	10	3000									0.00	3	
14448	13.25	14.64	1.39	5	10	82	0.5	1												
14449	14.64	15.52	0.88	2	14	69	0.4	2												
	15.52	17.52	2.00	3	2	73	.10	5	3500									0.00		
	17.52	19.52	2.00	6	6	93	.10	5	2800									0.00		
	19.52	20.74	1.22	10	24	115	.10	25	1600									0.00	5	
	20.74	21.13	0.39	4	3	109	.10	5	6200									0.00		
	21.13	23.13	2.00	3	6	78	.10	5	1400									0.00		
14450	23.13	24.25	1.12	98	17	68	0.7	1												
14451	24.25	25.41	1.16	8	17	87	0.7	2												
14452	25.41	27.95	2.54	33	8	88	0.5	1												
14453	27.95	29.25	1.30	31	11	87	0.5	1												
14454	29.25	30.37	1.12	57	20	63	0.5	2												
14455	30.37	31.15	0.78	81	11	50	0.7	1												
	31.15	32.61	1.46	6	4	32	.10	15	2600									0.00	5	
	32.61	33.57	0.96	11	5	29	.20	30	5300									0.00	2	
	33.57	34.24	0.67	11	4	61	.30	50	5300									0.00	2	
	34.24	34.81	0.57	13	6	18	.60	160	6500									0.00	2	
	34.81	36.93	2.12	6	7	12	.20	60	3600									0.00	5	
14456	68.30	69.65	1.35	182	6	62	0.7	1												
14457	69.65	70.92	1.27	256	10	65	0.8	2												
14458	70.92	72.28	1.36	804	6	107	1	20												
AVE.	3.66	13.25	9.59	58.252	73.345	105.85	0.24	11.77	2629.2										3.00	
AVE.	15.52	23.13	7.61	4.96	7.68	88.148	0.10	8.21	2597.9										0.80	
AVE.	31.15	36.93	5.78	8.10	5.46	26.15	0.23	52.353	4112.8										3.86	

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS				
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %		
100.89	103.82	2.93		31	17	120	.40	30	870									0.0	2	
103.82	105.46	1.64		73	34	2000	.40	20	870									0.0	2	
105.46	107.05	1.59		158	415	600	.60	10	800									0.0	2	
107.05	107.60	0.55		690	5250	7000	4.70	60	1200									0.0	1	
107.60	109.12	1.52		51	295	250	.40	5	1000									0.0	1	
109.12	110.34	1.22		72	520	315	.40	5	870									0.0	1	
110.34	111.86	1.52		27	225	240	.30	10	1200									0.0		
111.86	112.42	0.56		945	915	6200	2.40	60	1300									0.0		
112.42	114.00	1.58		116	275	1050	1.20	20	1500									0.0	1	
114.00	115.26	1.26		91	38	400	.60	20	1200									0.0	1	
143.40	145.40	2.00		108	16	460	.60	80	3100									0.0	1	
145.40	147.40	2.00		104	7	150	.50	50	3100									0.0	1	
147.40	149.40	2.00		26	7	120	.40	65	3900									0.0	1	
149.40	151.40	2.00		58	295	380	2.90	120	4100									0.0	3	
151.40	153.40	2.00		17	31	96	.80	110	3500									0.0	3	
153.40	155.40	2.00		28	59	182	.80	110	3600									0.0	3	
155.40	157.40	2.00		16	12	84	.30	55	3600									0.0	3	
157.40	159.40	2.00		10	14	90	.30	25	3200									0.0	3	
159.40	161.15	1.75		11	22	116	.30	40	3200									0.0	3	
161.15	161.82	0.67		178	4	170	.50	50	1400									0.0	2	
161.82	162.59	0.77		15	7	100	.20	25	2600									0.0	2	
162.59	164.70	2.11		78	18	230	.20	20	2500									0.0	2	
293.70	294.90	1.20		225		180	.20	5										0.0	1	
357.18	358.28	1.10		1250		70	.50	5										0.0		
405.25	405.58	0.33				75												0.0		
405.58	406.00	0.42		405		18	.10	5										0.0		
421.05	423.55	2.50		900		53	.20	40										0.0	3	
441.88	444.12	2.24		3900		210	1.30	5	1000									0.0		
505.45	508.23	2.78		77	15	53	.10											0.0	3	
508.23	509.90	1.67		24	10	90	.10	5	1300									0.0	3	
509.90	511.56	1.66		14	8	35	.10	5	1400									0.0	5	
511.56	513.66	2.10		78	25	95	.10	5	2000									0.0		
522.80	525.28	2.48		335	775	2500	5.30	170	4100									0.0	2	
525.28	527.60	2.32		14	22	22	.50	5	3900									0.0	2	
527.60	529.26	1.66		16	13	13	1.20	5	5600									0.0	2	
AVE.	103.82	115.26	11.44	155.94	526.46	1297.9	0.85	17.57	1081.7											
AVE.	143.40	164.70	21.30	49.232	45.378	187.94	0.69	65.491	3287.1											

HOLE NUMBER: 87-204

ASSAY SHEET

DATE: 17-September-1990

Sample	From (m)	To (m)	Length (m)	GCU PPM	GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T	IAU OZ/T	AU G/T	BA %	SG SG	NSR NSR	SUL %
	425.35	427.29	1.94	13	26	255	.20	5	1200										0.00	
	427.29	427.65	0.36	37	5	100	.30	15	1200										0.00	
	427.65	429.40	1.75	7	3	18	.10	25	1100										0.00	
	429.40	431.18	1.78	10	4	10	.20	5	1100										0.00	
	431.18	432.98	1.80	11	3	13	.20	5	1100										0.00	
	432.98	434.24	1.26	9	6	6	.10	10	1100										0.00	
	444.45	446.83	2.38	98	14	285	.30	5	990										0.00	
	446.83	447.68	0.85	89	18	355	.30	15	1200										0.00	
	447.68	447.99	0.31	3500	305	6600	15.00	80	1500										0.00	
AVE.	43.20	47.19	3.99	306.53	114.40	690.88	2.34	92.880	1622.3											
AVE.	67.08	76.21	9.13	75.204	9.53	120.80	0.29	35.838	2398.7											3.59
AVE.	87.97	94.14	6.17	112.17	63.486	503.98	1.35	69.096	1007.5											2.74
AVE.	419.15	423.79	4.64	181.05	191.52	1839.6	2.22	48.836	1555.4	0.06	0.15	0.68	0.18	6.238	0.005	0.1832	0.36	1.73	6.56	4.41

HOLE NUMBER: 87-204

ASSAY SHEET

PAGE: 2

Sample	From (m)	To (m)	Length (m)	ESTIMA GCU PPM	ASSAYS										GEOCHEMICAL				SUL %	COMMENTS			
					GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T	IAU OZ/T	AU G/T	BA %	SG SG			NSR NSR		
	17.27	18.67	1.40	440	64	1150	1.20	50	1500											0.00	3		
	18.67	19.71	1.04	460	31	675	1.40	120	1700											0.00	3		
	19.71	20.67	0.96	340	94	235	2.50	200	1600											0.00	3		
	20.67	21.39	0.72	500	42	178	1.40	40	1500											0.00	5		
	21.39	22.25	0.86	116	13	235	.60	25	1700											0.00	5		
	22.25	23.57	1.32	265	14	188	.90	40	1800											0.00	1		
	23.57	24.48	0.91	1300	7	235	2.60	80	1900											0.00	3		
	24.48	25.60	1.12	265	5	65	.40	20	1800											0.00	0		
	31.82	32.38	0.56	2000	19	165	1.80	85	2700											0.00	5		
	32.38	34.21	1.83	870	19	150	.90	45	2800											0.00			
	34.21	35.42	1.21	110	49	89	.50	55	2400											0.00			
	35.42	37.10	1.68	32	14	33	.40	60	2300											0.00			
	64.87	66.31	1.44	184	16	83	.80	70	3300											0.00	2		
	66.31	67.21	0.90	2600	255	1800	7.00	120	3300											0.00	2		
	67.21	68.05	0.84	690	570	1100	3.50	70	5600											0.00	2		
	68.05	68.66	0.61	260	235	460	1.60	60	4000											0.00	2		
	68.66	69.71	1.05	325	37	310	1.60	75	2900											0.00	2		
	69.71	71.01	1.30	137	24	305	.80	50	3200											0.00	2		
	80.57	81.75	1.18	88	44	395	.40	30	2200											0.00	2		
	81.75	83.06	1.31	175	210	3800	1.30	160	1800											0.00	8		
	83.06	83.93	0.87	77	168	120	1.20	380	2100											0.00	3		
	83.93	84.79	0.86	68	450	760	1.50	75	2200											0.00	7		
	84.79	85.33	0.54	355	1150	2500	2.90	35	2500											0.00	2		
	85.33	86.26	0.93	660	9	88	1.30	45	2000											0.00	6		
14459	86.26	87.95	1.69	270	44	572	1.6	60	1750														
14460	87.95	89.31	1.36	482	29	177	1.7	46	1800														
14461	89.31	91.20	1.89	231	22	179	0.8	38															
	91.20	92.16	0.96	63	270	485	1.20	60	2200											0.00	5		
	309.72	310.80	1.08	1100	20	156	.60	75	1600											0.00	30		
	312.42	313.34	0.92	170	9	137	.30	65	2200											0.00	25		
	338.11	338.81	0.70	2600	2	43	.60	25	2200											0.00	3		
	338.81	339.64	0.83	19500	2	126	5.70	240	260											0.00	80		
	353.09	354.93	1.84	940	2	64	.10	5	890											0.00	4		
	354.93	356.51	1.58	1000	2	60	.30	10	1200											0.00	3		
	356.51	358.35	1.84	166	2	149	.10	10	2200											0.00	3		
	358.35	359.73	1.38	630	2	70	.10	5	1700											0.00	6		
	359.73	361.03	1.30	540	2	94	.10	10	1600											0.00	3		
	403.90	404.90	1.00	4	15	10	.20	5	1100											0.00			

Sample	From (m)	To (m)	Length (m)	GCU PPM	GPB PPM	GZN PPM	GAG PPM	GAU PPB	GBA PPM	CU %	PB %	ZN %	IAG OZ/T	AG G/T	IAU OZ/T	AU G/T	BA %	SG SG	NSR NSR	SUL %		
	404.90	405.90	1.00	11	8	48	.30	10	1200											0.00		
	405.90	406.90	1.00	10	11	25	.40	50	1400											0.00	1	
	406.90	407.55	0.65							.06	.06	1.16	.27	9.26	.014	0.48	.63	2.80	11.72		3	
	407.55	408.52	0.97							.04	.04	.47	.22	7.54	.012	0.41	.67	2.80	7.65		2	
	408.52	409.22	0.70							.10	.48	1.16	1.43	49.02	.059	2.02	.81	2.80	34.20		3	
	409.22	409.77	0.55							.13	.48	1.68	.80	27.42	.055	1.89	.74	2.80	31.56		5	
	409.77	410.90	1.13							.32	.40	2.80	1.07	36.68	.030	1.03	.29	2.90	32.35		5	
	410.90	411.78	0.88							1.59	.44	3.15	2.00	68.56	.051	1.75	.24	3.30	62.98		20	
	411.78	412.79	1.01							.29	.16	2.03	1.01	34.62	.016	0.55	.26	3.00	23.68		10	
	412.79	414.44	1.65							.27	.15	1.36	.53	18.17	.011	0.38	.34	2.80	16.10		5	
	414.44	415.39	0.95							.50	.36	1.25	.81	27.77	.014	0.48	.45	2.90	21.66		20	
	415.39	416.14	0.75							1.28	.32	1.63	1.40	47.99	.032	1.10	.34	3.00	42.79		10	
	416.14	417.17	1.03							.31	.24	.56	.35	12.00	.016	0.55	.39	2.80	13.93		5	
	417.17	417.75	0.58							.48	.12	.32	.57	19.54	.024	0.82	.41	3.00	18.91		5	
	417.75	418.17	0.42							.78	.05	.20	1.54	52.79	.026	0.89	.39	3.00	28.92		10	
	418.17	419.58	1.41							.82	.28	.90	.79	27.08	.089	3.05	.42	2.90	47.84		5	
	419.58	420.32	0.74							.53	.25	1.19	.54	18.51	.013	0.45	.42	3.00	19.67		8	
	420.32	421.00	0.68							.91	.18	.43	.44	15.08	.018	0.62	.40	2.90	22.42		5	
	421.00	422.00	1.00							.24	.27	1.93	.37	12.68	.022	0.75	.34	3.00	20.68		5	
	422.00	422.51	0.51	1450	178	8000	5.30	160	7200										0.00		3	
	422.51	423.11	0.60	390	1050	5800	3.00	70	3400										0.00		2	
	423.11	423.90	0.79	66	78	385	1.10	85	2700										0.00		2	
	423.90	425.66	1.76	155	6	90	.80	15	1000										0.00			
	425.66	426.84	1.18	6	5	20	.20	5	1000										0.00			
	426.84	428.21	1.37	12	4	25	.30	5	990										0.00			
AVE.	17.27	25.60	8.33	445.40	34.09	408.48	1.33	70.240	1688.7												2.66	
AVE.	31.82	37.10	5.28	549.05	24.28	100.38	0.74	56.31	2538.6												0.53	
AVE.	64.87	71.01	6.14	629.07	153.87	597.09	2.29	72.956	3594.6												2.00	
AVE.	80.57	86.26	5.69	222.15	261.78	1341.6	1.28	123.17	2088.4												4.94	
AVE.	86.26	92.16	5.90	272.69	70.268	340.90	1.30	49.725	1274.2												0.81	
AVE.	406.90	422.00	15.10							0.50	0.25	1.38	0.80	27.32	0.030	1.03	0.42	2.92	26.94		7.32	

HOLE NUMBER: 87-207

ASSAY SHEET

DATE: 17-September-1990

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
	6.09	7.47	1.38						2200									0.0
	7.47	8.57	1.10	105	2	190	.10	10	2300									0.0
	8.57	10.09	1.52	6	3	68	.10	5	2100									0.0
	10.09	11.27	1.18	6	5	83	.10	5	2100									0.0
	11.27	13.23	1.96	20	7	82	.20	5	1800									0.0
	13.23	14.02	0.79	96	5	66	.30	5	1700									0.0
	14.02	15.18	1.16	13	4	79	.20	5	1800									0.0
AVE.	6.09	15.18	9.09	28.803	3.85	78.636	0.14	4.85	1667.7									
AVE.	7.47	15.18	7.71	33.958	4.54	92.711	0.16	5.71	1966.1									

HOLE NUMBER: 87-217

ASSAY SHEET

DATE: 17-September-1990

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
	25.62	26.89	1.27	260	3	30	.40	10	2300									
	31.77	33.34	1.57	600	6	128	1.10	30	2800									
	37.30	39.67	2.37	240	188	330	2.20	130	2700									
	39.67	41.28	1.61	38	20	205	1.70	260	2900									
	48.52	50.51	1.99	220	41	153	.80	110	2500									

HOLE NUMBER: 89-228

ASSAY SHEET

DATE: 17-September-1990

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS	
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T
12738	57.60	58.30	0.70	1490		70	1.6	25									0.0
12739	71.70	73.10	1.40	2500		51	1.2	5									0.0
12740	73.10	74.30	1.20	550		49	1.4	5									0.0
12741	139.95	141.20	1.25	242		84	0.8	5									0.0
12742	167.00	168.10	1.10	16		151	1.0	5									0.0
12743	172.20	173.30	1.10	20		50	1.0	5									0.0
12744	183.60	184.70	1.10	332		48	0.8	5									0.0
12745	184.70	185.80	1.10	90		40	0.8	5									0.0
12746	222.50	223.90	1.40	58		151	1.8	5									0.0
12747	223.90	225.30	1.40	17		52	0.5	5									0.0
12748	235.10	236.20	1.10	3		10	0.2	5									0.0
12749	236.20	237.35	1.15	7		18	0.3	5									0.0
12750	237.35	237.60	0.25	1950		4650	30.0	825	3100								0.0

HOLE NUMBER: 89-228

ASSAY SHEET

PAGE: 1

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS	
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T
12792	12.50	13.65	1.15	57	12	133	0.6	20									0.0
12793	13.65	15.05	1.40	1020	12	162	1.1	35	2200								0.0
12794	15.05	16.45	1.40	34	20	107	0.3	45	3500								0.0
12795	16.45	16.90	0.45	1850	3900	4100	4	45									0.0
12796	16.90	18.10	1.20	51	50	113	0.2	5									0.0
12797	34.45	34.80	0.35	44	22	62	0.4	25									0.0
12798	34.80	35.80	1.00	16	10	100	0.2	15	3760								0.0
12799	35.80	36.80	1.00	17	12	125	0.4	20	5000								0.0
12800	36.80	38.30	1.50	22	10	88	0.4	5	3400								0.0
12826	38.30	39.90	1.60	9	8	89	0.3	5	2340								0.0
12827	53.65	54.70	1.05	11	10	63	0.4	5	2800								0.0
12828	64.10	65.60	1.50	70	12	70	0.6	5									0.0
12829	65.60	67.10	1.50	116	11	82	0.6	5									0.0
12830	67.10	68.60	1.50	400	14	93	0.7	5									0.0
12831	116.30	117.30	1.00	6750	18	78	2.3	5									0.0
12832	117.30	118.30	1.00	6900	18	230	2.2	35									0.0
12833	118.30	119.35	1.05	12500	17	94	3.2	20									0.0
12834	119.35	119.85	0.50	2450	21	52	1.9	20									0.0
12835	119.85	121.05	1.20	4100	18	53	1.6	25									0.0
12836	121.05	122.05	1.00	13000	17	120	3.2	35									0.0
12837	206.20	207.70	1.50	2050	18	145	1.3	20									0.0
12838	207.70	209.20	1.50	425	24	135	1	15									0.0
12839	244.45	245.30	0.85	275	94	150	0.9	5									0.0
12840	245.30	246.20	0.90	265	17	66	0.7	5									0.0
12841	350.00	351.00	1.00	15	9	26	0.4	10									0.0
12842	351.00	352.10	1.10	94	62	165	1	15									0.0
12843	352.10	353.10	1.00	21	8	32	0.5	5									0.0
12844	404.00	405.10	1.10	34	20	102	0.7	5									0.0
12845	435.10	436.70	1.60	47	309	408	2.1	5									0.0
12846	436.70	438.20	1.50	329	1230	990	11.2	5									0.0
AVE.	12.50	18.10	5.60	434.79	334.57	448.24		28.795	1425.0								
AVE.	34.45	39.90	5.45	17.578	10.550	95.615	0.33	10.872	3230.1								
AVE.	64.10	68.60	4.50	195.33	12.333	81.667	0.63	5.0000									
ALT.AVG.	116.30	122.05	5.75	7986.1	17.904	107.18	2.42	23.652									

HOLE NUMBER: 89-244

ASSAY SHEET

DATE: 17-September-1990

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
12929	41.30	42.10	0.80	28	16	95	0.5	20	3000									0.0
12930	46.25	47.20	0.95	31	9	58	0.4	2	1800									0.0
12931	51.50	52.65	1.15	14	22	38	1	98										0.0
12932	84.70	85.90	1.20	223	18	91	0.8	2										0.0
12933	97.30	97.80	0.50	3000	15	37	1.5	1										0.0
12934	254.20	255.10	0.90	79	59	146	1.2	40										0.0
12935	255.10	256.00	0.90	60	11	91	0.2	6										0.0
12936	256.00	256.50	0.50	44	27	82	1.8	1135					0.035	1.21				11.0

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
12940	25.30	26.80	1.50	710	240	785	2.3	43										0.0
12941	26.80	28.30	1.50	365	140	520	1.4	26										0.0
12942	28.30	29.80	1.50	172	127	930	1.1	15										0.0
12943	29.80	31.30	1.50	165	142	1630	1.4	22										0.0
12944	31.30	33.20	1.90	590	51	4900	1.7	57										0.0
12945	33.20	33.80	0.60	300	75	5700	0.9	51										0.0
12946	36.10	36.60	0.50	113	158	395	1.4	108										0.0
12947	36.60	38.10	1.50	295	20	290	1.3	16										0.0
12948	39.20	40.00	0.80	460	13	174	1.6	5	1300									0.0
12949	40.00	40.90	0.90	500	11	200	1.4	2	1100									0.0
12950	118.30	118.75	0.45							2.99	0.01	0.11	0.37	12.7	0.023	0.8		49.5
13101	162.75	164.00	1.25	188	27	98	1.8	3										0.0
13102	236.55	237.00	0.45	4500	18	215	2.6	61										0.0
13103	373.05	374.10	1.05	40	16	45	0.7	4										0.0
13104	388.60	389.50	0.90	61	34	78	2.1	17										0.0
13105	389.50	390.25	0.75							0.349	0.12	2.29	0.57	19.7	0.055	1.88	2.91	35.0
13106	390.25	390.75	0.50							0.196	0.18	0.46	0.3	10.4	0.012	0.41	2.75	10.4
13107	390.75	391.40	0.65							0.96	0.92	2.05	1.8	61.8	0.029	1.01	2.99	42.7
13108	391.40	391.40	0.00							0.755	0.26	0.57	1.05	35.9	0.05	1.73	2.78	34.9
13109	391.90	392.55	0.65							0.487	0.03	0.12	0.53	18.2	0.029	0.99	2.89	19.4
13110	409.00	409.80	0.80	22	21	62	0.9	4										0.0
13111	409.80	410.60	0.80	38	29	83	1.3	15										0.0
AVE.	25.30	36.60	11.30	307.57	105.70	1657.1	1.22	31.142										
AVE.	29.80	33.80	4.00	387.12	88.725	3793.7	1.47	42.975										
AVE.	36.60	40.90	4.30	293.14	11.698	175.40	1.04	6.9302	472.09									
AVE.	389.50	392.55	3.05							0.426	0.26	1.10	0.69	23.60	0.028	0.96		

Sample	From (m)	To (m)	Length (m)	ASSAYS					GEOCHEMICAL					COMMENTS			
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T		AG G/T	AU OZ/T	AU G/T
13112	40.25	41.00	0.75	108	6	200	0.4	1									0.00
13113	46.00	47.45	1.45	176	11	58	0.8	4									0.00
13114	48.50	48.95	0.45	350	8	22	0.6	102									0.00
13115	177.00	178.50	1.50	540	12	40	0.8	2									0.00
13116	200.85	201.90	1.05	158	654	1640	5	112		.016	.06	.16	.14	5.0	.003	.112	2.76
13117	201.90	202.90	1.00	290	1160	3000	3.4	21		.029	.11	.30	.10	3.4	.001	.021	2.70
13118	202.90	203.20	0.30	870	2630	8500	13.8	89		.087	.26	.85	.40	13.8	.002	.089	8.11
13119	203.20	204.70	1.50	270	410	1700	3.6	42		.027	.04	.17	.10	3.6	.001	.042	2.04
13120	204.70	206.20	1.50	86	390	1730	1.4	48		.009	.04	.17	.04	1.4	.001	.048	1.43
13121	206.20	207.70	1.50	79	210	950	1	36									0.00
13122	207.70	209.20	1.50	56	209	340	0.8	32									0.00
13123	209.20	210.70	1.50	48	200	354	0.5	4									0.00
13124	210.70	212.20	1.50	59	222	400	0.8	19									0.00
13125	212.20	213.70	1.50	57	176	420	0.8	17									0.00
13126	213.70	215.20	1.50	91	384	660	1.2	26									0.00
13127	215.20	216.70	1.50	82	290	750	1	38									0.00
13128	216.70	218.20	1.50	66	195	502	1	30									0.00
13129	218.20	219.70	1.50	60	175	380	0.7	5									0.00
13130	219.70	221.20	1.50	85	170	510	1.2	19									0.00
13131	221.20	222.70	1.50	63	144	490	1	26									0.00
13132	222.70	224.20	1.50	155	580	2500	2.6	27		.015	.06	.25	.08	2.6	.001	.027	2.12
13133	224.20	225.70	1.50	243	372	1860	2.5	510		.024	.04	.19	.07	2.5	.015	.510	6.31
13134	225.70	227.20	1.50	79	250	730	0.8	177									0.00
13135	227.20	228.70	1.50	54	176	315	0.7	19									0.00
13136	228.70	230.20	1.50	77	307	810	1.3	21									0.00
13137	230.20	231.20	1.00	56	225	445	0.8	12									0.00
13138	231.20	232.70	1.50	48	92	265	0.7	47									0.00
13139	235.20	236.70	1.50	18	10	32	0.2	169									0.00
AVE.	200.85	207.70	6.85	199.91	605.94	2020.7	3.1810	51.723									0.00
ALT.AVG.	200.85	232.70	31.85	107.06	323.04	980.09	1.5381	59.397									0.00

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS		
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T	BA %
13282	34.80	35.35	0.55	2690	285	1500	3.7	75										
13283	55.65	56.55	0.90	371	117	5750	1.8	37										
13284	65.15	66.50	1.35	173	44	172	1.2	30										
13285	66.50	68.00	1.50	102	39	117	0.8	26										
13286	81.70	82.60	0.90	1155	52	385	2.3	88										
13287	106.85	107.80	0.95	73	36	161	1.2	49										
13289	111.60	112.75	1.15	14200	100	1200	5.9	140		1.42	0.01	0.12		5.9		0.14		
13290	112.75	114.25	1.50	521	19	106	1.4	14										
13291	114.25	115.25	1.00	3825	13	88	1.2	23										
13292	118.10	119.55	1.45	4340	15	96	2	48	1740									
13293	119.55	121.00	1.45	2270	12	83	1.3	30										
13295	122.45	123.90	1.45	31	19	43	0.9	12										
13294	140.20	140.70	0.50	2095	28	70	1.8	31										
13295	181.90	182.65	0.75	31	19	43	0.9	12										
13296	182.65	183.50	0.85	11	20	42	0.8	19	4500									
13297	183.50	184.40	0.90	13	18	47	1.1	20										
13298	184.40	185.80	1.40	9	21	41	1.1	9										
13299	187.30	188.05	0.75	417	20	73	1.5	29										
AVE.	111.60	115.25	3.65	5736.0	42.877	445.75	2.76	56.164										
AVE.	118.10	121.00	2.90	3305.0	13.500	89.500	1.6500	39.000	870.00									

Sample	From (m)	To (m)	Length (m)	ASSAYS						GEOCHEMICAL						COMMENTS	
				CU PPM	PB PPM	ZN PPM	AG PPM	AU PPB	BA PPM	CU %	PB %	ZN %	AG OZ/T	AG G/T	AU OZ/T		AU G/T
13801	28.66	30.78	2.12	250	189	153	1.2	4									
13802	52.87	54.59	1.72	355	14	168	0.7	6									
13803	54.59	55.63	1.04	182	22	180	0.9	3									
13804	55.63	56.99	1.36	42	17	106	0.5	3									
13805	56.99	58.34	1.35	1600	5	58	1.2	5									
13806	58.34	59.05	0.71	23700	70	158	6.4	170		2.37							
13807	59.05	59.95	0.90	440	15	110	0.8	5									
13808	59.95	61.35	1.40	410	18	168	0.8	7									
13809	61.35	62.24	0.89	525	21	215	0.7	24									
13810	62.24	63.40	1.16	215	25	83	0.6	26									
13811	63.40	64.97	1.57	475	325	238	0.8	3									
13812	77.27	78.63	1.36	138	17	94	0.8	2									
13813	78.63	79.85	1.22	250	16	98	0.7	1									
13814	94.00	95.50	1.50	760	24	115	1.2	26									
13815	95.50	96.71	1.21	1200	25	113	1.3	25									
13816	96.71	98.25	1.54	3400	26	141	1.9	41									
13817	98.25	99.88	1.63	3250	27	134	1.6	48									
13818	99.88	101.41	1.53	900	31	82	1.3	22									
13819	101.41	102.84	1.43	780	28	112	1.2	22									
AVE.	56.99	64.97	7.98	2684.1	81.841	148.62	1.33	24.810		0.21							
AVE.	95.50	99.88	4.38	2736.4	26.096	130.66	1.62	39.185									