

82F  
Rossland

Velvet Report

827860



To 4th Portal

To Rossland

To 8th Portal

VE-01

MAIN SHAFT

L2521

VE-02

L5205  
CG2523

L3027

PORTLAND  
SHAFT

VE-03

15928, 29

L4669

15926, 27  
TRENCH

+ Syenite

Monz

TRENCH

2700

2800

VELVET PROPERTY BOUNDARY

VELVET PROPERTY

To  
Big Sheep  
Creek

**MINNOVA Inc.**

FILE: D:\DWG\VELWORK

	Syenite	Monzonite	Lamprophylic Dykes	Mafic Volcanics	Serpentine	Diorite	Qtz Diorite	Felsite	Syenite Border Phase
Al <sub>2</sub> O <sub>3</sub>	16.81	17.02	15.56	17.31	0.63	17.23	18.19	16.62	17.49
Ba	0.11	0.06	0.14	0.05	0.01	0.07	0.05	0.04	0.05
CaO	2.86	4.98	5.57	4.71	3.35	5.67	4.83	2.82	4.83
Fe <sub>2</sub> O <sub>3</sub>	4.11	4.95	6.32	5.23	7.98	5.01	3.60	3.76	3.35
K <sub>2</sub> O	5.24	2.05	3.87	2.81	0.18	2.46	1.44	3.65	1.47
MgO	1.87	2.25	4.73	2.24	32.56	2.64	1.45	1.08	1.33
MnO <sub>2</sub>	0.09	0.11	0.12	0.10	0.19	0.11	0.11	0.08	0.08
Na <sub>2</sub> O	4.50	3.24	3.10	2.57	0.06	3.62	3.96	3.88	4.31
P <sub>2</sub> O <sub>5</sub>	0.13	0.17	0.21	0.16	0.44	0.20	0.20	0.11	0.16
SiO <sub>2</sub>	60.31	59.78	53.74	58.44	36.92	58.24	63.46	63.58	61.47
TiO <sub>2</sub>	0.52	0.44	0.82	0.43	0.02	0.52	0.37	0.31	0.34
S	0.09	0.37	0.11	0.11	0.12	0.07	0.02	0.04	0.08
LOSS ON IGNITION	2.32	4.29	4.75	6.14	17.60	1.70	1.40	1.85	1.40
TOTAL	98.78		99.05	100.30	100.06	97.54	99.08	97.82	96.36
Number of Observations	12	23	16	17	21	4	1	2	2

SAMPLE_NO	AL2O3	BA	CAO	FE2O3	K2O	MGO	MNO2	NA2O	P2O5	SIO2	TIO2	S	TOTAL%	ROCK	TYPE	LOCATION
BCD17951	16.66	.138	2.49	5.01	5.01	2.59	.10	4.49	.18	60.25	.64	.06	97.60	1	surface	
BCD17953	.43	.005	.01	7.33	.01	37.21	.24	.01	.49	40.20	.01	.08	86.00	2	surface	
BCD17954	15.44	.149	6.07	7.55	4.01	5.28	.15	3.21	.32	54.39	.86	.09	97.53	3	surface	
BCD17956	.41	.005	.49	10.00	.10	38.31	.25	.01	.56	37.80	.01	.06	88.01	2	surface	
BCE17957	17.75	.045	3.73	2.82	.87	.98	.05	5.16	.16	65.97	.29	.03	97.86	9	surface	
BCD17959	.40	.005	.04	7.78	.10	35.85	.08	.02	.50	42.23	.01	.02	87.03	2	surface	
BCD17961	.34	.005	.01	7.36	.03	35.34	.15	.03	.49	46.59	.01	.17	90.50	2	surface	
BCD17965	18.19	.051	4.83	3.60	1.44	1.45	.11	3.96	.20	63.46	.37	.02	97.70	5	surface	
BCS17970	.46	.005	.29	8.75	.19	41.88	.15	.06	.46	41.87	.01	.01	94.12	2	surface	
BCS17971	17.30	.030	.82	2.97	7.18	.53	.11	5.21	.08	63.60	.29	.02	98.15	1	surface	
BCS17455	14.54	.100	6.68	7.49	1.62	4.75	.13	3.09	.25	52.56	.77	.18	92.18	6	8th lev	
BCS17456	17.65	.050	4.68	4.36	1.57	1.84	.09	3.90	.14	59.47	.38	.09	94.23	4	8th lev	
BCS17457	.60	.005	3.79	5.77	.01	29.72	.11	.01	.40	36.81	.01	.16	77.37	2	8th lev	
BCS17459	16.98	.095	4.67	5.41	2.06	2.77	.11	3.53	.19	58.71	.78	.08	95.38	4	8th lev	
BCS17460	17.82	.035	5.23	4.39	1.22	2.23	.09	3.94	.16	59.66	.40	.12	95.29	3	8th lev	
BCS17461	16.10	.145	4.33	5.57	4.61	3.09	.12	4.28	.18	57.16	.76	.13	96.48	1	8th lev	
BCS17464	17.93	.045	4.34	4.28	2.85	1.58	.10	3.10	.15	58.94	.41	.07	93.79	4	8th lev	
BCS17467	17.22	.050	5.93	3.88	2.07	1.67	.11	3.47	.16	56.97	.39	.13	92.06	9	8th lev	
BCS17468	16.04	.140	4.77	5.09	4.57	2.71	.11	4.28	.17	56.75	.72	.12	95.46	1	8th lev	
BCS17469	17.58	.070	4.67	4.01	3.60	1.61	.10	3.08	.14	58.14	.43	.04	93.47	3	8th lev	
BCS17470	18.26	.060	1.92	4.30	2.65	2.53	.10	4.07	.13	61.15	.43	.02	95.61	7	8th lev	
BCS17471	18.55	.060	3.50	4.16	2.77	1.57	.11	3.17	.13	61.16	.42	.04	95.65	7	8th lev	
BCS17476	18.18	.055	5.64	4.39	1.08	1.50	.12	3.84	.17	61.15	.40	.08	96.61	7	4th lev	
BCS17477	15.71	.155	5.35	5.59	4.59	3.08	.13	3.85	.20	55.92	.77	.13	95.47	7	4th lev	
BCS17478	16.09	.130	5.44	6.62	4.76	5.83	.14	3.00	.22	53.48	.71	.12	96.56	6	4th lev	
BCS17479	16.49	.150	6.85	6.35	2.21	3.30	.12	2.93	.23	55.62	1.08	.17	95.51	7	4th lev	
BCS17482	17.14	.095	5.46	5.65	2.25	2.28	.12	3.51	.19	58.71	.78	.07	96.25	7	4th lev	
BCS17483	17.17	.055	4.33	5.24	2.89	1.70	.10	2.92	.16	59.71	.40	.04	94.71	8	4th lev	
BCS17527	18.04	.030	4.71	5.06	2.74	2.28	.12	3.17	.17	58.97	.42	.10	95.82	4	8th lev	
BCS17531	16.37	.120	4.53	5.35	5.56	3.49	.13	3.32	.17	54.89	.71	.09	94.74	6	8th lev	
BCS17533	16.35	.105	4.10	5.53	5.14	3.12	.12	3.82	.16	56.03	.76	.08	95.32	1	8th lev	
BCS17538	13.01	.050	4.07	7.99	2.01	2.56	.15	1.36	.18	63.35	.34	.50	95.57	7	8th lev	
BCS18276	17.66	.090	2.13	2.76	5.65	.91	.07	4.82	.10	62.63	.29	.06	97.17	1	8th lev	
BCS18278	18.57	.055	1.56	6.14	4.04	2.42	.05	.37	.11	61.04	.40	.05	94.81	4	8th lev	
BCS18279	15.61	.150	5.46	6.62	3.79	5.68	.11	3.29	.22	52.32	.90	.12	94.27	6	8th lev	
BCS18280	15.74	.145	6.41	6.88	3.35	6.49	.14	3.04	.24	49.37	.71	.09	92.60	6	8th lev	
BCS18281	16.77	.110	3.73	5.65	4.07	3.30	.09	3.64	.17	57.27	.77	.22	95.78	1	8th lev	
BCS18282	16.77	.045	4.48	6.19	3.03	3.06	.15	.51	.18	57.59	.38	.63	93.00	4	8th lev	
BCS18284	.73	.010	16.09	6.21	.01	22.19	.15	.01	.46	22.92	.01	.01	68.77	2	8th lev	
BCS18285	16.63	.100	6.53	7.29	1.91	4.65	.13	3.40	.22	51.68	.94	.12	93.60	6	8th lev	
BCS18286	16.07	.035	1.31	2.29	4.42	.46	.05	4.84	.06	67.45	.22	.04	97.26	8	8th lev	
BCS18287	18.13	.045	3.60	4.00	1.07	1.80	.09	4.43	.12	61.48	.41	.01	95.20	4	8th lev	

BCS18237	.50	.005	8.62	3.52	.43	28.64	.22	.08	.43	28.88	.01	.01	71.35	2	7th lev
BCS18278	18.57	.055	1.56	6.14	4.04	2.42	.05	.37	.11	61.04	.40	.05	94.81	4	8th lev
BCS18239	17.03	.105	1.31	8.40	5.38	3.23	.08	1.21	.14	58.48	.37	.06	95.80	4	7th lev
BCS18240	.67	.010	7.14	10.34	.74	35.88	.17	.14	.51	39.80	.01	.04	95.45	2	7th lev
BCS18244	.67	.010	.66	7.72	.33	36.34	.08	.06	.38	38.38	.01	.06	84.70	2	7th lev
BCS18275	13.27	.030	12.92	5.02	2.63	2.85	.18	.56	.27	48.84	.30	.05	86.92	4	8th lev
BCS18301	18.07	.035	6.70	4.08	1.01	1.44	.11	4.24	.18	60.79	.40	.01	97.07	3	7th lev
BCS18307	.32	.010	1.26	9.47	.01	31.18	.12	.01	.34	32.89	.01	.01	75.62	2	7th lev
BCS18308	.23	.010	.43	6.39	.01	33.46	.16	.01	.34	32.97	.01	.02	74.02	2	7th lev
BCS18309	.31	.010	1.76	10.47	.01	34.54	.16	.01	.44	34.20	.01	.04	81.94	2	7th lev
BCS18310	16.85	.100	1.71	2.92	5.00	1.39	.07	4.81	.10	63.65	.29	.06	96.95	1	7th lev
BCS18317	14.81	.160	4.17	6.38	3.84	5.29	.13	2.88	.20	57.05	.88	.08	95.86	6	7th lev
BCS18318	.48	.010	7.27	6.91	.01	24.53	.09	.15	.40	42.53	.01	.24	82.64	2	7th lev
BCS18320	.32	.005	1.34	8.13	.49	29.83	.12	.13	.37	35.38	.01	.02	76.14	2	7th lev
BCS18329	.33	.010	2.67	11.57	.98	28.74	.12	.13	.41	38.84	.01	.08	83.88	2	7th lev
BCD21451	17.58	.045	6.73	4.04	.88	1.35	.12	3.73	.19	60.79	.40	.02	95.87	7	vel-01
BCD21452	15.30	.140	6.29	6.21	2.54	4.17	.11	3.46	.22	53.60	1.04	.07	93.15	6	vel-01
BCD21453	16.70	.110	2.78	3.29	4.56	1.27	.08	4.55	.11	62.18	.41	.08	96.11	1	vel-01
BCD21454	17.61	.045	6.08	4.56	2.73	2.13	.12	1.35	.17	57.82	.42	.03	93.06	4	vel-01
BCD21457	17.95	.045	6.04	4.09	1.13	1.42	.12	4.01	.17	60.56	.40	.03	95.96	7	vel-01
BCD21471	15.63	.150	5.61	5.93	4.35	4.82	.12	3.16	.21	53.38	.87	.11	94.34	6	vel-01
BCD21479	18.12	.050	4.58	4.88	2.92	1.51	.08	2.46	.16	61.25	.37	.04	96.43	4	vel-01
BCD21480	16.82	.150	3.63	4.49	5.17	1.87	.10	5.36	.14	58.63	.62	.09	97.07	1	vel-01
BCD21483	18.07	.045	5.79	4.13	.93	1.45	.10	4.24	.16	61.05	.41	.02	96.40	7	vel-01
BCD21484	17.96	.045	6.17	4.58	1.34	1.49	.12	3.84	.17	60.95	.40	.03	97.09	7	vel-01
BCD21485	15.57	.150	6.71	6.86	4.61	6.36	.14	2.80	.26	51.95	.72	.10	96.22	6	vel-01
BCD21487	18.10	.045	5.26	4.19	1.44	1.39	.10	3.97	.16	61.57	.41	.09	96.73	7	vel-01
BCD21505	17.82	.055	3.98	4.42	1.72	1.62	.08	4.21	.14	60.74	.41	.03	95.24	7	vel-02
BCD21507	17.15	.100	2.10	2.81	5.24	.89	.08	4.67	.09	63.33	.30	.07	96.81	4	vel-02
BCD21508	17.49	.045	7.13	4.09	1.24	1.41	.10	3.68	.19	59.79	.38	.03	95.57	7	vel-02
BCD21509	17.55	.050	5.60	4.01	1.64	1.47	.10	3.61	.16	60.26	.38	.03	94.85	7	vel-02
BCD21510	14.38	.155	5.22	6.01	4.46	4.11	.11	2.86	.20	57.11	.82	.10	95.54	6	vel-02
BCD21516	16.91	.095	2.07	2.75	5.38	.76	.07	4.28	.08	64.03	.29	.14	96.85	1	vel-02
BCD21577	16.99	.040	3.59	3.43	3.45	1.33	.07	2.44	.13	62.05	.38	.38	94.28	4	vel-02
BCD21580	16.35	.040	7.29	6.01	2.45	2.49	.14	3.10	.21	52.48	.55	.02	91.13	4	vel-02
BCD21594	.39	.005	.01	8.29	.01	37.64	.23	.02	.42	38.74	.01	.14	85.88	2	vel-02
BCD21596	.29	.005	.11	8.18	.01	37.14	.24	.02	.45	38.96	.01	.10	85.49	2	vel-02
BCD21527	.39	.005	.01	7.43	.01	36.59	.18	.03	.40	38.80	.01	.14	83.96	2	vel-02
BCD21529	3.17	.060	3.86	6.85	.24	27.94	.22	.28	.42	37.81	.19	.38	81.43	2	vel-02
BCD21534	16.97	.045	4.09	3.15	1.14	1.44	.08	5.41	.15	63.68	.32	.14	96.62	4	vel-02
BCD19826	17.53	.105	1.70	3.25	6.56	.88	.07	4.44	.07	61.60	.41	.07	96.68	1	vel-03



BCD19827	16.53	.125	3.98	5.18	5.77	3.25	.10	3.40	.16	55.74	.69	.08	95.00	6	vel-03
BCD19828	17.89	.055	6.55	4.35	1.24	1.51	.11	3.85	.18	59.69	.42	.04	95.86	7	vel-03
BCD19831	18.18	.020	8.55	9.01	.38	4.12	.18	3.12	.25	48.39	.76	.01	92.98	4	vel-03
BCD19835	16.39	.140	4.88	5.28	4.20	3.19	.10	3.48	.18	56.19	.68	.10	94.80	6	vel-03
BCD19840	16.33	.150	4.80	5.74	5.05	3.47	.10	3.16	.18	54.18	.87	.11	94.15	6	vel-03
BCD19844	15.45	.050	4.11	8.21	3.18	2.96	.10	.78	.17	57.43	.36	2.10	94.89	7	vel-03
BCD19854	15.55	.035	2.71	10.71	3.39	3.00	.09	.44	.16	55.54	.36	5.00	96.99	7	vel-03
BCD19855	17.47	.045	5.15	5.43	2.48	2.22	.12	3.25	.17	56.58	.48	.07	93.47	7	vel-03
BCD19861	14.50	.180	7.04	7.17	3.16	5.93	.13	2.45	.26	50.61	1.05	.11	92.59	6	vel-03
BCD19864	14.55	.155	5.37	6.05	3.02	4.22	.13	2.87	.21	55.73	.85	.12	93.28	6	vel-03
BCD19865	17.37	.045	3.18	2.87	1.83	1.09	.05	5.43	.12	63.38	.30	.04	95.70	7	vel-03
BCD19867	16.96	.060	4.07	3.33	2.71	1.62	.09	3.03	.14	62.04	.35	.02	94.42	7	vel-03
BCD19868	13.48	.015	6.89	4.39	.76	8.05	.14	1.80	.26	53.96	.24	.01	90.00	7	vel-03
BCD19869	17.33	.055	2.32	2.53	3.71	2.96	.10	1.96	.13	63.56	.28	.03	94.97	7	vel-03
BCD19871	1.73	.030	14.56	9.10	.01	20.72	.69	.02	.54	28.77	.01	.64	76.82	2	vel-03

SAMPLE_NO	CU_PER	PB_PER	ZN_PER	AG_GMPTAG	OZPTAU_GMPTAU	OZPTWIDTH		
BCD17967	1.360	0.02	0.02	18.4	0.54	19.00	0.554	0
BCD17968	1.260	0.03	0.01	19.9	0.58	10.76	0.314	0
BCD17969	9.580	0.02	0.01	39.0	1.14	11.15	0.326	0
BCS17437	1.980	0.01	0.01	13.80	0.40	4.10	0.120	1.0
BCS17441	1.510	0.01	0.02	10.20	0.30	0.66	0.019	1.0
BCS18226	0.785	0.01	0.01	6.6	0.19	0.46	0.013	1.0
BCS18227	0.448	0.01	0.02	4.5	0.13	0.25	0.007	1.0
BCS18228	0.583	0.01	0.01	6.9	0.20	1.43	0.042	1.0
BCS18229	0.800	0.01	0.01	7.0	0.20	0.79	0.023	1.0
BCS18230	1.200	0.01	0.01	8.4	0.25	0.52	0.015	1.0
BCS18231	0.698	0.01	0.02	7.7	0.22	0.40	0.012	1.0
BCS18232	0.071	0.01	0.02	3.6	0.11	0.02	0.001	1.0
BCS18233	0.193	0.01	0.01	2.4	0.07	0.07	0.002	1.0
BCS18234	0.990	0.01	0.02	7.8	0.23	2.15	0.063	1.0
BCS18235	2.490	0.01	0.01	11.2	0.33	1.20	0.035	1.0
BCS18236	1.420	0.01	0.01	7.7	0.22	2.59	0.076	1.0
BCS18243	0.032	0.01	0.01	0.8	0.02	0.02	0.001	1.0
BCS18245	0.075	0.01	0.01	2.5	0.07	0.03	0.001	1.0
BCS18246	0.460	0.01	0.01	4.1	0.12	0.50	0.015	1.0
BCS18247	0.502	0.01	0.01	8.3	0.24	0.70	0.020	1.0
BCS18248	1.730	0.01	0.01	7.7	0.22	1.32	0.039	1.0
BCS18249	0.820	0.01	0.01	6.2	0.18	0.78	0.023	1.0
BCS18250	0.252	0.01	0.01	3.6	0.11	0.82	0.024	1.0
BCS18251	0.560	0.01	0.01	4.5	0.13	4.71	0.137	1.0
BCS18252	1.120	0.01	0.01	4.3	0.13	0.25	0.007	1.0
BCS18253	2.590	0.01	0.01	12.0	0.35	0.32	0.009	1.0
BCS18254	1.080	0.01	0.01	8.4	0.25	1.06	0.031	1.0
BCS18255	2.370	0.01	0.01	15.8	0.46	0.46	0.013	1.0
BCS18256	0.790	0.01	0.01	7.5	0.22	0.39	0.011	1.0
BCS18257	1.810	0.01	0.01	9.7	0.28	0.98	0.029	1.0
BCS18258	0.163	0.01	0.01	1.9	0.06	0.21	0.006	1.0
BCS18259	0.228	0.01	0.01	1.8	0.05	0.05	0.001	1.0
BCS18260	0.232	0.01	0.01	2.1	0.06	0.22	0.006	1.5
BCS18261	0.382	0.01	0.01	2.2	0.06	0.18	0.005	1.5
BCS18262	0.930	0.01	0.01	5.7	0.17	0.17	0.005	1.5
BCS18263	0.196	0.01	0.01	1.8	0.05	0.19	0.006	1.5
BCS18264	0.294	0.01	0.01	2.2	0.06	0.18	0.005	1.5
BCS18265	0.443	0.01	0.01	3.6	0.11	0.19	0.006	1.0
BCS18270	0.235	0.01	0.01	3.1	0.09	0.03	0.001	1.0
BCS18271	0.650	0.01	0.02	6.5	0.19	0.18	0.005	1.5
BCS18272	4.820	0.01	0.03	23.4	0.68	2.06	0.060	1.5
BCS18273	0.940	0.01	0.02	7.5	0.22	0.24	0.007	2.0
BCS18274	0.800	0.01	0.01	4.8	0.14	0.18	0.005	2.0
BCS18289	0.920	0.01	0.02	6.3	0.18	0.27	0.008	2.0
BCS18290	10.95	0.01	0.01	62.0	1.81	33.00	0.963	2.0
BCS18292	0.990	0.01	0.01	8.6	0.25	7.310	0.213	0.75
BCS18294	1.240	0.01	0.02	19.8	0.58	31.00	0.904	2.0
BCS18311	1.930	0.01	0.01	11.6	0.34	3.48	0.102	2.0
BCS18312	3.280	0.01	0.01	14.3	0.42	3.78	0.110	2.0
BCS18313	1.940	0.01	0.01	9.7	0.28	0.59	0.017	2.0
BCS18314	4.160	0.01	0.07	25.4	0.74	29.40	0.858	2.5
BCS18315	4.550	0.01	0.03	64.0	1.87	51.75	1.509	0
BCS18321	2.120	0.01	0.02	20.5	0.60	27.40	0.799	1.0
BCS18323	7.900	0.01	0.02	41.8	1.22	11.00	0.321	1.5
BCS18324	1.390	0.01	0.01	9.9	0.29	1.50	0.044	1.0

BCS18325	5.720	0.01	0.01	44.3	1.29	3.74	0.109	2.0
BCS18326	4.090	0.02	0.02	20.8	0.61	1.16	0.034	1.7
BCS18327	2.010	0.01	0.01	12.2	0.36	0.82	0.024	2.0
BCS18328	1.420	0.01	0.02	10.6	0.31	0.80	0.023	0.7
BCS18330	1.730	0.01	0.01	9.4	0.27	0.46	0.013	0.4
BCS18331	0.625	0.01	0.01	4.2	0.12	0.07	0.002	1.5
BCS18332	3.500	0.01	0.01	24.0	0.70	11.11	0.324	2.5
BCS18333	2.920	0.01	0.01	17.6	0.51	1.02	0.030	2.5
BCS18334	0.724	0.01	0.02	7.2	0.21	0.28	0.008	1.0
BCS18335	3.110	0.01	0.02	20.4	0.60	1.04	0.030	2.0
BCS18336	3.030	0.01	0.01	22.5	0.66	4.43	0.129	1.0
BCS18337	0.417	0.01	0.02	6.4	0.19	3.59	0.105	1.5
BCS18338	2.10	0.01	0.01	16.9	0.49	1.11	0.032	2.0
BCS18339	1.870	0.01	0.02	19.8	0.58	0.41	0.012	1.5
BCS18340	4.320	0.01	0.01	23.0	0.67	2.22	0.065	3.0
BCS18341	9.980	0.01	0.01	47.6	1.39	4.50	0.131	0.6
BCS18342	0.916	0.01	0.01	8.1	0.24	0.35	0.010	1.5
BCS17440	1.590	0.01	0.02	10.2	0.30	0.41	0.012	1.0
BCS17484	0.455	0.01	0.01	3.8	0.11	0.69	0.020	1.0
BCS17487	0.279	0.01	0.01	4.2	0.12	2.21	0.064	1.0
BCS17487	0.279	0.01	0.01	4.2	0.12	2.21	0.064	1.0


## VELVET ASSAYS

CORRELATION MATRIX: (99.0 INDICATES COEFFICIENT COULD NOT BE CALCULATED)

	CU_PER	PB_PER	ZN_PER	AG_GMPT	AU_GMPT	WIDTH
CU_PER	1.000	0.162	0.150	0.895	0.450	0.125
PB_PER	0.162	1.000	0.004	0.187	0.158	-0.352
ZN_PER	0.150	0.004	1.000	0.255	0.468	0.159
AG_GMPT	0.895	0.187	0.255	1.000	0.702	0.051
AU_GMPT	0.450	0.158	0.468	0.702	1.000	-0.057
WIDTH	0.125	-0.352	0.159	0.051	-0.057	1.000




VELVET ASSAYS




STATISTICS FOR VARIABLES:	CU_PER	AU_GMPT
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.03	0.02
MAXIMUM:	10.95	51.75
MEAN:	1.89	4.17
STANDARD ERROR OF MEAN:	0.26	1.05
STANDARD DEVIATION:	2.24	9.09
COEFFICIENT OF VARIATION:	118.48	217.94
SKEWNESS:	2.34	3.22
KURTOSIS:	5.62	10.85
CORRELATION COEFFICIENT:	0.4498	

VELVET ASSAYS




STATISTICS FOR VARIABLES:	CU_PER	AG_GMPT
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.03	0.80
MAXIMUM:	10.95	64.00
MEAN:	1.89	12.86
STANDARD ERROR OF MEAN:	0.26	1.50
STANDARD DEVIATION:	2.24	12.97
COEFFICIENT OF VARIATION:	118.48	100.86
SKEWNESS:	2.34	2.16
KURTOSIS:	5.62	4.83
CORRELATION COEFFICIENT:	0.8954	

VELVET ASSAYS




STATISTICS FOR VARIABLES:	AG_GMPT	AU_GMPT
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.80	0.02
MAXIMUM:	64.00	51.75
MEAN:	12.86	4.17
STANDARD ERROR OF MEAN:	1.50	1.05
STANDARD DEVIATION:	12.97	9.09
COEFFICIENT OF VARIATION:	100.86	217.94
SKEWNESS:	2.16	3.22
KURTOSIS:	4.83	10.85
CORRELATION COEFFICIENT:	0.7025	

VELVET ASSAYS




STATISTICS FOR VARIABLES:	WIDTH	CU_PER
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.00	0.03
MAXIMUM:	3.00	10.95
MEAN:	1.26	1.89
STANDARD ERROR OF MEAN:	0.07	0.26
STANDARD DEVIATION:	0.59	2.24
COEFFICIENT OF VARIATION:	46.76	118.48
SKEWNESS:	0.39	2.34
KURTOSIS:	0.41	5.62
CORRELATION COEFFICIENT:	0.1251	

VELVET ASSAYS



STATISTICS FOR VARIABLES:	WIDTH	AU_GMPT
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.00	0.02
MAXIMUM:	3.00	51.75
MEAN:	1.26	4.17
STANDARD ERROR OF MEAN:	0.07	1.05
STANDARD DEVIATION:	0.59	9.09
COEFFICIENT OF VARIATION:	46.76	217.94
SKEWNESS:	0.39	3.22
KURTOSIS:	0.41	10.85
CORRELATION COEFFICIENT:	-0.0571	


VELVET ASSAYS



STATISTICS FOR VARIABLES:	WIDTH	AG_GMPT
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.00	0.80
MAXIMUM:	3.00	64.00
MEAN:	1.26	12.86
STANDARD ERROR OF MEAN:	0.07	1.50
STANDARD DEVIATION:	0.59	12.97
COEFFICIENT OF VARIATION:	46.76	100.86
SKEWNESS:	0.39	2.16
KURTOSIS:	0.41	4.83
CORRELATION COEFFICIENT:	0.0513	




VELVET ASSAYS




STATISTICS FOR VARIABLES:	AU+AG	CU_PER
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.82	0.03
MAXIMUM:	115.75	10.95
MEAN:	17.03	1.89
STANDARD ERROR OF MEAN:	2.36	0.26
STANDARD DEVIATION:	20.41	2.24
COEFFICIENT OF VARIATION:	119.84	118.48
SKEWNESS:	2.61	2.34
KURTOSIS:	7.97	5.62
CORRELATION COEFFICIENT:	0.7694	

VELVET ASSAYS



STATISTICS FOR VARIABLES:	AG/AU	AU_GMPT
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.64	0.02
MAXIMUM:	180.00	51.75
MEAN:	18.52	4.17
STANDARD ERROR OF MEAN:	3.00	1.05
STANDARD DEVIATION:	26.01	9.09
COEFFICIENT OF VARIATION:	140.45	217.94
SKEWNESS:	3.88	3.22
KURTOSIS:	19.02	10.85
CORRELATION COEFFICIENT:	-0.2760	

VELVET ASSAYS



STATISTICS FOR VARIABLES:	AG/AU	CU_PER
NUMBER OF OBSERVATIONS:	75	75
MINIMUM:	0.64	0.03
MAXIMUM:	180.00	10.95
MEAN:	18.52	1.89
STANDARD ERROR OF MEAN:	3.00	0.26
STANDARD DEVIATION:	26.01	2.24
COEFFICIENT OF VARIATION:	140.45	118.48
SKEWNESS:	3.88	2.34
KURTOSIS:	19.02	5.62
CORRELATION COEFFICIENT:	-0.2462	