

13-Dec-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK96-1370

ED-1
830624
FORAN MINES
2500-#3 BENTALL CENTRE - PO BOX 49200
595 BARRARD STREET
VANCOUVER, B.C.
V7X 1L1

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: WAYNE TYNER/B. ZINKHOFFER


No. of Samples received: 13
Sample Type: CORE
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	1	5	<0.2	2.23	<5	90	5	1.73	<1	21	90	55	5.93	<10	2.28	707	4	<0.01	96	910	112	10	<20	143	<0.01	<10	39	<10	<1	101
2	2	5	0.4	0.78	<5	55	<5	3.86	1	23	67	83	6.30	<10	2.04	1393	6	0.01	81	620	158	5	<20	362	<0.01	<10	17	<10	1	155
3	3	5	<0.2	2.00	<5	85	5	1.44	<1	23	84	60	5.82	<10	1.97	678	5	<0.01	88	800	26	10	<20	113	<0.01	<10	34	<10	<1	118
4	4	5	<0.2	1.14	<5	75	<5	2.73	<1	25	73	78	4.97	<10	1.76	1328	5	<0.01	81	780	34	15	<20	221	<0.01	<10	21	<10	<1	82
5	5	5	<0.2	2.36	<5	80	<5	1.19	<1	25	91	44	5.79	<10	2.12	825	5	<0.01	90	820	14	5	<20	95	<0.01	<10	38	<10	<1	108
6	6	5	0.4	1.29	5	80	<5	2.42	<1	19	156	38	4.37	<10	1.66	1585	7	<0.01	66	480	44	10	<20	247	<0.01	<10	23	<10	<1	79
7	7	5	0.2	0.30	<5	45	5	4.29	<1	15	135	38	4.00	<10	1.76	1796	10	<0.01	37	380	110	15	<20	556	<0.01	<10	6	<10	2	64
8	8	5	0.4	0.78	<5	55	<5	2.63	2	23	129	59	5.43	<10	1.50	1189	7	0.02	83	790	98	5	<20	288	<0.01	<10	27	<10	<1	117
9	9	5	<0.2	0.51	300	90	<5	2.87	<1	11	85	20	3.13	<10	0.99	427	8	<0.01	23	450	8	15	<20	97	<0.01	<10	16	<10	5	50
10	10	5	<0.2	1.21	15	220	5	0.58	<1	14	119	18	3.17	<10	0.71	268	4	0.02	27	440	12	<5	<20	24	0.08	<10	19	<10	2	47
11	11	5	0.2	0.55	<5	55	5	4.53	<1	21	59	67	4.81	<10	2.04	1530	5	0.02	78	550	92	15	<20	503	<0.01	<10	12	<10	2	102
12	12	5	<0.2	0.92	<5	65	<5	4.60	1	26	72	56	5.30	<10	2.27	1791	5	0.02	105	650	26	20	<20	475	<0.01	<10	23	<10	<1	96
13	13	5	0.6	0.98	40	85	<5	1.56	<1	15	73	57	4.76	<10	1.15	311	9	<0.01	67	1550	62	<5	<20	104	<0.01	<10	23	<10	<1	204

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn	
QC/DATA:																															
Resplit:																															
R/S 1	1	5	<0.2	2.21	<5	95	<5	1.83	<1	22	88	54	6.19	<10	2.27	739	5	<0.01	100	970	96	<5	<20	143	<0.01	<10	39	<10	<1	102	
Repeat:																															
1	1	5	<0.2	2.27	<5	95	<5	1.80	<1	22	94	55	6.20	<10	2.31	732	5	<0.01	100	980	100	10	<20	143	<0.01	<10	39	<10	<1	111	
Standard:																															
GEO'96		145	1.0	1.69	60	150	<5	1.75	<1	19	59	76	3.97	<10	1.04	668	<1	0.02	24	640	24	<5	<20	54	0.11	<10	74	<10	6	67	

df/1370
XLS/96Foran

per 
 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer

23-Oct-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK96-1246

FORAN MINES
2500-#3 BENTALL CENTRE - PO BOX 49200
595 BURRARD STREET
VANCOUVER, B.C.
V7X 1L1

ATTENTION: WAYNE TYNER/B. ZINKHOFFER


Phone: 604-573-5700
Fax : 604-573-4557

No. of Samples received: 2
Sample Type: CORE
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: WAYNE TURNER

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	01 LINE 18	5	0.4	0.85	<5	50	<5	7.74	<1	14	46	45	5.66	<10	1.47	691	6	<0.01	45	500	44	<5	<20	356	<0.01	<10	16	<10	<1	146
2	02 LINE 18	5	0.4	0.71	<5	110	<5	6.23	<1	14	99	36	3.47	<10	1.48	734	7	0.01	29	700	6	<5	<20	296	<0.01	<10	13	<10	4	67
QC/DATA:																														
Repeat:																														
1	01 LINE 18	5	0.4	0.85	<5	50	<5	8.06	<1	14	48	43	5.93	<10	1.48	723	7	<0.01	46	530	50	<5	<20	341	<0.01	<10	16	<10	<1	158
Standard:																														
GEO'96		150	1.2	1.80	60	160	<5	1.75	<1	19	64	80	4.00	<10	1.01	671	<1	0.01	23	690	20	<5	<20	58	0.11	<10	73	<10	9	66

df/1246
XLS/96Foran


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

10/23/96 (WED) 14:56 [TX/RX NO 5798]

10/23/96 14:58 0004 010 4997

BU-1504 AMM.

10/23/96



ASSAY CERTIFICATE



Foran Mining Corporation File # 96-4470

P.O. Box 49200, 2500 - 59, Vancouver

SAMPLE#	Mo %	Cu %	Pb %	Zn %	Ag** oz/t	Ni %	Co %	Mn %	Fe %	As %	U %	Th %	Cd %	Sb %	Bi %	Au** oz/t
406	<.001	.002	<.01	<.01	<.01	.002	.001	.02	2.50	<.01	<.01	<.01	<.001	<.001	<.01	.001
409	<.001	.002	<.01	<.01	.01	.004	.001	.03	2.38	<.01	<.01	<.01	<.001	<.001	<.01	.001
415	<.001	.003	<.01	<.01	.01	.002	<.001	.03	2.11	<.01	<.01	<.01	<.001	<.001	<.01	<.001
420	.001	.002	<.01	.01	.01	.004	.001	.04	2.53	<.01	<.01	<.01	<.001	<.001	<.01	<.001
428	<.001	.002	<.01	.01	.02	.005	.001	.04	2.65	<.01	<.01	<.01	<.001	<.001	<.01	.001
RE 428	<.001	.002	<.01	.01	.01	.004	.001	.03	2.65	<.01	<.01	<.01	<.001	<.001	<.01	<.001

1 GM SAMPLE LEACHED IN 50 ML AQUA - REGIA, DILUTE TO 100 ML, ANALYSIS BY ICP.

AG** & AU** BY FIRE ASSAY FROM 1.A.T. SAMPLE.

- SAMPLE TYPE: CORE

Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 16 1996

DATE REPORT MAILED:

Sept 18/96

SIGNED BY.....D.TOYE, C.LEONG, J.WANG; CERTIFIED B.C. ASSAYERS

AA
LL

ASSAY CERTIFICATE

AA
LL

Foran Mining Corporation File # 96-4470

P.O. Box 49200, 2500 - 59, Vancouver

SAMPLE#	Mo %	Cu %	Pb %	Zn %	Ag** oz/t	Ni %	Co %	Mn %	Fe %	As %	U %	Th %	Cd %	Sb %	Bi %	Au** oz/t
406	<.001	.002	<.01	<.01	<.01	.002	.001	.02	2.50	<.01	<.01	<.01	<.001	<.001	<.01	.001
409	<.001	.002	<.01	<.01	.01	.004	.001	.03	2.38	<.01	<.01	<.01	<.001	<.001	<.01	.001
415	<.001	.003	<.01	<.01	.01	.002	<.001	.03	2.11	<.01	<.01	<.01	<.001	<.001	<.01	<.001
420	.001	.002	<.01	.01	.01	.004	.001	.04	2.53	<.01	<.01	<.01	<.001	<.001	<.01	<.001
428	<.001	.002	<.01	.01	.02	.005	.001	.04	2.65	<.01	<.01	<.01	<.001	<.001	<.01	.001
RE 428	<.001	.002	<.01	.01	.01	.004	.001	.03	2.65	<.01	<.01	<.01	<.001	<.001	<.01	<.001

1 GM SAMPLE LEACHED IN 50 ML AQUA - REGIA, DILUTE TO 100 ML, ANALYSIS BY ICP.

AG** & AU** BY FIRE ASSAY FROM 1.A.T. SAMPLE.

- SAMPLE TYPE: CORE

Samples beginning 'RE' are Reruns and 'RRE' are Reject Reruns.

DATE RECEIVED: SEP 16 1996

DATE REPORT MAILED: Sept 18/96

SIGNED BY: *C. Leong* D. TOYE, C. LEONG, J. WANG; CERTIFIED B.C. ASSAYERS

12-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK96-796

FORAN MINES
2500-#3 BENTALL CENTRE - PO BOX 49200
595 BURREARD STREET
VANCOUVER, B.C.
V7X 1L1

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: WAYNE TYNER/B. ZINKHOFFER

No. of Samples received: 135
Sample Type: SOIL
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	BL9N 175 W	<5	<0.2	2.40	<5	210	<5	0.08	<1	5	14	15	2.67	<10	0.13	518	2	<0.01	7	1120	8	<5	20	7	0.06	<10	39	<10	<1	29
2	BL9N 150 W	<5	<0.2	1.83	<5	70	<5	0.06	<1	6	7	6	1.75	<10	0.08	1166	1	<0.01	4	890	4	<5	<20	4	0.06	<10	37	<10	<1	28
3	BL9N 125 W	<5	<0.2	2.36	<5	100	<5	0.05	<1	4	11	13	2.34	<10	0.17	264	<1	<0.01	4	1050	6	<5	<20	7	0.08	<10	34	<10	1	25
4	BL9N 100 W	<5	<0.2	2.46	<5	55	<5	0.07	<1	8	10	14	2.12	<10	0.17	1238	2	0.01	5	1070	2	<5	<20	4	0.05	<10	42	<10	2	34
5	BL9N 75 W	5	<0.2	3.53	10	60	<5	0.04	<1	5	9	14	1.94	<10	0.05	223	<1	<0.01	6	830	4	<5	<20	3	0.10	<10	28	<10	4	14
6	BL9N 50 W	<5	<0.2	1.60	10	115	<5	0.10	<1	5	21	28	2.04	<10	0.18	132	2	0.01	12	1050	6	<5	<20	11	0.05	<10	44	<10	<1	23
7	BL9N 25 W	<5	0.6	1.85	10	280	<5	0.10	<1	7	37	26	3.81	<10	0.47	617	7	0.02	15	1390	16	<5	<20	24	0.05	<10	71	<10	<1	58
8	BL9N 0	5	0.6	1.95	5	285	<5	0.04	<1	7	26	23	4.09	<10	0.35	448	9	<0.01	15	1120	10	<5	<20	22	0.03	<10	69	<10	<1	95
9	BL9N 550 E	<5	<0.2	0.44	<5	25	<5	0.02	<1	2	6	5	0.89	<10	0.03	41	1	<0.01	3	490	8	<5	<20	4	0.03	<10	27	<10	1	12
10	BL9N 575 E	<5	<0.2	1.79	<5	25	<5	0.02	<1	2	7	6	1.57	<10	0.04	55	4	<0.01	1	540	6	<5	<20	2	0.07	<10	27	<10	2	7
11	BL9N 600 E	<5	<0.2	0.87	<5	20	<5	0.02	<1	3	7	4	1.43	<10	0.03	77	5	<0.01	3	220	6	<5	<20	2	0.08	<10	39	<10	1	11
12	BL9N 625 E	<5	<0.2	0.75	<5	20	<5	0.02	<1	3	8	5	1.56	<10	0.04	80	6	<0.01	4	250	8	<5	20	2	0.09	10	44	<10	1	13
13	BL9N 650 E	<5	<0.2	0.59	<5	25	<5	0.03	<1	2	5	2	0.93	<10	0.07	61	2	<0.01	3	620	4	<5	<20	3	0.04	10	23	<10	1	12
14	BL9N 700 E	<5	<0.2	2.47	<5	20	<5	0.02	<1	2	5	7	1.28	<10	0.01	12	<1	<0.01	2	450	8	<5	<20	1	0.09	<10	21	<10	2	4
15	BL9N 725 E	<5	<0.2	1.13	<5	20	<5	0.02	<1	2	6	6	1.42	<10	0.05	35	3	<0.01	3	830	12	<5	<20	3	0.06	<10	24	<10	1	11
16	BL9N 750 E	5	<0.2	0.80	<5	45	<5	0.04	<1	2	6	6	1.25	<10	0.05	851	5	<0.01	3	710	4	<5	<20	2	0.02	<10	26	<10	1	18
17	BL10N 200 W	<5	0.4	2.75	15	165	<5	0.13	<1	8	21	37	2.38	<10	0.37	264	2	<0.01	14	1550	8	<5	<20	17	0.05	<10	45	<10	2	39
18	BL10N 175 W	<5	<0.2	4.19	10	115	<5	0.09	<1	9	24	33	2.51	<10	0.30	533	<1	<0.01	11	1150	6	<5	<20	9	0.09	<10	49	<10	3	32
19	BL10N 150 W	<5	<0.2	2.24	<5	65	<5	0.07	<1	5	11	25	1.89	<10	0.13	176	1	<0.01	5	1040	2	<5	<20	6	0.05	<10	40	<10	2	22
20	BL10N 125 W	<5	<0.2	2.53	<5	80	<5	0.07	<1	5	21	20	2.45	<10	0.22	182	2	<0.01	10	1100	6	<5	<20	7	0.05	<10	42	<10	1	30

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
21	BL10N 100 W	5	<0.2	2.05	<5	115	<5	0.06	<1	4	19	12	2.01	<10	0.21	372	2	<0.01	7	870	6	<5	<20	6	0.06	<10	42	<10	1	27
22	BL10N 75 W	<5	<0.2	1.61	<5	75	<5	0.05	<1	3	16	10	1.51	<10	0.12	60	1	<0.01	6	1050	6	<5	<20	7	0.05	<10	36	<10	<1	14
23	BL10N 50 W	<5	<0.2	1.85	10	500	<5	0.11	<1	5	48	36	2.99	<10	0.52	236	<1	<0.01	12	890	6	<5	<20	44	0.14	<10	75	<10	<1	27
24	BL10N 25 W	<5	<0.2	2.47	15	480	<5	0.11	<1	14	71	48	4.00	<10	0.77	1025	3	0.01	18	960	4	<5	<20	51	0.12	<10	89	<10	<1	48
25	BL10N 0	<5	0.2	2.34	10	230	<5	0.08	<1	7	41	24	2.81	<10	0.24	351	4	<0.01	16	1190	4	<5	<20	6	0.05	<10	56	<10	1	63
26	BL10N 550 E	5	<0.2	0.89	<5	25	<5	0.02	<1	3	7	5	1.65	<10	0.08	308	4	<0.01	3	550	6	<5	<20	2	0.04	<10	32	<10	1	15
27	BL10N 575 E	<5	<0.2	0.92	<5	20	<5	0.03	<1	4	7	5	1.75	<10	0.08	168	8	<0.01	4	460	4	<5	<20	2	0.07	<10	44	<10	<1	21
28	BL10N 600 E	5	<0.2	0.25	<5	20	<5	0.02	<1	<1	2	3	0.39	<10	0.02	26	2	<0.01	1	310	6	<5	<20	2	0.02	<10	12	<10	<1	5
29	BL10N 625 E	<5	<0.2	1.50	<5	25	<5	0.02	<1	2	5	5	1.42	<10	0.02	59	3	<0.01	2	520	8	<5	<20	2	0.07	10	20	20	1	6
30	BL10N 650 E	5	<0.2	0.31	<5	15	<5	0.01	<1	1	3	2	0.57	<10	0.02	40	3	<0.01	1	280	4	<5	<20	2	0.02	10	13	<10	<1	6
31	BL10N 675 E	<5	0.2	0.79	<5	25	<5	0.02	<1	1	4	3	0.89	<10	0.02	34	3	<0.01	1	420	6	<5	<20	2	0.04	10	15	<10	<1	6
32	BL10N 700 E	<5	<0.2	1.52	<5	20	<5	0.01	<1	2	4	4	1.15	<10	0.01	58	3	<0.01	1	450	8	<5	<20	2	0.05	<10	19	<10	1	7
33	BL10N 725 E	<5	<0.2	2.74	5	20	<5	0.03	<1	3	7	8	1.46	20	0.06	43	2	<0.01	2	950	10	<5	<20	3	0.09	<10	23	<10	12	8
34	BL10N 750 E	<5	0.2	2.24	15	15	<5	0.05	<1	5	14	13	2.26	60	0.16	93	22	0.01	6	620	10	<5	<20	4	0.11	70	33	<10	38	27
35	BL11N 225 W	<5	0.2	2.00	<5	155	<5	0.07	<1	6	16	15	2.26	<10	0.17	691	2	<0.01	7	1090	6	<5	<20	6	0.05	<10	39	<10	1	28
36	BL11N 200 W	<5	<0.2	1.95	<5	140	<5	0.06	<1	4	21	11	1.77	<10	0.20	359	<1	<0.01	7	1020	8	<5	<20	5	0.05	<10	39	<10	1	29
37	BL11N 175 W	<5	0.4	1.37	<5	140	<5	0.04	<1	3	14	10	1.67	<10	0.08	444	3	<0.01	8	1550	10	<5	<20	5	0.01	<10	38	<10	<1	22
38	BL11N 150 W	<5	<0.2	1.90	<5	185	<5	0.03	<1	7	19	17	2.82	<10	0.31	419	2	<0.01	9	1150	10	<5	<20	8	0.07	<10	67	<10	<1	53
39	BL11N 125 W	<5	<0.2	0.66	<5	35	<5	0.02	<1	2	6	4	0.89	<10	0.02	47	<1	<0.01	3	410	4	<5	<20	3	0.04	<10	26	<10	<1	9
40	BL11N 100 W	<5	<0.2	1.03	<5	55	<5	0.06	<1	4	8	8	1.51	<10	0.07	65	<1	<0.01	4	730	10	<5	<20	5	0.10	10	28	<10	<1	15
41	BL11N 75 W	<5	0.2	1.47	<5	55	<5	0.07	<1	6	11	12	2.35	<10	0.16	264	2	<0.01	7	1090	6	<5	<20	6	0.05	<10	45	<10	2	25
42	BL11N 50B W	5	<0.2	2.44	<5	60	<5	0.06	<1	4	15	20	1.99	<10	0.16	207	1	<0.01	6	1070	2	<5	<20	5	0.06	<10	32	<10	2	21
43	BL11N 50A W	<5	0.2	2.87	5	135	<5	0.15	<1	8	19	37	2.24	<10	0.21	694	3	<0.01	9	1530	4	<5	<20	13	0.04	<10	40	<10	2	31
44	BL11N 25 E	<5	0.4	1.48	5	255	<5	0.04	<1	4	16	14	3.01	<10	0.19	421	9	<0.01	8	1050	8	<5	<20	5	0.04	<10	76	<10	<1	40
45	BL11N 50 E	<5	<0.2	2.51	15	445	<5	0.06	<1	5	47	37	4.66	<10	0.61	165	9	<0.01	17	1270	16	<5	<20	14	0.06	<10	107	<10	<1	64
46	BL11N 75 E	<5	<0.2	4.14	30	185	<5	0.11	<1	22	42	41	4.73	<10	0.72	424	<1	<0.01	42	770	6	<5	<20	18	0.17	<10	55	<10	2	83
47	BL11N 250 E	10	<0.2	1.89	40	140	<5	0.12	<1	10	39	23	4.35	<10	0.37	1074	7	<0.01	15	1060	10	<5	<20	11	0.06	<10	66	<10	<1	99
48	BL11N 275 E	<5	<0.2	1.97	25	80	10	0.07	<1	8	27	18	3.84	<10	0.21	1337	9	<0.01	9	860	10	<5	<20	7	0.07	<10	74	<10	<1	66
49	BL11N 300 E	<5	<0.2	1.77	95	105	<5	0.04	<1	4	33	25	3.43	20	0.34	259	12	<0.01	7	1030	12	<5	<20	14	0.06	<10	72	<10	2	47
50	BL11N 325 E	5	<0.2	1.98	50	110	<5	0.06	<1	6	55	25	4.35	<10	0.48	439	8	<0.01	10	810	10	<5	<20	8	0.11	<10	99	<10	<1	57
51	BL11N 350 E	<5	<0.2	1.92	45	115	5	0.06	<1	7	56	25	4.45	<10	0.48	449	8	<0.01	9	850	12	<5	<20	9	0.11	<10	101	<10	<1	61
52	BL11N 375 E	<5	<0.2	1.38	15	40	<5	0.03	<1	4	24	8	2.61	<10	0.15	94	3	<0.01	4	420	10	<5	<20	3	0.11	<10	81	<10	1	20
53	BL11N 400 E	5	0.6	2.37	15	50	<5	0.03	<1	5	22	18	2.20	<10	0.15	396	9	<0.01	7	1190	6	<5	<20	5	0.05	<10	40	<10	3	24
54	BL11N 425 E	<5	0.2	1.72	<5	45	<5	0.03	<1	3	12	9	1.93	<10	0.09	158	13	<0.01	4	970	6	<5	<20	4	0.06	<10	32	<10	2	19
55	BL11N 450 E	5	0.2	1.93	<5	20	<5	0.08	<1	3	5	6	1.61	30	0.03	36	10	<0.01	4	1260	4	<5	<20	3	0.04	20	22	<10	15	10

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
56	BL11N 475 E	<5	<0.2	1.49	<5	25	<5	0.02	<1	3	6	5	1.70	<10	0.04	59	4	<0.01	3	600	12	<5	<20	3	0.08	<10	31	<10	2	11
57	BL11N 500 E	<5	<0.2	0.71	<5	35	<5	0.03	<1	4	10	7	1.83	<10	0.10	344	2	<0.01	4	730	6	<5	<20	5	0.04	<10	42	<10	3	20
58	BL11N 525 E	<5	<0.2	1.84	<5	25	<5	0.03	<1	4	7	10	1.56	40	0.04	179	7	<0.01	2	640	8	<5	<20	2	0.08	30	23	<10	14	13
59	BL11N 550 E	<5	<0.2	1.15	<5	25	<5	0.03	<1	3	6	5	1.69	<10	0.04	313	5	<0.01	3	520	8	<5	<20	3	0.07	<10	31	<10	1	13
60	BL11N 575 E	<5	<0.2	0.80	<5	20	<5	0.02	<1	2	5	3	0.94	<10	0.04	116	4	<0.01	2	400	8	<5	<20	1	0.05	<10	19	<10	1	8
61	BL11N 600 E	5	<0.2	1.09	<5	<5	<5	0.08	<1	3	4	5	1.33	30	0.09	51	2	0.01	2	630	2	<5	<20	3	0.06	10	24	<10	10	11
62	BL11N 625 E	<5	<0.2	0.68	<5	30	<5	0.03	<1	2	6	4	1.21	<10	0.06	319	7	<0.01	3	580	6	<5	<20	3	0.04	<10	25	<10	1	17
63	BL11N 650 E	<5	<0.2	1.25	<5	35	<5	0.03	<1	4	6	6	1.69	<10	0.04	132	5	<0.01	3	560	6	<5	<20	4	0.07	<10	35	<10	<1	14
64	BL11N 675 E	<5	<0.2	1.78	<5	25	<5	0.03	<1	3	6	8	1.77	<10	0.03	72	4	<0.01	2	550	6	<5	<20	3	0.07	<10	31	<10	2	10
65	BL11N 700 E	5	<0.2	0.76	<5	20	<5	0.02	<1	3	5	4	1.41	<10	0.03	368	7	<0.01	2	480	8	<5	<20	2	0.07	<10	24	<10	1	11
66	BL12N 150 W	<5	<0.2	3.85	5	35	<5	0.05	<1	4	6	10	1.53	<10	0.05	175	<1	0.01	2	1010	6	<5	<20	5	0.12	<10	21	<10	6	8
67	BL12N 100 W	5	<0.2	1.75	5	55	<5	0.06	<1	3	10	6	1.31	<10	0.10	91	<1	0.01	4	930	6	<5	<20	5	0.05	<10	27	<10	2	15
68	BL12N 75 W	<5	<0.2	2.81	20	165	<5	0.15	<1	12	46	23	2.59	<10	0.53	361	<1	0.01	20	1470	6	<5	<20	12	0.10	<10	61	<10	5	41
69	BL12N 50 W	<5	0.2	2.64	5	105	<5	0.07	<1	12	12	14	2.11	<10	0.14	1343	3	<0.01	6	1290	12	<5	<20	6	0.05	<10	33	<10	3	35
70	BL12N 0	5	<0.2	2.48	30	275	5	0.14	<1	7	67	23	3.97	<10	0.59	211	<1	0.01	11	960	4	<5	<20	9	0.19	<10	88	<10	2	28
71	BL12N 25 E	<5	<0.2	3.09	5	35	<5	0.09	<1	4	11	10	2.03	<10	0.12	77	<1	0.01	4	1020	6	<5	<20	5	0.09	10	33	<10	4	18
72	BL12N 50 E	<5	<0.2	2.98	20	95	<5	0.17	<1	14	50	21	2.88	<10	0.36	1413	2	0.01	17	1640	4	<5	<20	13	0.06	<10	50	<10	4	49
73	BL12N 75 E	<5	<0.2	2.18	10	110	<5	0.10	<1	8	34	18	3.40	<10	0.32	409	2	0.01	15	990	6	<5	<20	8	0.11	<10	58	<10	1	53
74	BL12N 100 E	<5	<0.2	4.85	20	290	<5	0.24	<1	15	56	62	3.51	<10	0.78	141	<1	0.03	40	1130	4	<5	<20	24	0.12	10	64	<10	4	51
75	BL12N 125 E	<5	<0.2	2.65	<5	135	5	0.21	<1	18	40	28	4.20	<10	0.55	811	4	0.01	23	1330	6	<5	<20	23	0.08	<10	75	<10	1	96
76	BL12N 150 E	5	<0.2	3.39	15	165	<5	0.10	<1	14	45	35	4.65	<10	0.60	665	3	0.01	24	1060	8	<5	<20	15	0.10	<10	76	<10	2	83
77	BL12N 175 E	<5	<0.2	2.39	20	60	<5	0.22	<1	13	27	24	3.44	<10	0.36	1268	4	0.01	13	1290	4	<5	<20	15	0.08	<10	64	<10	5	99
78	BL12N 200 E	<5	<0.2	1.45	<5	25	<5	0.04	<1	3	7	9	1.56	<10	0.12	115	3	<0.01	3	450	6	<5	<20	7	0.06	10	28	<10	5	18
79	BL12N 225 E	5	<0.2	3.14	5	40	<5	0.09	<1	4	11	10	2.10	<10	0.12	79	<1	0.01	4	1010	6	<5	<20	6	0.09	10	34	<10	3	20
80	BL12N 250 E	<5	<0.2	2.42	65	105	<5	0.03	<1	5	44	29	4.53	20	0.49	176	17	<0.01	7	720	16	<5	<20	13	0.07	<10	116	<10	5	66
81	BL12N 275 E	<5	<0.2	2.70	160	155	<5	0.03	<1	6	57	32	4.66	20	0.59	342	14	<0.01	8	750	8	<5	<20	15	0.08	<10	104	<10	1	62
82	BL12N 300 E	<5	<0.2	1.95	70	150	<5	0.03	<1	6	44	44	4.19	10	0.45	182	12	<0.01	10	730	18	<5	<20	9	0.10	10	77	<10	5	49
83	BL12N 325 E	5	0.2	2.83	<5	105	<5	0.03	<1	6	56	25	4.23	<10	0.62	345	4	<0.01	9	940	6	<5	<20	7	0.10	<10	96	<10	1	48
84	BL12N 350 E	<5	0.2	2.51	10	110	<5	0.04	<1	7	64	25	4.58	<10	0.58	495	7	<0.01	10	710	6	<5	<20	19	0.11	<10	112	<10	<1	58
85	BL12N 375 E	<5	<0.2	1.71	70	60	5	0.03	<1	5	39	36	5.22	<10	0.34	109	22	<0.01	7	620	8	<5	20	6	0.07	20	71	<10	3	34
86	BL12N 400 E	<5	<0.2	1.69	35	110	5	0.02	<1	4	43	28	3.69	20	0.34	122	23	<0.01	8	650	14	<5	<20	15	0.07	<10	69	<10	7	41
87	BL12N 425 E	<5	<0.2	3.48	26	220	5	0.03	<1	7	88	42	7.32	10	0.84	235	52	<0.01	10	1090	8	<5	<20	27	0.13	<10	134	<10	<1	63
88	BL12N 450 E	<5	<0.2	2.19	325	110	<5	0.04	<1	7	42	38	4.25	30	0.47	231	14	<0.01	16	570	16	<5	<20	8	0.07	<10	82	<10	15	67
89	BL12N 475 E	<5	0.2	1.63	5	30	<5	0.01	<1	3	6	7	1.80	20	0.12	473	9	<0.01	3	500	12	<5	<20	3	0.02	<10	18	<10	6	17
90	BL12N 500 E	<5	<0.2	1.44	<5	30	<5	0.02	<1	3	6	8	1.82	20	0.12	357	8	<0.01	3	550	8	<5	<20	3	0.05	<10	23	<10	5	18

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
91	BL12N 525 E	5	<0.2	0.83	<5	20	<5	0.02	<1	3	4	6	1.56	10	0.08	436	13	<0.01	3	570	8	<5	<20	5	0.02	<10	19	<10	4	15
92	BL12N 550 E	<5	<0.2	1.18	<5	25	<5	0.03	<1	4	9	9	1.80	<10	0.07	289	7	<0.01	4	460	6	<5	<20	3	0.07	<10	39	<10	2	18
93	BL12N 575 E	<5	<0.2	1.05	<5	20	<5	0.02	<1	3	4	6	1.26	<10	0.06	308	4	<0.01	2	350	6	<5	<20	2	0.03	<10	19	<10	2	11
94	BL12N 600 E	5	<0.2	0.88	<5	25	<5	0.02	<1	2	5	6	1.59	<10	0.05	184	8	<0.01	2	400	6	<5	<20	4	0.04	<10	18	<10	3	11
95	BL12N 625 E	<5	<0.2	0.78	<5	5	<5	0.04	<1	4	5	2	1.30	<10	0.05	72	<1	<0.01	3	310	4	<5	<20	4	0.08	<10	41	<10	5	12
96	BL12N 650 E	5	<0.2	0.92	<5	25	<5	0.02	<1	2	3	4	1.27	<10	0.07	306	14	<0.01	<1	350	6	<5	<20	5	0.04	<10	15	10	2	10
97	BL12N 675 E	<5	<0.2	2.82	30	110	5	0.04	<1	6	71	28	5.08	10	0.61	343	17	<0.01	7	770	10	<5	<20	10	0.14	<10	118	<10	2	38
98	BL12N 700 E	<5	<0.2	3.76	15	45	<5	0.05	<1	7	13	12	1.95	<10	0.09	425	<1	0.01	4	1140	8	<5	<20	5	0.10	<10	31	<10	6	12
99	BL13N 250 W	5	<0.2	2.23	<5	175	<5	0.08	<1	9	31	15	2.97	<10	0.51	1119	2	<0.01	12	1650	6	<5	<20	6	0.08	<10	69	<10	1	55
100	BL13N 225 W	<5	0.2	1.18	<5	110	<5	0.07	<1	10	13	10	1.88	<10	0.17	1617	2	<0.01	5	990	6	<5	<20	6	0.07	<10	48	<10	2	29
101	BL13N 200 W	<5	<0.2	2.02	<5	425	<5	0.04	<1	2	30	23	1.88	<10	0.53	291	<1	<0.01	11	800	4	<5	<20	5	0.06	<10	47	<10	2	23
102	BL13N 175 W	<5	<0.2	1.32	<5	70	<5	0.04	<1	8	7	6	1.55	<10	0.07	445	1	<0.01	4	950	4	<5	<20	4	0.06	<10	38	<10	3	16
103	BL13N 150 W	5	<0.2	1.75	<5	65	<5	0.06	<1	5	9	11	1.77	<10	0.09	302	<1	<0.01	4	910	4	<5	<20	5	0.05	<10	36	<10	2	14
104	BL13N 125 W	<5	0.6	2.98	5	90	<5	0.08	<1	4	13	21	1.38	<10	0.16	101	1	<0.01	6	1510	4	<5	<20	6	0.05	<10	28	<10	5	19
105	BL13N 100 W	<5	<0.2	0.03	<5	<5	<5	<0.01	<1	<1	<1	<1	0.02	<10	<0.01	1	<1	<0.01	<1	10	<2	<5	<20	<1	<0.01	<10	<1	<10	<1	<1
106	BL13N 75 W	<5	<0.2	2.67	10	130	<5	0.08	<1	7	30	26	2.64	<10	0.36	483	<1	0.01	13	840	8	<5	<20	5	0.08	<10	68	<10	3	48
107	BL13N 50 W	5	<0.2	2.39	10	270	<5	0.07	<1	7	47	32	2.87	<10	0.58	493	<1	0.01	20	500	8	<5	<20	4	0.11	<10	84	<10	2	56
108	BL13N 25 W	<5	<0.2	2.84	20	295	5	0.09	<1	8	49	29	3.25	<10	0.58	308	<1	0.02	19	660	6	<5	<20	4	0.12	<10	94	<10	4	45
109	BL13N 0	<5	<0.2	0.39	<5	50	<5	0.09	<1	5	12	5	1.46	<10	0.13	193	<1	0.02	6	750	2	<5	<20	5	0.06	<10	47	<10	2	27
110	BL13N 25 E	10	<0.2	3.21	15	445	<5	0.12	<1	14	52	47	3.22	<10	0.65	771	<1	0.02	21	770	6	<5	<20	9	0.12	<10	86	<10	4	53
111	BL13N 50A E	<5	<0.2	1.73	55	110	5	0.03	<1	12	44	38	6.09	<10	0.38	424	11	<0.01	24	780	10	<5	<20	<1	0.06	<10	69	<10	2	99
112	BL13N 50B E	<5	<0.2	3.90	20	125	5	0.09	<1	10	20	23	3.04	<10	0.28	694	2	0.02	9	960	6	<5	<20	4	0.13	<10	58	<10	4	29
113	BL13N 75 E	<5	<0.2	2.03	10	90	<5	0.05	<1	4	20	12	1.99	<10	0.20	109	1	0.02	6	910	6	<5	<20	3	0.07	<10	40	<10	2	22
114	BL13N 100 E	<5	<0.2	2.39	5	40	<5	0.04	<1	4	14	10	2.01	<10	0.11	87	<1	0.01	5	920	6	<5	<20	3	0.10	<10	38	<10	2	19
115	BL13N 125 E	<5	<0.2	4.16	30	190	<5	0.09	<1	13	59	44	5.88	<10	0.60	338	8	0.01	31	1710	6	<5	<20	14	0.09	<10	61	<10	2	67
116	BL13N 175 E	5	<0.2	1.86	10	75	<5	0.08	<1	6	15	12	1.98	<10	0.13	744	6	0.01	7	1020	4	<5	<20	5	0.06	<10	42	<10	<1	28
117	BL13N 200 E	<5	<0.2	3.85	15	40	5	0.25	<1	10	25	16	2.00	20	0.48	199	<1	0.04	13	990	6	<5	<20	13	0.12	<10	42	<10	18	30
118	BL13N 225 E	<5	<0.2	3.37	15	145	5	0.13	<1	10	46	37	4.04	<10	0.53	412	2	0.02	21	980	6	<5	<20	10	0.11	<10	72	<10	3	60
119	BL13N 250 E	5	<0.2	2.96	5	125	10	0.23	<1	11	39	16	3.99	<10	0.47	565	3	0.02	24	1060	10	<5	<20	23	0.09	<10	70	<10	2	116
120	BL13N 275 E	<5	<0.2	3.01	5	140	5	0.13	1	14	35	22	4.20	<10	0.49	829	3	0.01	25	1140	10	<5	<20	16	0.08	<10	71	<10	2	99
121	BL13N 300 E	<5	<0.2	2.52	<5	110	5	0.16	2	23	30	25	4.41	10	0.34	2265	6	0.02	23	1560	22	<5	<20	27	0.05	<10	70	<10	6	278
122	BL13N 325 E	5	<0.2	1.30	70	65	<5	0.04	<1	7	28	27	4.70	20	0.23	252	14	0.01	18	640	12	<5	<20	3	0.04	<10	49	<10	6	97
123	BL13N 400 E	<5	<0.2	2.51	110	100	<5	0.03	<1	6	43	36	5.70	<10	0.44	276	19	0.01	8	1050	12	<5	<20	8	0.07	<10	133	<10	<1	70
124	BL13N 425 E	<5	<0.2	2.88	80	100	<5	0.05	<1	8	47	31	4.31	10	0.42	379	6	0.01	11	770	6	<5	<20	9	0.11	<10	81	<10	5	53
125	BL13N 450 E	<5	<0.2	2.34	80	150	5	0.06	<1	13	37	33	4.79	<10	0.43	2472	7	0.01	10	940	12	<5	<20	7	0.13	<10	91	<10	6	57

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
126	BL13N 475 E	<5	<0.2	2.46	65	125	5	0.07	<1	11	57	52	5.35	30	0.64	390	13	0.01	20	740	14	<5	<20	15	0.11	<10	90	<10	10	68
127	BL13N 500 E	<5	<0.2	2.19	75	90	5	0.04	<1	6	78	27	5.81	<10	0.64	594	9	0.01	6	850	6	<5	<20	6	0.10	<10	135	<10	<1	55
128	BL13N 525 E	5	<0.2	1.25	55	65	<5	0.01	<1	3	16	21	2.51	10	0.19	168	19	0.01	4	580	12	<5	<20	8	0.04	<10	33	<10	2	33
129	BL13N 550 E	<5	<0.2	2.54	55	120	10	0.02	<1	6	56	43	5.55	10	0.45	193	20	0.01	7	940	10	<5	<20	7	0.10	<10	94	<10	<1	46
130	BL13N 575 E	<5	<0.2	1.78	20	60	10	0.02	<1	4	18	24	2.95	20	0.21	213	33	0.01	4	800	10	<5	<20	5	0.05	<10	44	<10	4	40
131	BL13N 600 E	<5	<0.2	1.82	15	35	5	0.02	<1	3	9	14	2.32	<10	0.13	195	13	0.01	3	490	8	<5	<20	2	0.05	<10	35	<10	4	23
132	BL13N 625 E	<5	<0.2	1.34	10	30	<5	0.06	<1	3	6	10	2.03	30	0.15	282	13	0.01	5	490	8	<5	<20	9	0.03	<10	19	<10	10	34
133	BL13N 650 E	<5	<0.2	1.36	15	30	<5	0.06	<1	3	7	10	2.37	30	0.23	213	11	0.01	4	580	10	<5	<20	6	0.05	<10	24	<10	9	36
134	BL13N 675 E	<5	<0.2	1.32	15	40	<5	0.06	<1	3	8	8	2.22	10	0.10	164	9	0.01	3	440	6	<5	<20	8	0.03	<10	32	<10	4	27
135	BL13N 700 E	<5	<0.2	2.65	5	35	<5	0.04	<1	4	8	10	2.02	<10	0.03	227	3	0.02	3	560	6	<5	<20	2	0.09	<10	30	<10	3	18

QC DATA:**Repeat:**

1	BL9N 175 W	<5	<0.2	2.39	<5	210	<5	0.08	<1	5	14	15	2.67	<10	0.13	515	2	<0.01	6	1100	10	<5	<20	7	0.06	<10	39	<10	<1	29
10	BL9N 575 E	<5	<0.2	1.77	5	25	<5	0.02	<1	2	8	7	1.55	<10	0.04	55	5	<0.01	2	520	6	<5	<20	3	0.07	<10	26	<10	2	7
19	BL10N 150 W	<5	<0.2	2.23	<5	70	<5	0.07	<1	5	10	25	1.88	<10	0.13	178	1	<0.01	5	1020	4	<5	<20	6	0.06	<10	40	<10	2	21
28	BL10N 600 E	5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
36	BL11N 200 W	<5	<0.2	1.97	<5	135	<5	0.06	<1	4	20	11	1.75	<10	0.20	354	<1	<0.01	6	1040	4	<5	<20	5	0.05	<10	39	<10	1	28
45	BL11N 50 E	<5	<0.2	2.52	30	440	<5	0.06	<1	5	48	38	4.64	<10	0.63	163	9	<0.01	17	1330	16	<5	<20	14	0.05	<10	106	<10	<1	63
54	BL11N 425 E	<5	0.4	1.69	<5	40	<5	0.03	<1	3	11	8	1.89	<10	0.09	157	13	<0.01	4	940	6	<5	<20	3	0.06	<10	31	<10	1	19
63	BL11N 650 E	<5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
80	BL12N 250 E	<5	<0.2	2.52	50	105	<5	0.04	<1	6	70	28	4.63	10	0.60	190	17	<0.01	8	760	10	<5	<20	9	0.14	<10	117	<10	2	59
89	BL12N 475 E	<5	<0.2	1.55	<5	30	<5	0.03	<1	3	7	5	1.70	<10	0.17	415	8	<0.01	3	400	8	<5	<20	4	0.06	<10	23	<10	3	18
98	BL12N 700 E	<5	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-


Et #. Tag # Au(ppb) Ag Al % As Ba Bi Ca % Cd Co Cr Cu Fe % La Mg % Mn Mo Na % Ni P Pb Sb Sn Sr Ti % U V W Y Zn

QC DATA:

Standard:

GEO'96	140	1.2	1.88	65	155	<5	1.87	<1	19	64	85	4.31	<10	1.03	736	<1	0.02	25	730	18	<5	<20	64	0.13	<10	83	<10	4	65
GEO'96	140	1.2	1.87	70	155	<5	1.89	<1	20	65	84	4.35	<10	1.03	741	<1	0.02	26	740	18	<5	<20	62	0.13	<10	84	<10	4	66
GEO'96	140	1.2	1.88	65	155	<5	1.90	<1	20	67	94	4.39	<10	1.06	734	<1	0.02	25	760	20	<5	<20	64	0.13	<10	85	<10	4	67
GEO'96	150	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	

df/785br
XLS96/FORAN


ECO-TECH LABORATORIES LTD.
Frank J. Pezzotti, A. Sc. T.
B.C. Certified Assayer

8-Aug-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK96-747

FORAN MINES
2500-#3 BENTALL CENTRE - PO BOX 49200
595 BURRARD STREET
VANCOUVER, B.C.
V7X 1L1

Phone: 604-573-5700
Fax : 604-573-4557

ATTENTION: WAYNE TYNER/B. ZINKHOFFER

No. of Samples received: 5
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: NOT INDICATED

Values in ppm unless otherwise reported

Et #	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Tl %	U	V	W	Y	Zn
1	quartz main showing	5	0.4	0.07	<5	<5	<5	0.02	<1	2	226	17	2.13	<10	<0.01	66	14	<0.01	5	30	2	<5	<20	<1	<0.01	<10	3	<10	<1	6
2	sulphite from contact showing	5	<0.2	1.32	<5	520	<5	0.64	<1	4	256	29	1.36	<10	0.32	324	11	0.07	19	300	10	<5	<20	36	0.09	<10	38	<10	3	38
3	chart from contact showing	5	<0.2	2.17	<5	255	<5	0.98	<1	14	157	9	2.57	<10	0.69	664	3	0.20	29	490	6	<5	<20	92	0.15	<10	44	<10	4	59
4	sulphite from main showing A	5	<0.2	4.47	<5	110	<5	3.26	<1	16	158	25	4.20	<10	0.59	316	6	0.24	29	1250	<2	<5	<20	389	0.12	<10	41	<10	2	25
5	sulphite from main showing B	5	0.4	5.64	20	115	<5	4.03	<1	8	104	32	2.67	10	0.18	144	5	0.40	12	520	6	<5	<20	409	0.07	<10	19	<10	2	24
QC/DATA:																														
Resplit:																														
3	chart from contact showing	5	<0.2	2.11	<5	275	<5	0.94	<1	13	162	7	2.52	<10	0.68	661	4	0.19	28	500	6	<5	<20	88	0.15	<10	44	<10	3	59
Repeat:																														
1		5	0.6	0.08	<5	5	<5	0.02	<1	2	228	17	2.17	<10	<0.01	62	14	<0.01	5	30	<2	<5	<20	1	<0.01	<10	3	<10	<1	6
Standard:																														
GEO'95		155	1.0	1.73	65	150	<5	1.79	<1	18	62	78	4.08	<10	0.94	703	<1	0.02	25	710	20	<5	20	60	0.11	<10	77	<10	3	66

df/759R
XLS/96Foran


ECO-TECH LABORATORIES LTD.
per Frank J. Pezzotti, A.Sc.T.
B.C. Certified Assayer

08/08/96 (THU) 21:47 [TX/RX NO 93121]

08/08/96 21:47 [TX/RX NO 93121]

29-Jul-96

ECO-TECH LABORATORIES LTD.
10041 East Trans Canada Highway
KAMLOOPS, B.C.
V2C 6T4

ICP CERTIFICATE OF ANALYSIS AK96-695

FORAN MINES
2500-#3 BENTALL CENTRE - PO BOX 49200
595 BURRARD STREET
VANCOUVER, B.C.
V7X 1L1

ATTENTION: WAYNE TYNER/B. ZINKHOFFER

Phone: 604-573-5700
Fax : 604-573-4557

No. of Samples received: 3
Sample Type: ROCK
PROJECT #: NONE GIVEN
SHIPMENT #: NONE GIVEN
Samples submitted by: FORAN

Values in ppm unless otherwise reported

Et #.	Tag #	Au(ppb)	Ag	Al %	As	Ba	Bi	Ca %	Cd	Co	Cr	Cu	Fe %	La	Mg %	Mn	Mo	Na %	Ni	P	Pb	Sb	Sn	Sr	Ti %	U	V	W	Y	Zn
1	GOZEN	5	0.2	3.65	5	60	<5	2.41	<1	17	137	26	3.29	<10	0.34	107	<1	0.36	35	580	18	<5	<20	312	0.12	<10	44	<10	2	23
2	R GOZEN	5	<0.2	3.79	<5	110	<5	1.27	<1	16	180	28	3.77	<10	1.81	248	1	0.33	28	600	18	<5	<20	139	0.18	<10	132	<10	<1	31
3	RI GOZEN	5	0.4	6.34	15	45	<5	4.08	1	22	87	109	4.73	30	1.29	706	<1	0.77	16	2630	24	<5	40	522	0.18	<10	164	<10	3	174

QC/DATA:


Repeat:

1	GOZEN	5	<0.2	3.71	<5	55	<5	2.44	<1	17	137	25	3.34	<10	0.34	105	<1	0.36	36	590	18	<5	<20	312	0.11	<10	44	<10	2	23
---	-------	---	------	------	----	----	----	------	----	----	-----	----	------	-----	------	-----	----	------	----	-----	----	----	-----	-----	------	-----	----	-----	---	----

Standard:

GEO'96	150	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
--------	-----	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---

df/5088R
XLS/96Foran


 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.T.
 B.C. Certified Assayer