


| Sample # | -60 +150 HN. |          | - 150 HN |          |
|----------|--------------|----------|----------|----------|
|          | Wt (g)       | Au (ppb) | Wt (g)   | Au (ppb) |
| T137     | 0.74         | 5,200    | 0.96     | 2,500    |
| T138     | 0.53         | 63,000   | 0.76     | 6,600    |
| T139     | 2.04         | 17,000   | 0.60     | 32,000   |
| W142     | 3.24         | 5,180    | 2.51     | 70       |
| W143     | 4.95         | 620      | 1.26     | 2,200    |
| W145     | 2.60         | < 20     | 2.18     | 520      |
| W146     | 0.74         | < 60     | 0.43     | 3,700    |
| W147     | 2.14         | 3,400    | 0.98     | 3,600    |
| W162     | 3.92         | 22,860   | 1.16     | 10,000   |
| 0569     | 7.44         | 2,500    | 0.72     | 5,300    |
| 0581     | 5.31         | 3,500    | 0.83     | 1,700    |
| 82       | 2.30         | 3,000    | 1.16     | 3,500    |
| 83       | 7.53         | 800      | 0.86     | 3,200    |
| 84       | 0.68         | < 20     | 0.50     | 11,000   |
| 0585     | 2.09         | 3,800    | 0.48     | 41,000   |
| 0590     | 1.14         | < 10     | 0.36     | 4,500    |
| 91       | 4.83         | 15,000   | 0.91     | 20,000   |
| 92       | 6.08         | 12,000   | 1.64     | 43,000   |

840750  
 CHURAS CREEK

| <u>Sample #</u> | <u>-60 +150 HN</u> |                 | <u>-150 HN</u> |                 |
|-----------------|--------------------|-----------------|----------------|-----------------|
|                 | <u>wt (g)</u>      | <u>Au (ppb)</u> | <u>wt (g)</u>  | <u>Au (ppb)</u> |
| 0593            | 8.50               | <10             | 2.78           | 2,400           |
| 94              | 5.12               | <10             | 1.14           | 1,700           |
| 95              | 9.34               | 4,600           | 2.24           | 4,500           |
| 0596            | 4.49               | 7,800           | 2.95           | 3,700           |
| 0598            | 1.28               | 4,800           | 1.53           | 480             |
| 99              | 2.57               | 10              | 0.73           | <10             |
| 9600            | 5.36               | 3,900           | 2.56           | 3,300           |
| 01              | 3.04               | <10             | 1.49           | 140             |
| 0602            | 0.69               | 20              | 1.51           | 380             |
| 0606            | 1.93               | 11,000          | 0.07           | <50             |
| 0638            | 1.70               | 10              | 0.41           | 9,400           |
| 0639            | 11.60              | 160             | 5.70           | 14,000          |
| 0641            | 7.94               | 1,700           | 2.72           | 1,300           |
| 42              | 2.36               | 10              | 0.94           | 17,000          |
| 43              | 4.56               | 8,100           | 2.47           | 1,100           |
| 44              | 1.15               | 5,100           | 1.33           | 5,000           |
| 45              | 1.44               | <10             | 0.65           | 880             |
| 46              | 3.27               | <10             | 1.10           | 1,500           |
| 47              | 3.71               | <10             | 0.94           | 5,900           |
| 48              | 1.60               | 6,500           | 1.29           | 3,100           |
| 49              | 0.69               | <20             | 0.30           | <30             |
| 0650            | 6.22               | 990             | 1.80           | 1,100           |

| Sample # | -60 +150 MN |          | -150 HN |          |
|----------|-------------|----------|---------|----------|
|          | wt (g)      | Au (ppb) | wt (g)  | Au (ppb) |
| 0659     | 3.23        | < 10     | 0.89    | 3,200    |
| 0660     | 5.35        | 1,800    | 0.86    | 21,000   |
| 0690     | 2.54        | 10       | 1.50    | 10       |
| 91       | 3.66        | 9,300    | 1.11    | 13,000   |
| 92       | 2.17        | 99,000   | 3.48    | 13,000   |
| 93       | 1.23        | 120,000  | 1.35    | 22,000   |
| 94       | 1.29        | 2,400    | 1.36    | 2,200    |
| 95       | 2.77        | <10      | 2.97    | 2,900    |
| 96       | 1.70        | 890      | 1.16    | <10      |
| 97       | 3.41        | 2,800    | 1.63    | 24,000   |
| 98       | 3.33        | 3,000    | 3.11    | 2,700    |
| 99       | 3.22        | 19,000   | 1.76    | 17,000   |
| 0700     | 4.93        | 44,000   | 1.93    | 2,700    |
| 01       | 0.83        | <10      | 0.72    | 3,600    |
| 02       | 3.35        | 4,800    | 1.92    | 6,500    |
| 03       | 3.45        | 15,000   | 2.28    | 780      |
| 04       | 2.60        | 4,100    | 1.15    | 12,000   |
| 05       | 1.20        | 11,000   | 1.41    | 4,300    |
| 06       | 2.15        | <10      | 0.53    | 4,800    |
| 07       | 2.12        | <10      | 1.30    | 3,500    |
| 08       | 9.31        | 8,300    | 1.92    | 34,000   |
| 09       | 3.12        | 14,000   | 1.99    | 2,600    |
| 0700 10  | 3.17        | 8,300    | 0.64    | 2,600    |
| 11       | 5.20        | 6,500    | 1.59    | 11,000   |
| 12       | 4.73        | 15,000   | 6.31    | 1,900    |
| 0700 13  | 4.49        | 37,000   | 5.98    | 1,200    |

| <u>Sample #</u>               | <u>-60 + 150 MN</u> |                 | <u>-150 HN</u> |                 |
|-------------------------------|---------------------|-----------------|----------------|-----------------|
|                               | <u>wt (g)</u>       | <u>Au (ppb)</u> | <u>wt (g)</u>  | <u>Au (ppb)</u> |
| <del>00</del> <sup>7</sup> 16 | 2.37                | 10              | 1.34           | 600             |
| <del>00</del> <sup>7</sup> 17 | 2.64                | 6,800           | 1.55           | 3,700           |
| <del>00</del> <sup>7</sup> 19 | 5.11                | 1,900           | 11.61          | 460             |
| 20                            | 2.92                | <10             | 16.90          | 20              |
| 21                            | 5.41                | 6,200           | 2.50           | 6,100           |
| 22                            | 3.07                | <10             | 1.29           | 4,400           |
| <del>00</del> <sup>7</sup> 23 | 3.53                | 1,900           | 1.30           | 110             |
| <del>00</del> <sup>7</sup> 30 | 6.41                | 1,700           | 1.52           | 370             |



Soils Anomalous in Au, Hg, Sb


GOLDQUEST CLAIMS

1983 GRID

Heavy Mineral Results

13,000 gold in ppb in the -150 mesh fraction of the non-magnetic heavy mineral concentrate. (fine fraction) Analysis by NAA

— Vein at Blackdome  
 - - - height of land



Blackdome Mining Corp.  
 203,000 tons  
 0.79 oz/ton Au, 3.76 oz/ton Ag  
 Production: May 1986

|   |                       |                    |        |
|---|-----------------------|--------------------|--------|
| GOLDQUEST I LIMITED PARTNERSHIP                     |                       |                    |        |
| <i>CHURN CREEK CLAIMS<br/>HEAVY MINERAL RESULTS</i> |                       |                    |        |
| PLAN No.<br>918                                     | DRAWN BY:<br>GEO-COMP | DATE<br>MAR '86    | FIGURE |
| Originator: GRP                                     |                       | N.T.S.<br>92/0/7,8 |        |
| MINEQUEST EXPLORATION ASSOCIATES LTD.               |                       |                    |        |