

BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

RECEIVED
SEP 2 1976

840811

Mtn. Tegart

Geochemical Lab Report

Minerals Staff
CHEVRON STANDARD LIMITED
VANCOUVER OFFICE

Extraction Hot Aqua Regia
Method Atomic Absorption
Fraction Used _____

Report No. 26 - 847 - PROJECT: C 429
From Chevron Standard Ltd.
Date August 30, 19 76

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm		SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	
14/8/76/ 1	16	33	72		14/8/76/31	13	63	89	
2	13	125	1120		32	9	56	151	
3	26	710	2400		33	10	40	86	
4	12	68	200		15/8/76/ 1	6	23	65	
5	19	152	450		2	10	29	72	
6	8	32	93		3	22	47	57	
7	17	43	67		4	8	35	54	
8	9	31	78		5	17	35	95	
9	6	30	122		6	20	41	53	
10	10	300	1600		7	16	138	310	
11	15	112	200		8	13	57	265	
12	12	61	107		9	6	26	71	
13	12	75	365		10	23	38	60	
14	8	50	260		11	14	54	255	
15	18	44	160		12	11	33	84	
16	13	41	97		13	12	57	70	
17	9	37	78		14	33	55	127	
18	5	24	131		15	24	51	108	
19	8	54	500		16	9	26	82	
20	10	93	290		17	10	34	78	
21	14	88	250		18	20	64	90	
22	8	46	225		18/8/76/ 1	22	30	49	
23	11	64	225		2	11	24	50	
24	7	62	390		3	19	42	73	
25	13	60	200		4	5	30	145	
26	16	49	196		5	14	34	168	
27	8	44	155		6	19	53	130	
28	8	106	530		7	18	39	40	
29	27	1090	3700		8	13	24	53	
30	11	39	134		9	8	25	64	

RECEIVED

SEP 2 1976

Geochemical Lab Report

Report No. 26 - 847

Page No. 2
 Minerals Staff
 CHEVRON STANDARD LABORATORY
 VANCOUVER

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm		SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	
18/8/76/10	7	29	98		18/8/76/45	9	20	61	
11	10	34	152		46	13	24	60	
12	15	27	90		47	9	22	62	
13	9	25	87		48	10	19	52	
14	5	23	71		49	24	59	94	
15	10	27	102		50	9	34	77	
16	13	27	83		51	10	29	91	
17	15	23	77		52	20	41	88	
18	9	24	148		53	19	33	77	
19	10	23	71		19/8/76/ 1	15	26	45	
20	9	35	126		2	12	21	50	
21	10	31	90		3	9	20	53	
22	12	25	78		4	18	23	50	
23	7	18	77		5	9	20	65	
24	10	20	54		6	6	19	56	
25	15	61	61		7	7	19	41	
26	12	42	52		8	25	32	46	
27	7	19	54		9	14	23	59	
28	5	23	59		10	12	20	54	
29	6	19	54		11	7	22	50	
30	6	20	54		12	10	21	60	
31	17	26	75		13	11	26	52	
32	6	22	87		14	12	23	64	
33	6	21	60		15	22	21	75	
34	5	22	60		16	16	25	75	
35	6	22	57		17	10	22	50	
36	9	29	51		18	8	19	83	
37	9	21	62		19	13	14	50	
38	6	17	50		20	5	18	26	
39	7	20	76		21	23	30	71	
40	10	20	54		22	4	14	29	
41	7	19	55		23	6	24	61	
42	7	18	37		24	7	24	48	
43	6	18	60		25	20	39	40	
44	11	23	60		21/8/76/ 1	7	26	51	


BONDAR-CLEGG & COMPANY LTD.

Geochemical Lab Report

 Report No. 26 - 760

 Page No. 4

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm					REMARKS
N/400 E4 L-10/8/76 - 29	24	42	110	✓				LINE N/400 E 400
30	19	300	17000	✓				
31	7	33	180	✓				
32	7	31	120	✓				
33	22	460	284	✓				
34	8	38	340	✓				
35	6	29	109	✓				
36	11	50	156	✓				
N4 E12 37	4	19	46	✓				Line N 400 E 1200
N600 E 0 38	14	18	60	✓				Line N 600 E 0
39	8	20	62	✓				E 100'
40	9	42	146	✓				
41	17	63	116	✓				
42	8	18	58	✓				
43	19	19	55	✓				
44	6	22	100	✓				
45	6	25	143	✓				
46	7	27	140	✓				
47	24	60	220	✓				
48	20	66	179	✓				
49	20	63	154	✓				E 1100
N600 E 12 50	8	30	53	✓				Line N 600 E 1200
L-12/8/76 - 1	7	20	21					
2	10	45	64					
3	16	28	89					
4	16	25	63					
L-24/7/76 - 1	13	23	68					
L-25/7/76 - 6	25	42	104					
L-26/7/76 - 3	10	37	64					
5	21	38	71					
L-27/7/76 - 1A	9	21	46					
1B	6	10	22					
3	11	13	24					
4	7	12	23					
L-28/7/76 - 2	9	36	29					



1976 *M469 NT TELART*
BONDAR-CLEGG & COMPANY LTD.


1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

Geochemical Lab Report

Extraction Hot Aqua Regia Report No. 26 - 394
 Method Atomic Absorption From Chevron Minerals
 Fraction Used _____ Date July 13 19 76

RECEIVED
C479
JUL 15 1976
 Minerals Staff
CHEVRON STANDARD LIMITED
 VANCOUVER OFFICE

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Mo ppm	Ag* ppm			REMARKS
L 21/6/76 - 3	30	28	55	-	0.6			
Rock 5B	>20000	40	32	-	29.			
22/6/76 - 1	2860	>20000	146	-	68.			
3	4	7	56	-	0.2			
4	10	98	73	-	0.2			
5	4	16	53	-	0.3			
6	10	18	47	-	0.2			
23/6/76 - 1	28	40	54	-	0.4			
2	5	18	131	-	0.4			
Rock 3A	2080	1780	13	-	4.7			
3B	9	17	35	-	0.2			
4	4	13	25	-	0.2			
5	7	13	44	-	0.2			
6	4	15	30	-	0.4			
7	31	34	63	-	0.8			
8	10	18	46	-	0.4			
24/6/76 - 1	33	23	47	-	0.3			
2	43	22	43	-	0.6			
Rock 3	118	395	76	-	1.5			
4	2	16	37	-	0.2			
5	15	18	24	-	0.2			
26/6/76 - 1	14	122	500	-	0.4			
2	9	46	210	-	0.2			
3	11	32	41	-	0.2			
Rock 5	130	18500	7700	-	8.3			
6	7	37	105	-	0.2			
27/6/76 - Rock 1A		315	450	4	8.3			
1B	80	54	83	3	0.5			
2	17	90	175	2	0.5			
29/6/76 - 1	8	24	36	-	0.4			



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

JWS


Geochemical Lab Report

RECEIVED
AUG 3 1976

Minerals Staff
CHEVRON STANDARD LIMITED
VANCOUVER OFFICE
C 429

Extraction U; Hot HNO₃ Report No. 26 - 529
Cu, Pb, Zn, Ag, Cd; Hot Aqua Regia
U; Fluorimetric
 Method Cu, Pb, Zn, Ag, Cd; Atomic Absorption From Chevron Standard
 Fraction Used _____ Date July 28 19 76

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag* ppm	Cd* ppm	U ppm	REMARKS
RS 9/7/76 - 1	5	40	230	-	1.0	-	
2	5	33	112	-	0.7	-	
3	6	100	710	-	1.3	-	
L 6/7/76 - 1	37	19	38	-	-	1	
2	36	35	32	-	-	1	
3	23	40	160	-	-	-	
4	29	27	88	-	-	-	
5	12	21	102	-	-	-	
6	24	29	82	-	-	-	
7	28	51	167	-	-	-	
8	11	22	138	-	-	-	
9	6	12	93	-	-	-	
L 8/7/76 - 1B	10	39	129	0.2	1.1	-	
L 11/7/76 - 1	8	45	135	-	-	-	
2	8	30	100	-	-	-	
3	23	36	115	-	-	-	
4	4	18	45	-	-	-	
L 13/7/76 - 2	8	34	50	-	-	-	
4	19	28	63	-	-	-	
5	30	36	82	-	-	-	
6	19	34	96	-	-	-	
L 14/7/76 - 3	13	28	57	-	-	-	
5	5	18	46	-	-	-	
L 15/7/76 - 1	11	37	54	-	-	-	
2	10	26	28	-	-	-	
3	10	62	115	-	-	0.4	
5	12	102	480	-	-	0.8	
6	8	102	370	-	-	-	
7	15	37	152	-	-	0.4	
8	20	32	26	-	-	-	



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

Geochemical Lab Report *Jubilee Mtn*

Extraction Hot Aqua Regia

Report No. 26 - 301 PROJECT: C 429


Method Atomic Absorption

From Chevron Standard Ltd.

Fraction Used _____

Date June 29, 19 76

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag* ppm	SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag* ppm
L16/ 5/76 - 3	51	24	128	0.4	L19/6/76 - 8	4	11	46	0.2
4	15	18	64	0.2	9	8	16	62	0.2
5	6	20	22	0.2	10	12	20	66	0.2
6	5	20	31	0.2	L20/6/76 - 1	13	15	27	0.2
7	6	18	29	0.2	3	9	14	41	0.2
8	4	12	46	0.2	4	12	19	36	0.2
9	9	11	66	0.3	5	7	12	16	0.2
L17/6/76 - 3	3	19	58	0.2	6	16	50	62	0.2
4	7	11	50	0.2	7	14	28	52	0.4
5	10	14	49	0.2	9	14	800	180	0.2
6	14	13	44	0.2	10	10	12	24	0.2
7	13	15	51	0.2	11	8	18	54	0.2
8	12	22	26	0.2	12	4	23	48	0.2
9	6	16	50	0.2	13	5	10	60	0.2
10	8	20	68	0.2	14	4	8	32	0.2
11	12	18	68	0.2	15	9	15	30	1.3
12	10	18	49	0.2	16	10	14	40	0.2
13	10	38	50	0.2	17	6	17	26	0.2
14	10	34	42	0.2	L21/6/76 - 1	6	21	36	0.2
15	6	30	29	0.2	4	5	22	36	0.3
L18/6/76 - 2	6	11	34	0.2	5B	28	39	130	0.3
3	4	10	65	0.2	Rock				
4	5	6	22	0.2	L19/6/76 - 7	9	280	9	0.5
5	11	9	66	0.2					
6	7	26	100	0.2					
7	1	18	86	0.2					
L19/6/76 - 2	5	12	30	0.2					
4	8	15	60	0.2	* background corrected				
5	3	18	49	0.2					
6	5	20	37	0.2					



BONDAR-CLEGG & CO. COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

Tegart Mountain Geochemical Lab Report

Extraction Hot Aqua Regia

Report No. 26 - 847 PROJECT: C 429

Method Atomic Absorption

From Chevron Standard Ltd.

Fraction Used _____

Date August 30, 19 76

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm		SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	
8700 NX 0100E 14/8/76/ 1	16	33	72	✓	2700E 14/8/76/31	13	63	89	✓
1200E	13	125	1120	✓	1400E 32	9	56	151	✓
2300E	26	710	2400	✓	0100E 33	10	40	86	✓
3400E	12	68	200	✓	16700 NX 0100E 15/8/76/ 1	6	23	65	✓
4500E	19	152	450	✓	1400E 2	10	29	72	✓
4600E	8	32	93	✓	2400E 3	22	47	57	✓
5700E	17	43	67	✓	3400E 4	8	35	54	✓
6800E	9	31	78	✓	4400E 5	17	35	95	✓
7900E	6	30	122	✓	5400E 6	20	41	53	✓
8100E	10	300	1600	✓	6400E 7	16	138	310	✓
91100E	15	112	200	✓	14700 NX 0100E 8	13	57	265	✓
10400 NX 0100E 12	12	61	107	✓	19700 NX 0100E 9	6	26	71	✓
131400E	12	75	365	✓	1400E 10	23	38	60	✓
142400E	8	50	260	✓	2400E 11	14	54	255	✓
3153700E	18	44	160	✓	3400E 12	11	33	84	✓
4164700E	13	41	97	✓	4400E 13	12	57	70	✓
5175700E	9	37	78	✓	14750 NX 4700E 14	33	55	127	✓
6187700E	5	24	131	✓	3400E 15	24	51	108	✓
7197700E	8	54	500	✓	2400E 16	9	26	82	✓
10400 NX 8700E 20	10	93	290	✓	1400E 17	10	34	78	✓
12400 NX 0100E 21	14	88	250	✓	0100E 18	20	64	90	✓
1220100E	8	46	225	✓	27005 NX 0100E 18/8/76/ 1	22	30	49	✓
2230700E	11	64	225	✓	1400E 2	11	24	50	✓
3240700E	7	62	390	✓	2400E 3	19	42	73	✓
4250700E	13	60	200	✓	3400E 4	5	30	145	✓
5260700E	16	49	196	✓	4400E 5	14	34	168	✓
6270700E	8	44	155	✓	5400E 6	19	53	130	✓
14100 NX 235400E 28	8	106	530	✓	6400E 7	18	39	40	✓
4290700E	27	1090	3700	✓	7400E 8	13	24	53	✓
3300700E	11	39	134	✓	8400E 9	8	25	64	✓

Geochemical Lab Report

Report No. 26 - 847

Page No. 2


RECEIVED

SEP 2 1978

Block 5/11

WATERBURY LIMITED

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm		SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	
9+00E 18/8/76/10	7	29	98	✓	7+00E 18/8/76/45	9	20	61	✓
10+00E 11	10	34	152	✓	9+00E 46	13	24	60	✓
11+00E 12	15	27	90	✓	9+00E 47	9	22	62	✓
12+00E 13	9	25	87	✓	10+00E 48	10	19	52	✓
13+00E 14	5	23	71	✓	11+00E 49	24	53	94	✓
14+00E 15	10	27	102	✓	12+00E 50	9	34	77	✓
15+00E 16	13	27	83	✓	13+00E 51	10	29	91	✓
0+00S X 15+00E 17	15	23	77	✓	14+00E 52	20	41	83	✓
14+00E 18	9	24	148	✓	15+00E 53	19	33	77	✓
13+00E 19	10	23	71	✓	8+00S X 0+00E 19/8/76/1	15	26	45	✓
12+00E 20	9	35	126	✓	1+00E 2	12	21	50	✓
11+00E 21	10	31	90	✓	2+00E 3	9	20	53	✓
4+00S X 0+00E 22	12	25	78	✓	3+00E 4	18	23	50	✓
1+00E 23	7	18	77	✓	4+00E 5	9	20	65	✓
2+00E 24	10	20	54	✓	5+00E 6	6	19	56	✓
3+00E 25	15	61	61	✓	6+00E 7	7	19	41	✓
4+00E 26	12	42	52	✓	7+00E 8	25	32	46	✓
5+00E 27	7	19	54	✓	8+00E 9	14	23	50	✓
6+00E 28	5	23	59	✓	9+00E 10	12	20	54	✓
7+00E 29	6	19	54	✓	10+00E 11	7	22	50	✓
8+00E 30	6	20	54	✓	11+00E 12	10	21	60	✓
9+00E 31	17	26	75	✓	12+00E 13	11	26	52	✓
10+00E 32	6	22	87	✓	13+00E 14	12	23	64	✓
11+00E 33	6	21	60	✓	14+00E 15	22	21	75	✓
12+00E 34	5	22	60	✓	15+00E 16	16	25	75	✓
13+00E 35	6	22	57	✓	2+00N X 13+00E 17	10	22	50	✓
14+00E 36	9	29	51	✓	14+00E 18	8	19	83	✓
15+00E 37	9	21	62	✓	15+00E 19	13	14	50	✓
6+00S X 0+00E 38	6	17	50	✓	4+00N X 13+00E 20	5	18	26	✓
1+00E 39	7	20	76	✓	14+00E 21	23	30	71	✓
2+00E 40	10	20	54	✓	15+00E 22	4	14	29	✓
3+00E 41	7	19	55	✓	6+00N X 23 13+00E	6	24	61	✓
4+00E 42	7	18	37	✓	24 14+00E	7	24	48	✓
5+00E 43	6	18	60	✓	25 15+00E	20	39	40	✓
6+00E 44	11	23	60	✓	21/8/76/1	7	26	51	✓
					19+50N X 5+00E				



MT. TEGART M469

BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

JUL 26 1977

Minerals
CHEVRON STANDARD LIMITED
VANCOUVER OFFICE

Geochemical Lab Report

Extraction Hot Aqua Regia

Report No. 27 - 609 PROJECT: M 429

Method Atomic Absorption

From Chevron Standard Ltd.

Fraction Used _____

Date July 22, 19 77

SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm		SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm	
05N 00E	12	52	0.2		1N 5+50E	35	240	0.2	
0+50E	13	72	0.2		6+00E	29	136	0.2	
1+00E	12	67	0.2		6+50E	35	168	0.2	
1+50E	15	76	0.2		7+00E	27	188	0.2	
2+00E	30	92	0.2		7+50E	28	106	0.2	
2+50E	25	310	0.2		8+00E	31	84	0.2	
3+00E	19	100	0.2		8+50E	33	164	0.2	
3+50E	28	152	0.2		9+00E	33	104	0.2	
4+00E	30	104	0.2		150N 00E	20	102	0.2	
4+50E	33	112	0.2		0+50E	12	36	0.2	
5+00E	25	252	0.2		1+00E	12	44	0.2	
5+50E	23	80	0.2		1+50E	14	53	0.2	
6+00E	30	74	0.2		2+00E	12	180	0.5	<
6+50E	16	46	0.2		2+50E	58	96	0.3	<
7+00E	11	28	0.2		3+00E	26	120	0.2	
7+50E	14	94	0.2		3+50E	26	112	0.2	
8+00E	29	152	0.2		4+00E	37	188	0.2	
8+50E	13	133	0.2		4+50E	38	140	0.3	<
9+00E	24	85	0.2		5+00E	21	81	0.2	
1N 00E	12	40	0.2		5+50E	25	104	0.2	
0+50E	13	144	0.2		6+00E	22	148	0.2	
1+00E	11	29	0.2		6+50E	16	72	0.2	
1+50E	12	45	0.2		7+00E	22	93	0.2	
2+00E	18	67	0.2		7+50E	32	96	0.3	<
2+50E	12	44	0.2		8+00E	34	132	0.2	
3+00E	39	101	0.2		8+50E	29	104	0.2	
3+50E	30	116	0.2		9+00E	31	104	0.2	
4+00E	27	184	0.2		250N 00E	10	63	0.2	
4+50E	20	124	0.2		0+50E	14	52	0.2	
5+00E	37	240	0.2		1+00E	12	40	0.2	

BONDAR-LEGG & COMPANY LTD.

Geochemical Lab Report

Report No. 27 - 609

Page No. 2

RECEIVED
JUL 26 1977

Minerals Staff
CHEVRON STANDARD LIMITED
VANCOUVER OFFICE

SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm		SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm	
250N 1+50E	23	146	0.3	<	350N 00E	19	96	0.2	
2+00E	14	55	0.2		0+50E	18	52	0.2	
2+50E	16	71	0.2		1+00E	14	60	0.2	
3+00E	20	57	0.2		1+50E	16	60	0.2	
3+50E	18	62	0.2		2+00E	15	50	0.2	
4+00E	21	81	0.2		2+50E	14	116	0.2	
4+50E	27	196	0.2		3+00E	29	141	0.2	
5+00E (1)	42	384	0.3	<	3+50E	21	72	0.2	
5+00E (2)	26	88	0.2		4+00E	32	125	0.2	
5+50E	43	140	0.2		4+50E	36	136	0.2	
6+00E	70	240	0.2		5+00E	46	400	0.2	
6+50E	42	121	0.2		5+50E	90	500	1.0	↖
7+00E	37	100	0.2		6+00E	49	420	0.4	<
7+50E	24	90	0.2		6+50E	57	180	0.3	<
8+00E	22	68	0.2		7+00E	40	120	0.2	
8+50E	44	102	0.2		7+50E	50	147	0.2	
9+00E	43	205	0.2		8+00E	140	264	0.7	<
3N 00E	17	52	0.2		8+50E	48	160	0.2	
0+50E	14	32	0.2		9+00E	33	150	0.2	
1+00E	22	132	0.2		450N 00E	14	52	0.2	
1+50E	33	164	0.2		0+50E	18	63	0.2	
2+00E	17	86	0.2		1+00E	29	124	0.2	
2+50E	19	66	0.2		1+50E	34	159	0.2	
3+00E	19	104	0.2		2+00E	20	80	0.2	
3+50E	22	84	0.2		2+50E	42	184	0.2	
4+00E	25	161	0.2		3+00E	47	160	0.5	<
4+50E	33	180	0.2		3+50E	54	200	0.3	<
5+00E	76	380	0.5	<	4+00E	27	72	0.3	<
5+50E	38	340	0.3	<	4+50E	450	2300	1.6	↖
6+00E	50	372	0.6	<	5+00E	220	1250	2.0	
6+50E	57	241	0.3	<	5+50E	39	168	0.4	<
7+00E	50	144	0.2		6+00E	22	128	0.2	
8+00E	39	120	0.2		6+50E	18	88	0.2	
8+50E	27	84	0.2		7+00E	11	69	0.2	
9+00E	36	125	0.2		7+50E	21	84	0.2	

7 7+00


JUL 26 1977

Geochemical Lab Report

Report No. 27 - 609

Minerals Staff
 Page No. 3
 CHEVRON STANDARD LIMITED
 VANCOUVER OFFICE

SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm		SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm	
450N 8+00E	16	60	0.2		550N 7+00E	21	97	0.2	
8+50E	23	64	0.2		7+50E	24	84	0.2	
9+00E	34	107	0.2		8+00E	19	88	0.2	
5N 00E	16	76	0.2		8+50E	20	88	0.2	
0+50E	13	53	0.2		9+00E	37	185	0.4	←
1+00E	19	68	0.2						
1+50E	12	52	0.2						
2+50E A	18	80	0.2						
2+50E B	96	260	0.2						
3+00E	28	148	0.2						
3+50E	79	232	1.0	←					
4+00E	46	232	0.2						
4+50E	15	48	0.2						
5+00E	10	22	0.2						
5+50E	25	69	0.3	←					
6+00E	17	66	0.2						
6+50E	14	93	0.2						
7+00E	20	88	0.2						
7+50E	20	96	0.2						
8+00E	19	64	0.2						
8+50E	22	85	0.2						
9+00E	38	186	0.2						
550N 00E	16	53	0.2						
0+50E	12	48	0.2						
1+00E	16	84	0.2						
1+50E	16	56	0.2						
2+00E	17	172	0.2						
3+00E	108	320	0.5	←					
3+50E	58	172	0.4	←					
4+00E	24	49	0.2						
4+50E	25	110	0.2						
5+00E	12	48	0.2						
5+50E	11	44	0.2						
6+00E	14	62	0.2						
6+50E	13	62	0.2						



RECEIVED

Geochemical Lab Report

CHEMICAL ANALYSIS

Extraction Hot Aqua Regia

Report No. 27 - 609 PROJECT: M 429

Method Atomic Absorption

From Chevron Standard Ltd.

Fraction Used _____

Date July 22, 19 77

SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm		SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm	
05N 00E	12	52	0.2		1N 5+50E	35	240	0.2	
0+50E	13	72	0.2		6+00E	29	136	0.2	
1+00E	12	67	0.2		6+50E	35	168	0.2	
1+50E	15	76	0.2		7+00E	27	188	0.2	
2+00E	30	92	0.2		7+50E	28	106	0.2	
2+50E	25	310	0.2		8+00E	31	84	0.2	
3+00E	19	100	0.2		8+50E	33	164	0.2	
3+50E	28	152	0.2		9+00E	33	104	0.2	
4+00E	30	104	0.2		150N 00E	20	102	0.2	
4+50E	33	112	0.2		0+50E	12	36	0.2	
5+00E	25	252	0.2		1+00E	12	44	0.2	
5+50E	23	80	0.2		1+50E	14	53	0.2	
6+00E	30	74	0.2		2+00E	12	180	0.5	
6+50E	16	46	0.2		2+50E	58	96	0.3	
7+00E	11	28	0.2		3+00E	26	120	0.2	
7+50E	14	94	0.2		3+50E	26	112	0.2	
8+00E	29	152	0.2		4+00E	37	188	0.2	
8+50E	13	133	0.2		4+50E	38	140	0.3	
9+00E	24	85	0.2		5+00E	21	81	0.2	
1N 00E	12	40	0.2		5+50E	25	104	0.2	
0+50E	13	144	0.2		6+00E	22	148	0.2	
1+00E	11	29	0.2		6+50E	16	72	0.2	
1+50E	12	45	0.2		7+00E	22	93	0.2	
2+00E	18	67	0.2		7+50E	32	96	0.3	
2+50E	12	44	0.2		8+00E	34	132	0.2	
3+00E	39	101	0.2		8+50E	29	104	0.2	
3+50E	30	116	0.2		9+00E	31	104	0.2	
4+00E	27	184	0.2		250N 00E	10	63	0.2	
4+50E	20	124	0.2		0+50E	14	52	0.2	
5+00E	37	240	0.2		1+00E	12	40	0.2	


RECEIVED
JUL 26 1977

Geochemical Lab Report

Report No. 27 - 609

Page No. 3
C.I. 3
MADE IN CANADA

SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm		SAMPLE NO.	Pb ppm	Zn ppm	Cd ppm	
450N 8+00E	16	60	0.2		550N 7+00E	21	97	0.2	
8+50E	23	64	0.2		7+50E	24	84	0.2	
9+00E	34	107	0.2		8+00E	19	88	0.2	
5N 00E	16	76	0.2		8+50E	20	88	0.2	
0+50E	13	53	0.2		9+00E	37	185	0.4	
1+00E	19	68	0.2						
1+50E	12	52	0.2						
2+50E A	18	80	0.2						
2+50E B	96	260	0.2						
3+00E	28	148	0.2						
3+50E	79	232	1.0						
4+00E	46	232	0.2						
4+50E	15	48	0.2						
5+00E	10	22	0.2						
5+50E	25	69	0.3						
6+00E	17	66	0.2						
6+50E	14	93	0.2						
7+00E	20	88	0.2						
7+50E	20	96	0.2						
8+00E	19	64	0.2						
8+50E	22	85	0.2						
9+00E	38	186	0.2						
550N 00E	16	53	0.2						
0+50E	12	48	0.2						
1+00E	16	84	0.2						
1+50E	16	56	0.2						
2+00E	17	172	0.2						
3+00E	108	320	0.5						
3+50E	58	172	0.4						
4+00E	24	49	0.2						
4+50E	25	110	0.2						
5+00E	12	48	0.2						
5+50E	11	44	0.2						
6+00E	14	62	0.2						
6+50E	13	62	0.2						



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

BCC Report No. 27-609

RECEIVED
JUL 26 1977
Minerals Staff
CHEVRON STANDARD LIMITED
VANCOUVER OFFICE

In your recent sample submission, received July 18/77,
the following samples were listed as included with the
shipment. However, we note that they are missing:


500N 2+100E

The following were not listed, but included:

2+50E A, 2+50E B

BONDAR-CLEGG & COMPANY LTD.

Don Van Loche



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

RECEIVED
AUG 2 1977
CHEVRON ST
VANCOUVER OFFICE

Geochemical Lab Report

Extraction Hot Aqua Regia Report No. 27 - 663 PROJECT: M 429

Method Atomic Absorption From Chevron Standard Ltd.

Fraction Used _____ Date July 28, 19 77

SAMPLE NO.	Pb ppm	Zn ppm			SAMPLE NO.	Pb ppm	Zn ppm		
PEDSOL 1	18	64			125+00N 4+00E	62	260		
2	13	32			4+50E	22	116		
3	25	56			5+00E	20	92		
4	20	52			5+50E	30	120		
5	12	62			6+00E	35	164		
6	17	108			130+00N 0+00E	230	440		
7	12	40			0+50E	52	232		
8	19	34			1+00E	18	40		
9	12	24			1+50E	20	60		
15N 0+00E	66	236			2+00E	28	86		
0+50E	74	192			2+50E	19	56		
1+00E	19	54			3+00E	14	40		
1+50E	19	44			3+50E	26	92		
2+00E	10	48			4+00E	20	93		
2+50E	15	44			4+50E	24	152		
3+00E	11	56			5+00E	16	44		
3+50E	18	52			5+50E	26	114		
4+00E	12	48			6+00E	42	470		
4+50E	17	64			135+00N 0+00E	31	76		
5+00E	28	108			0+50E	26	48		
5+50E	410	1800			1+00E	40	90		
6+00E	50	460			1+50E	15	84		
125+00N 0+00E	66	168			2+00E	30	112		
0+50E	42	176			2+50E	15	68		
1+00E	24	104			3+00E	20	146		
1+50E	21	68			3+50E	25	148		
2+00E	17	76			4+00E	NS	NS		
2+50E	48	264			4+50E	27	154		
3+00E	31	120			5+00E	17	92		
3+50E	102	580			5+50E	29	108		


RECEIVED
AUG 2 - 1977

Geochemical Lab Report

Report No. 27 - 663

Page No. 2

SAMPLE NO.	Pb ppm	Zn ppm	Ag ppm		SAMPLE NO.	Pb ppm	Zn ppm		
135+00N 6+00E	48	334	-						
145+00N 0+00E	30	138	-						
0+50E	380	400	-						
1+00E	35	62	-						
1+50E	16	46	-						
2+00E	12	62	-						
2+50E	16	74	-						
3+00E	27	232	-						
3+50E	14	72	-						
4+00E	20	108	-						
4+50E	114	50	-						
5+00E	14	36	-						
5+50E	290	2000	-						
6+00E	18	52	-						
1550N 0+00E	25	48	-						
0+50E	15	41	-						
1+00E	22	38	-						
1+50E	16	44	-						
2+00E	18	38	-						
2+50E	20	52	-						
3+00E	13	49	-						
3+50E	14	57	-						
4+00E	14	58	-						
4+50E	14	42	-						
5+00E	37	162	-						
5+50E	3000	10000	-						
6+00E	40	210	-						
Rocks ZAP 8	1480	5200	2.4						
9	8800	9600	4.7						
10	1000	1300	-						
11	480	17000	-						
12	200	7600	-						



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

Geochemical Lab Report

RECEIVED
AUG 2 - 1977
Minerals Stan
CHEVRON STANDARD LIMITED
VANCOUVER OFFICE

Extraction Hot Aqua Regia

Report No. 27 - 663 PROJECT: M 429


Method Atomic Absorption

From Chevron Standard Ltd.

Fraction Used _____

Date July 28, 19 77

SAMPLE NO.	Pb ppm	Zn ppm			SAMPLE NO.	Pb ppm	Zn ppm		
PEDSOL 1	18	64			125+00N				
2	13	32			4+00E	62	260		
3	25	56			4+50E	22	116		
4	20	52			5+00E	20	92		
5	12	62			5+50E	30	120		
6	17	108			6+00E	35	164		
7	12	40			130+00N				
8	19	34			0+00E	230	440		
9	12	24			0+50E	52	232		
15N 0+00E	66	236			1+00E	18	40		
0+50E	74	192			1+50E	20	60		
1+00E	19	54			2+00E	28	86		
1+50E	19	44			2+50E	19	56		
2+00E	10	48			3+00E	14	40		
2+50E	15	44			3+50E	26	92		
3+00E	11	56			4+00E	20	93		
3+50E	18	52			4+50E	24	152		
4+00E	12	48			5+00E	16	44		
4+50E	17	64			5+50E	26	114		
5+00E	28	108			6+00E	42	470		
5+50E	410	1800			135+00N				
6+00E	50	460			0+00E	31	76		
125+00N 0+00E	66	168			0+50E	26	48		
0+50E	42	176			1+00E	40	90		
1+00E	24	104			1+50E	15	84		
1+50E	21	68			2+00E	30	112		
2+00E	17	76			2+50E	15	68		
2+50E	48	264			3+00E	20	146		
3+00E	31	120			3+50E	25	148		
3+50E	102	580			4+00E	NS	NS		
					4+50E	27	154		
					5+00E	17	92		
					5+50E	29	108		



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

RECEIVED
AUG 2 - 1977
Minerals Section
CHEVRON STANDARD
VANCOUVER OFFICE

Geochemical Lab Report

Extraction Hot Aqua Regia

Report No. 27 - 663 PROJECT: M 429

Method Atomic Absorption

From Chevron Standard Ltd.

Fraction Used _____

Date July 28, 19 77

SAMPLE NO.	Pb ppm	Zn ppm			SAMPLE NO.	Pb ppm	Zn ppm		
PEDSOL 1	18	64			125+00N				
2	13	32			4+00E	62	260		
3	25	56			4+50E	22	116		
4	20	52			5+00E	20	92		
5	12	62			5+50E	30	120		
6	17	108			6+00E	35	164		
7	12	40			130+00N				
8	19	34			0+00E	230	440		
9	12	24			0+50E	52	232		
15N 0+00E	66	236			1+00E	18	40		
0+50E	74	192			1+50E	20	60		
1+00E	19	54			2+00E	28	86		
1+50E	19	44			2+50E	19	56		
2+00E	10	48			3+00E	14	40		
2+50E	15	44			3+50E	26	92		
3+00E	11	56			4+00E	20	93		
3+50E	18	52			4+50E	24	152		
4+00E	12	48			5+00E	16	44		
4+50E	17	64			5+50E	26	114		
5+00E	28	108			6+00E	42	470		
5+50E	410	1800			135+00N				
6+00E	50	460			0+00E	31	76		
125+00N 0+00E	66	168			0+50E	26	48		
0+50E	42	176			1+00E	40	90		
1+00E	24	104			1+50E	15	84		
1+50E	21	68			2+00E	30	112		
2+00E	17	76			2+50E	15	68		
2+50E	48	264			3+00E	20	146		
3+00E	31	120			3+50E	25	148		
3+50E	102	580			4+00E	NS	NS		
					4+50E	27	154		
					5+00E	17	92		
					5+50E	29	108		

Geochemical Lab Report

RECEIVED
AUG 2 - 1977
CHEVRON ST
VANCOUVER

Report No. 27 - 663

Page No. _____

SAMPLE NO.	Pb ppm	Zn ppm	Ag ppm		SAMPLE NO.	Pb ppm	Zn ppm		
135+00N									
6+00E	48	334	-						
145+00N									
0+00E	30	138	-						
0+50E	380	400	-						
1+00E	35	62	-						
1+50E	16	46	-						
2+00E	12	62	-						
2+50E	16	74	-						
3+00E	27	232	-						
3+50E	14	72	-						
4+00E	20	108	-						
4+50E	114	50	-						
5+00E	14	36	-						
5+50E	290	2000	-						
6+00E	18	52	-						
1550N									
0+00E	25	48	-						
0+50E	15	41	-						
1+00E	22	38	-						
1+50E	16	44	-						
2+00E	18	38	-						
2+50E	20	52	-						
3+00E	13	49	-						
3+50E	14	57	-						
4+00E	14	58	-						
4+50E	14	42	-						
5+00E	37	162	-						
5+50E	3000	10000	-						
6+00E	40	210	-						
Rocks ZAP 8	1480	5200	2.4						
9	8800	9600	4.7						
10	1000	1300	-						
11	480	17000	-						
12	200	7600	-						

To: Chevron Standard Ltd.

REPORT No A27 - 541

PAGE No. 1

901 - 355 Burrard Street
Vancouver, B.C.
V6C 2G8

RECEIVED
AUG 16 1977
Minerals
CHEVRON STATION
VANCOUVER OFFICE

BONDAR-CLEGG & COMPANY LTD.


DATE: August 9, 1977

CERTIFICATE OF ASSAY

Samples submitted: August 5, 1977
Results completed: August 9, 1977

I hereby certify that the following mineral samples are the results of assays made by us upon the herein described mineral pulp mineral samples.

MARKED	GOLD		SILVER	Pb	Zn						TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
ZAP 8				0.19	0.43						
9				0.96	0.79						
10				0.12	0.15						
11				0.06	1.42						
12				0.03	0.64						


Registered Assayer, Province of British Columbia

To: Chevron Standard Ltd.

REPORT No A27-462

PAGE No. 1

BONDAR-CLEGG & COMPANY LTD.

DATE: July 28, 1977

901 - 355 Burrard Street
Vancouver, B.C.
V6C 2G8

RECEIVED
AUG 2 - 1977
Minerals Staff
CHEVRON STANDARD LIMITED
VANCOUVER OFFICE

CERTIFICATE OF ASSAY

Samples submitted: July 25, 1977
Results completed: July 28, 1977
PROJECT: M 429 #4

I hereby certify that the following are the results of assays made by us upon the herein described pul ore samples.

MARKED	GOLD		SILVER	Pb	Zn						TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
FED 18				△0.01	0.08						
19				△0.01	0.05						
20				△0.01	0.10						
21				0.01	0.07						
22				0.02	0.05						
ZAP 1				△0.01	0.03	2 m	} Trench #1.				
2				0.06	3.20	2 m					
3				0.10	3.76	1 m					
4				0.10	8.10	1 m					
5				0.01	1.55	1.5 m					
6				0.01	8.70	0.5 m					
7				0.04	0.18						

Samples 2-6
6 m of 4.15% Zn.
weighted.

