



860145

MEMORANDUM

To: D.Hanson - Geologist

Date: 8 Feb, 1991

From: B.Taplin - Mill Metallurgist

File:

Subject: DOME MOUNTAIN ORE SAMPLE GRADES

Copies: G.Duthie, file

Grades for the three Dome Mountain samples are as indicated in the following table. These results are averages of both head samples and flotation test products.

Sample	% Cu	g/t Ag	% Zn	% Fe	% Sb	% Pb	g/t Au
#1 - Avg	.68	116	.90	6.99	.063	.27	33.79
- s	.025	8.7	.12	.67	.01	.01	3.45
#2 - avg	.52	96.3	1.37	5.49	.091	.22	36.68
- s	.026	7.5	.24	.75	.023	.02	7.77
#3 - avg	.49	113	5.02	7.83	.027	1.18	35.22
- s	.012	8.5	.20	1.82	.003	.12	2.88

B.Taplin
Mill Metallurgist