



Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers
212 BROOKSBANK AVE. NORTH VANCOUVER.
BRITISH COLUMBIA CANADA V7J-1C1
PHONE (604) 984-0221

To: KODE CONTRACTING LTD.

RR#8 SITE #6, COMPARTMENT 77,
PRINCE GEORGE, BC
V2N 4M6

Project :
Comments: ATTN: ED KOVACH

860465

**Page No. : 1-B
Tot. Pages: 1
Date : 12-APR-88
Invoice #: I-8813754
P.O. # :

Limestone

CERTIFICATE OF ANALYSIS A8813754

| SAMPLE DESCRIPTION | PREP CODE | V ppm (ICP) | Al % (ICP) | Be ppm (ICP) | Ca % (ICP) | Cu ppm (ICP) | Ag ppm AAS | Ti % (ICP) | Sr ppm (ICP) | Na % (ICP) | K % (ICP) | | | | |
|------------------------|-----------|-------------|------------|--------------|------------|--------------|------------|------------|--------------|------------|-----------|--|--|--|--|
| 22 4 10/20 | 217 232 | < 1 | 0.02 | < 0.5 | >25.0 | 3 | 0.5 | < 0.01 | 178 | < 0.01 | < 0.01 | | | | |
| 22 10 10/20 | 217 232 | < 1 | 0.03 | < 0.5 | >25.0 | 2 | 0.5 | < 0.01 | 235 | < 0.01 | 0.01 | | | | |
| 22 4 20/30 | 217 232 | < 1 | 0.02 | < 0.5 | >25.0 | 4 | 0.5 | < 0.01 | 187 | < 0.01 | < 0.01 | | | | |
| 22 6 20/30 | 217 232 | 4 | 0.06 | < 0.5 | 24.6 | 4 | 0.5 | < 0.01 | 166 | < 0.01 | 0.01 | | | | |
| 22 10 20/30 | 217 232 | 14 | 0.95 | < 0.5 | >25.0 | 15 | 0.5 | < 0.04 | 190 | 0.24 | 0.26 | | | | |
| 22 4 30/40 | 217 232 | < 1 | < 0.01 | < 0.5 | >25.0 | 1 | 0.5 | < 0.01 | 189 | < 0.01 | < 0.01 | | | | |
| 22 6 30/40 | 217 232 | 2 | 0.03 | < 0.5 | >25.0 | 2 | 0.5 | < 0.01 | 219 | < 0.01 | 0.01 | | | | |
| 22 10 30/40 | 217 232 | 5 | 0.25 | < 0.5 | >25.0 | 5 | 0.5 | 0.01 | 262 | 0.09 | 0.07 | | | | |
| 22 3 35/45 | 217 232 | 5 | 0.26 | < 0.5 | >25.0 | 4 | 0.5 | 0.01 | 245 | 0.09 | 0.06 | | | | |
| 22 3A 35/45 | 217 232 | 10 | 0.45 | < 0.5 | >25.0 | 10 | 0.5 | 0.02 | 178 | 0.06 | 0.10 | | | | |
| 22 5 40/50 | 217 232 | 44 | 2.35 | < 0.5 | 20.2 | 31 | 0.5 | 0.16 | 175 | 0.04 | 1.01 | | | | |

CERTIFICATION :



Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: KODE CONTRACTING LTD.

RR#8 SITE #6, COMPARTMENT 77,
PRINCE GEORGE, BC
V2N 4M6

A8815702

Comments: ATTN: ED KOVACH

CERTIFICATE A8815702

KODE CONTRACTING LTD.

PROJECT :

P.O.# : NONE

Samples submitted to our lab in Vancouver, BC.

This report was printed on 3-JUN-88.

SAMPLE PREPARATION

| CHEMEX CODE | NUMBER SAMPLES | DESCRIPTION |
|-------------|----------------|-------------------------|
| 214 | 11 | Received sample as pulp |
| 232 | 11 | Total ICP digestion |

ANALYTICAL PROCEDURES

| CHEMEX CODE | NUMBER SAMPLES | DESCRIPTION | METHOD | DETECTION LIMIT | UPPER LIMIT |
|-------------|----------------|--|-------------|-----------------|-------------|
| 592 | 11 | SiO ₂ %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 594 | 11 | Al ₂ O ₃ %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 586 | 11 | Fe ₂ O ₃ (total) %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 593 | 11 | MgO %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 588 | 11 | CaO %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 599 | 11 | Na ₂ O %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 821 | 11 | K ₂ O %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 595 | 11 | TiO ₂ %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 597 | 11 | P ₂ O ₅ %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 596 | 11 | MnO %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 542 | 11 | BaO %: Whole rock | ICP-AES | 0.01 | 99.00 |
| 475 | 11 | L.O.I. %: Loss on ignition | FURNACE | 0.01 | 99.00 |
| 540 | 11 | Total % | CALCULATION | 0.01 | N/A |



Chemex Labs Ltd.

Analytical Chemists * Geochemists * Registered Assayers

212 BROOKSBANK AVE. NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: KODE CONTRACTING LTD.

RR#8 SITE #6, COMPARTMENT 77,
PRINCE GEORGE, BC
V2N 4M6

Project:

Comments: ATTN: ED KOVACH

**Page No. : 1-A
Tot. Pages: 1
Date : 12-APR-88
Invoice #: I-8813754
P.O. # :

CERTIFICATE OF ANALYSIS A8813754

| SAMPLE DESCRIPTION | PREP CODE | Mo ppm (ICP) | W ppm (ICP) | Zn ppm (ICP) | P ppm (ICP) | Pb ppm (ICP) | Bi ppm (ICP) | Cd ppm (ICP) | Co ppm (ICP) | Ni ppm (ICP) | Ba ppm (ICP) | Fe % (ICP) | Mn ppm (ICP) | Cr ppm (ICP) | Mg % (ICP) |
|------------------------|-----------|--------------|-------------|--------------|-------------|--------------|--------------|--------------|--------------|--------------|--------------|------------|--------------|--------------|------------|
| 22 4 10/20 | 217 232 | < 1 | < 10 | 20 | 100 | 8 | 4 | < 0.5 | < 1 | 1 | 50 | 0.04 | 24 | 8 | 0.08 |
| 22 10 10/20 | 217 232 | < 1 | < 10 | 21 | 90 | 2 | < 2 | < 0.5 | < 1 | 4 | 20 | 0.05 | 40 | 9 | 0.05 |
| 22 4 20/30 | 217 232 | < 1 | < 10 | 17 | 100 | < 2 | 4 | < 0.5 | < 1 | 2 | 10 | 0.03 | 22 | 6 | 0.08 |
| 22 6 20/30 | 217 232 | < 1 | < 10 | 15 | 470 | 6 | 2 | < 0.5 | < 1 | 6 | 10 | 0.09 | 38 | 27 | 0.21 |
| 22 10 20/30 | 217 232 | 1 | 20 | 134 | 450 | < 2 | 4 | 1.5 | 10 | 100 | 290 | 1.30 | 1210 | 52 | ~ 7 |
| 22 4 30/40 | 217 232 | < 1 | < 10 | 22 | 70 | < 2 | 4 | < 0.5 | < 1 | 2 | < 10 | 0.03 | 18 | 4 | 0.09 |
| 22 6 30/40 | 217 232 | < 1 | < 10 | 15 | 320 | 2 | 4 | < 0.5 | < 1 | 3 | 20 | 0.08 | 53 | 6 | 0.41 |
| 22 10 30/40 | 217 232 | < 1 | < 10 | 26 | 110 | 18 | 2 | < 0.5 | < 1 | 6 | 40 | 0.22 | 66 | 14 | 0.18 |
| 22 3 35/45 | 217 232 | < 1 | < 10 | 23 | 110 | 4 | 4 | < 0.5 | < 1 | 5 | 40 | 0.20 | 60 | 9 | 0.18 |
| 22 3A 35/45 | 217 232 | 1 | 20 | 98 | 200 | < 2 | 4 | 1.0 | < 1 | 61 | 210 | 0.93 | 980 | 41 | 0.09 |
| 22 5 40/50 | 217 232 | 1 | < 10 | 33 | 1230 | 8 | 6 | 0.5 | 11 | 21 | 490 | 1.43 | 450 | 47 | 0.28 |

CERTIFICATION :



Chemex Labs Ltd.

Analytical Chemists • Geochemists • Registered Assayers

212 BROOKSBANK AVE., NORTH VANCOUVER,
BRITISH COLUMBIA, CANADA V7J-2C1

PHONE (604) 984-0221

To: KODE CONTRACTING LTD.

RR#8 SITE #6, COMPARTMENT 77,
PRINCE GEORGE, BC
V2N 4M6

Project:

Comments: ATTN: ED KOVACH

**Page No. : 1
Tot. Pages: 1
Date : 3-JUN-88
Invoice #: I-8815702
P.O. #: NONE

*Lower than
Dahl Lx.
Lower than
Dahl Lx.*

CERTIFICATE OF ANALYSIS A8815702

Loss on Ignition

| SAMPLE DESCRIPTION | PREP CODE | SiO2 % | Al2O3 % | Fe2O3 % | MgO % | CaO % | Na2O % | K2O % | TiO2 % | P2O5 % | MnO % | BaO % | LOI % | TOTAL % |
|------------------------|-----------|--------|---------|---------|-------|-------|--------|--------|--------|--------|--------|--------|-------|---------|
| NO 4 10/20 | 214 232 | 1.62 | 0.49 | 0.16 | 0.20 | 55.12 | 0.04 | 0.06 | < 0.01 | 0.02 | < 0.01 | < 0.01 | 38.71 | 96.42 |
| NO 10 10/20 | 214 232 | 2.73 | 0.13 | 0.19 | 0.15 | 53.52 | 0.08 | 0.10 | < 0.01 | 0.01 | < 0.01 | < 0.01 | 38.55 | 95.46 |
| NO 4 20/30 | 214 232 | 1.77 | 0.09 | 0.17 | 0.22 | 53.79 | 0.06 | 0.05 | < 0.01 | 0.02 | < 0.01 | < 0.01 | 38.53 | 94.70 |
| NO 6 20/30 | 214 232 | 33.62 | 0.18 | 0.23 | 0.44 | 35.41 | 0.04 | 0.11 | < 0.01 | 0.10 | < 0.01 | < 0.01 | 28.31 | 98.44 |
| NO 10 20/30 | 214 232 | 18.53 | 1.99 | 2.23 | 0.37 | 41.36 | 0.35 | 0.31 | 0.09 | 0.08 | 0.18 | 0.03 | 33.32 | 98.8 |
| NO 4 30/40 | 214 232 | 1.26 | 0.05 | 0.16 | 0.25 | 54.20 | 0.06 | 0.01 | < 0.01 | 0.01 | < 0.01 | < 0.01 | 38.56 | 94.56 |
| NO 10 30/40 | 214 232 | 6.22 | 0.17 | 0.23 | 0.79 | 50.34 | 0.08 | < 0.01 | < 0.01 | 0.06 | < 0.01 | < 0.01 | 39.18 | 97.07 |
| NO 10 30/40 | 214 232 | 4.44 | 0.56 | 0.44 | 0.41 | 51.42 | 0.17 | 0.17 | 0.02 | 0.02 | 0.01 | < 0.01 | 39.60 | 97.26 |
| NO 3 35/45 | 214 232 | 4.68 | 0.65 | 0.43 | 0.41 | 51.56 | 0.19 | 0.07 | 0.03 | 0.03 | 0.01 | < 0.01 | 39.32 | 97.38 |
| NO 3A 35/45 | 214 232 | 12.08 | 1.02 | 1.61 | 0.23 | 46.18 | 0.18 | 0.16 | 0.04 | 0.04 | 0.14 | 0.02 | 36.42 | 98.12 |
| NO 5 40/50 | 214 232 | 33.07 | 5.02 | 2.51 | 0.55 | 30.26 | 0.12 | 1.48 | 0.34 | 0.29 | 0.07 | 0.06 | 25.13 | 98.90 |

CERTIFICATION :

BCA