

860534

no. 2 vein
width

2.5	—	—
3.0	—	X
21.2	—	X
6.5	—	X
4.5	—	X
7.0	—	X
7.0	—	X
1) 49.7	—	X

7.1 ft.

Average width

Pb		Zn		Ag		Au	
%	% ft.	%	% ft.	oz	oz ft.	\$	\$ ft.
32.1	80.2	3.9	9.75	3.0	7.5	.62	1.55
5.6	16.8	2.1	6.3	.32	.96	.11	.33
11.55	24.9	4.98	105.6	.52	11.02	.41	8.69
21.36	138.8	22.2	144.3	.60	33.80	.21	1.37
3.76	169.2	4.45	20.0	.08	.36	.11	.50
2.4	16.8	23.8	166.6	.08	.56	.62	4.34
5.68	25.4	12.75	63.75	T.	—	.41	2.05
	695.1		516.30		24.30		18.83
14.0 %	14.0 % Average	10.4 %	Average	49.02	Average	0.38 \$	Average
T. T. L. Silver ✓				4.64 ^{oz.}			
				7.1 ft.			

[Handwritten signature]

No. 3 vein

width, ft.

8.0

12.5

Note: In following section 12 ft. lean not sampled. Calculated as 7 ft wide and give an arbitrary value of 1% Pb and 1% Zn. 08 ag & 11 au

17.0

10.8

4) 48.3

12.1 ft

Average

width, ft.	Pb		Zn		Ag		Au	
	%	%-ft.	%	%-ft.	oz.	oz.-ft.	¢	¢-ft.
8.0	4.96	39.68	7.00	56.0	.10	0.8	.21	1.68
12.5	12.7	15.7 159.0 158.75	8.8	110.0	.87	10.9	.15	1.87 1.88
17.0	6.86	116.62	4.8	81.5	.47	8.0	.29	4.93
10.8	4.12	44.4	7.26	78.3	.17	.18 1.84	.50	5.4
		359.45		325.8		21.54		13.89
	7.44%	Average	6.75%	Average	.45	Average	.29	Average
					oz.			
					2.79	ozs		
					12.1 ft.			

T.T.L. Silver 2.79 ozs 12.1 ft.

No. 4 Vlin

<u>Width</u>	<u>Pb</u>		<u>Zn</u>		<u>Ag</u>		<u>Cu</u>	
	%	% ft.	%	% ft.	oz	oz. ft.	\$	\$/ft.
{ 1.5	13.12	19.7	.50	.75	.90	1.35	.31	.46
	8.0	3.64	29.1	1.10	8.80	.10	.80	.11
25.0	1.36	34.0	4.30	107.5	.26	6.50	.41	10.25
18.0	1.68	30.2	3.25	58.5	.20	3.6	.11	1.98
5.0	4.60	23.0	5.60	28.0	.12	.60	.31	1.55
6.0	4.16	25.0	14.75	88.5	.20	1.20	.31	1.86
4.0	2.60	10.4	13.75	55.0	.22	.88	.83	3.32
6 67.5		171.4		433.05		20.25		20.30
11.25'				347.05		14.93		
Average	2.54 %		5.14 %		.22 oz.		.30	
	Average		Average		Average		Average	
					T. T. L.	(1.5)		

No. 5 vein

width ft.	Pb		Zn		Ag		Au	
	%	% ft.	%	% ft.	oz	oz ft.	¢	¢ ft.
15.5	.56	8.7	15.50	241.2	T.	0	.11	1.71
14.0	.64	8.9	8.95	125.3	.40	5.60	.21	2.94
14.0	.32	4.5	4.40	61.6	.38	5.32	.83	11.62
3) <u>43.5</u>		<u>22.1</u>		<u>428.1</u>		<u>10.92</u>		<u>16.27</u>
14.2 ft. Average	0.51%	Average	9.84%	Average	.25 oz	Average	.37¢	Average
					T.T.L. ✓	17 oz.		

No. 2 Vein

sample no	width	T. T. L. Silver oz/ton	Ag ft. ozs.
1321	2.5	15.0	37.5
1313	3.0	4.7	14.1
08	1.7	0.8	1.36
09	5.0	11.6	58.0
10	2.5	0.8	2.0
11	5.0	5.1	25.5
12	7.0	1.4	9.8
01	6.5	9.8	63.7
02	4.5	1.2	5.4
03	7.0	0.7	4.9
04	5.0	1.7	8.5
	<u>749.7</u>		<u>230.8</u>
	7.1		Average $\frac{4.64}{7.1}$ oz.

No. 3
blini

Sample no	width	T. T. L. silver ozs/don	ag ft. ozs
1318	8.0	1.2	9.6
1315 } 16 } 17 }	9.0 1.0 2.5	5.2 10.9 3.0	46.8 10.9 7.5
1314 } 1336 } no sample }	5.0 7.0 5.0	2.8 — 6.7	14.0 — 33.5
1336 } 05 } 06 } 07 }	3.0 2.5 5.3	1.0 2.9 0.4	3.0 7.25 2.12

4) 48.3
12.1

48.3) 134.7
2.79 ozs.
12.1 ft.

No. 4 vein

Sample no.

width

T. T. L.
Silver
oz. / lb.

Ag
ft. ozs.

- { 1324 }
- { 25 }
- 23
- 22
- 31
- 32
- 35

1.5
8.0
25.0
18.0
5.0
6.0
4.0

6) 67.5
11.25

13.4
1.6
0.6
0.8
2.8
2.3
2.8

20.1
12.8
15.0
14.4
14.0
13.8
11.2

67.5) 101.3 (1.5
67.5
33.80

Average
1.5 oz ✓
11.25

no. 5 vein

~~width ft.~~
Sample no.

Width, ft.

T. T. L.
Silver
oz/ton

Ag
ft. ozs.

1329

14.0

T.

—

1326

15.5

0.3

~~4.65~~
4.65

1333

14.0

0.2

2.8

43.5'

7.5

.5
.25

.17

.17 ✓

Summary of Assay Results, by Veins

width no. 1 vein	length	assay values				gross \$
		Pb%	Zn	Ag oz.	au \$	
7.0 ft.	50 ft.	1.6	5.9	F. T.T.L. 0.6	.41 F.T.L.	7.91 8.21
7.1	185 ft.	14.0	10.4	0.49 T.T.L. 4.64	.38 T.T.L.	25.02 27.10
12.1	235 ft.	7.44	6.75	0.45 T.T.L. 2.79	.29 F.T.L.	14.70 15.88
11.25	265 ft.	2.54	5.14	0.22 T.T.L. 1.5	.30 F.T.L.	8.09 8.73
14.2	290 ft. (3 timbers only)	0.51	9.84	0.25 T.T.L. 0.17	.37 F.T.L.	10.84 10.81

bleck
bleck

Pb @ 5¢
Zn @ 5¢
Ag @ 50¢
au @ 20.00