

88-I-01

P-I-01

SAMPLE#	No PPM	Cu PPM	Pb PPM	Zn PPM	Ag PPM	Mi PPM	Co PPM	Mn PPM	Fe %	As PPM	U PPM	Au PPM	Th PPM	Sr PPM	Cd PPM	Sb PPM	Bi PPM	V PPM	Ca %	P %	La PPM	Cr PPM	Mg %	Ba PPM	Ti %	B PPM	Al %	Na %	K %	V PPM	Au* PPM
29026	1	17	8	20	.3	105	18	450	3.61	2	5	ND	1	9	2	2	2	81	2.92	.004	2	192	3.13	1	.02	10	2.27	.02	.01	1	2
29027	1	24	12	27	.3	161	29	604	3.66	2	5	ND	1	13	1	2	2	74	5.00	.003	2	305	3.04	1	.02	10	2.60	.01	.01	1	1
29028	1	62	10	34	.2	270	28	506	4.01	2	5	ND	1	8	1	2	2	67	1.98	.004	2	621	5.66	1	.02	7	3.32	.01	.01	2	1
29029	1	27	10	36	.4	329	30	490	3.79	3	5	ND	1	9	1	4	3	51	2.50	.002	2	665	6.18	1	.01	5	3.24	.01	.01	1	1
29030	1	44	18	37	.4	320	31	552	3.98	2	5	ND	1	9	1	3	2	56	2.00	.002	2	671	6.35	1	.02	6	3.38	.01	.01	1	1
29031	1	23	10	9	.2	42	9	261	1.74	2	5	ND	1	9	1	2	2	47	2.38	.005	2	62	1.57	1	.02	6	1.12	.03	.01	1	1
29032	1	7	14	26	.3	187	22	422	3.60	2	5	ND	1	9	1	2	2	71	2.07	.004	2	278	3.87	1	.02	7	2.43	.02	.01	1	1
29033	1	28	10	32	.3	202	24	658	5.07	3	5	ND	1	17	1	2	2	111	3.97	.011	2	181	3.63	1	.01	12	2.68	.02	.01	1	1
29034	1	24	10	23	.2	111	19	577	4.10	2	5	ND	1	19	1	2	2	105	3.65	.005	2	147	2.82	3	.01	8	1.81	.03	.02	1	1
29035	1	86	9	43	.2	115	24	776	4.96	4	5	ND	1	24	1	3	2	112	3.94	.003	2	292	4.23	4	.01	8	2.29	.02	.02	1	1
29036	1	90	6	37	.3	155	23	824	4.89	9	5	ND	1	36	1	40	2	116	6.19	.003	2	192	4.59	4	.01	14	.65	.02	.01	7	1
29037	1	13	3	41	.4	246	29	876	5.03	15	5	ND	1	24	2	87	2	122	4.97	.002	2	278	4.99	6	.01	13	.49	.03	.02	27	1
29038	1	84	59	48	1.5	299	29	858	5.41	25	5	ND	1	24	1	100	4	92	4.23	.002	2	212	3.94	7	.01	8	.41	.02	.04	12	9

SAMPLE#	No PPM	Cu PPM	Pb PPM	Zn PPM	Ag PPM	Mi PPM	Co PPM	Mn PPM	Fe %	As PPM	U PPM	Au PPM	Th PPM	Sr PPM	Cd PPM	Sb PPM	Bi PPM	V PPM	Ca %	P %	La PPM	Cr PPM	Mg %	Ba PPM	Ti %	B PPM	Al %	Na %	K %	W SAMPLES	AU-100 NATIVE	AVG.	
29039	1	310	172	55	7.6	81	18	701	4.23	3979	5	ND	1	42	2	230	3	72	11.59	.002	2	81	4.10	6	.01	2	.31	.02	.04	10	400	.003	ND .003
29040	1	1341	2464	243	77.7	39	7	1645	7.83	49251	5	ND	1	41	12	1698	46	50	8.43	.002	2	23	3.13	7	.01	4	.23	.01	.04	15	430	.021	ND .021
29041	1	3784	2547	1201	124.0	10	5	2074	20.59	75120	5	2	1	8	46	1866	172	14	3.53	.001	2	1	1.63	2	.01	6	.11	.01	.01	12	450	.031	ND .031
29042	1	313	46	44	9.4	163	26	1418	4.88	9999	5	ND	1	30	1	164	4	69	5.50	.002	2	134	3.88	10	.01	8	.47	.01	.07	9	31	.07	9 31
29043	1	1161	167	167	20.4	168	26	1429	5.35	9999	5	ND	1	26	6	147	2	72	4.13	.002	2	124	3.86	11	.01	10	.45	.01	.07	3	115	.07	3 115
29044	1	320	22	38	2.3	158	24	976	4.97	803	5	ND	1	31	1	54	2	90	5.62	.002	2	155	3.82	9	.01	9	.50	.02	.05	15	126	.05	15 126
29045	1	38	7	47	.5	85	21	814	5.00	47	5	ND	1	27	1	14	2	131	3.64	.004	2	59	2.52	5	.01	11	.89	.03	.02	7	3	.02	7 3
29046	1	47	9	52	.2	84	22	663	4.76	10	5	ND	1	21	1	4	2	106	3.10	.005	2	69	2.61	3	.02	12	2.06	.02	.01	1	1	.01	1 1
29047	1	20	6	36	.3	109	22	565	4.17	5	5	ND	1	16	1	2	2	98	3.09	.005	2	129	2.33	3	.03	10	1.76	.03	.01	1	1	.01	1 1
29048	1	3	8	31	.2	224	25	518	4.13	2	5	ND	1	13	1	2	2	79	2.88	.004	2	242	3.46	2	.02	4	2.43	.03	.01	1	1	.01	1 1
29049	1	7	5	12	.2	60	12	298	2.39	3	5	ND	1	14	1	2	2	65	2.87	.004	2	112	1.94	4	.02	11	1.79	.08	.01	1	3	.01	1 3
29050	1	3	10	23	.2	289	26	402	3.60	41	5	ND	1	9	1	7	3	59	2.23	.003	2	342	4.06	1	.02	10	2.46	.02	.01	1	1	.01	1 1
29051	1	25	8	33	.2	96	22	522	4.21	24	5	ND	1	9	1	2	2	88	2.32	.004	2	349	4.80	1	.03	12	2.59	.02	.01	1	2	.01	1 2
29052	1	13	8	27	.2	85	19	385	3.56	15	5	ND	1	7	1	2	2	81	1.42	.006	2	141	2.67	1	.04	7	1.97	.03	.01	1	1	.01	1 1
29053	1	7	11	29	.1	127	22	505	4.37	3	5	ND	1	9	1	2	2	87	2.59	.004	2	182	3.34	1	.03	5	2.57	.02	.01	1	1	.01	1 1

0.013 g/b
12.5 feet

860594
Indata

88-I-01

88-I-02

2

29054	1	21	9	21	.2	124	22	491	4.48	2	5	WD	1	11	1	2	2	134	4.28	.012	2	190	2.76	1	.02	7	2.41	.02	.01	1	2
29055	1	21	9	14	.3	83	11	315	2.78	2	5	WD	1	9	1	2	2	33	2.21	.015	2	161	2.06	2	.03	11	1.65	.03	.02	1	1
29056	1	12	9	19	.1	41	15	518	4.36	2	5	WD	1	18	1	2	2	152	4.99	.008	2	48	2.34	1	.03	8	2.19	.02	.02	1	1
29057	1	3	10	23	.2	133	22	562	4.56	2	5	WD	1	13	1	2	2	129	3.96	.005	2	189	3.16	1	.03	6	2.62	.02	.02	1	1
29058	1	8	10	25	.1	101	21	621	4.84	2	5	WD	1	20	1	2	2	153	5.41	.010	2	135	3.36	1	.03	7	2.87	.02	.01	1	2
29059	1	4	8	14	.1	43	13	313	3.01	2	5	WD	1	10	1	2	2	76	1.77	.006	2	77	1.79	2	.03	5	1.69	.04	.01	1	1
29060	1	91	13	33	.1	85	18	455	3.70	3	5	WD	1	12	1	2	2	67	2.02	.005	2	206	2.82	2	.03	7	2.29	.03	.01	1	1
29061	1	32	9	30	.2	200	22	482	4.15	4	5	WD	1	12	1	3	2	81	1.99	.011	2	231	3.85	1	.03	7	2.78	.02	.01	1	1
29062	1	18	15	33	.2	274	28	394	4.16	2	5	WD	1	9	1	2	3	77	.53	.003	2	523	4.85	3	.01	8	3.01	.02	.01	1	1
29063	1	27	10	23	.1	120	20	388	4.25	6	5	WD	1	12	1	3	2	117	1.58	.005	2	206	2.88	2	.03	7	2.32	.03	.01	1	1
29064	1	34	12	22	.1	99	16	432	3.34	2	5	WD	1	11	1	2	2	83	2.47	.008	2	158	2.29	2	.04	7	1.96	.02	.01	1	1
29065	1	53	2	19	.2	46	14	625	3.25	2	5	WD	1	33	1	2	2	78	5.39	.006	2	37	1.91	3	.01	8	1.00	.03	.01	2	1
29066	1	10	6	23	.1	116	18	443	4.01	2	5	WD	1	12	1	3	2	104	2.54	.005	2	169	2.45	2	.01	3	2.13	.03	.01	1	1

88-I-02

29057	1	26	18	36	.2	97	21	502	5.04	237	5	WD	1	15	1	10	2	127	2.22	.005	2	170	2.71	2	.02	2	2.48	.04	.01	2	580	.001	WD	.001
29068	1	9	8	38	.1	154	32	778	6.62	54	5	WD	1	18	1	5	2	146	2.29	.009	2	340	3.73	3	.01	7	2.78	.02	.01	4	470	.001	WD	.001
29069	1	8	2	27	.1	97	30	574	5.69	36	5	WD	1	9	1	11	2	170	.53	.002	2	133	1.17	3	.01	7	.92	.02	.03	3	470	.001	WD	.001
29070	1	7	7	27	.1	166	26	785	5.10	36	5	WD	1	22	1	7	2	138	2.89	.001	2	184	2.46	5	.01	8	1.00	.02	.05	4	470	.001	WD	.001
29071	1	70	2	28	.1	276	38	775	5.75	45	5	WD	1	27	1	9	2	100	3.47	.001	2	204	2.20	14	.01	6	.64	.01	.11	4	480	.001	WD	.001
29072	1	24	3	28	.1	84	22	692	5.43	58	5	WD	1	35	1	38	2	94	4.25	.002	2	93	2.51	14	.01	5	.60	.02	.12	3	450	.001	WD	.001
29073	1	810	531	267	25.8	124	26	774	4.66	8821	5	WD	1	895	7	403	33	60	5.45	.102	2	103	2.40	87	.01	9	1.00	.01	.07	10	410	.009	WD	.009
29074	1	99	13	36	.4	125	25	757	4.90	264	5	WD	1	51	1	61	2	112	6.19	.003	2	160	3.53	8	.01	5	.66	.01	.03	8	450	.001	WD	.001
29075	1	109	20	50	.4	188	25	911	5.29	223	5	WD	1	21	1	100	3	99	4.59	.002	2	171	3.26	9	.01	4	.77	.01	.06	6	440	.002	WD	.002
29076	1	2096	378	366	62.9	69	13	1567	18.68	73400	5	WD	1	11	13	603	121	35	2.90	.002	2	12	1.71	5	.01	2	.36	.01	.03	2	450	.019	WD	.019
29077	1	815	718	256	47.8	55	13	1912	4.84	4945	5	WD	1	22	13	822	6	75	6.64	.002	2	50	2.71	10	.01	2	.40	.02	.06	8	620	.004	WD	.004
29078	1	62	11	24	.1	116	22	615	5.40	57	5	WD	1	20	1	11	2	158	3.91	.004	2	164	3.19	3	.01	2	2.25	.02	.01	1	560	.001	WD	.001
29079	1	168	9	23	.1	105	22	568	5.14	24	5	WD	1	17	1	5	2	172	4.44	.006	2	190	3.20	2	.01	2	2.58	.03	.01	1	550	.001	WD	.001
29080	1	208	4	27	.1	145	20	412	4.33	24	5	WD	1	9	1	2	2	119	2.10	.011	2	122	3.06	1	.03	2	2.65	.04	.01	1	560	.001	WD	.001
29081	1	22	2	34	.1	39	17	459	3.89	12	5	WD	1	11	1	2	2	99	2.24	.004	2	75	2.36	2	.04	6	2.29	.06	.01	1	580	.001	WD	.001

8.2ft
88

88-I-03

29082	1	25	8	16	.1	14	10	367	3.38	4	5	WD	1	13	1	2	3	84	3.56	.018	2	48	1.46	2	.01	3	1.71	.03	.01	1	2
29083	1	25	4	13	.1	17	7	294	2.37	3	5	WD	1	11	1	2	2	50	2.86	.016	2	36	1.39	3	.02	6	1.35	.04	.02	1	1
29084	1	18	8	33	.2	231	29	830	4.56	111	5	WD	1	29	1	2	3	105	8.41	.002	2	629	4.89	1	.01	2	3.40	.01	.01	1	1
29085	1	4	16	27	.1	199	30	637	5.05	57	5	WD	1	21	1	2	2	136	4.61	.004	2	611	4.98	1	.01	2	3.62	.02	.01	1	1
29086	1	33	6	20	.1	53	17	419	3.63	15	5	WD	1	20	1	2	2	91	3.71	.003	2	103	2.66	3	.03	3	2.58	.06	.01	1	1
29087	1	87	8	13	.1	35	13	259	2.94	58	5	WD	1	6	1	2	2	84	1.74	.006	2	44	1.62	2	.02	2	1.57	.07	.01	1	1

88-I-02

88-I-03

88-I-03

	PPM	PPK	PPH	PPM	PPK	PPH	PPM	PPK	PPH	%	PPM	PPK	PPH	PPM	PPK	PPH	%	%	PPM	PPK	PPH	%	%	PPM	PPK	PPH	PPM	PPK	PPH		
29301	1	11	2	8	.1	75	11	232	1.99	2	5	WD	1	11	1	2	2	44	.99	.009	2	126	1.59	3	.02	2	1.35	.05	.01	1	1
29302	1	1	3	11	.1	119	16	301	3.05	2	5	WD	1	9	1	2	2	49	.50	.008	2	228	2.37	1	.01	2	1.83	.04	.01	1	1
29303	1	1	9	18	.1	155	26	835	4.71	5	5	WD	1	51	1	2	2	106	3.36	.008	2	192	3.48	5	.01	2	1.88	.02	.01	1	2
29304	1	1	2	15	.1	130	24	731	4.39	4	5	WD	1	46	1	2	2	119	4.35	.008	2	221	3.89	4	.01	7	1.68	.02	.01	1	1
29305	1	1	8	16	.1	117	25	725	4.80	4	5	WD	1	37	1	2	7	121	3.77	.006	2	179	3.66	7	.01	3	1.71	.02	.01	1	1
29306	1	1	6	17	.1	151	27	901	4.59	22	5	WD	1	63	1	3	3	105	5.84	.004	2	171	3.91	3	.01	10	.54	.02	.01	17	1
29307	1	17	9	16	.5	59	17	877	3.98	29	5	WD	1	52	1	2	2	98	6.04	.001	2	43	3.42	4	.01	9	.39	.02	.03	7	1
29308	1	24	6	28	.2	64	19	774	4.80	44	5	WD	1	41	1	3	2	98	5.23	.003	2	71	2.99	11	.01	3	.78	.02	.04	3	5
29309	1	9	12	25	.1	57	19	809	5.25	33	5	WD	1	28	1	3	2	123	4.33	.004	2	84	3.26	8	.01	8	1.95	.02	.01	1	1
29310	1	1	4	19	.1	124	20	695	4.33	5	5	WD	1	42	1	4	2	103	3.54	.006	2	153	3.42	7	.01	2	1.97	.05	.01	1	1
29311	1	18	5	21	.1	92	21	717	4.72	10	5	WD	1	27	1	4	2	110	3.27	.005	2	125	3.10	9	.01	2	2.07	.03	.02	1	3
29312	1	27	2	10	.1	24	11	452	3.94	4	5	WD	1	17	1	5	2	47	2.34	.016	2	54	1.56	9	.01	5	1.08	.03	.03	1	1
29313	1	14	2	12	.4	22	10	756	3.28	127	5	WD	1	16	1	4	2	44	2.84	.015	2	49	1.40	14	.01	12	1.32	.02	.06	1	7
29314	1	30	10	11	.1	33	16	727	3.81	221	5	WD	1	23	1	8	2	101	4.78	.009	2	59	1.81	6	.01	6	1.69	.03	.04	1	12
29315	1	11	6	39	.1	190	31	842	4.88	18	5	WD	1	25	1	7	5	106	4.23	.005	2	478	5.14	3	.01	4	3.24	.01	.01	1	19
29316	1	21	2	11	.1	48	14	379	3.26	6	5	WD	1	12	1	5	2	99	2.44	.011	2	92	1.57	5	.02	5	1.39	.03	.01	1	2
29317	1	19	2	14	.1	56	17	449	3.52	6	5	WD	1	20	1	4	2	78	2.34	.009	2	70	2.31	4	.01	5	1.33	.03	.02	1	24
29318	1	1	5	21	.1	218	19	366	3.13	4	5	WD	1	32	1	2	2	41	2.14	.013	2	312	3.74	6	.01	6	2.56	.08	.02	3	20
29319	1	33	5	25	.1	226	26	720	4.95	134	5	WD	1	56	1	6	2	65	5.30	.002	2	188	3.73	4	.01	2	.73	.03	.01	8	26
29320	1	175	140	31	2.8	53	17	828	4.83	192	5	WD	1	70	1	2	7	129	5.69	.003	2	111	3.86	6	.01	5	.37	.02	.03	11	8
29321	1	28	5	19	.1	77	22	761	5.08	25	5	WD	1	23	1	3	2	157	2.99	.001	2	98	3.19	3	.01	4	.35	.02	.01	7	3
29322	1	26	6	33	.2	440	33	669	5.42	12	5	WD	1	21	1	2	2	83	3.02	.003	2	326	5.73	5	.01	6	2.58	.01	.01	4	4
29323	1	2	5	28	.1	445	33	645	4.80	13	5	WD	1	25	1	2	2	73	2.94	.004	2	300	5.72	12	.01	4	3.03	.02	.03	1	1
29324	1	114	8	25	.1	109	24	687	5.48	15	5	WD	1	31	1	4	2	142	2.57	.004	2	98	3.28	11	.01	5	1.14	.03	.02	5	5
29325	1	34	7	23	.1	187	22	592	4.37	4	5	WD	1	18	1	2	3	95	3.67	.004	2	220	3.98	3	.01	10	2.39	.02	.01	1	19
29326	1	55	2	16	.2	102	18	744	3.73	12	5	WD	1	42	1	10	6	83	4.96	.004	2	130	3.13	6	.01	7	.89	.02	.01	9	57
29327	1	180	7	22	.3	104	22	697	4.62	1503	5	WD	1	35	1	22	5	88	5.60	.004	2	140	3.59	6	.01	5	.54	.02	.01	48	320
29328	1	38	2	19	.1	38	18	587	4.55	13	5	WD	1	19	1	2	2	120	2.16	.008	2	28	2.55	4	.01	7	1.17	.03	.01	5	13
29329	1	73	2	24	.1	116	23	686	4.49	9	5	WD	1	33	1	3	3	98	4.26	.004	2	136	3.33	7	.01	8	1.27	.03	.01	12	17
29330	1	64	6	23	.2	68	22	690	5.14	20	5	WD	1	22	1	18	2	155	3.85	.009	2	142	3.44	4	.01	2	2.14	.02	.02	3	16
29331	1	33	3	26	.1	156	20	525	3.92	8	5	WD	1	9	1	3	2	100	2.63	.005	2	287	3.59	3	.01	4	2.76	.03	.01	1	33
29332	1	5	7	36	.1	198	22	476	4.23	2	5	WD	1	7	1	3	2	31	1.48	.004	2	301	3.54	2	.02	2	2.64	.02	.01	1	13
29333	1	50	4	25	.2	144	18	391	3.85	4	6	WD	1	7	1	4	2	90	1.39	.007	2	145	2.73	1	.02	2	2.14	.02	.01	1	4
29334	1	9	7	31	.1	614	37	522	4.50	72	5	WD	1	9	1	3	2	89	2.93	.003	2	285	4.39	1	.01	4	3.03	.01	.01	1	6
29335	1	28	2	21	.1	56	17	786	4.51	2	6	WD	1	30	1	2	2	206	4.43	.005	2	67	3.06	2	.01	4	1.75	.01	.01	1	2
29336	.1	137	4	26	.2	91	35	613	6.68	16	5	WD	1	36	1	10	2	96	4.93	.012	2	115	3.67	4	.01	4	1.60	.01	.02	1	6
29337	1	17	7	18	.2	79	20	516	4.85	2	5	WD	1	27	1	2	4	138	3.58	.003	2	165	3.48	4	.01	6	2.05	.02	.01	2	9
29338	1	37	5	14	.2	41	18	538	4.39	2	5	WD	1	22	1	5	2	144	2.86	.005	2	37	2.59	2	.01	7	1.52	.02	.01	1	7
29339	1	35	11	18	.1	60	15	563	4.54	2	5	WD	1	20	1	2	2	123	2.74	.004	2	54	2.81	2	.01	9	1.63	.02	.01	1	3
29340	1	9	7	24	.2	214	26	738	5.05	41	5	WD	1	42	1	2	2	117	4.67	.002	2	256	4.40	4	.01	10	1.95	.01	.01	1	5
29341	1	3	13	17	.2	53	16	555	4.16	2	5	WD	1	27	1	2	2	134	3.85	.003	2	80	3.23	3	.01	6	2.16	.02	.01	1	1
29342	1	4	5	21	.1	155	21	458	4.77	2	5	WD	1	14	1	2	2	116	2.41	.009	2	161	3.44	3	.01	7	2.36	.02	.01	1	2
29343	1	2	6	12	.1	75	13	286	2.88	2	5	WD	1	14	1	2	2	87	2.17	.005	2	98	2.15	5	.01	7	1.86	.05	.01	1	1
29344	1	16	7	19	.1	163	23	410	4.57	9	5	WD	1	11	1	2	2	104	2.71	.012	2	197	2.99	3	.02	6	2.60	.02	.01	1	1
29345	1	82	8	27	.2	45	17	547	4.21	2	5	WD	1	22	1	2	2	112	4.34	.018	2	82	2.48	4	.12	5	2.65	.06	.01	1	4
29346	1	1	4	16	.1	124	17	258	2.50	13	5	WD	1	6	1	2	2	45	1.89	.004	2	241	2.47	1	.01	3	1.85	.03	.01	1	2
29347	1	36	2	14	.2	95	19	298	2.75	10	5	WD	1	7	1	3	2	64	1.85	.007	2	118	1.79	2	.02	6	1.55	.04	.01	1	27
29348	1	7	3	8	.1	27	11	140	2.57	2	5	WD	1	7	1	6	2	92	.80	.010	2	37	1.02	1	.03	3	1.10	.05	.01	1	1
29349	1	12	4	7	.2	18	10	157	2.93	2	5	WD	1	3	1	6	2	116	1.86	.014	2	14	.80	1	.04	8	.98	.04	.01	1	1
29350	1	32	4	12	.1	28	14	233	3.74	2	5	WD	1	4	1	3	2	141	.99	.009	2	19	1.40	1	.04	2	1.53	.04	.01	1	1

0.003 oz/ton
16.4 feet

88-I-03

88-I-04

29351	1	7	2	9	.2	110	12	107	1.59	3	5	ND	1	5	1	3	2	47	.41	.006	2	114	1.66	5	.02	3	1.24	.04	.01	1	1
29352	1	56	6	22	.1	164	19	263	2.75	3	5	ND	1	5	1	2	2	43	.66	.004	2	262	2.82	3	.02	2	2.04	.03	.01	1	1
29353	1	3	8	15	.1	251	20	202	2.95	2	5	ND	1	8	1	2	2	36	.50	.004	2	196	3.53	5	.01	10	2.55	.05	.01	1	1
29354	1	82	11	28	.2	57	20	534	4.63	2	5	ND	1	10	1	2	2	129	1.07	.012	2	90	2.64	7	.02	6	2.41	.03	.03	1	1
29355	1	86	7	30	.1	4	16	501	5.67	2	5	ND	1	14	1	2	2	108	1.40	.027	2	10	1.37	5	.04	5	2.26	.03	.01	1	36

88 I-04

88-I-50

	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	PPM	PPM		
29356	1	10	4	9	.1	31	9	249	1.91	2	5	ND	1	7	1	2	2	56	1.25	.007	2	54	1.04	6	.02	2	1.68	.04	.01	1	1
29357	1	16	3	14	.1	91	16	259	2.71	11	5	ND	1	8	1	2	2	54	.75	.004	2	110	2.13	6	.01	2	1.85	.04	.01	1	1
29358	1	119	7	20	.2	38	15	329	3.00	2	5	ND	1	9	1	2	2	69	1.19	.006	2	99	1.65	4	.04	2	1.74	.04	.01	1	4
29359	1	57	2	32	.1	71	23	724	4.71	2	6	ND	1	46	2	2	2	111	4.22	.005	2	129	3.04	17	.01	7	1.45	.04	.01	5	2
29360	1	24	6	29	.3	108	26	795	5.51	47	5	ND	1	54	1	4	2	111	5.49	.002	2	132	3.68	14	.01	7	.42	.02	.02	7	1
29361	1	16	4	27	.3	246	24	1041	5.29	197	5	ND	1	53	1	31	2	120	7.44	.002	2	107	4.24	7	.01	2	.37	.02	.01	5	1
29362	1	43	20	30	1.2	141	21	1132	5.55	384	5	ND	1	42	1	45	2	110	5.12	.003	2	149	3.60	14	.01	2	.82	.02	.06	2	16
29363	1	30	24	55	1.5	193	28	1749	5.17	485	5	ND	1	47	2	25	2	95	4.97	.002	2	301	4.79	11	.01	2	1.72	.01	.05	1	23
29364	1	15	9	39	.1	241	29	1089	5.37	98	5	ND	1	50	1	6	2	104	5.11	.003	2	335	5.19	10	.01	2	2.17	.01	.03	1	28
29365	1	19	7	24	.2	253	26	412	3.62	13	5	ND	1	20	1	2	2	62	2.03	.005	2	289	3.91	5	.01	2	2.57	.04	.01	1	5
29366	1	12	3	12	.1	60	14	308	2.60	3	5	ND	1	7	1	4	2	63	1.46	.005	2	115	1.81	3	.01	8	1.43	.03	.01	1	4
29367	1	78	6	20	.2	43	19	595	4.94	12	5	ND	1	15	1	3	2	153	2.59	.007	2	52	2.12	5	.01	2	1.47	.03	.01	2	21
29368	1	28	4	28	.1	159	21	804	4.95	109	5	ND	1	55	1	6	2	91	9.76	.002	2	158	4.05	4	.01	2	.43	.02	.01	10	5
29369	1	2	6	38	.1	213	32	871	5.83	59	5	ND	1	64	1	6	2	110	4.51	.001	2	170	3.85	7	.01	4	.48	.02	.01	27	1
29370	1	4	6	37	.1	262	31	960	5.74	62	5	ND	1	49	1	6	2	75	8.43	.001	2	133	4.93	6	.01	2	.42	.02	.01	23	1
29371	1	14	10	34	.1	147	25	747	4.94	11	5	ND	1	46	1	6	2	86	4.94	.004	2	139	3.08	14	.01	2	.96	.02	.01	8	1
29372	1	200	4	21	.2	30	22	606	6.03	96	5	ND	1	24	1	6	2	112	3.57	.015	2	41	2.51	7	.01	2	.55	.02	.01	13	5
29373	1	28	5	41	.1	280	35	1099	6.35	40	5	ND	1	40	1	3	2	103	6.59	.003	2	181	4.45	10	.01	5	.42	.02	.01	21	1
29374	1	21	5	30	.1	155	24	699	4.69	4	5	ND	1	37	1	2	2	85	4.93	.004	2	146	3.76	42	.01	2	1.10	.02	.01	9	4
29375	1	22	3	23	.2	112	19	467	3.56	8	5	ND	1	17	1	2	2	68	3.10	.007	2	181	2.80	13	.01	10	1.77	.04	.02	1	13
29376	1	234	11	21	2.3	46	8	1001	4.38	3637	5	ND	1	13	1	21	3	48	3.16	.001	2	53	2.14	17	.01	2	.31	.01	.06	4	70
29377	1	147	4	28	.8	65	16	767	4.88	263	5	ND	1	25	2	6	2	70	4.42	.001	2	84	3.18	18	.01	5	.43	.01	.08	14	9
29378	1	111	7	11	7	84	28	950	5.19	97	5	ND	1	14	1	8	7	110	1.15	.007	7	119	1.04	18	.01	1	.71	.01	.08	7	25
29379	1	481	17	13	14	49	11	141	1.14	1110	5	ND	1	14	1	14	14	44	1.41	.007	7	17	1.47	15	.01	7	.71	.41	.41	1	27
29380	1	1848	97	85	10	67	15	918	8.48	8077	8	ND	1	16	6	117	100	14	1.11	.001	7	1	1.95	9	.01	7	.11	.41	.41	14	318
29381	1	990	43	56	13.0	116	16	591	9.04	832	6	ND	3	25	4	22	82	45	1.92	.001	2	79	1.82	9	.01	5	.37	.01	.05	3	52
29382	1	55	9	39	.6	169	24	777	5.13	110	5	ND	1	51	2	3	2	93	4.98	.002	2	256	3.77	9	.01	5	1.33	.01	.03	2	36
29383	1	36	5	20	.1	56	15	632	3.78	18	5	ND	1	51	1	4	2	87	5.24	.002	2	54	3.21	4	.01	7	.36	.02	.01	3	7
29384	1	117	2	25	.1	120	26	584	5.32	14	5	ND	1	31	1	2	2	100	4.29	.003	2	87	2.63	7	.01	6	.84	.02	.03	2	21
29385	1	152	3	14	.1	28	20	389	3.86	11	5	ND	1	16	1	2	2	78	2.94	.006	2	27	1.95	5	.01	5	1.23	.02	.03	1	524
29386	1	156	7	25	.1	53	21	453	5.03	14	5	ND	1	30	1	3	2	141	2.14	.011	2	65	2.46	4	.01	4	1.93	.02	.01	1	107
29387	1	114	3	26	.3	65	22	727	4.72	6	5	ND	1	19	2	2	2	106	4.64	.004	2	61	3.12	4	.01	6	1.42	.02	.01	2	36
29388/29389	1	85	5	24	.2	105	22	754	4.24	9	5	ND	1	37	2	2	2	85	5.19	.003	2	175	3.16	6	.01	7	1.58	.01	.03	2	1
29390	1	38	3	17	.2	42	16	528	4.27	8	5	ND	1	25	2	3	2	97	4.28	.003	2	50	2.61	9	.01	10	.90	.02	.09	2	28
29391	1	14	18	31	.1	225	25	676	4.22	95	5	ND	1	25	1	2	2	93	3.73	.003	2	162	3.07	10	.01	9	1.98	.02	.12	1	1

0.013 oz/ton
3.28 ft.

88-I-05

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Hg	Co	Mn	Pb	As	U	Au	Yb	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Yt	B	Al	W	K	V	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
29392	1	7	2	33	.2	57	16	488	3.81	4	5	ND	1	12	1	3	3	82	2.78	.003	2	170	2.33	5	.01	9	1.89	.04	.03	1	8
29393	1	40	6	38	.2	103	26	702	5.31	95	5	ND	1	18	1	3	2	107	4.14	.002	2	212	2.95	7	.01	9	2.26	.02	.08	1	1
29394	1	171	8	20	.5	45	13	1177	6.80	391	5	ND	1	49	1	9	12	31	11.19	.002	2	44	3.20	6	.01	9	.58	.01	.07	2	1
29395	1	22	8	46	.2	237	35	839	5.80	77	9	ND	2	14	1	2	2	133	4.29	.008	2	529	3.86	6	.01	9	3.19	.02	.09	2	9
29396	1	47	4	19	.1	54	21	389	3.42	26	5	ND	2	8	1	9	2	108	1.71	.006	2	84	1.82	4	.02	11	1.60	.03	.06	1	193
29397	1	12	2	22	.1	93	28	620	4.12	37	5	ND	1	14	1	6	2	108	4.44	.005	2	104	2.39	6	.01	6	1.99	.02	.10	1	4
29398	1	16	8	18	.1	33	14	284	4.28	8	5	ND	2	9	1	6	2	101	1.62	.015	2	58	1.45	4	.05	7	2.80	.05	.04	1	6
29399	1	16	5	16	.2	100	20	329	2.95	2	5	ND	2	6	1	2	4	75	1.95	.004	2	140	1.82	2	.02	9	1.50	.04	.03	1	26
29400	1	1	4	31	.1	229	22	320	2.95	7	5	ND	1	5	1	2	2	45	1.94	.013	2	420	3.89	1	.01	6	2.52	.02	.01	1	3

0.006 oz/ton
3.3 ft

88-I-05

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Hg	Co	Mn	Fe	As	U	Au	Tb	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Ti	B	Al	Na	K	V	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
29088	1	18	9	32	.2	197	17	250	2.49	2	5	ND	1	9	1	2	2	34	.73	.007	2	275	3.12	6	.02	4	2.36	.06	.01	1	1
29089	1	13	5	16	.1	82	10	232	2.06	2	5	ND	2	17	1	2	2	34	1.67	.014	2	72	1.50	25	.03	7	1.57	.02	.04	1	1
29090	1	46	4	15	.1	39	10	230	2.45	2	5	ND	1	14	1	2	2	39	1.00	.015	2	58	1.15	4	.04	7	1.43	.04	.01	1	1
29091	1	72	4	14	.2	45	9	308	1.98	2	5	ND	1	26	1	2	2	51	1.88	.014	2	47	1.25	8	.04	8	1.53	.06	.03	1	1
29092	1	86	4	42	.1	50	20	524	3.55	2	5	ND	1	25	1	2	2	76	1.89	.004	2	134	2.81	4	.02	6	2.52	.01	.01	1	1
29093	1	88	8	60	.1	242	33	1016	5.78	36	5	ND	1	30	1	2	2	136	4.44	.005	2	476	6.66	4	.01	6	4.01	.02	.03	1	1
29094	1	180	4	32	.2	125	20	734	4.55	9	6	ND	1	34	1	2	2	188	5.35	.014	2	197	4.83	3	.01	7	2.39	.02	.04	1	2
29095	1	109	7	42	.1	82	24	903	4.94	5	5	ND	1	32	1	2	3	140	4.62	.006	2	184	4.68	4	.01	7	2.72	.01	.03	1	1
29096	1	8	4	32	.1	158	23	835	4.66	7	5	ND	1	30	1	2	3	125	4.76	.005	2	219	4.52	3	.01	8	2.58	.01	.02	1	2
29097	1	8	8	42	.1	255	31	881	5.27	8	5	ND	1	31	1	2	2	120	4.64	.004	2	374	5.96	3	.01	7	3.24	.02	.01	1	1
29098	1	2	4	39	.2	230	30	954	5.38	70	6	ND	1	35	1	5	2	120	5.51	.004	2	317	4.70	3	.01	9	2.12	.01	.01	2	1
29099	1	138	64	89	3.7	164	21	917	5.17	1400	7	ND	1	77	3	62	10	74	8.10	.004	2	164	4.93	3	.01	6	.53	.02	.01	2	100 - 0.004 oz/ft 1.6 ft
29100	1	7	4	32	.1	100	21	663	5.08	2	5	ND	1	28	1	6	2	136	3.45	.005	2	144	2.85	3	.01	10	1.24	.01	.01	1	1
29101	1	39	8	43	.2	153	26	788	5.39	148	5	ND	1	33	1	3	2	138	4.56	.006	2	249	4.15	4	.01	9	2.50	.01	.04	1	3
29102	1	48	5	51	.1	298	34	919	5.19	4	5	ND	1	40	1	2	2	121	5.58	.002	2	477	6.12	3	.01	10	3.41	.01	.02	1	4
29103	1	29	6	49	.3	269	41	877	6.26	28	5	ND	1	39	1	2	2	113	5.47	.002	2	389	5.32	3	.01	8	3.28	.01	.04	2	38
29104	1	27	6	31	.2	126	21	981	4.32	18	5	ND	1	47	1	3	2	84	7.19	.004	2	227	4.43	4	.01	13	2.89	.01	.05	2	36
29105	1	85	4	28	.1	98	19	758	4.56	7	5	ND	1	21	1	2	2	94	4.14	.007	2	181	3.48	3	.01	9	2.41	.01	.05	1	14
29106	1	13	4	25	.1	26	14	547	4.45	2	5	ND	1	25	1	2	2	107	3.91	.013	2	39	2.87	2	.01	8	2.87	.02	.03	1	1
29107	1	43	10	39	.8	118	24	814	5.35	212	5	ND	1	31	1	10	5	119	4.35	.005	2	248	4.50	7	.01	7	3.88	.01	.05	1	28
29108	1	166	12	44	1.8	119	23	845	6.84	71	5	ND	1	16	1	11	2	117	3.12	.007	2	238	4.89	9	.01	10	3.76	.01	.08	1	13
29109	1	147	6	41	.5	86	24	660	5.30	19	5	ND	1	18	1	21	2	128	3.26	.008	2	160	4.41	5	.01	7	3.31	.01	.04	1	4
29110	1	16	7	44	.1	173	27	747	5.51	2	5	ND	1	26	1	2	2	149	3.49	.007	2	194	4.17	4	.01	6	2.82	.01	.02	1	1
29111	1	44	5	43	.1	183	22	748	4.58	11	5	ND	1	36	1	8	2	114	5.77	.004	2	135	3.99	3	.01	8	.86	.01	.01	5	2
29112	1	92	5	48	.1	73	28	749	4.75	18	5	ES	2	28	1	2	3	128	4.62	.005	2	118	3.98	2	.01	5	1.58	.01	.02	2	1
29113	1	390	118	81	11.7	76	19	810	5.99	1000	5	ND	1	36	3	218	17	117	6.89	.003	2	188	4.81	2	.01	4	.47	.01	.01	1	100 - 0.003 oz/ft 1.3 ft
29114	1	19	7	46	.2	15	22	764	6.93	24	5	ND	1	21	1	5	2	197	1.78	.024	2	18	2.38	5	.01	11	1.85	.01	.02	1	1
29115	1	52	8	48	.2	20	20	714	5.38	62	5	ND	1	28	1	6	2	135	3.51	.019	2	21	2.55	5	.01	9	2.59	.02	.02	1	3
29116	1	38	6	59	.1	51	22	829	5.35	18	5	ND	1	23	1	3	2	152	3.68	.018	2	88	3.86	4	.01	5	2.29	.02	.02	1	1
29117	1	28	5	45	.1	52	19	713	4.51	20	5	ND	1	33	1	2	2	117	5.18	.004	2	91	3.22	4	.01	8	.51	.02	.01	2	1
29118	1	44	5	43	.1	45	19	594	4.85	6	5	ND	1	18	1	2	3	118	2.73	.007	2	118	2.66	3	.03	7	2.36	.02	.01	1	1
29119	1	18	5	32	.1	158	25	636	4.25	33	5	ND	1	15	1	2	2	121	3.23	.005	2	358	4.22	1	.01	4	3.17	.01	.02	1	1
29120	1	64	4	34	.1	66	21	695	4.44	212	5	ND	1	16	1	2	2	118	3.95	.018	2	121	2.58	2	.01	7	2.76	.03	.05	1	9
29121	1	56	5	43	.1	55	22	765	5.01	26	5	ND	1	22	1	2	2	201	5.01	.009	2	84	3.82	1	.01	4	3.82	.02	.01	1	1
29122	1	626	4	54	.1	39	21	716	4.78	57	5	ND	1	20	1	2	2	142	3.83	.018	2	56	2.66	1	.05	3	2.55	.02	.01	1	6
29123	1	9	4	37	.1	134	22	494	4.81	4	5	ND	1	16	1	2	2	91	2.95	.006	2	381	4.20	1	.03	3	3.89	.03	.01	1	1
29124	1	14	10	39	.1	173	27	784	4.88	5	5	ND	1	13	1	2	2	141	4.17	.008	2	408	4.63	1	.04	2	3.57	.01	.01	2	2
29125	1	7	5	12	.1	36	11	331	2.58	3	5	ND	1	8	1	3	2	93	2.52	.012	2	68	1.46	1	.04	2	1.21	.03	.01	2	1
29126	1	84	8	36	.1	115	21	549	3.98	5	5	ND	1	12	1	3	2	95	2.62	.008	2	258	3.70	1	.04	3	2.68	.02	.01	2	1
STD C/AU-R	17	59	41	133	6.6	68	28	1851	4.88	41	17	8	36	47	17	16	19	57	.46	.007	48	57	.92	176	.86	34	2.81	.86	.14	13	518

68-I-06

1.06

88-I-06

EASTFIELD RESOURCES LTD. FILE # 88-2935

T
over 7

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Tl	Sr	Cd	Sb	Bi	V	Ca	F	La	Cr	Mg	Ba	Ti	B	Al	Na	K	V	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
29127	1	13	8	21	.1	121	20	526	4.48	12	5	ND	1	14	1	3	2	122	2.10	.009	2	136	3.11	3	.03	2	2.99	.31	.02	2	1
29128	1	12	8	13	.2	28	6	294	1.92	9	5	ND	1	15	1	2	2	33	2.64	.014	2	27	1.03	6	.03	3	1.17	.02	.04	1	1
29129	1	1	8	12	.2	186	23	546	3.77	15	5	ND	1	15	1	3	2	80	2.27	.006	2	300	4.53	2	.02	2	3.38	.02	.02	1	1
29130	1	56	4	21	.3	66	14	379	3.27	5	5	ND	1	15	1	2	3	58	1.90	.012	2	95	2.29	2	.04	5	2.06	.01	.01	1	1
29131	1	19	7	19	.2	42	12	534	3.26	5	6	ND	1	10	1	2	2	88	4.99	.018	2	66	2.27	1	.05	6	2.06	.05	.01	1	1
29132	1	7	6	10	.1	9	6	239	2.78	3	5	ND	1	9	1	2	2	26	1.12	.017	2	4	1.08	2	.04	11	1.26	.01	.01	1	2
29133	1	18	11	25	.1	77	20	567	4.52	21	5	ND	1	19	1	2	2	130	2.99	.007	2	157	3.28	1	.03	3	2.92	.05	.01	1	1
29134	1	38	7	12	.1	3	5	208	2.31	2	5	ND	1	11	1	2	2	9	1.19	.019	2	5	.50	3	.05	6	1.17	.01	.03	1	1
29135	1	103	7	40	.1	90	22	552	3.58	2	5	ND	1	6	1	2	2	66	1.37	.005	2	421	3.97	1	.03	3	2.99	.01	.02	1	1
29136	1	23	5	10	.1	8	4	216	2.55	2	5	ND	1	12	1	2	2	10	1.44	.016	2	21	.61	4	.05	7	1.08	.05	.03	1	1
29137	1	123	8	33	.1	132	22	487	3.71	2	5	ND	1	9	1	2	2	65	1.32	.004	2	352	4.22	2	.02	6	3.31	.02	.02	1	1
29138	1	16	6	22	.2	111	20	401	3.44	3	5	ND	1	14	1	2	2	59	2.02	.005	2	206	3.31	3	.02	8	2.63	.01	.02	2	1
29139	1	6613	18	167	8.6	33	59	115	25.33	198	5	ND	3	3	5	3	297	13	.33	.001	2	11	.46	2	.01	4	.52	.01	.01	6	33
29140	1	220	10	36	.2	64	18	545	5.45	21	5	ND	1	21	1	2	9	86	2.95	.007	2	112	3.35	18	.01	4	3.52	.01	.07	1	2
29141	1	41	9	18	.1	132	20	474	3.58	9	5	ND	1	16	1	2	3	82	2.09	.005	2	265	3.73	6	.02	5	2.98	.02	.02	1	1
29142	1	4	6	9	.2	107	15	239	2.41	2	5	ND	1	7	1	2	3	38	.63	.014	2	245	2.51	2	.03	5	1.87	.01	.02	1	2
29143	1	15	4	7	.1	9	4	153	1.92	3	5	ND	1	10	1	3	4	10	.66	.017	2	5	.68	3	.05	4	.95	.07	.02	1	1
29144	1	1	6	6	.1	228	21	303	3.14	6	5	ND	1	6	1	2	2	48	1.36	.007	2	281	3.98	1	.02	4	2.94	.06	.01	1	1
29145	1	2	7	6	.1	193	17	260	2.86	7	5	ND	1	13	1	3	2	52	.88	.008	2	157	3.30	3	.03	2	2.75	.06	.02	1	1
29146	1	6	6	14	.2	13	7	263	2.71	2	5	ND	1	9	1	3	2	34	1.64	.014	2	13	1.28	1	.05	4	1.50	.03	.01	1	2
29147	1	18	14	18	.3	117	27	680	5.74	2	5	ND	1	10	1	2	2	133	4.48	.031	2	280	3.89	1	.15	2	3.86	.01	.02	1	1
29148	1	6	5	11	.1	20	8	277	2.79	4	7	ND	1	9	1	3	3	43	1.94	.018	2	35	1.12	5	.06	3	1.42	.05	.03	1	2
29149	1	3	8	13	.1	103	20	387	3.97	3	5	ND	1	11	1	3	2	97	1.73	.007	2	226	3.25	2	.03	2	2.86	.08	.02	1	1
29150	1	5	7	9	.2	19	7	240	2.86	4	6	ND	1	13	1	2	3	26	1.82	.015	2	33	1.01	3	.05	12	1.25	.05	.02	1	1
29151	1	6	4	14	.1	22	10	252	3.36	2	5	ND	1	9	1	3	2	48	.82	.014	2	38	1.22	2	.04	2	1.42	.04	.02	1	2
29152	1	3	5	16	.1	84	14	261	2.56	7	6	ND	1	16	1	2	2	60	1.28	.012	2	157	2.74	3	.03	3	1.96	.05	.01	1	1
29153	1	6	8	10	.1	132	17	343	2.98	13	6	ND	1	13	1	2	2	67	1.41	.008	2	248	3.39	3	.03	8	2.41	.05	.01	1	1
29154	1	66	9	26	.2	129	23	484	5.52	26	5	ND	1	10	1	3	2	129	1.76	.010	2	241	4.45	11	.01	8	3.91	.01	.05	1	2
29155	1	9	7	30	.1	80	21	649	5.28	20	5	ND	1	14	1	2	2	142	2.67	.009	2	182	3.60	8	.01	5	3.30	.01	.04	1	1
29156	1	12	8	19	.1	120	23	627	4.86	3	5	ND	1	14	1	3	3	142	3.14	.006	2	243	4.46	5	.02	6	3.70	.01	.02	1	2
29157	1	2	6	1	.1	485	33	589	4.34	10	5	ND	1	15	1	3	2	97	2.56	.004	2	345	6.75	3	.02	3	4.41	.01	.01	1	1
29158	1	2	6	15	.1	155	23	593	4.82	4	5	ND	1	13	1	2	3	114	3.36	.005	2	312	4.83	2	.02	3	3.35	.04	.01	1	1
29159	1	1	9	11	.1	185	24	559	3.99	11	5	ND	1	17	1	2	2	96	3.04	.005	2	364	4.82	3	.01	8	3.38	.02	.02	1	1
29160	1	309	11	36	.5	31	13	326	6.42	73	5	ND	1	7	1	2	16	58	.87	.018	2	58	3.03	35	.01	6	3.53	.01	.10	1	1
29161	1	29	8	27	.1	179	28	715	5.36	5	5	ND	1	22	1	2	3	136	3.67	.004	2	446	5.60	3	.02	6	4.49	.01	.02	1	2
29162	1	14	8	33	.3	90	20	622	4.25	2	5	ND	1	18	1	2	3	114	3.85	.008	2	154	3.82	4	.03	4	3.37	.01	.03	1	1
29163	1	8	10	26	.1	66	16	515	4.63	13	5	ND	1	17	1	2	2	86	2.99	.012	2	115	3.64	4	.01	3	3.61	.01	.04	1	1
STD C/AU-R	18	57	43	132	6.7	67	29	1057	4.05	41	21	6	37	47	17	18	21	56	.49	.004	38	56	.92	175	.66	39	1.97	.08	.14	12	500

V

EASTFIELD RESOURCES LTD. FILE # 88-2935

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Tl	B	Al	Na	K	V	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
29164	1	1301	19	55	1.1	247	44	465	13.67	5	5	ND	1	9	1	14	82	150	1.25	.010	2	619	6.61	2	.01	2	6.39	.01	.03	15	4
29165	1	936	15	41	.4	319	32	374	11.66	976	5	ND	1	6	1	10	53	151	.75	.005	2	504	8.32	1	.01	6	6.34	.01	.04	1	33
29166	1	1444	12	35	1.3	577	47	406	11.61	25340	5	ND	1	32	1	87	94	58	3.39	.003	2	268	4.33	5	.01	15	2.17	.01	.04	1	1020
29167	1	440	11	36	.7	189	51	612	3.16	534	6	ND	1	27	1	15	2	134	3.01	.006	2	266	5.85	5	.01	15	3.95	.01	.06	1	52
29168	1	35	8	30	.1	165	26	773	5.45	186	5	ND	1	21	1	3	2	155	4.84	.008	2	274	4.90	2	.01	2	4.39	.01	.01	1	7
29169	1	3	11	36	.1	102	27	844	5.95	10	5	ND	1	26	1	2	2	250	5.03	.009	2	255	4.75	2	.02	6	4.26	.01	.02	1	1
29170	1	25	9	35	.1	104	20	643	4.86	6	5	ND	1	29	1	3	2	149	4.00	.010	2	140	3.99	1	.01	2	3.48	.01	.01	2	1
29171	1	12	7	47	.1	144	25	672	5.32	2	5	ND	1	23	1	2	2	174	3.36	.007	2	199	4.73	2	.01	2	4.03	.01	.03	1	1
29172	1	3	9	37	.1	227	27	683	5.20	3	5	ND	1	22	1	4	2	158	3.54	.006	2	309	5.34	2	.02	2	4.39	.01	.05	1	2
29173	1	7	7	21	.1	73	14	421	4.12	10	5	ND	1	16	1	2	2	81	2.13	.020	2	132	2.72	2	.01	2	2.40	.03	.03	1	1
29174	1	29	9	39	.1	222	26	697	5.03	2	5	ND	1	31	1	2	2	150	4.56	.005	2	296	5.06	3	.02	2	4.13	.03	.08	1	1
29175	1	25	8	37	.1	129	22	582	4.91	2	5	ND	1	21	1	3	2	151	4.77	.010	2	164	4.12	2	.02	2	3.37	.04	.03	1	2
29176	1	3	9	36	.1	223	28	754	5.12	2	6	ND	1	23	1	3	2	159	4.93	.006	2	311	5.44	2	.03	2	4.27	.01	.07	2	1
29177	1	4	9	24	.1	91	19	616	4.29	2	5	ND	1	32	1	4	2	153	4.72	.021	2	163	3.73	2	.02	4	3.15	.01	.04	2	1
29178	1	7	5	34	.1	131	23	779	4.82	2	5	ND	1	20	1	2	2	142	4.36	.010	2	212	4.28	4	.01	4	3.19	.01	.05	1	1
29179	1	9	5	36	.1	164	26	814	4.97	46	5	ND	1	40	1	3	2	128	4.85	.007	2	132	4.63	6	.01	12	2.35	.03	.08	1	1
29180	1	3	7	31	.2	260	30	706	4.43	2	5	ND	1	28	1	5	2	98	3.86	.006	2	430	6.13	4	.01	4	3.47	.01	.04	1	1
29181	1	9	7	28	.2	223	27	842	4.79	3	5	ND	1	44	1	4	2	112	5.23	.006	2	381	6.23	3	.01	6	3.40	.02	.03	2	1
29182	1	1	5	23	.1	247	31	840	4.44	51	6	ND	1	79	1	6	2	96	7.68	.005	2	358	5.91	4	.01	14	2.70	.01	.06	1	2
29183	1	4	10	23	.1	43	21	553	5.88	4	5	ND	1	14	1	4	2	256	1.85	.009	2	37	3.72	2	.01	5	3.43	.03	.01	1	1
29184	1	2	9	27	.1	87	21	557	5.59	22	5	ND	1	16	1	3	2	206	2.70	.008	2	118	4.17	2	.01	2	4.12	.01	.02	1	1
29185	1	12	4	16	.1	86	13	741	3.82	534	5	ND	1	45	1	3	2	75	9.50	.010	2	112	5.34	2	.01	5	1.92	.01	.02	3	3
29186	1	22	9	32	.1	106	22	654	5.10	36	5	ND	1	26	1	2	2	158	3.90	.007	2	188	4.58	3	.01	9	3.10	.01	.04	1	1
29187	1	8	9	26	.1	120	21	725	4.64	27	5	ND	1	41	1	3	2	114	5.33	.007	2	183	4.64	2	.01	10	2.80	.01	.05	1	1
29188	1	7	5	24	.1	94	18	636	4.43	9	5	ND	1	30	1	3	2	85	4.56	.011	2	126	3.67	4	.01	9	2.24	.01	.07	1	2
29189	1	4	6	32	.1	81	19	720	5.59	6	5	ND	1	27	1	2	2	134	3.69	.008	2	117	4.31	3	.01	7	3.38	.01	.05	1	1
29190	1	6	9	30	.1	60	19	731	5.45	6	5	ND	1	34	1	2	2	143	3.68	.009	2	81	3.61	3	.01	15	2.80	.01	.07	1	1
29191	1	16	7	24	.1	51	17	573	5.01	10	5	ND	1	37	1	5	2	66	3.29	.019	2	48	2.74	3	.01	20	1.67	.01	.12	2	1
29192	1	18	6	27	.1	102	24	727	5.92	36	7	ND	1	59	1	6	2	88	5.68	.020	2	110	3.90	6	.01	21	1.99	.03	.17	1	1
29193	1	8	6	22	.1	61	18	590	4.70	2	5	ND	1	23	1	2	2	152	3.22	.010	2	112	2.59	11	.02	5	1.97	.01	.20	1	1
29194	1	1	5	25	.1	126	20	446	3.56	2	5	ND	1	18	1	3	2	66	2.58	.005	2	315	4.24	2	.01	5	2.81	.01	.03	1	2
29195	1	1	5	29	.1	187	23	547	3.76	2	5	ND	1	24	1	2	2	71	3.40	.004	2	378	4.79	2	.01	6	3.22	.01	.02	2	1
29196	1	2	6	19	.1	99	17	394	3.15	3	5	ND	1	14	1	2	2	62	2.81	.008	2	214	3.67	2	.02	7	2.58	.05	.02	1	1
29197	1	3	5	20	.1	61	15	383	3.30	2	5	ND	1	13	1	2	2	94	1.73	.012	2	143	2.83	2	.05	5	2.22	.03	.02	1	2
29198	1	7	11	33	.2	92	26	724	4.95	14	5	ND	1	17	1	2	2	153	5.46	.012	2	260	3.69	3	.04	4	3.61	.02	.05	1	1
29199	1	10	8	24	.2	54	14	947	3.36	14	5	ND	1	99	1	4	2	95	16.41	.006	2	167	2.63	2	.02	6	2.60	.02	.01	2	2
29200	1	1	7	31	.1	115	24	598	4.95	32	5	ND	1	14	1	3	2	124	3.50	.008	2	236	4.67	1	.03	6	4.06	.01	.01	1	1
STD C/AU-R	17	58	42	132	6.9	68	28	1057	4.11	38	19	6	36	47	18	16	20	56	.49	.091	38	55	.92	175	.06	39	1.98	.05	.14	12	510

0.011 oz/liter
4.9 feet

407

E.O.H

E.O.H 88-I-07

Holes 88-100

GEOCHEMICAL ANALYSIS CERTIFICATE

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR NH FE SR CA P LA CR NG BA TI B W AND LIMITED FOR NA K AND AL. AU DETECTION LIMIT BY ICP IS 3 PPM.
 - SAMPLE TYPE: Core AU* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE.

DATE RECEIVED: AUG 2 1988 DATE REPORT MAILED: *Aug 6/88* ASSAYER: *C. Leong* D. TOYE OR C. LEONG, CERTIFIED B.C. ASSAYERS

EASTFIELD RESOURCES LTD. File # 88-3156 Page 1

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Tl	B	Al	Na	K	W	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	%	%	%	PPM	PPM	
E 74764	1	16	3	25	.1	155	18	519	3.31	140	5	ND	1	22	2	7	3	45	4.75	.002	2	103	3.27	2	.01	9	.60	.01	.07	1	1
E 74765	1	73	2	28	.1	129	16	606	3.10	170	5	ND	1	60	2	26	2	32	13.21	.005	2	57	5.26	4	.01	10	.41	.02	.11	1	1
E 74766	1	7	3	43	.1	310	39	804	5.07	246	5	ND	1	44	3	8	2	75	10.17	.003	2	192	4.59	6	.01	12	.98	.01	.13	2	3
E 74767	1	4	5	43	.2	312	36	885	5.59	12	5	ND	1	25	3	2	2	137	8.98	.003	2	605	6.14	3	.01	7	4.02	.01	.04	1	1
E 74768	1	5	5	31	.1	156	26	610	5.41	6	5	ND	1	19	2	2	2	158	5.33	.012	2	255	4.72	2	.01	3	3.60	.01	.04	1	1
E 74769	1	26	6	37	.1	65	22	435	5.88	22	5	ND	1	16	1	2	2	240	2.45	.010	2	100	3.94	2	.01	2	3.99	.02	.02	1	1
E 74770	1	40	9	20	.1	24	15	341	4.12	197	5	ND	1	19	1	3	2	99	2.44	.019	2	34	2.43	4	.01	2	2.52	.02	.07	1	7
E 74771	1	26	5	26	.1	71	20	493	4.82	250	5	ND	1	41	1	4	2	104	3.16	.016	2	130	3.62	4	.01	7	3.38	.01	.06	1	4
E 74772	1	7	9	37	.1	97	25	633	4.66	25	5	ND	1	33	3	2	4	140	4.54	.015	2	213	4.24	5	.02	15	3.13	.02	.10	1	1
E 74773	1	2212	2	46	.1	299	42	684	6.19	74	5	ND	1	28	3	2	5	160	4.30	.005	2	790	6.57	4	.01	5	4.42	.01	.05	1	3
E 74774	1	32	8	35	.1	282	38	704	5.10	64	5	ND	1	52	2	3	2	135	10.13	.004	2	711	5.90	2	.01	4	4.27	.01	.05	1	1
E 74775	1	53	7	29	.1	214	27	619	4.46	17	5	ND	1	37	3	2	2	130	6.47	.014	2	491	5.58	8	.02	10	3.86	.01	.15	1	1
E 74776	1	2	2	24	.1	55	19	457	3.29	11	5	ND	1	47	2	2	2	101	4.50	.012	2	186	3.40	1	.04	10	2.43	.03	.02	1	1
E 74777	1	3	9	31	.1	90	25	666	4.78	13	5	ND	1	60	1	2	4	165	9.96	.011	2	346	4.40	1	.04	3	3.37	.02	.01	3	1
E 74778	1	13	3	27	.1	204	24	506	3.74	69	5	ND	1	23	3	5	2	97	4.51	.012	2	314	4.31	1	.03	8	2.97	.02	.04	1	1
E 74779	1	3	3	20	.1	158	22	404	3.12	33	5	ND	1	24	3	2	2	59	4.65	.003	2	336	3.42	1	.02	3	2.74	.03	.02	1	13
E 74780	1	2	2	8	.1	57	10	187	1.47	2	5	ND	1	16	1	2	2	46	3.59	.005	2	75	1.34	2	.04	15	1.80	.05	.02	1	1
E 74781	1	3	2	10	.1	96	13	296	1.99	2	5	ND	1	12	2	2	2	63	4.90	.004	2	168	1.46	2	.08	4	1.88	.06	.01	1	1
E 74782	1	4	7	18	.1	93	16	228	2.70	2	5	ND	1	10	2	2	2	89	.83	.015	2	141	2.45	1	.06	4	2.11	.04	.01	1	1
E 74783	1	5	2	15	.1	136	17	231	2.48	2	5	ND	1	15	1	3	2	52	3.07	.012	2	165	2.86	2	.02	3	2.37	.03	.02	1	1
E 74784	1	5	2	17	.1	88	16	219	2.56	2	5	ND	1	13	1	2	2	70	.83	.007	2	184	2.36	2	.03	6	2.16	.03	.01	1	1
E 74785	1	3	4	18	.1	28	17	276	3.35	2	5	ND	1	14	1	2	2	88	.90	.010	2	18	2.14	2	.04	2	2.25	.02	.01	1	2
E 74786	1	5	5	16	.1	139	17	222	2.68	2	5	ND	1	9	1	2	2	81	1.01	.013	2	258	3.12	1	.02	4	2.20	.04	.02	1	1
E 74787	1	29	3	28	.1	132	25	617	4.83	290	5	ND	1	32	1	3	3	166	5.24	.012	2	234	4.38	2	.01	3	3.65	.01	.04	1	4
E 74788	1	10	5	26	.1	98	22	764	4.45	36	5	ND	1	52	1	3	4	143	9.48	.012	2	178	3.82	2	.01	7	3.15	.01	.06	1	1
E 74789	1	6	7	25	.1	110	25	648	4.68	4	5	ND	1	25	2	2	2	157	4.65	.011	2	237	4.67	3	.02	5	3.59	.01	.05	1	1
E 74790	1	82	7	19	.1	127	19	289	3.89	2	5	ND	1	15	1	2	2	187	1.60	.013	2	185	3.13	4	.05	3	2.56	.05	.03	1	1
E 74791	1	2	5	21	.1	52	20	430	3.71	2	5	ND	1	12	2	2	2	120	2.81	.007	2	287	3.52	2	.03	7	2.82	.02	.04	1	1
E 74792	1	7	7	18	.1	60	17	307	3.01	2	5	ND	1	15	1	2	2	86	1.78	.005	2	213	3.04	4	.03	2	2.26	.04	.02	1	1

GEOCHEMICAL ANALYSIS CERTIFICATE

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO₃-H₂O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR MN PB SR CA P LA CR HG BA TI B W AND LIMITED FOR NA K AND AL. AU DETECTION LIMIT BY ICP IS 3 PPM.
 - SAMPLE TYPE: Core AU ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE.

DATE RECEIVED: JUL 25 1988

DATE REPORT MAILED: July 29/88

ASSAYER: C. Leong D. TOYE OR C. LEONG, CERTIFIED B.C. ASSAYERS

EASTFIELD RESOURCES LTD.

File # 88-2934

Page 1

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Ti	B	Al	Na	K	W	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
R K 74701	1	6	6	19	.3	134	16	338	3.72	2	5	ND	2	6	1	2	2	81	.71	.010	2	141	2.33	2	.03	2	2.13	.16	.02	1	1
K 74702	1	3	5	19	.2	95	13	257	2.40	6	5	ND	1	9	1	3	2	43	1.37	.009	2	146	2.23	2	.02	4	2.08	.13	.01	1	2
K 74703	1	12	4	22	.2	55	14	268	2.62	2	5	ND	2	6	1	4	2	50	1.03	.007	2	133	2.01	1	.02	5	1.93	.10	.01	1	1
K 74704	1	14	4	14	.2	52	9	236	2.31	3	5	ND	1	7	1	2	2	27	1.42	.013	2	69	1.31	2	.03	2	1.28	.04	.02	1	1
K 74705	1	1	10	27	.3	195	22	375	3.26	26	5	ND	2	13	1	2	2	61	1.71	.006	2	286	4.04	2	.02	2	3.07	.16	.02	1	1
K 74706	1	1	4	10	.2	40	8	188	1.89	2	5	ND	1	10	1	2	2	42	1.00	.017	2	54	1.17	3	.03	2	1.23	.08	.02	1	2
K 74707	1	14	9	22	.4	49	13	378	3.85	12	5	ND	2	11	1	2	2	54	1.79	.020	2	99	1.93	2	.09	6	2.03	.09	.02	1	1
K 74708	1	88	9	37	.2	81	19	504	3.83	9	5	ND	2	11	1	2	2	74	2.17	.011	2	270	3.77	1	.05	3	2.94	.08	.02	1	3
K 74709	1	52	7	34	.2	73	17	418	3.38	2	5	ND	1	7	1	2	2	46	.73	.009	2	177	2.79	1	.03	4	2.23	.11	.02	1	1
K 74710	1	87	6	40	.2	118	19	388	3.16	2	5	ND	1	6	1	2	2	46	.71	.005	2	306	3.29	1	.02	4	2.53	.13	.01	1	2
K 74711	1	59	5	31	.1	165	19	329	2.90	5	5	ND	1	5	1	2	2	36	.53	.006	2	307	3.50	1	.02	2	2.49	.11	.01	1	1
K 74712	1	2	5	21	.2	183	17	291	2.40	2	5	ND	2	24	1	2	2	33	1.11	.005	2	296	3.19	6	.01	19	3.27	.20	.02	1	1
K 74713	1	56	6	24	.2	87	14	264	2.68	2	5	ND	2	5	1	2	2	43	1.20	.007	2	155	2.07	1	.02	4	1.93	.08	.01	1	1
K 74714	1	1	6	22	.1	156	17	198	2.25	4	5	ND	2	7	1	2	2	26	.65	.005	2	305	3.07	1	.01	18	2.23	.15	.01	1	1
K 74715	1	2	7	33	.2	171	24	465	4.11	7	5	ND	1	10	1	2	2	88	1.59	.006	2	320	4.41	1	.03	4	3.27	.10	.01	1	1
K 74716	1	13	6	17	.2	71	12	298	2.55	2	5	ND	2	19	1	2	2	62	3.28	.008	2	138	2.09	4	.02	8	2.20	.10	.01	1	1
K 74717	1	21	5	25	.1	64	15	283	2.72	4	5	ND	1	23	1	2	2	52	1.41	.006	2	90	2.01	2	.02	5	2.13	.06	.01	2	1
K 74718	1	1	4	13	.2	91	12	221	2.20	15	5	ND	2	15	1	2	2	44	1.21	.009	2	156	2.09	2	.02	22	1.77	.12	.01	1	2
K 74719	1	3	4	10	.2	6	4	135	2.75	4	5	ND	2	13	1	2	2	8	.57	.011	2	6	.33	3	.04	6	.92	.05	.04	1	1
K 74720	1	3	4	13	.2	19	7	191	3.28	9	5	ND	2	12	1	2	2	13	.88	.018	2	31	.66	6	.06	5	1.30	.08	.06	1	1
K 74721	1	3	5	16	.2	43	10	274	3.11	2	5	ND	2	10	1	2	2	33	1.29	.016	2	99	1.45	2	.07	4	1.58	.05	.02	1	2
K 74722	1	7	6	22	.3	105	18	409	3.64	2	5	ND	2	8	1	2	2	73	2.00	.025	2	206	2.91	1	.13	10	2.49	.08	.01	1	1
K 74723	1	4	3	15	.2	35	9	285	3.18	9	5	ND	2	9	1	2	2	21	1.08	.016	2	83	1.32	2	.04	2	1.47	.08	.01	1	1
K 74724	1	3	6	15	.2	138	14	264	2.88	14	5	ND	1	9	1	2	2	45	1.15	.013	2	112	2.32	2	.04	4	1.83	.05	.01	1	2
K 74725	1	5	7	13	.2	72	15	279	2.85	5	5	ND	2	13	1	2	2	63	2.32	.007	2	90	1.96	2	.03	2	1.85	.04	.02	1	1
K 74726	1	1144	17	53	1.6	211	31	579	11.81	245	5	ND	2	9	1	7	53	172	1.64	.009	2	425	6.98	12	.01	8	6.82	.08	.04	1	16
K 74727	1	160	14	48	.4	175	29	592	6.74	25	5	ND	2	13	1	3	4	147	1.81	.006	2	450	6.22	8	.01	7	4.93	.07	.03	1	2
K 74728	1	26	11	39	.2	105	22	377	6.90	184	5	ND	2	7	1	19	3	122	.87	.016	2	230	4.43	29	.01	4	3.98	.06	.19	1	5
K 74729	1	36	15	44	.3	68	16	433	8.08	62	5	ND	2	10	1	9	2	134	.85	.026	2	122	4.94	21	.01	3	5.09	.04	.08	1	4
K 74730	1	227	22	76	.7	165	24	637	13.45	15	5	ND	3	12	1	7	23	204	1.44	.026	2	425	8.90	6	.01	5	9.23	.04	.03	1	2
K 74731	1	1304	19	96	1.7	91	19	552	13.64	4	5	ND	2	4	2	6	71	211	.49	.028	2	128	8.75	1	.01	6	9.91	.04	.01	1	2
K 74732	1	214	22	78	.3	210	24	462	12.54	7	5	ND	4	2	1	7	12	194	.21	.017	2	516	10.12	1	.01	4	9.51	.06	.01	1	1
K 74733	1	1116	19	64	1.4	301	36	320	13.68	8	5	ND	1	2	2	5	39	194	.06	.006	2	610	9.69	1	.01	4	7.46	.97	.62	5	3
K 74734	1	305	20	72	.6	171	25	435	13.41	2	5	ND	1	1	1	3	13	220	.87	.012	2	447	10.01	1	.01	2	9.22	.03	.01	1	2
K 74735	1	352	15	59	.4	223	29	387	11.55	4	5	ND	1	1	1	4	18	204	.84	.005	2	550	11.08	1	.01	5	8.67	.04	.01	1	1
V K 74736	1	1100	23	65	1.3	194	87	417	17.74	29190	5	ND	1	1	1	43	95	172	.87	.011	2	284	8.07	1	.01	8	8.19	.06	.01	4	3845
STD C/AU-2	17	52	42	132	6.8	68	28	1059	4.10	42	16	7	36	47	18	16	19	56	.49	.083	38	56	.92	175	.86	36	1.36	.06	.14	12	475

0.112 oz/ft
1.64 ft

EASTFIELD RESOURCES LTD. FILE # 88-2934

SAMPLE#	Mo PPM	Cu PPM	Pb PPM	Zn PPM	Ag PPM	Ni PPM	Co PPM	Mn PPM	Fe %	As PPM	U PPM	Au PPM	Th PPM	Sr PPM	Cd PPM	Sb PPM	Bi PPM	V PPM	Ca %	P %	La PPM	Cr PPM	Hg %	Ba PPM	Ti %	B PPM	Al %	Na %	K %	W PPM	Au* PPB
K 74737	1	265	17	69	.1	225	30	542	13.66	55	5	ND	1	1	1	9	15	244	.05	.014	2	534	10.41	1	.01	4	9.73	.16	.01	1	5
K 74738	1	1080	19	79	1.0	123	24	577	14.37	13	5	ND	1	1	1	13	82	241	.08	.024	2	251	9.89	10	.01	6	9.56	.16	.02	1	9
K 74739	1	979	23	64	.7	174	23	526	14.95	2	5	ND	2	5	1	6	56	221	.12	.024	2	329	8.18	6	.01	4	8.54	.19	.02	1	15
K 74740	1	782	15	73	.6	200	20	522	14.17	853	5	ND	1	1	1	14	78	182	.04	.012	2	392	10.33	1	.01	3	9.52	.12	.01	1	10
K 74741	1	1033	21	76	.8	202	23	630	15.29	9	5	ND	1	2	1	11	63	247	.05	.008	2	281	9.17	2	.01	5	9.65	.01	.01	1	14
K 74742	1	1435	20	62	.7	192	32	556	17.45	82	5	ND	1	4	1	8	75	230	.07	.009	2	253	7.62	4	.01	6	8.76	.12	.01	1	22
K 74743	1	1188	19	61	.6	178	17	598	16.26	2	5	ND	1	1	1	12	95	270	.04	.010	2	226	9.24	1	.01	4	9.11	.11	.01	1	13
K 74744	1	1041	11	32	.6	465	40	563	13.11	4836	5	ND	1	6	1	22	76	79	1.09	.006	2	336	8.06	1	.01	4	3.65	.09	.01	1	113
K 74745	1	436	5	17	.2	447	44	527	6.20	104	5	ND	1	5	1	7	17	53	1.00	.902	2	648	9.52	1	.01	5	1.76	.09	.01	1	15
K 74746	1	772	8	22	.6	614	47	691	7.64	6361	5	ND	1	12	1	15	55	39	3.01	.002	2	391	5.97	1	.01	3	1.54	.10	.01	1	230
K 74747	1	581	9	35	.7	355	38	645	8.29	5762	5	ND	1	54	1	29	22	89	6.32	.003	2	395	6.12	5	.01	12	3.66	.15	.03	1	172
K 74748	1	50	10	37	.1	216	33	865	5.73	180	5	ND	1	23	1	8	2	119	9.92	.003	2	436	6.03	2	.01	5	4.65	.11	.02	1	6
K 74749	1	69	7	26	.2	75	22	537	4.77	42	5	ND	1	17	1	2	2	109	4.43	.005	2	44	4.10	4	.01	8	4.15	.18	.04	1	1
K 74750	1	136	10	27	.1	103	31	455	6.14	124	5	ND	1	13	1	2	2	145	2.51	.009	2	157	4.70	3	.01	8	4.89	.06	.03	1	3
K 74751	1	95	6	27	.1	51	16	491	5.36	235	5	ND	1	12	1	2	2	94	2.29	.022	2	85	2.98	1	.01	7	3.05	.07	.03	1	5
K 74752	1	9	5	32	.1	101	20	797	4.99	6	5	ND	1	31	1	2	2	169	5.03	.009	2	178	4.05	1	.01	3	3.55	.11	.01	2	1
K 74753	1	6	6	24	.1	93	17	690	4.59	4	5	ND	1	25	1	2	2	139	4.55	.009	2	162	3.43	1	.01	5	3.12	.07	.01	1	2
K 74754	1	5	7	33	.1	137	26	751	5.89	9	5	ND	1	19	1	2	2	238	3.87	.007	2	292	4.77	1	.02	4	4.31	.15	.01	1	2
K 74755	1	2	3	29	.1	209	25	793	4.32	11	5	ND	1	32	1	2	2	128	5.85	.007	2	405	5.30	2	.01	4	3.90	.11	.01	1	1
K 74756	1	4	6	30	.1	92	23	801	5.11	3	5	ND	1	25	1	2	2	178	4.04	.010	2	233	4.83	4	.02	6	3.89	.18	.08	1	1
K 74757	1	9	9	38	.1	75	27	757	6.41	2	5	ND	1	19	1	2	2	336	4.57	.005	2	223	4.86	3	.04	4	4.37	.16	.07	2	2
K 74758	1	6	6	25	.2	12	12	425	5.21	5	5	ND	1	13	1	2	2	65	1.56	.029	2	15	2.22	3	.04	10	2.40	.08	.06	1	3
K 74759	1	8	5	26	.1	33	15	590	4.92	2	5	ND	1	27	1	2	2	100	3.23	.026	2	92	2.55	5	.04	4	2.29	.12	.10	1	2
K 74760	1	1	6	38	.2	137	24	780	5.15	2	5	ND	1	23	1	2	2	144	3.43	.009	2	236	5.12	6	.03	3	3.91	.18	.13	1	2
K 74761	1	4	7	30	.1	189	25	767	5.03	6	5	ND	1	24	1	2	2	120	5.21	.005	2	317	4.78	2	.01	6	3.73	.01	.02	1	2
K 74762	1	4	7	26	.1	142	20	718	4.83	2	5	ND	1	21	1	2	2	115	5.51	.005	2	229	4.27	2	.01	6	3.35	.01	.02	1	1
K 74753	1	10	5	38	.1	247	29	822	5.47	18	5	ND	1	31	1	2	2	104	5.55	.006	2	366	5.44	3	.01	9	3.68	.13	.04	1	2
STD C/AU-2	18	58	41	132	6.6	67	28	1046	3.99	39	19	6	36	47	17	16	18	55	.48	.067	37	55	.91	174	.06	33	1.90	.66	.13	12	500

↑
-004 oz/ton
6.6ft

EOH 88-I-08

Hole 9	E 74901	1	4	6	24	.1	93	21	401	3.79	53	5	ND	1	12	1	3	2	99	2.57	.012	2	162	3.00	4	.03	3	2.59	.02	.04	1	1
	E 74902	1	4	2	14	.1	78	12	174	2.42	2	5	ND	1	7	1	2	2	32	1.17	.013	2	74	1.61	1	.03	4	1.49	.03	.01	1	1
	E 74903	1	4	2	15	.1	91	12	148	2.64	2	5	ND	1	7	1	2	2	24	.79	.015	2	164	2.01	2	.03	4	1.57	.03	.01	1	1
	E 74904	1	5	3	21	.1	121	18	173	2.67	2	5	ND	1	8	1	2	2	74	1.04	.004	2	232	2.69	3	.03	2	2.32	.06	.02	1	1
	E 74905	1	3	6	18	.1	87	17	177	3.05	2	5	ND	1	19	1	3	2	87	1.57	.012	2	171	2.17	5	.04	3	2.58	.11	.03	1	1
	E 74905	1	9	2	18	.1	135	16	162	2.38	2	5	ND	1	5	1	2	4	35	.78	.006	2	241	2.86	1	.02	5	1.95	.03	.01	1	1
	E 74907	1	3	3	17	.1	130	15	171	1.89	2	5	ND	1	5	1	2	2	29	1.41	.005	2	235	2.82	1	.02	6	1.93	.04	.02	1	1
Hole 9	E 74908	1	3	2	8	.1	61	8	103	1.20	2	5	ND	1	9	1	2	2	15	1.15	.005	2	108	1.40	2	.01	3	1.29	.07	.01	2	1
	E 74909	1	4	10	19	.2	91	16	331	3.72	2	5	ND	1	7	1	2	3	102	2.12	.011	2	208	2.91	1	.03	2	2.41	.06	.01	1	3
	E 74910	1	5	8	14	.1	8	10	231	4.12	2	5	ND	1	9	1	2	2	97	.94	.013	2	18	1.09	4	.06	5	1.91	.11	.07	2	1
	E 74911	1	3	5	16	.2	125	14	180	2.55	2	5	ND	1	6	1	2	4	32	1.28	.007	2	241	2.48	1	.03	3	1.74	.05	.01	1	12
	E 74912	1	9	6	14	.1	58	10	200	2.96	2	5	ND	1	10	1	2	2	45	1.51	.014	2	123	1.72	2	.05	2	1.73	.07	.03	1	2
	E 74913	1	2	2	20	.1	166	18	207	2.45	2	5	ND	1	4	1	2	2	34	.69	.003	2	310	3.72	1	.01	2	2.23	.04	.01	1	1
	E 74914	1	3	6	17	.1	74	14	255	3.15	2	5	ND	1	17	1	2	2	63	2.06	.012	2	162	2.53	2	.03	3	2.11	.07	.02	1	1
	STD C/AU-R	19	62	42	132	7.1	72	30	1150	4.35	43	16	7	40	50	18	17	20	60	.50	.096	40	60	.97	180	.08	34	2.05	.06	.15	13	490

GEOCHEMICAL ANALYSIS CERTIFICATE

ICP - .500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG. C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
 THIS LEACH IS PARTIAL FOR MN FE SR CA P LA CR NG BA TI B W AND LIMITED FOR NA K AND AL. AU DETECTION LIMIT BY ICP IS 3 PPM.
 - SAMPLE TYPE: Core AU* ANALYSIS BY ACID LEACH/AA FROM 10 GM SAMPLE.

DATE RECEIVED: AUG 1 1988 DATE REPORT MAILED: Aug 5/88 ASSAYER: C. Leong D. TOYE OR C. LEONG, CERTIFIED B.C. ASSAYERS

EASTFIELD RESOURCES LTD. File # 88-3124

Handwritten: H.L.P. 9

Handwritten: 55.5-56.50

Handwritten: 55.5-60.5

Handwritten: E.O.H

Handwritten: 0.009 oz/ft
1.64'

Handwritten: 0.016
3.28 ft

Handwritten: 0.062 oz/ft
6.56 ft

SAMPLE#	Mn	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	%	%	%	%	PPM	PPM
E 74915	1	3	2	21	.1	96	16	487	3.31	2	5	ND	1	17	1	2	2	68	4.39	.010	2	254	2.86	2	.03	5	2.37	.03	.02	1	3
E 74916	1	2	3	22	.1	141	19	346	3.13	2	5	ND	1	10	1	2	2	55	1.65	.004	2	381	4.01	2	.02	6	2.84	.03	.01	1	1
E 74917	1	1	3	23	.1	217	25	515	3.63	2	5	ND	1	24	1	2	2	81	3.00	.004	2	472	5.37	1	.02	3	3.49	.01	.02	1	1
E 74918	1	8	6	29	.1	293	34	792	4.24	79	5	ND	1	36	1	2	2	108	5.11	.002	2	601	5.68	1	.01	3	3.77	.01	.01	1	1
E 74919	1	559	14	41	1.5	254	27	885	8.71	15119	5	ND	2	18	1	106	22	42	4.63	.007	2	216	3.25	6	.01	8	2.15	.01	.03	3	320
E 74920	1	2	5	22	.2	129	20	388	3.51	25	5	ND	1	10	1	25	2	77	1.44	.007	2	255	3.98	2	.03	6	2.77	.02	.02	1	2
E 74921	1	9	4	24	.1	341	33	608	4.24	278	5	ND	1	20	1	40	2	94	4.71	.004	2	492	5.78	1	.02	4	3.91	.01	.02	1	1
E 74922	1	7	3	20	.1	141	18	297	3.18	3	5	ND	1	13	1	2	2	66	1.01	.006	2	221	3.72	2	.02	8	2.77	.03	.01	1	1
E 74923	1	1510	12	58	1.5	334	28	481	13.95	12	5	ND	1	3	1	9	189	188	.40	.010	2	722	9.17	2	.01	5	7.46	.01	.02	2	14
E 74924	1	1804	10	46	.9	324	30	346	16.91	196	5	ND	2	2	1	10	61	151	.30	.006	2	643	8.03	1	.01	2	6.04	.01	.01	6	13
E 74925	1	1107	10	55	1.1	354	36	475	16.41	9185	5	ND	1	6	1	47	185	172	1.85	.009	2	260	7.70	3	.01	13	4.55	.01	.02	5	220
E 74926	1	2056	7	52	2.6	390	46	420	17.22	12078	5	ND	2	15	1	76	250	94	2.22	.005	2	200	7.03	2	.01	11	1.52	.01	.02	9	875
E 74927	1	313	4	29	.7	374	33	595	7.18	1615	5	ND	1	23	1	22	27	62	2.56	.003	2	228	7.61	4	.01	11	1.12	.01	.03	4	19
E 74928	1	46	5	19	.2	498	45	826	3.87	325	5	ND	1	19	1	6	2	26	3.34	.002	2	322	7.89	2	.01	5	1.44	.01	.02	2	4
E 74929	1	44	2	4	.1	517	51	931	2.91	178	5	ND	1	19	1	5	2	23	3.43	.002	2	682	3.95	1	.01	2	.64	.01	.01	2	1
E 74930	1	18	2	6	.1	318	30	840	3.20	109	5	ND	1	16	1	3	2	7	3.60	.002	2	163	6.87	1	.01	3	.20	.01	.01	1	1
E 74931	1	172	3	5	.4	736	68	730	4.20	527	5	ND	1	9	1	5	2	10	2.31	.002	2	190	7.33	1	.01	3	.29	.01	.01	1	975
E 74932	1	2391	3	21	3.1	605	56	386	9.49	34909	5	11	1	7	1	118	113	25	1.39	.001	2	306	4.32	1	.01	4	.67	.01	.02	1	6870
E 74933	1	1129	4	9	1.0	807	51	827	6.77	7907	5	ND	1	9	1	15	66	11	1.84	.002	2	132	6.77	1	.01	10	.41	.01	.01	1	410
E 74934	1	2013	4	13	2.2	885	66	495	9.92	12390	5	ND	1	4	1	29	106	10	.79	.001	2	120	5.69	1	.01	2	.42	.01	.01	1	285
E 74935	1	47	3	4	.1	1253	85	866	6.78	232	5	ND	1	3	1	8	2	15	.63	.002	2	346	12.29	1	.01	7	.28	.01	.01	1	4
E 74936	1	17	2	2	.1	928	62	563	4.64	136	5	ND	1	2	1	5	2	9	.39	.002	2	180	5.05	1	.01	6	.21	.01	.01	1	5
E 74937	1	92	4	4	.1	751	62	515	4.90	172	5	ND	1	2	1	5	3	22	.59	.003	2	140	7.63	1	.01	2	.69	.01	.01	1	17
E 74938	1	159	2	4	.1	560	46	494	4.13	228	5	ND	1	11	1	2	2	18	1.91	.002	2	355	4.54	1	.01	3	.69	.01	.03	1	1
E 74939	1	55	2	2	.1	626	43	574	2.62	282	5	ND	1	21	1	4	2	23	4.07	.002	2	98	4.13	1	.01	3	.75	.01	.02	1	10
E 74940	1	3	2	17	.1	58	11	227	2.07	6	5	ND	1	10	1	2	2	43	1.35	.011	2	140	2.05	1	.04	2	1.54	.02	.02	1	1
E 74941	1	5	3	17	.1	65	15	483	3.41	8	5	ND	1	12	1	2	2	82	3.39	.010	2	137	2.45	1	.03	4	2.08	.03	.01	1	1
E 74942	1	5	3	20	.1	249	25	535	3.43	2	5	ND	1	19	1	2	2	51	4.83	.004	2	400	4.64	1	.02	6	3.15	.01	.01	1	1
STD C/AD-R	17	58	39	132	6.6	68	28	1056	4.08	37	18	7	36	48	17	16	20	56	.49	.090	35	56	.91	173	.06	56	1.98	.06	.14	12	470

E.O.H 88-I-09

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Yt	B	Al	Na	K	V	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
E 74943	1	16	2	24	.3	61	12	311	3.04	2	5	ND	1	6	1	2	2	37	.53	.014	2	98	1.66	9	.03	2	1.74	.04	.04	1	1
E 74944	1	2	3	16	.3	69	12	241	2.79	2	5	ND	1	9	1	2	2	35	1.34	.011	2	136	1.76	5	.03	2	1.38	.03	.02	1	1
E 74945	1	1	2	13	.1	90	10	151	1.75	2	5	ND	1	3	1	2	2	19	.46	.013	2	185	2.06	1	.02	3	1.44	.04	.02	1	1
E 74946	1	25	3	20	.4	61	15	372	3.18	4	5	ND	1	10	1	2	2	51	.91	.030	2	111	2.03	2	.11	2	2.10	.05	.03	1	2
E 74947	1	3	3	17	.3	165	18	254	2.97	3	5	ND	1	3	1	2	2	48	.81	.007	2	270	3.25	1	.02	4	2.33	.03	.02	1	1
E 74948	1	4	4	16	.2	67	16	346	4.26	2	5	ND	1	7	1	3	2	59	.61	.013	2	67	1.77	1	.03	3	1.90	.04	.02	1	1
E 74949	1	3	3	14	.2	87	12	259	2.76	2	5	ND	1	7	1	3	2	48	.75	.010	2	92	1.63	1	.03	4	1.68	.05	.01	1	1
E 74950	1	2	2	26	.3	111	20	401	3.70	2	5	ND	1	10	1	2	2	70	1.28	.007	2	113	3.04	1	.03	4	2.59	.03	.02	1	1
E 74951	1	3	3	23	.2	90	16	251	2.87	10	5	ND	1	6	1	3	2	60	1.09	.007	2	170	2.32	1	.02	2	1.98	.04	.03	1	2
E 74952	1	11	5	34	.4	128	23	551	4.70	45	5	ND	1	11	1	4	2	122	3.54	.006	2	301	4.29	4	.02	3	3.79	.02	.02	2	1
E 74953	1	1	3	13	.1	135	14	217	2.07	2	5	ND	1	8	1	2	2	28	1.41	.006	2	226	2.60	1	.02	2	1.93	.04	.01	1	1
E 74954	1	4	3	13	.2	28	10	208	3.11	2	5	ND	1	7	1	2	2	35	.85	.014	2	60	1.13	1	.05	2	1.33	.05	.02	1	1
E 74955	1	3	3	13	.2	81	12	191	2.55	2	5	ND	1	11	1	2	2	39	1.38	.015	2	153	2.17	2	.03	4	2.04	.08	.02	1	1
E 74956	1	2	5	12	.2	59	11	160	2.56	2	5	ND	1	13	1	2	2	22	1.11	.012	2	112	1.74	3	.03	2	2.04	.09	.03	1	2
E 74957	1	4	2	9	.2	4	5	170	2.95	2	5	ND	1	11	1	2	2	7	1.05	.020	2	5	.46	3	.05	3	1.18	.05	.03	1	1
E 74958	1	4	3	11	.4	21	7	190	2.69	3	5	ND	1	14	1	2	2	17	1.16	.017	2	51	.92	4	.04	5	1.62	.09	.05	1	1
E 74959	1	1	2	14	.1	137	15	267	2.64	2	5	ND	1	15	1	2	2	28	1.42	.006	2	206	3.26	2	.01	2	2.77	.09	.02	1	1
E 74960	1	3	3	16	.2	73	13	311	3.68	2	5	ND	1	8	1	5	2	34	1.46	.013	2	154	2.35	2	.04	11	2.15	.05	.02	1	1
E 74961	1	3	2	12	.3	12	7	222	3.68	2	5	ND	1	8	1	2	2	11	.82	.020	2	18	.96	3	.05	2	1.52	.04	.03	1	1
E 74962	1	16	8	40	.3	182	27	769	5.23	45	5	ND	1	32	1	4	2	135	4.33	.004	2	452	6.72	2	.01	4	5.22	.01	.02	1	1
E 74963	1	313	9	46	.7	450	34	673	6.00	212	5	ND	2	30	1	2	2	107	3.85	.005	2	398	6.67	1	.01	2	4.67	.01	.01	1	5
E 74964	1	3	7	23	.3	254	21	471	3.47	10	5	ND	1	23	1	2	2	70	3.03	.007	2	283	4.60	2	.03	4	3.25	.03	.03	1	1
E 74965	1	5	4	20	.1	75	15	343	3.68	2	5	ND	1	10	1	13	2	77	1.56	.010	2	179	3.06	2	.03	3	2.50	.04	.01	1	1
E 74966	1	33	11	32	1.2	171	25	646	5.39	227	5	ND	1	13	1	16	2	135	2.51	.008	2	323	5.88	3	.02	4	4.62	.03	.02	2	4
E 74967	1	1279	17	62	2.5	366	47	536	16.19	71	5	ND	2	6	2	9	75	239	1.31	.008	2	770	8.31	2	.01	6	6.82	.01	.02	2	15
E 74968	1	1145	4	22	1.1	737	53	492	9.05	925	5	ND	1	14	1	17	43	50	3.10	.002	2	270	6.21	1	.01	4	1.68	.01	.01	2	47
E 74969	1	31	2	7	.1	608	47	762	3.76	82	5	ND	1	4	1	8	2	6	.73	.002	2	193	12.63	1	.01	4	.25	.01	.01	1	4
E 74970	1	395	2	11	.5	551	47	560	5.26	546	5	ND	1	5	1	9	34	11	1.14	.002	2	124	9.87	1	.01	5	.32	.01	.02	1	16
E 74971	1	95	2	8	.3	1216	62	889	3.72	520	5	ND	1	3	1	11	2	1	.46	.002	2	40	13.03	1	.01	4	.02	.01	.01	1	12
E 74972	1	113	2	11	.8	1220	63	1212	3.43	500	5	ND	1	5	1	56	2	1	.85	.002	2	32	14.04	1	.01	3	.02	.01	.01	1	22
E 74973	1	611	3	13	2.8	1186	130	1097	4.66	3902	5	4	1	8	1	38	8	1.98	.001	2	134	8.99	1	.01	5	.24	.01	.01	1	24	
E 74974	1	7140	15	99	10.2	517	44	392	16.92	15162	5	ND	2	6	4	20	1439	41	1.60	.001	2	292	3.89	1	.01	2	1.42	.01	.01	1	919
E 74975	1	1441	8	34	1.7	318	43	268	11.59	34588	5	ND	1	2	1	84	181	116	.40	.001	2	734	6.79	1	.01	4	3.57	.01	.01	1	919
E 74976	1	644	2	24	1.0	556	43	996	4.51	800	5	ND	1	11	1	6	6	40	3.40	.001	2	250	7.31	1	.01	5	2.43	.01	.01	1	38
E 74977	1	833	4	19	1.1	634	70	305	12.46	23332	5	3	1	3	1	84	63	27	.59	.001	2	342	4.35	1	.01	5	1.19	.01	.01	1	919
E 74978	1	369	2	12	.3	369	27	561	4.04	202	5	ND	1	4	1	2	4	14	.91	.001	2	396	4.80	1	.01	4	.58	.01	.01	1	24

0.020 oz/ton
4.9 feet

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Yt	B	Al	Na	K	V	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
E 74979	1	560	2	20	.6	627	41	448	5.28	3768	5	ND	1	3	1	16	14	19	.56	.001	2	218	5.39	1	.01	2	.76	.01	.01	1	565
E 74980	1	2153	5	40	1.8	897	74	495	7.66	34398	5	ND	1	4	1	22	20	14	.61	.003	2	174	5.97	1	.01	2	.86	.01	.01	1	618
E 74981	1	323	8	18	.5	810	63	695	5.69	3529	5	3	1	5	1	14	18	20	.90	.001	2	348	6.20	1	.01	4	.53	.01	.01	1	618
E 74982	1	23	7	23	.1	682	37	597	3.77	44	5	ND	1	3	1	2	2	52	2.36	.001	2	433	6.23	1	.01	4	1.20	.01	.01	1	4
E 74983	1	10	6	23	.1	722	39	816	3.74	30	5	ND	1	4	1	4	2	33	3.74	.002	2	293	6.90	1	.01	9	.60	.01	.01	1	6
STD C/AU-B	19	61	42	131	6.9	71	28	1026	4.12	43	20	8	39	49	18	17	20	62	.52	.094	40	60	.92	193	.08	33	1.96	.06	.15	13	505

88-I-10

X 74904	1	11	5	21	.1	216	23	539	3.28	2	5	WD	2	5	1	3	2	77	2.95	.001	2	919	4.73	1	.01	6	2.00	.01	.01	2	14
X 74905	1	55	4	35	.1	671	65	669	4.84	2	5	WD	1	5	1	6	2	19	.50	.002	2	369	18.02	1	.01	35	.93	.01	.01	1	6
X 74906	1	68	5	44	.1	721	52	638	4.68	2	5	WD	2	5	1	4	3	26	.46	.002	2	329	14.53	1	.01	20	2.77	.01	.01	1	5
X 74907	1	142	8	46	.1	483	41	879	4.13	2	5	WD	2	7	1	5	3	48	2.05	.001	2	363	14.03	1	.01	17	4.56	.01	.01	2	6
STD C/AD-R	17	57	38	129	6.6	66	28	1061	4.18	43	20	7	37	48	17	17	20	55	.50	.089	38	55	.92	177	.06	37	1.99	.06	.13	12	500

E 74151	1	3	2	18	.1	61	10	217	2.41	4	5	ND	1	7	1	2	2	27	.62	.010	2	100	1.58	1	.02	2	1.63	.04	.01	1	1
E 74152	1	2	2	14	.3	68	10	182	2.04	5	5	ND	1	7	1	3	2	26	.63	.011	2	117	1.53	3	.02	3	1.58	.06	.02	1	3
E 74153	1	15	3	22	.1	53	14	385	3.46	9	5	ND	1	8	1	2	2	64	1.01	.024	2	106	2.09	2	.09	2	2.27	.05	.01	1	3
E 74154	1	3	4	17	.1	144	15	198	2.36	4	5	ND	1	8	1	2	2	40	.74	.008	2	186	2.80	2	.02	2	2.31	.05	.01	1	1
E 74155	1	2	7	22	.4	136	15	204	2.31	3	5	ND	1	5	1	3	2	30	.37	.005	2	314	3.06	1	.02	3	2.05	.02	.03	1	1
E 74156	1	1	4	18	.4	106	13	233	2.09	8	6	ND	1	10	1	3	2	35	2.25	.005	2	207	2.49	1	.02	3	2.02	.01	.02	2	1
E 74157	1	3	2	17	.2	39	13	287	2.94	3	5	ND	1	13	1	2	2	64	.62	.007	2	50	1.91	1	.03	2	1.94	.02	.01	1	1
E 74158	1	2	4	17	.1	109	14	213	2.33	3	5	ND	1	15	1	2	2	35	1.64	.006	2	202	2.41	1	.02	2	1.93	.03	.01	1	2
E 74159	1	3	2	14	.1	97	12	166	2.51	3	5	ND	1	5	1	2	2	54	.87	.007	2	176	2.07	1	.02	2	1.62	.03	.01	1	1
E 74160	1	4	2	16	.2	73	13	212	2.72	4	5	ND	1	6	1	2	2	50	.75	.015	2	147	2.18	1	.03	2	1.67	.02	.01	1	1
E 74161	1	2	2	20	.1	122	16	242	2.63	2	5	ND	1	11	1	2	2	36	1.16	.011	2	217	2.88	1	.02	2	2.12	.02	.01	1	1
E 74162	1	3	5	23	.2	140	19	355	3.33	29	5	ND	1	13	1	2	2	57	1.76	.007	2	289	3.59	2	.02	2	2.74	.01	.01	1	1

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
E 74163	1	3	3	10	.1	15	11	190	3.06	2	5	ND	1	15	1	2	4	59	.81	.009	2	20	1.07	1	.05	3	1.44	.03	.02	1	3
E 74164	1	3	2	12	.1	62	12	162	2.80	4	5	ND	1	8	1	3	2	37	.68	.011	2	117	1.40	2	.04	4	1.47	.03	.01	1	1
E 74165	1	15	3	14	.1	75	12	156	2.18	2	5	ND	1	8	1	3	4	32	.88	.008	2	168	1.80	2	.02	2	1.62	.04	.03	1	1
E 74166	1	1	4	17	.1	91	14	364	2.83	5	5	ND	1	18	1	3	2	73	2.13	.006	2	273	3.40	2	.02	2	2.41	.02	.02	1	1
E 74167	1	57	9	27	.1	180	15	579	4.24	172	5	ND	1	14	1	3	2	118	5.01	.007	2	142	4.02	17	.01	3	3.54	.01	.05	1	4
E 74168	1	3	4	22	.1	204	22	535	3.94	9	5	ND	1	18	1	2	2	113	3.39	.006	2	242	4.62	1	.03	2	3.48	.02	.02	1	1
E 74169	1	22	2	29	.2	40	14	372	3.07	2	5	ND	1	12	1	2	3	52	2.90	.001	2	22	2.61	2	.02	2	2.52	.01	.01	1	1
E 74170	1	17	2	20	.1	164	14	518	2.14	8	5	ND	1	17	1	2	2	43	10.90	.004	2	166	1.98	1	.02	2	2.80	.04	.01	1	1
E 74171	1	4	6	21	.1	265	22	724	2.93	214	5	ND	1	21	1	2	2	61	7.68	.004	2	299	3.77	1	.01	3	2.47	.01	.01	1	1
E 74172	1	16	5	15	.1	889	44	733	3.25	397	5	ND	1	11	1	11	3	10	2.48	.004	2	146	6.10	1	.01	3	.71	.01	.01	1	29

K 74173	1	30	2	11	.3	825	63	508	4.48	257	5	ND	2	6	1	3	2	20	1.39	.002	2	284	9.03	1	.01	3	.60	.01	.01	1	2
K 74174	1	22	2	9	.2	719	54	949	3.15	161	5	ND	1	12	1	56	2	10	4.04	.002	2	106	7.14	1	.01	2	.25	.01	.02	1	1
K 74175	1	2	4	25	.2	182	21	999	3.24	9	5	ND	1	16	1	18	2	87	5.50	.001	2	488	5.17	1	.01	5	2.96	.01	.01	1	2
K 74176	1	9	3	19	.2	630	37	833	3.66	5	5	ND	1	6	1	7	2	34	1.87	.001	2	162	9.01	1	.01	4	1.75	.01	.01	1	1
K 74177	1	7	2	21	.1	718	44	699	3.66	10	5	ND	1	6	1	2	2	25	1.42	.001	2	96	10.38	1	.01	5	2.03	.01	.01	1	1
K 74178	1	87	3	10	.1	1004	57	458	4.11	75	5	ND	1	4	1	11	2	8	.74	.002	2	118	8.75	1	.01	3	.35	.01	.01	1	1
K 74179	1	82	2	14	.1	450	45	716	3.85	204	5	ND	1	7	1	3	2	44	1.70	.002	2	316	8.88	1	.01	2	1.69	.01	.01	1	1
-E 74180	1	.021	3	14	1.0	522	31	626	5.48	3302	5	ND	1	18	1	73	53	8	3.90	.002	2	136	5.58	1	.01	2	.30	.01	.02	1	1
K 74181	1	57	2	6	.1	645	58	588	3.12	289	5	ND	1	3	1	6	2	2	.50	.002	2	74	18.45	1	.01	9	.86	.01	.01	1	3
K 74182	1	26	2	6	.1	537	60	609	3.36	140	5	ND	1	1	1	6	2	2	.22	.002	2	90	11.99	1	.01	3	.05	.01	.01	1	1
K 74183	1	831	2	13	.8	828	51	494	5.86	4888	5	ND	1	4	1	11	96	7	.58	.002	2	175	9.77	1	.01	3	.26	.01	.01	1	1
STD C/AU-R	18	58	36	132	7.2	67	28	1046	4.00	38	18	7	36	47	17	16	19	55	.49	.008	38	55	.90	173	.86	36	1.95	.06	.14	12	518

0.01060216 / 1.6'

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	V	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
E 74184	1	155	5	14	.2	679	45	608	4.28	995	5	ND	2	8	1	8	8	27	2.21	.004	2	268	11.17	1	.01	4	1.22	.01	.03	1	21
E 74185	1	54	2	11	.1	723	53	611	4.24	234	5	ND	2	5	1	8	2	16	.88	.002	2	315	13.23	1	.01	6	.75	.01	.02	1	48
E 74186	1	51	2	6	.1	562	54	683	4.04	60	5	ND	2	2	1	10	2	5	.40	.002	2	183	11.89	1	.01	3	.08	.01	.02	1	8
E 74187	1	19	2	7	.1	593	71	957	4.52	70	5	ND	2	1	1	18	2	3	.23	.002	2	227	14.19	1	.01	7	.04	.01	.01	1	11
E 74188	1	198	4	8	.1	678	53	753	3.79	323	5	ND	2	3	1	13	30	5	.55	.002	2	116	12.39	1	.01	14	.17	.01	.01	1	39
E 74189	1	923	5	18	2.1	1511	422	653	5.53	115	6	10	2	3	1	31	44	7	.41	.002	2	273	11.92	1	.01	4	.17	.01	.01	1	11200
E 74190	1	3706	8	27	5.8	698	59	4377	13.04	49615	9	2	3	14	1	131	52	6	2.06	.002	2	118	10.97	1	.01	3	.13	.01	.02	2	1020
E 74191	1	361	4	12	.5	571	45	841	5.86	8070	5	ND	2	9	1	21	2	32	2.10	.002	2	435	9.87	1	.01	4	1.23	.01	.02	1	106
E 74192	1	20	3	7	.1	672	69	796	3.76	115	5	ND	1	1	1	23	2	2	.17	.002	2	96	13.28	1	.01	3	.07	.01	.02	1	2
E 74193	1	5	3	7	.1	771	69	848	4.13	16	5	ND	2	1	1	5	2	1	.17	.002	2	113	14.39	1	.01	10	.01	.01	.01	1	1
E 74194	1	1	3	8	.1	438	39	552	4.33	6	5	ND	1	1	1	3	2	14	.30	.002	2	204	12.86	1	.01	4	.13	.01	.01	1	14
E 74195	1	1	3	20	.1	276	29	754	4.01	7	5	ND	2	7	1	3	2	52	3.53	.002	2	354	8.74	1	.01	5	1.59	.01	.01	2	2
E 74196	1	7	2	9	.1	537	62	889	3.94	11	5	ND	1	1	1	6	2	3	.27	.002	2	122	14.72	1	.01	6	.83	.01	.01	1	6
E 74197	1	191	6	7	3.3	1493	201	756	3.61	2417	5	73	1	1	1	38	1215	2	.11	.002	2	126	13.74	1	.01	4	.02	.01	.01	1	86400
E 74198	1	496	6	12	.7	1207	158	501	4.57	1572	5	7	2	4	1	17	177	18	.85	.002	2	194	14.24	1	.01	5	.60	.01	.02	1	8120
E 74199	1	60	2	10	.1	914	50	578	3.61	132	5	ND	2	3	1	9	3	9	.58	.002	2	130	15.49	1	.01	4	.35	.01	.01	1	8120
E 74200	1	12	3	9	.1	586	51	726	3.70	30	5	ND	1	2	1	10	2	18	.30	.002	2	220	15.17	1	.01	4	.60	.01	.01	1	2
E 74218	1	7	2	8	.1	504	59	774	4.10	10	5	ND	1	1	1	6	2	6	.26	.002	2	170	13.63	1	.01	4	.16	.01	.01	1	35
E 74219	1	2	3	25	.1	404	38	359	3.61	7	5	ND	1	3	1	7	2	153	.57	.003	2	944	15.64	1	.01	32	1.76	.01	.01	1	21
E 74220	1	2	2	17	.1	974	54	277	4.78	35	5	ND	2	3	1	8	2	15	.65	.002	2	189	14.05	1	.01	26	.19	.01	.01	1	26
E 74221	1	7	5	34	.1	477	36	616	3.91	15	5	ND	2	3	1	4	2	132	.91	.003	2	769	16.31	1	.01	41	2.44	.01	.01	1	12

0.12 oz/l
6.6'

0.92 oz/l
19.68'

SAMPLE#	No PPM	Cu PPM	Pb PPM	Zn PPM	Ag PPM	Hg PPM	Co PPM	Mn PPM	Fe %	As PPM	U PPM	Au PPM	Tb PPM	Sr PPM	Cd PPM	Sb PPM	Bi PPM	V PPM	Ca %	P %	La PPM	Cr PPM	Mg %	Ba PPM	Ti %	B PPM	Al %	Na %	K %	W PPM	As ⁺ PPM
E 74793	1	7	2	17	.1	211	20	152	1.90	2	5	ND	1	6	1	2	2	25	.60	.003	2	383	3.17	2	.01	2	2.25	.06	.01	1	1
E 74794	1	1	3	11	.1	139	12	141	1.14	2	5	ND	1	11	1	2	2	15	1.01	.002	2	284	2.05	2	.01	4	1.94	.09	.01	1	1
E 74795	2	1	2	20	.1	404	24	257	1.23	23	5	ND	1	5	1	30	2	16	2.22	.002	2	282	2.64	1	.01	2	1.16	.01	.01	2	4
E 74796	1	22	2	21	.3	930	76	511	4.90	3	5	ND	1	6	1	7	2	11	2.55	.001	2	333	7.08	1	.01	21	.18	.01	.01	1	3
E 74797	1	26	2	29	.1	200	32	583	3.86	2	5	ND	1	9	1	6	2	55	2.38	.001	2	297	5.61	6	.01	6	4.53	.01	.06	1	4
E 74798	1	2	3	26	.1	177	28	506	2.89	3	5	ND	1	17	1	2	2	60	3.24	.001	2	369	4.95	5	.01	6	4.04	.01	.04	1	3
E 74799	1	1	2	50	.1	236	35	928	4.59	5	5	ND	1	4	1	2	2	103	1.02	.010	2	731	6.56	2	.02	4	5.27	.01	.02	1	1
E 74800	1	94	2	23	.1	231	32	972	3.66	20	5	ND	1	10	2	2	2	48	4.17	.001	2	373	5.46	1	.01	2	2.18	.01	.01	2	6
E 74801	1	60	3	17	.1	224	40	848	4.13	43	5	ND	1	6	1	10	2	13	2.25	.001	2	89	6.77	1	.01	2	.60	.01	.01	1	5
E 74802	1	36	2	30	.1	300	48	989	4.86	110	5	ND	1	9	2	10	2	63	3.07	.001	2	393	6.55	1	.01	5	2.75	.01	.01	1	14
E 74803	1	144	6	32	3.9	336	47	1037	5.57	307	5	ND	1	15	2	13	2	107	2.63	.001	2	806	6.52	1	.01	8	3.41	.01	.01	1	8
E 74804	1	23	2	16	.5	656	58	746	3.71	156	5	ND	1	6	1	12	2	12	1.62	.001	2	164	6.88	1	.01	4	.32	.01	.01	1	29
E 74805	1	838	7	22	5.9	848	57	772	5.42	2220	5	ND	1	11	1	91	310	5	2.79	.001	2	76	6.39	1	.01	3	.30	.01	.01	1	65
E 74806	1	187	3	29	2.4	943	62	541	7.36	416	5	ND	1	6	1	23	17	6	1.62	.001	2	145	5.58	1	.01	2	.20	.01	.01	1	82
E 74807	1	571	2	18	.6	909	68	620	5.59	454	5	ND	1	3	1	9	59	5	.67	.001	2	184	7.09	1	.01	2	.23	.01	.01	1	69
E 74808	1	109	2	18	.1	784	55	592	3.64	307	5	ND	1	5	1	5	5	15	.91	.001	2	164	8.04	1	.01	5	1.19	.01	.01	1	8
E 74809	1	16	2	13	.1	515	41	427	4.10	15	5	ND	1	1	1	2	2	10	.22	.001	2	95	7.59	1	.01	2	.35	.01	.01	2	3
E 74810	1	169	2	14	.3	683	48	435	4.69	62	5	ND	1	1	1	4	2	3	.16	.001	2	125	7.29	1	.01	7	.13	.01	.01	3	7
E 74811	1	71	2	19	.1	625	47	415	3.71	36	5	ND	1	2	1	3	2	32	.23	.001	2	246	7.96	1	.01	3	1.68	.01	.01	1	7
E 74812	1	28	2	11	.1	660	61	833	3.70	73	5	ND	1	1	1	2	2	2	.88	.001	2	90	8.34	1	.01	2	.02	.01	.01	2	7
E 74813	1	227	2	13	.1	811	56	821	3.77	465	5	ND	1	1	1	5	2	1	.21	.001	2	42	7.49	1	.01	3	.01	.01	.01	2	8
E 74814	1	728	2	18	.8	2144	60	947	4.60	1297	5	ND	1	1	1	11	24	1	.19	.001	2	90	7.91	1	.01	5	.02	.01	.01	2	24
E 74815	1	1466	5	25	1.9	765	51	730	7.12	2155	5	ND	1	5	1	121	47	15	.79	.001	2	143	6.26	1	.01	2	1.09	.01	.01	1	37
E 74816	1	138	2	14	.1	950	52	489	4.31	124	5	ND	1	1	1	2	3	5	.54	.001	2	98	7.17	1	.01	3	.19	.01	.01	1	39
E 74817	1	19	3	15	.1	689	45	522	3.47	46	5	ND	1	2	1	2	2	17	.70	.001	2	93	7.44	1	.01	2	1.25	.01	.01	1	5
E 74818	1	24	4	28	.1	509	35	584	3.43	27	5	ND	1	7	1	4	2	42	2.69	.001	2	128	7.01	1	.01	6	3.17	.01	.01	1	3
E 74819	1	190	2	26	1.7	1092	79	514	5.72	3101	5	ND	1	7	1	20	60	23	1.30	.001	2	124	5.78	1	.01	2	1.57	.01	.01	1	3
E 74820	1	233	5	20	.2	1065	80	908	4.06	2716	5	ND	1	1	1	17	10	1	.15	.002	2	47	7.33	1	.01	3	.02	.01	.01	2	9
E 74821	1	625	4	24	1.1	1238	58	759	4.64	2313	5	ND	1	6	1	16	32	4	1.01	.001	2	123	6.79	1	.01	3	.15	.01	.01	1	78
E 74822	1	29	5	15	.1	937	48	470	3.53	160	5	ND	1	2	1	5	2	11	.88	.001	2	119	7.85	1	.01	3	.30	.01	.01	1	14
E 74823	1	8	2	16	.1	810	48	571	3.45	19	5	ND	1	3	1	2	2	11	2.25	.001	2	125	7.26	1	.01	2	.77	.01	.01	1	3
E 74824	1	2	2	18	.1	486	38	588	3.50	4	5	ND	1	4	1	2	2	31	1.93	.002	2	147	6.86	1	.01	3	1.93	.01	.01	1	4
E 74825	1	4	2	16	.1	716	52	500	3.24	18	5	ND	1	1	1	2	2	9	.77	.001	2	75	7.32	1	.01	7	.64	.01	.01	1	6
E 74826	1	54	2	14	.1	843	54	503	3.44	314	5	ND	1	1	1	6	2	7	.49	.002	2	92	7.32	1	.01	4	.28	.01	.01	1	7
E 74827	1	3	8	16	.1	998	54	384	3.19	29	5	ND	1	1	1	2	2	9	.36	.002	2	185	7.16	1	.01	8	.20	.01	.01	1	5
E 74828	1	5	2	16	.1	858	54	399	3.41	51	5	ND	1	2	1	2	2	6	1.14	.001	2	76	7.39	1	.01	6	.38	.01	.01	1	3
E 74829	1	6	4	16	.1	367	52	325	2.57	331	5	ND	1	2	1	8	2	11	.69	.001	2	189	7.42	1	.01	2	.74	.01	.01	1	2
E 74830	1	366	6	15	.4	797	46	716	4.13	560	5	ND	1	4	1	12	2	3	1.47	.001	2	63	7.79	1	.01	2	.27	.01	.01	1	29
E 74831	1	6	2	16	.1	811	48	451	3.30	13	5	ND	1	1	1	2	2	9	1.21	.001	2	88	7.16	1	.01	6	.65	.01	.01	1	1
E 74832	1	2	4	31	.1	764	43	452	3.07	4	5	ND	1	1	1	2	2	20	.41	.002	2	85	7.83	1	.01	10	2.00	.01	.02	1	1

0.004 oz/ton
1.6 feet

0.019 oz/ton
1.6 feet

0.006 oz/ton
1.6 feet

0.013 oz/ton
1.6 feet

0.011 oz/ton
2.3 feet

R 74023	1	1	3	11	.1	286	36	385	3.98	2	5	ND	1	1	1	2	3	16	.18	.001	2	476	7.48	1	.01	2	.16	.01	.01	1	1
R 74034	1	3	2	11	.1	429	56	510	3.83	10	5	ND	1	1	1	2	2	2	.17	.001	2	66	7.83	1	.01	5	.02	.01	.01	1	2
R 74035	1	5	4	13	.3	655	52	469	3.23	275	5	ND	1	2	1	28	2	1	.30	.001	2	50	7.54	1	.01	3	.01	.01	.01	1	3
R 74036	1	5	2	14	.3	668	46	438	3.35	405	5	ND	1	5	1	30	2	2	1.45	.001	2	50	7.49	1	.01	2	.04	.01	.01	1	9
R 74037	1	9	32	46	2.4	245	35	1096	3.67	84	5	ND	1	6	1	5	2	94	2.62	.001	2	596	6.81	1	.01	4	3.86	.01	.01	1	4
R 74038	1	8	6	22	.2	277	25	707	2.74	93	5	ND	1	6	1	25	4	57	5.37	.001	2	366	4.45	1	.01	2	2.12	.01	.01	1	1
R 74039	1	5	4	40	.2	236	30	971	4.13	12	5	ND	1	6	1	2	2	102	5.90	.001	2	724	5.69	1	.01	2	3.69	.01	.01	3	3
R 74040	1	5	2	18	.2	312	28	790	2.51	275	5	ND	1	7	1	52	2	44	4.96	.001	2	278	5.04	1	.01	2	1.18	.01	.01	1	1
R 74041	1	36	3	18	2.9	505	35	859	2.56	2220	5	ND	1	8	1	113	2	41	4.16	.001	2	292	5.24	1	.01	2	1.86	.01	.01	2	12
R 74042	1	1	3	9	.2	199	31	722	2.33	121	5	ND	1	8	1	5	2	19	4.10	.001	2	211	6.29	1	.01	2	.27	.01	.01	1	1
R 74043	1	1	2	10	.1	256	31	535	2.99	8	5	ND	1	1	1	5	2	4	.20	.001	2	93	7.79	1	.01	2	.10	.01	.01	1	1
R 74044	1	6	15	11	1.2	377	38	529	3.37	30	5	ND	1	1	1	3	2	6	.22	.001	2	133	7.29	1	.01	5	.24	.01	.01	1	81
R 74045	1	7	128	10	2.6	306	33	468	3.19	10	5	ND	1	1	1	3	2	5	.31	.001	2	117	7.67	1	.01	2	.12	.01	.01	1	20
R 74046	1	1	2	13	.2	246	30	617	3.17	6	5	ND	1	1	1	2	2	28	.23	.001	2	357	7.88	1	.01	3	.55	.01	.01	1	1
R 74047	1	1	5	15	.2	281	32	746	3.12	2	5	ND	1	1	1	2	2	18	.89	.001	2	288	8.37	1	.01	3	.82	.01	.01	1	1
R 74048	1	4	2	8	.1	455	58	662	3.72	177	5	ND	1	1	1	10	2	5	.87	.002	2	219	14.44	1	.01	8	.12	.01	.01	1	2
R 74049	1	63	1093	10	33.5	744	62	725	4.57	1374	5	ND	1	6	2	32	2	4	.72	.002	2	97	12.86	2	.01	11	.10	.01	.01	1	182
R 74050	1	164	3	8	.9	735	59	784	3.27	1001	5	ND	1	1	1	21	2	1	.25	.002	2	94	14.73	1	.01	9	.03	.01	.01	1	9
R 74051	1	3	3	8	.2	392	40	639	3.89	7	5	ND	1	1	1	4	2	1	.85	.002	2	43	15.85	1	.01	10	.02	.01	.01	1	1
R 74052	1	2	2	7	.1	309	43	639	3.21	10	5	ND	1	1	1	4	2	1	.84	.002	2	54	15.24	1	.01	6	.01	.01	.01	1	1
R 74053	1	3	2	8	.1	265	38	594	3.85	9	5	ND	1	1	1	6	2	2	.84	.002	2	158	14.42	1	.01	10	.02	.01	.01	1	5
R 74054	1	2	2	8	.1	291	37	749	3.31	6	5	ND	1	1	1	7	2	9	.18	.002	2	124	14.81	1	.01	7	.19	.01	.01	1	1
R 74055	1	2	2	8	.1	270	36	607	4.00	6	5	ND	1	1	1	7	2	3	.18	.002	2	214	14.64	1	.01	11	.02	.01	.01	1	2
R 74056	1	2	2	8	.1	390	44	586	3.75	4	5	ND	1	1	1	7	2	9	.18	.002	2	247	14.85	1	.01	7	.16	.01	.01	1	3
R 74057	1	171	2	17	.6	437	32	415	4.18	2837	5	ND	1	2	1	2	6	14	.44	.002	2	113	11.82	2	.01	5	.57	.01	.01	2	23
R 74058	1	8	6	35	.2	292	27	666	2.81	286	5	ND	1	3	1	8	2	31	.45	.001	2	159	13.31	1	.01	7	3.81	.01	.01	1	1
R 74059	1	206	2	24	.7	425	27	633	11.00	53764	5	ND	1	6	3	37	26	3	2.41	.002	2	187	7.10	2	.01	2	.11	.01	.01	1	235 - 0.006 oz/lb 1 foot
R 74060	1	3	2	25	.2	381	42	842	4.25	223	5	ND	1	4	1	2	2	49	2.38	.002	2	759	12.82	1	.01	11	1.52	.01	.01	1	1
R 74061	1	3	2	26	.2	422	37	739	4.30	137	5	ND	1	3	1	2	2	64	1.38	.002	2	835	13.79	1	.01	11	1.71	.01	.01	1	1
R 74062	1	5	2	12	.1	791	48	822	4.83	6	5	ND	1	4	1	2	2	6	2.22	.002	2	74	12.85	1	.01	11	.20	.01	.01	1	1
R 74063	1	15	2	17	.1	699	48	750	3.91	42	5	ND	1	2	1	2	2	12	1.30	.002	2	189	12.71	1	.01	4	.45	.01	.01	1	1
R 74064	1	24	2	18	.2	752	48	519	4.84	160	5	ND	1	1	1	2	2	3	.72	.002	2	180	12.59	1	.01	4	.12	.01	.01	1	1
R 74065	1	2222	2	36	4.2	800	43	492	10.98	26747	5	ND	2	3	2	10	243	19	.89	.001	2	368	8.82	1	.01	7	.78	.01	.01	1	280 - 0.008 oz/lb 2.3 foot
R 74066	1	40	2	20	.4	564	47	563	4.82	354	5	ND	1	4	1	4	2	29	1.10	.002	2	213	10.78	1	.01	7	1.32	.01	.01	1	2
R 74067	1	4	2	35	.2	490	37	622	3.69	23	5	ND	1	3	1	2	2	44	1.14	.001	2	224	10.93	1	.01	4	2.88	.01	.01	1	1
R 74068	1	9	2	14	.3	715	56	788	6.22	240	5	ND	1	2	1	2	2	7	.55	.002	2	333	12.87	1	.01	5	.14	.01	.01	1	1
R 74069	1	112	2	17	.5	956	64	792	4.24	1614	5	ND	1	3	2	7	13	6	.90	.002	2	168	11.81	1	.01	4	.24	.01	.01	1	2
R 74070	1	12	2	20	.1	553	49	626	3.77	277	5	ND	1	2	1	9	3	14	.49	.002	2	170	12.94	1	.01	7	1.17	.01	.01	3	1
R 74071	1	4	2	18	.1	1808	68	660	4.96	11	5	ND	1	1	1	2	2	10	.62	.002	2	382	14.24	1	.01	13	.38	.01	.01	1	3
R 74072	1	4	2	20	.3	1857	48	376	4.86	15	5	ND	1	3	1	2	2	4	2.36	.002	2	120	11.52	1	.01	15	.89	.01	.01	1	2
R 74073	1	12	2	15	.1	980	62	731	4.10	50	5	ND	1	1	1	4	2	4	.69	.001	2	285	12.19	1	.01	3	.87	.01	.01	1	1
R 74074	1	4	4	33	.1	251	26	646	3.66	5	5	ND	1	5	1	2	2	84	3.88	.001	2	769	8.15	3	.01	8	3.71	.01	.89	1	1
R 74075	1	12	2	17	.2	531	45	783	3.65	117	5	ND	1	5	1	2	2	7	2.56	.002	2	87	9.74	1	.01	3	.18	.01	.01	1	1
R 74076	1	61	2	19	.5	944	51	779	4.83	1311	5	ND	1	7	1	3	2	9	2.84	.002	2	245	11.49	1	.01	4	.31	.01	.01	1	4
R 74077	1	3	2	10	.1	750	70	931	4.12	45	5	ND	1	1	1	13	2	3	.11	.002	2	187	14.61	1	.01	6	.84	.01	.01	1	1
R 74078	1	2	2	20	.1	1847	47	482	4.89	17	5	ND	2	1	1	3	2	32	.17	.002	2	399	15.12	1	.01	21	.21	.01	.01	2	1

E 74222	1	4	5	26	.3	227	20	586	2.33	2	5	ND	1	3	1	2	2	35	1.83	.001	4	217	5.24	1	.01	8	3.19	.01	.02	1	1
E 74223	1	4	2	13	.2	447	39	361	3.67	12	5	ND	2	2	2	2	2	12	.46	.001	2	214	6.49	1	.01	9	.25	.01	.01	1	1
E 74224	1	4	6	43	.4	328	35	678	3.65	18	5	ND	3	16	1	2	2	63	2.16	.001	3	288	15.00	1	.01	14	3.73	.01	.01	1	2
E 74225	1	565	10	22	1.6	434	32	983	6.85	4277	5	ND	2	25	1	12	35	4	3.60	.001	3	80	6.17	2	.01	9	.15	.01	.01	5	135
E 74226	1	11	2	17	.4	602	42	466	3.73	54	5	ND	3	2	1	2	2	29	.31	.002	3	380	14.62	1	.01	9	.62	.01	.01	2	1
E 74227	1	7	3	16	.7	642	45	818	4.02	62	5	ND	3	1	1	2	2	9	.10	.001	2	171	15.53	1	.01	10	.31	.01	.01	1	3
E 74228	1	17	4	13	.1	458	37	478	3.91	30	5	ND	3	1	1	2	2	18	.12	.002	2	259	14.96	1	.01	11	.58	.01	.01	1	1
E 74229	1	2	2	16	.3	481	36	412	3.80	2	5	ND	3	1	2	2	2	12	.14	.001	3	107	14.88	1	.01	11	.59	.01	.01	1	1
E 74230	1	3	2	10	.1	432	36	476	4.30	6	5	ND	4	1	1	2	2	13	.08	.002	4	154	14.79	1	.01	8	.15	.01	.01	1	1
E 74231	1	7	2	15	.3	449	37	346	4.67	11	5	ND	4	1	1	2	2	35	.19	.001	2	171	14.77	1	.01	10	.82	.01	.01	1	1
E 74232	1	5	5	16	.2	630	46	653	3.66	9	5	ND	3	1	1	2	2	8	.14	.002	2	109	15.33	1	.01	12	.91	.01	.01	2	1
E 74233	1	2	2	17	.2	487	41	551	3.91	3	5	ND	4	1	1	2	2	13	.27	.002	2	137	14.33	1	.01	11	.91	.01	.01	1	1
E 74234	1	8	2	14	.1	863	43	609	3.12	227	5	ND	3	4	2	15	2	5	.74	.002	2	144	14.95	1	.01	7	.19	.01	.01	1	2
E 74235	1	4	3	17	.1	1509	58	729	2.55	198	5	ND	2	1	1	3	2	3	.19	.001	2	63	15.60	1	.01	8	.09	.01	.01	1	1
E 74236	1	119	4	19	.3	1463	56	540	2.72	1863	5	ND	3	2	1	7	2	8	.58	.001	3	116	13.93	1	.01	9	.30	.01	.01	1	1
E 74237	3	11184	10	146	18.2	865	78	33	43.07	1013	5	ND	10	1	4	22	396	3	.01	.004	2	26	.60	8	.01	5	.13	.01	.02	34	229
E 74238	1	14424	7	106	23.6	783	40	188	20.73	50496	5	ND	5	4	4	152	3908	5	.99	.008	2	152	2.37	4	.01	5	.17	.01	.01	1	438
E 74239	1	1900	2	24	1.7	745	41	249	11.91	2642	5	ND	4	1	1	8	146	6	.28	.001	2	163	4.66	2	.01	5	.28	.01	.01	4	21
E 74240	1	1815	2	19	1.4	742	40	342	10.59	15372	5	ND	4	3	3	11	146	2	1.02	.001	2	104	3.79	2	.01	7	.09	.01	.01	2	89
E-74241	1	41	2	13	.3	542	32	512	3.68	358	5	ND	3	2	1	2	2	12	.83	.001	2	154	13.83	1	.01	8	.34	.01	.01	1	1
E 74242	1	379	2	15	.4	845	46	380	3.99	1060	5	ND	3	1	1	9	7	5	.46	.002	4	131	6.25	1	.01	6	.16	.01	.02	1	4
E 74243	1	144	2	15	.3	985	53	627	3.43	1041	5	ND	3	4	1	8	9	3	1.84	.002	2	163	6.16	1	.01	7	.88	.01	.01	1	6
E 74244	1	22	5	14	.1	562	47	675	3.64	244	5	ND	2	2	2	2	2	8	.76	.001	2	172	14.26	1	.01	9	.40	.01	.01	1	4
E 74245	1	164	2	14	.3	691	49	563	4.07	2803	5	ND	2	3	1	12	2	15	1.22	.001	2	343	5.95	1	.01	10	.21	.01	.01	1	40
SAMPLE#	No	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Tl	B	Al	Na	K	V	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
E 74245	1	2	2	29	.4	806	71	389	5.01	21	5	ND	3	1	3	4	4	33	.65	.001	2	586	18.05	1	.01	30	.76	.01	.01	1	1

0.004 oz/ton
1.64 feet

0.005 oz/ton
6 feet

74988	1	546	2	11	.9	612	43	565	5.37	6993	5	ND	1	3	1	16	46	12	.02	.001	2	308	9.95	1	.01	6	.30	.01	.01	1	194
74989	1	15	2	25	.2	964	60	597	6.32	887	5	ND	1	1	1	5	2	13	.29	.002	2	283	11.54	1	.01	6	.23	.01	.01	2	2
74990	1	201	2	17	.6	475	41	639	6.06	3082	5	ND	1	5	1	9	24	12	1.32	.002	2	244	9.39	1	.01	3	.30	.01	.01	1	81
74991	1	14	5	20	.1	241	31	1005	3.71	52	5	ND	1	4	1	2	2	55	6.76	.001	2	558	6.61	1	.01	5	3.07	.01	.01	1	3
74992	1	153	2	15	.6	517	52	567	5.81	842	5	ND	2	1	1	2	3	7	.48	.002	2	293	11.20	3	.01	8	.13	.01	.01	1	24
74993	1	11	2	15	.1	856	60	745	4.10	65	5	ND	1	1	1	2	2	4	.74	.002	2	215	12.17	1	.01	4	.08	.01	.01	1	1
74994	1	16	2	18	.1	771	61	918	4.22	438	5	ND	1	2	1	7	2	6	.67	.002	2	287	13.05	1	.01	5	.23	.01	.01	1	7
74995	1	10	2	8	.1	827	64	927	4.36	46	5	ND	1	2	1	4	2	4	.75	.002	2	163	12.06	1	.01	5	.04	.01	.01	1	1
74996	1	15	2	13	.2	361	53	600	4.25	12	5	ND	1	3	1	2	2	7	.59	.002	2	158	11.51	1	.01	4	.19	.01	.01	1	2
74997	1	7	2	14	.1	298	39	587	4.93	6	5	ND	1	2	1	2	2	24	.51	.002	2	468	11.31	1	.01	2	.67	.01	.01	2	1
74998	1	6	2	13	.2	311	35	655	4.58	4	5	ND	1	6	1	3	2	28	.91	.002	2	533	11.94	1	.01	4	.82	.01	.01	1	1
74999	1	8	2	20	.1	497	50	630	4.96	11	5	ND	1	2	1	3	2	23	.90	.002	2	407	13.60	1	.01	27	.57	.01	.01	1	2
75000	1	22	4	22	.2	482	48	844	4.35	6	5	ND	1	6	1	3	2	41	2.55	.002	2	558	11.12	1	.01	31	1.41	.01	.01	1	1
74251	1	14	2	15	.3	745	57	715	4.94	22	5	ND	2	1	2	2	4	.10	.001	2	135	7.54	1	.01	6	.13	.01	.01	2	10	
74252	1	19	2	14	.4	840	62	485	4.81	117	5	ND	3	1	4	3	2	2	.08	.002	2	79	16.25	1	.01	10	.06	.01	.01	1	15
74253	1	2003	4	29	3.8	1188	401	670	9.13	30023	5	ND	3	5	4	109	60	13	.99	.001	2	318	6.00	1	.01	10	.67	.01	.01	1	1725
74254	1	1040	2	18	1.9	633	83	650	8.10	49076	5	ND	2	7	3	164	85	22	2.05	.001	2	354	5.77	1	.01	8	.78	.01	.01	1	985
74255	1	50	2	12	.2	622	42	689	3.60	98	5	ND	2	4	3	4	2	10	2.07	.001	2	305	6.46	1	.01	11	.52	.01	.01	1	7

0.014 oz/ton
3.3 feet

0.002 oz/ton
3.3 feet

0.040 oz/ton
6.6 feet

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Tl	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
E 74001	1	76	10	36	.1	199	29	709	5.72	10	5	ND	1	14	1	8	2	102	2.35	.003	2	314	4.02	24	.02	2	4.02	.04	.10	1	3
E 74002	1	78	2	19	.1	61	16	296	3.75	11	5	ND	1	7	1	9	2	56	.52	.009	2	106	2.04	17	.02	3	2.18	.04	.07	1	1
E 74003	1	106	6	17	.1	51	15	375	3.96	3	5	ND	1	18	1	4	2	91	1.34	.010	2	85	2.10	5	.02	3	2.70	.09	.01	1	3
E 74004	1	341	13	16	.5	34	22	423	4.78	7	5	ND	1	50	1	7	9	87	3.33	.009	2	19	1.30	24	.01	2	3.61	.22	.04	1	1
E 74005	1	263	10	21	.2	31	19	408	4.75	16	5	ND	1	41	1	9	2	116	2.49	.010	2	30	1.78	27	.01	3	3.87	.20	.04	1	3
E 74006	1	366	6	33	.3	172	49	750	6.25	2	5	ND	1	36	1	2	2	101	5.90	.001	2	299	2.62	9	.01	4	3.00	.02	.03	1	1
E 74007	1	54	11	26	.1	104	19	615	4.92	2	5	ND	1	26	1	2	2	98	3.93	.005	2	212	3.16	11	.01	4	4.47	.09	.02	1	1
E 74008	1	16	7	8	.1	22	7	286	2.55	2	5	ND	1	83	1	2	2	57	3.71	.002	2	31	1.38	36	.01	2	4.33	.16	.01	1	2
E 74009	1	38	10	9	.1	19	10	242	2.55	2	5	ND	1	52	1	3	2	79	2.14	.007	2	15	1.22	20	.01	2	3.31	.24	.01	1	1
E 74010	1	191	9	34	.1	44	27	710	6.21	5	5	ND	1	12	1	6	2	130	2.47	.006	2	156	3.43	5	.01	3	3.79	.02	.03	1	3
E 74011	1	96	6	19	.1	44	17	411	2.76	5	5	ND	1	43	1	3	3	78	2.56	.003	2	112	2.07	17	.01	2	3.69	.16	.01	1	1
E 74012	1	42	9	12	.1	33	12	327	3.08	2	5	ND	1	60	1	2	2	76	4.10	.003	2	84	1.44	24	.01	4	4.17	.15	.03	1	1
E 74013	1	66	6	13	.2	42	16	260	3.31	2	5	ND	1	10	1	2	2	63	.72	.009	2	56	1.44	10	.02	2	1.95	.06	.06	1	1
E 74014	1	329	11	22	.5	27	24	420	6.18	6	5	ND	1	12	1	6	4	115	2.26	.013	2	21	1.84	21	.01	4	2.63	.05	.06	1	1
E 74015	1	132	3	16	.1	24	19	273	4.58	5	5	ND	1	7	1	3	2	136	.61	.013	2	27	1.38	9	.03	2	1.82	.06	.04	1	1
E 74016	1	170	6	8	.1	19	17	203	3.06	2	5	ND	1	35	1	4	2	78	1.48	.013	2	13	.97	17	.02	4	2.72	.12	.01	1	3
E 74017	1	215	11	14	.2	35	23	407	3.77	5	5	ND	1	45	1	3	2	83	4.92	.008	2	43	1.40	36	.01	7	4.14	.06	.05	1	5
E 74018	1	140	7	15	.1	34	20	462	4.50	2	5	ND	1	36	1	2	3	109	4.79	.009	2	53	1.92	18	.01	8	3.71	.11	.03	1	5
E 74019	1	203	7	13	.2	39	25	270	3.59	2	5	ND	1	61	1	2	2	76	2.88	.011	2	42	1.46	19	.01	2	4.45	.20	.01	1	1
E 74020	1	3690	7	24	11.1	40	24	251	8.10	40	5	ND	1	41	2	26	85	53	3.01	.005	2	39	.94	25	.01	2	2.50	.09	.04	3	7
E 74021	1	45	3	14	.1	49	11	421	3.56	3	5	ND	1	27	1	4	2	79	6.61	.006	2	84	1.86	25	.01	7	3.41	.06	.05	1	1
E 74022	3	605	83	118	4.4	62	13	563	5.10	630	5	ND	1	39	2	760	21	59	12.28	.003	2	93	1.33	7	.01	9	.89	.01	.02	330	60
E 74023	1	430	95	94	6.1	25	12	336	12.96	360	5	ND	1	6	3	61	510	10	2.53	.061	2	17	.42	3	.01	5	.16	.01	.01	161	37
E 74024	1	550	21	62	1.1	216	21	694	5.34	303	5	ND	1	57	1	48	12	71	6.61	.004	2	203	2.12	19	.01	5	1.25	.02	.04	38	17
E 74025	1	283	8	41	.4	207	24	756	5.22	91	5	SD	1	55	1	56	6	94	4.98	.003	2	225	3.24	15	.01	6	.72	.01	.06	6	1
E 74026	1	482	5	25	.3	36	11	459	3.27	24	5	ND	1	52	87	300	25	22	4.37	.019	2	44	2.34	15	.01	3	.32	.01	.11	25	210
E 74027	1	96	5	25	.3	36	11	459	3.27	24	5	ND	1	23	1	13	2	50	2.71	.017	2	44	1.72	24	.01	9	1.32	.03	.13	2	6
E 74028	1	191	5	30	.5	60	19	764	4.93	30	5	ND	1	34	1	5	6	101	5.85	.004	2	86	3.01	11	.01	4	1.71	.02	.07	25	2
E 74029	1	24	6	24	.1	75	26	526	5.06	2	5	ND	1	14	1	2	2	134	2.72	.007	2	139	3.03	8	.01	2	3.16	.05	.03	1	2
E 74030	1	35	8	20	.1	52	15	332	3.29	3	5	ND	1	13	1	2	2	105	1.53	.014	2	95	1.86	7	.03	3	2.08	.07	.02	1	1
E 74031	1	73	2	17	.2	43	15	246	3.14	2	5	ND	1	5	1	3	2	82	.86	.015	2	67	1.61	4	.04	2	1.39	.04	.01	1	1
E 74032	1	132	2	14	.1	22	12	235	3.12	2	5	ND	1	16	1	2	2	105	.80	.015	2	24	1.47	11	.03	3	1.72	.06	.01	1	1
E 74033	1	23	7	12	.3	56	12	255	2.62	2	5	ND	1	49	1	2	2	49	2.14	.007	2	60	1.73	12	.01	4	3.36	.14	.06	1	7
E 74034	1	330	8	45	1.5	371	53	804	14.77	21	5	ND	1	25	1	7	8	104	3.45	.014	2	515	3.94	2	.01	3	3.55	.01	.04	687	1
E 74035	1	114	7	26	.2	255	21	561	4.36	2	5	ND	1	15	1	2	7	75	3.36	.002	2	426	3.81	4	.01	3	2.93	.03	.01	6	1
E 74036	1	117	9	37	.2	163	32	593	6.84	2	5	ND	1	5	1	2	2	96	1.26	.009	2	284	4.30	4	.04	4	3.71	.04	.02	8	3
STD C/AE-R	17	58	37	132	5.5	66	27	1074	3.98	37	17	6	36	47	17	19	21	57	.45	.064	39	55	.89	171	.86	37	1.91	.06	.14	13	490

.00602
0.981

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Th	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Ti	B	Al	Na	K	F	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
E 74037	1	37	8	35	.1	159	23	514	4.66	2	5	ND	1	5	1	2	2	71	.91	.005	2	335	3.94	1	.02	2	3.33	.03	.02	1	1
E 74038	1	17	3	13	.2	34	11	226	2.31	6	5	ND	1	7	1	2	2	45	.60	.013	2	70	1.55	3	.04	2	1.51	.06	.03	1	1
E 74039	1	51	7	21	.2	31	14	298	3.31	2	5	ND	1	9	1	5	2	63	.55	.011	2	39	1.97	13	.03	2	2.02	.06	.07	2	1
E 74040	1	13	3	11	.1	23	9	186	2.05	3	5	ND	1	5	1	3	2	39	.34	.013	2	37	1.20	16	.03	2	1.22	.05	.10	1	1
E 74041	1	33	5	16	.1	46	13	303	3.17	2	5	ND	1	7	1	2	2	50	.97	.012	2	139	1.97	22	.02	2	2.04	.05	.13	1	2
E 74042	1	32	3	12	.1	39	12	389	2.71	4	5	ND	1	12	1	4	2	68	2.11	.007	2	124	1.77	18	.01	2	1.74	.06	.11	1	1
E 74043	1	49	5	18	.1	117	20	410	4.24	2	5	ND	1	25	1	2	2	74	2.27	.002	2	195	2.35	13	.01	2	2.46	.10	.08	1	1
E 74044	1	43	8	27	.1	137	18	587	4.38	2	5	ND	1	31	1	2	3	95	2.80	.004	2	222	3.39	12	.01	4	3.47	.10	.06	1	2
E 74045	1	851	7	38	.9	189	29	623	10.51	6	5	ND	1	17	1	2	2	100	2.15	.001	2	145	3.38	9	.01	2	3.53	.05	.06	5	1
E 74046	1	56	6	20	.1	79	11	417	3.80	2	5	ND	1	15	1	2	6	68	1.91	.003	2	107	2.28	16	.01	2	2.59	.10	.05	1	2
E 74047	1	368	11	30	.3	145	23	472	7.31	4	5	ND	1	15	1	2	7	86	2.62	.004	2	204	2.62	30	.02	4	3.61	.12	.14	21	1
E 74048	1	30	2	7	.1	9	4	200	1.66	2	5	ND	1	19	1	2	2	45	1.54	.014	2	9	.82	6	.02	2	1.91	.11	.01	1	1
E 74049	1	201	7	13	.2	12	11	261	3.57	3	5	ND	1	16	1	2	2	62	2.52	.016	2	24	1.27	18	.01	2	2.07	.08	.07	1	1
E 74050	1	110	2	9	.2	3	8	242	2.59	3	5	ND	1	20	1	2	2	51	1.66	.017	2	1	.85	9	.02	4	1.68	.09	.04	1	1
E 74051	1	63	5	9	.3	6	6	260	2.22	5	5	ND	1	19	1	2	2	50	2.16	.021	2	5	.93	7	.01	3	1.72	.08	.05	2	1
E 74052	1	55	6	15	.2	20	9	399	2.82	3	5	ND	1	14	1	2	2	72	2.88	.007	2	28	1.49	3	.01	2	1.74	.04	.05	1	1
E 74053	1	390	3	12	.4	14	20	396	5.25	2	5	ND	1	24	1	2	4	43	6.51	.011	2	4	.73	7	.01	2	1.91	.07	.05	2	2
E 74054	1	169	4	17	.1	23	13	388	4.10	2	5	ND	1	11	1	2	2	76	2.94	.015	2	49	1.65	10	.01	4	2.04	.03	.07	1	2
E 74055	1	184	5	19	.2	17	14	472	4.03	6	5	ND	1	10	1	3	2	72	2.72	.014	2	5	1.81	5	.01	3	2.07	.02	.04	1	1
E 74056	1	159	5	15	.2	17	14	368	3.81	3	5	ND	1	14	1	2	2	69	2.67	.017	2	8	1.44	5	.01	2	2.03	.04	.05	1	1
E 74057	1	126	6	19	.1	23	15	403	3.83	2	5	ND	1	8	1	2	2	62	2.54	.014	2	39	1.90	5	.01	4	2.21	.01	.05	1	1
E 74058	1	161	4	17	.3	40	26	371	4.26	3	5	ND	1	11	1	2	2	53	1.66	.010	2	31	1.78	6	.01	2	2.26	.06	.03	1	1
E 74059	1	13	5	12	.1	19	10	322	2.52	2	5	ND	1	9	1	2	2	35	.99	.012	2	36	1.48	2	.02	2	1.86	.07	.01	1	1
E 74060	1	78	3	13	.2	16	12	317	2.69	5	5	ND	1	18	1	2	2	47	1.65	.015	2	25	1.27	6	.02	2	2.28	.11	.02	1	1
E 74061	1	33	3	29	.1	30	16	507	3.97	2	5	ND	1	15	1	2	2	84	3.08	.015	2	93	2.18	7	.01	3	2.94	.08	.05	2	3
E 74062	1	102	4	27	.3	32	16	483	4.51	2	5	ND	1	14	1	2	2	82	2.89	.014	2	74	2.25	10	.01	5	2.97	.05	.06	1	2
E 74063	1	98	2	24	.1	26	17	346	3.69	2	5	ND	1	16	1	2	2	70	1.30	.016	2	62	1.96	23	.03	2	2.75	.10	.10	1	1
E 74064	1	74	2	33	.1	35	22	468	4.91	2	5	ND	1	9	1	2	2	89	1.82	.014	2	84	2.81	21	.02	4	3.35	.05	.11	1	2
E 74065	1	61	2	18	.1	28	13	283	3.86	2	5	ND	1	18	1	2	2	58	1.05	.014	2	76	1.68	14	.03	2	2.40	.12	.05	1	1
E 74066	1	51	2	13	.1	21	11	191	2.65	2	5	ND	1	20	1	2	2	54	.86	.015	2	51	1.40	15	.03	3	2.39	.14	.08	1	2
E 74067	1	97	3	19	.2	24	16	405	3.85	2	5	ND	1	20	1	2	2	90	1.71	.012	2	54	2.09	13	.03	2	2.89	.10	.05	1	1
E 74068	1	98	2	15	.2	10	12	263	3.42	2	5	ND	1	32	1	2	2	140	.63	.013	2	7	1.43	50	.05	3	2.09	.06	.23	1	1
E 74069	1	109	2	16	.1	14	16	364	3.84	2	5	ND	1	26	1	2	2	114	1.06	.011	2	5	1.84	54	.04	2	2.62	.07	.24	1	1
E 74070	1	304	2	13	.4	23	23	274	3.87	2	5	ND	1	14	1	2	2	75	1.59	.010	2	8	1.26	14	.02	3	1.88	.08	.06	1	1
E 74071	1	163	3	16	.2	54	19	321	4.27	2	5	ND	1	23	1	2	2	137	1.16	.009	2	74	1.88	28	.03	2	3.40	.15	.07	1	1
E 74072	1	79	2	14	.1	22	12	246	3.86	2	5	ND	1	24	1	2	2	97	1.21	.013	2	26	1.31	17	.04	2	2.40	.13	.07	1	1
E 74073	1	16	3	21	.2	31	16	238	3.23	2	5	ND	1	47	1	2	2	56	1.79	.004	2	33	1.85	13	.02	4	4.30	.19	.06	1	1
E 74074	1	23	3	8	.2	13	7	138	1.80	2	5	ND	1	55	1	2	3	68	1.69	.009	2	15	.62	18	.03	3	2.72	.14	.04	1	1
E 74075	1	36	3	17	.2	16	9	167	2.80	2	5	ND	1	26	1	2	2	45	1.28	.009	2	5	.95	12	.02	3	2.38	.17	.03	1	2
E 74076	1	77	2	12	.2	16	13	207	2.64	2	5	ND	1	22	1	2	2	73	1.06	.012	2	3	1.80	9	.04	2	1.93	.12	.04	1	1
E 74077	1	70	2	12	.2	15	12	239	2.66	2	5	ND	1	25	1	2	2	82	1.34	.012	2	4	1.84	8	.04	2	1.87	.11	.02	1	1
E 74078	1	229	4	16	.4	18	19	332	3.80	2	5	ND	1	17	1	2	2	103	1.96	.012	2	5	1.44	7	.03	3	2.19	.12	.03	1	1
E 74079	1	168	3	18	.4	21	18	318	3.67	3	5	ND	1	12	1	2	2	86	1.45	.010	2	18	1.51	4	.03	2	2.32	.08	.03	1	2
E 74080	1	80	2	14	.4	43	14	264	3.81	2	5	ND	1	5	1	2	2	69	.97	.013	2	31	1.39	4	.03	2	1.58	.06	.02	1	2
E 74081	1	176	18	17	.6	32	14	213	2.64	5	5	ND	1	18	1	3	2	52	.63	.014	2	16	1.82	7	.03	2	1.17	.06	.01	1	1
E 74082	1	144	2	13	.3	22	18	214	3.83	3	5	ND	1	15	1	2	2	87	1.19	.012	2	4	1.81	10	.04	4	1.97	.13	.03	1	1
E 74083	1	58	2	9	.1	17	13	169	2.89	2	5	ND	1	35	1	2	2	76	1.59	.011	2	4	.65	11	.04	3	2.48	.21	.04	1	2
E 74084	1	3	3	20	.2	129	18	229	3.80	2	5	ND	1	7	1	2	2	41	.49	.006	2	314	3.11	5	.02	3	2.77	.07	.03	1	15

R 74079	1	209	5	61	.5	249	30	729	5.54	88	5	ND	1	23	1	5	6	104	3.93	.002	2	396	4.48	15	.01	2	.70	.01	.02	13	1
R 74080	1	718	7	50	1.4	107	17	728	6.47	103	5	ND	1	21	1	24	9	130	7.73	.001	2	254	4.68	7	.01	4	.33	.02	.01	145	5
R 74081	1	518	74	44	6.3	81	21	454	7.14	809	5	ND	1	15	1	69	58	4.13	.002	2	79	2.79	8	.01	6	.26	.02	.05	202	49	
R 74082	1	320	9	34	.6	33	22	611	4.41	152	5	ND	1	19	1	9	5	131	3.10	.002	2	25	2.53	21	.01	7	.44	.02	.06	10	2
R 74083	1	286	4	28	.5	26	22	645	4.67	171	5	ND	1	18	1	13	4	150	3.84	.002	2	20	2.63	10	.01	7	.45	.02	.05	16	4
R 74084	1	438	17	44	2.7	52	36	536	11.21	870	5	ND	1	13	1	71	150	4.02	.001	2	40	2.20	8	.01	2	.33	.02	.05	24	88	
R 74085	1	80	3	14	.3	34	7	595	3.85	102	5	ND	1	46	1	4	2	93	11.95	.002	2	54	4.08	9	.01	8	.53	.04	.02	37	2
R 74086	1	226	4	16	.4	29	16	416	4.33	48	5	ND	1	32	1	3	2	132	3.86	.007	2	22	1.90	19	.01	5	.93	.04	.05	5	4
R 74087	1	389	12	28	.9	106	16	522	7.15	348	5	ND	1	39	1	2	24	111	4.76	.004	2	183	3.20	23	.01	8	2.24	.01	.08	9	6
R 74088	1	594	4	30	1.1	30	13	602	7.24	47	5	ND	1	37	1	2	2	139	5.31	.015	2	70	2.62	23	.01	5	2.50	.01	.10	2	3
R 74089	1	433	10	20	6.4	25	11	162	8.32	166	5	ND	1	14	1	3	40	6	2.55	.001	2	17	.60	5	.01	2	.12	.01	.01	13	12
R 74090	1	969	10	34	2.3	75	22	527	8.65	880	5	ND	1	13	1	25	28	192	4.20	.004	2	150	2.13	12	.01	5	2.04	.02	.06	78	99
R 74091	1	295	5	30	.9	22	15	543	5.04	27	5	ND	1	29	1	2	3	150	3.73	.017	2	23	2.21	32	.01	6	3.27	.13	.09	1	1
R 74092	1	164	5	21	.5	32	16	519	5.24	41	5	ND	1	16	1	2	2	161	3.07	.016	2	29	2.33	17	.01	6	2.97	.07	.07	1	3
R 74093	1	45	8	20	.2	54	18	475	4.64	17	5	ND	1	7	1	2	5	142	1.74	.010	2	72	2.50	8	.05	3	2.65	.04	.04	1	1
R 74094	1	60	4	14	.3	18	13	327	3.24	6	5	ND	1	5	1	2	4	122	.91	.008	2	19	1.61	6	.07	7	1.77	.05	.02	1	2
R 74095	1	186	2	12	.3	19	17	296	2.95	6	5	ND	1	7	1	2	2	106	.88	.008	2	18	1.38	7	.05	5	1.62	.06	.02	1	1
R 74096	2	166	2	18	.2	32	16	203	2.66	2	5	ND	1	4	1	2	2	64	.57	.011	2	57	1.38	5	.02	2	1.36	.05	.01	1	5
R 74097	1	60	13	21	.1	101	22	537	5.11	51	5	ND	1	26	1	2	2	113	3.19	.014	2	148	3.02	12	.01	2	3.02	.10	.03	1	1
R 74098	1	42	9	17	.1	50	23	482	4.28	5	5	ND	1	60	1	2	2	117	3.77	.015	2	63	2.46	12	.01	2	4.28	.22	.02	2	2
R 74099	1	80	7	12	.1	21	22	298	3.19	2	5	ND	1	57	1	2	2	137	2.80	.018	2	34	1.60	13	.02	6	3.71	.24	.02	1	3
R 74900	1	377	12	19	.7	23	15	364	5.70	10	5	ND	1	25	1	2	3	114	2.17	.015	2	39	2.21	21	.01	3	3.36	.09	.07	1	4
R 74101	1	58	10	17	.1	24	17	368	4.47	2	5	ND	1	38	1	2	2	119	1.86	.016	2	30	2.56	12	.02	2	3.90	.17	.03	1	1
R 74102	1	6	12	18	.1	93	19	464	4.18	9	5	ND	1	47	1	2	2	111	3.75	.014	2	177	3.50	14	.01	5	4.65	.13	.04	2	2
R 74103	1	2	15	24	.1	215	27	576	5.13	29	5	ND	1	24	1	3	2	112	4.15	.006	2	449	5.22	2	.01	4	4.26	.01	.01	1	1
R 74104	1	495	16	25	.7	110	18	507	6.26	84	5	ND	1	28	2	2	12	95	4.31	.003	2	213	3.36	15	.01	5	3.82	.05	.03	1	4
R 74105	1	47	10	20	.1	218	20	522	3.52	85	5	ND	1	39	1	2	3	67	5.10	.003	2	634	3.94	3	.01	2	3.04	.04	.01	2	1
R 74106	1	3	4	16	.1	145	16	326	2.93	12	5	ND	1	36	1	2	3	62	2.62	.003	2	360	3.12	7	.01	4	3.07	.11	.01	1	1
R 74107	1	18	8	24	.1	146	20	566	4.52	2	5	ND	1	13	1	2	2	109	3.46	.007	2	261	3.90	3	.02	2	3.15	.02	.01	2	1
R 74108	1	137	5	14	.1	26	15	394	4.22	2	5	ND	1	5	1	2	2	155	1.14	.008	2	52	2.05	4	.04	5	1.90	.03	.01	1	1
R 74109	2	24	2	11	.1	25	12	263	2.92	2	5	ND	1	5	1	2	2	100	.87	.010	2	50	1.75	4	.03	2	1.62	.05	.01	1	1
R 74110	1	570	17	26	2.5	69	16	357	6.96	91	5	ND	1	24	1	5	29	99	3.36	.006	2	202	2.16	10	.01	7	2.82	.07	.04	3	7
R 74111	1	45	9	17	.1	45	13	312	3.29	2	5	ND	1	13	1	2	2	105	1.00	.008	2	76	2.18	5	.02	3	2.27	.07	.01	1	1
R 74112	1	11	3	15	.1	42	11	321	3.84	2	5	ND	1	3	1	2	3	81	.42	.008	2	64	1.93	5	.04	6	1.81	.04	.01	1	1
R 74113	1	57	5	16	.1	32	10	292	2.51	2	5	ND	1	5	1	2	2	79	.70	.007	2	59	1.62	7	.02	2	1.58	.03	.03	1	2
R 74114	1	15	4	12	.1	41	18	201	1.96	2	5	ND	1	3	1	2	2	44	.38	.004	2	147	1.53	3	.01	2	1.36	.03	.01	1	2
R 74115	1	13	2	14	.1	67	18	211	2.81	2	5	ND	1	3	1	3	2	39	.47	.004	2	159	1.81	3	.01	2	1.46	.03	.01	1	1
R 74116	1	251	5	18	.3	48	14	375	4.46	117	5	ND	1	8	1	3	2	67	3.93	.006	2	126	1.56	6	.01	5	1.68	.03	.02	38	2
R 74117	1	26	2	11	.1	28	10	247	2.85	3	5	ND	1	4	1	2	2	48	.83	.005	2	70	1.37	4	.01	6	1.40	.05	.01	1	1
R 74118	1	15	2	9	.2	25	8	226	1.80	2	5	ND	1	4	1	2	2	42	.97	.005	2	62	1.14	5	.01	2	1.31	.05	.01	1	1
R 74119	1	93	8	19	.2	68	20	411	4.47	2	5	ND	1	7	1	2	2	117	.78	.005	2	153	2.71	47	.02	3	3.89	.05	.02	1	1
R 74120	1	31	12	22	.1	66	21	682	5.33	3	5	ND	1	26	1	2	2	147	1.35	.014	2	171	3.06	14	.02	3	5.18	.18	.01	1	1
R 74121	1	186	6	18	.1	44	22	420	4.97	2	5	ND	1	16	1	2	2	134	1.02	.004	2	188	2.58	29	.01	2	3.69	.11	.01	1	1

K 74122	1	15	2	20	.1	137	22	682	4.42	276	5	ND	1	68	1	7	2	82	7.48	.002	2	189	3.64	6	.01	4	.22	.02	.01	7	1
K 74123	1	206	9	32	1.1	71	18	592	4.26	2506	5	ND	1	71	1	78	6	74	7.42	.003	2	115	3.11	15	.01	6	.35	.02	.02	6	8
K 74124	1	179	12	25	1.6	83	15	658	4.20	298	5	ND	1	70	1	65	8	64	7.34	.003	2	106	3.07	10	.01	5	.36	.02	.04	8	5
K 74125	1	209	22	36	1.9	84	16	707	4.37	364	5	ND	1	86	1	70	10	76	9.08	.004	2	134	3.37	13	.01	6	.41	.02	.02	9	8
K 74126	1	253	8	21	.4	31	20	629	6.00	129	5	ND	1	29	1	52	2	132	3.84	.006	2	37	2.37	12	.01	4	.47	.02	.03	9	1
K 74127	1	296	2	21	.3	42	28	543	6.43	79	5	ND	1	21	1	8	2	138	3.39	.006	2	44	2.49	17	.01	7	.52	.02	.02	11	1
K 74128	1	1637	12	54	7.4	17	10	456	9.85	14748	5	ND	1	25	3	64	18	60	3.07	.001	2	19	2.11	27	.01	8	.55	.03	.07	8	123
K 74129	1	277	4	29	.5	100	30	622	6.20	31	5	ND	1	53	2	2	2	98	4.81	.003	2	142	3.64	14	.01	7	1.27	.05	.03	8	1
K 74130	1	128	10	19	.2	41	20	592	4.82	32	5	ND	1	24	1	2	2	107	3.27	.007	2	58	2.78	8	.01	4	2.11	.03	.02	1	1
K 74131	1	59	6	16	.1	24	14	464	4.21	2	5	ND	1	13	1	2	2	113	2.14	.007	2	34	2.18	7	.01	3	2.32	.07	.02	1	1
SAMPLE#	Mo	Cu	Pb	Zn	Ag	H1	Co	Mn	Fe	As	U	Au	TH	Se	Cd	Sb	Bi	V	Ca	P	La	Cr	Hg	Ba	Tl	B	Al	Na	K	W	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
K 74132	1	788	13	23	2.5	42	25	593	8.99	369	5	ND	1	21	1	2	19	103	4.59	.006	2	39	2.23	12	.01	2	3.04	.05	.06	5	7
K 74133	1	227	9	16	.1	63	24	412	4.36	20	5	ND	1	10	1	3	2	99	1.61	.011	2	89	2.22	3	.02	2	2.51	.06	.02	1	1
K 74134	1	146	8	16	.1	48	18	463	4.59	15	5	ND	1	18	1	4	2	119	2.47	.014	2	95	2.30	7	.02	6	2.99	.07	.03	1	2
K 74135	1	720	14	22	2.6	21	9	303	5.70	3909	5	ND	1	5	1	19	31	48	1.71	.015	2	37	1.49	31	.01	4	1.99	.01	.10	1	71
K 74136	1	111	6	15	.1	27	15	401	5.10	23	5	ND	1	12	1	2	2	111	1.59	.011	2	38	1.89	9	.01	2	2.97	.06	.05	1	1
K 74137	1	172	7	14	.3	34	15	314	4.30	761	5	ND	1	14	1	3	3	75	1.74	.015	2	78	1.90	12	.01	2	2.44	.04	.05	1	32
K 74138	1	8	14	24	.1	121	23	579	4.46	4	5	ND	1	23	1	2	2	113	3.09	.001	2	346	4.97	2	.02	2	4.35	.02	.01	1	1
K 74139	1	182	6	10	.1	19	26	139	4.24	6	5	ND	1	13	1	3	2	118	.78	.016	2	24	.98	11	.04	2	1.40	.07	.06	1	1
K 74140	1	8	5	13	.1	42	13	299	2.88	6	5	ND	1	16	1	2	2	71	1.91	.006	2	118	2.15	13	.02	4	2.06	.07	.02	1	1
K 74141	1	392	10	16	1.8	63	18	274	5.44	35	5	ND	1	62	1	3	75	51	2.75	.004	2	121	1.61	37	.01	5	3.30	.16	.04	6	4
K 74142	1	12	7	21	.1	125	17	301	3.13	4	5	ND	1	13	1	3	2	50	.50	.004	2	281	3.16	15	.02	8	2.68	.04	.01	1	1

0.003 oz/lb
1.6 feet

74351	2	95	4	15	.2	93	19	336	3.45	45	5	WD	2	11	1	2	2	87	1.93	.007	2	257	2.24	3	.04	5	2.30	.08	.02	1	7
74352	2	250	2	14	.6	62	23	274	3.83	27	5	WD	3	17	3	2	2	126	.71	.015	2	139	1.95	4	.06	9	2.47	.12	.02	1	4
74353	1	180	2	10	.1	27	19	293	3.02	6	5	WD	1	14	1	2	2	113	1.12	.013	2	47	1.52	3	.06	4	2.11	.10	.01	1	1
74354	2	197	8	15	.3	170	29	306	4.25	13	5	WD	1	29	3	8	2	120	2.56	.012	2	209	2.32	6	.03	6	3.52	.21	.01	1	1
74355	1	134	3	16	.2	67	17	438	4.21	11	5	WD	1	26	1	2	2	139	3.63	.012	2	94	2.38	8	.02	3	3.30	.15	.03	1	1
74356	2	149	7	21	.3	109	23	435	5.83	196	5	WD	3	13	2	3	2	132	1.21	.004	2	150	2.15	14	.01	7	3.76	.09	.06	1	1
74357	1	197	32	51	1.2	113	24	430	5.83	133	5	WD	2	13	3	4	2	148	2.44	.012	2	141	2.81	22	.01	10	3.62	.02	.05	1	2
74358	1	12	2	21	.1	178	22	339	3.86	6	5	WD	1	43	1	4	2	63	1.88	.004	2	332	4.07	61	.01	8	3.37	.05	.02	1	1
74359	1	78	3	18	.2	87	20	528	4.23	60	5	WD	1	32	1	4	2	94	11.79	.005	2	123	2.26	19	.01	11	1.76	.02	.03	10	1
74360	1	121	11	33	.5	147	25	715	5.94	13	5	WD	1	24	4	5	2	125	6.06	.004	2	354	3.91	14	.01	7	3.38	.04	.03	5	6
74361	17	911	10	56	1.4	79	17	759	10.42	22	5	WD	1	20	2	3	3	160	4.46	.016	2	119	2.78	12	.01	10	2.98	.01	.12	383	1
74362	38	3348	14	46	5.1	105	30	607	26.86	41	5	WD	4	11	1	22	13	62	2.58	.012	2	100	1.11	5	.01	10	1.23	.01	.05	278	1
74363	83	2250	3	52	2.7	78	22	1150	20.55	40	5	WD	3	18	1	21	3	96	4.20	.014	2	158	2.13	7	.01	6	1.65	.01	.07	427	2
74364	2	829	6	63	1.7	119	10	468	9.77	20	5	WD	1	26	1	12	2	118	2.02	.004	2	240	2.93	8	.01	9	2.19	.01	.12	4	1
74365	5	1680	17	51	9.2	31	8	1292	15.10	9032	5	WD	4	26	1	426	75	8	2.97	.002	2	32	1.15	5	.01	8	.14	.01	.04	185	420
74366	2	84	9	22	.6	45	16	503	4.26	543	5	WD	2	25	2	21	2	101	2.63	.019	3	71	1.61	13	.01	8	1.82	.05	.08	2	37
74367	1	14	4	20	.2	171	22	342	3.38	11	5	WD	1	5	1	6	2	67	1.35	.005	2	482	4.15	2	.01	5	2.70	.04	.02	1	1
74368	1	7	4	17	.1	155	17	362	2.81	18	5	WD	1	9	1	4	2	64	2.71	.004	2	414	2.87	3	.02	3	2.86	.04	.01	1	2
74369	1	16	2	11	.2	25	11	297	2.68	20	5	WD	1	5	1	2	2	83	.88	.022	2	29	1.42	2	.04	5	1.32	.05	.02	1	1
74370	2	35	2	16	.4	42	14	432	3.67	10	5	WD	1	12	1	2	2	110	2.66	.013	3	73	1.97	3	.03	6	2.11	.07	.03	1	1
74371	2	124	8	13	.1	24	18	450	4.28	2	5	WD	1	14	3	4	3	90	3.76	.021	2	27	1.49	5	.01	9	2.33	.04	.08	2	1
74372	2	53	8	13	.2	19	11	278	3.94	2	5	WD	2	9	2	2	2	87	1.59	.024	2	23	1.22	6	.01	8	2.13	.04	.08	1	1
74373	1	42	3	16	.1	23	13	441	3.97	5	5	WD	1	6	1	2	3	99	3.83	.023	2	35	1.55	3	.01	5	2.83	.03	.03	1	1
74374	3	2	2	22	.2	128	18	564	3.69	2	5	WD	2	19	3	2	2	83	3.54	.008	3	296	3.11	5	.01	11	1.94	.05	.04	1	1
74375	1	2	2	24	.1	109	19	797	5.78	4	5	WD	1	25	1	4	2	85	11.89	.005	2	222	3.12	3	.01	6	2.33	.02	.03	3	2
74376	1	2	3	26	.1	136	22	522	4.12	2	5	WD	1	17	1	4	6	94	3.21	.012	3	324	3.68	3	.01	3	2.75	.04	.01	3	1
74377	1	2	9	30	.2	325	32	487	4.61	3	5	WD	3	8	2	2	2	60	1.75	.004	2	408	5.31	2	.01	8	3.63	.02	.01	1	1
74378	1	1	8	27	.1	180	23	768	4.31	2	5	WD	1	15	2	2	2	86	2.61	.005	2	278	4.26	1	.01	8	2.56	.02	.01	1	1
74379	1	1	3	20	.1	103	17	460	3.41	7	5	WD	1	10	1	2	3	71	3.17	.004	2	264	2.95	2	.01	5	2.13	.04	.01	1	1
74380	1	3	8	23	.1	122	19	666	4.32	2	5	WD	1	9	1	2	2	92	4.48	.016	2	298	2.98	3	.01	7	2.75	.04	.01	2	1

} 0.006 oz/ton
5.6 feet

SAMPLE#	Mo	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Tb	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Yt	B	Al	Na	K	W	Au*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPM
K 74201	1	37	3	11	.2	42	10	175	2.87	35	5	ND	1	6	1	4	5	76	1.02	.008	2	89	1.10	5	.04	2	1.37	.04	.06	1	2
K 74202	1	36	2	11	.1	42	11	180	3.34	24	5	ND	1	5	1	3	2	90	.66	.007	2	118	1.24	8	.04	3	1.50	.05	.11	1	2
K 74203	1	87	16	35	.4	31	24	365	4.58	13	5	ND	1	16	1	2	2	117	1.24	.040	2	27	1.75	4	.20	6	2.16	.04	.05	1	1
K 74204	1	67	2	23	.1	34	22	336	4.77	28	5	ND	1	10	1	2	2	109	1.19	.032	2	54	1.84	2	.20	2	2.02	.04	.03	2	1
K 74205	1	29	5	15	.1	52	15	292	3.34	15	5	ND	1	6	1	2	5	74	1.26	.012	2	143	1.79	7	.04	2	1.79	.04	.10	1	2
K 74206	2	20	6	10	.4	15	9	256	3.69	2	5	ND	2	9	1	2	2	70	1.73	.019	3	21	.97	7	.04	8	1.53	.03	.09	1	1
K 74207	1	19	6	12	.1	26	12	314	3.23	7	5	ND	1	9	1	2	2	75	2.15	.009	2	32	1.17	3	.02	6	1.52	.03	.06	1	36
K 74208	1	63	2	8	.4	108	25	188	4.24	20	5	ND	2	6	1	3	2	15	1.02	.002	2	57	.40	5	.01	11	.82	.01	.15	1	1
K 74210	1	151	3	21	.3	114	22	465	4.10	11	5	ND	2	9	2	2	2	137	2.08	.006	2	239	2.89	2	.02	8	2.74	.03	.04	1	1
K 74211	1	14	2	32	.2	163	25	363	3.07	35	5	ND	1	10	1	4	2	75	1.70	.007	5	284	2.96	2	.03	4	2.54	.03	.03	1	1
K 74212	1	75	3	9	.3	22	8	164	1.80	3	5	ND	1	11	1	2	2	38	1.79	.009	4	42	.75	2	.03	7	.90	.04	.03	1	1
K 74213	2	86	2	10	.3	22	7	176	1.99	2	5	ND	2	5	1	2	2	40	1.17	.011	2	24	.83	4	.04	9	.93	.04	.04	1	1
K 74214	1	39	3	21	.1	143	20	249	2.61	4	5	ND	2	7	1	2	2	61	.78	.005	3	234	1.99	4	.83	8	1.96	.05	.05	1	1
K 74215	1	62	2	12	.3	28	13	191	3.09	2	5	ND	2	6	1	2	2	103	1.22	.005	4	62	1.09	3	.02	7	1.34	.05	.04	1	1
K 74216	1	71	3	11	.4	27	13	195	2.93	2	5	ND	2	6	1	2	2	95	1.02	.004	2	64	1.10	3	.02	8	1.35	.06	.04	1	4
K 74217	1	28	2	9	.2	26	10	168	2.32	2	5	ND	3	5	3	2	2	78	.87	.004	2	59	.94	2	.01	9	1.18	.05	.03	1	1

E 74256	1	19	3	35	.1	148	23	611	4.70	10	5	ND	1	15	1	2	2	102	4.21	.005	2	276	3.00	15	.01	0	3.00	.02	.03	1	1
E 74257	1	46	2	29	.2	132	23	732	5.03	213	5	ND	1	21	1	9	4	120	6.07	.010	2	256	3.62	3	.01	5	3.34	.02	.04	2	14
E 74258	1	45	2	40	.1	133	25	728	5.36	10	5	ND	1	21	1	2	2	123	4.42	.009	2	255	4.58	2	.02	6	3.94	.01	.03	2	1
E 74259	1	35	2	57	.1	127	25	680	5.20	24	5	ND	1	22	1	2	3	114	2.57	.009	2	184	4.24	2	.03	6	3.67	.02	.01	1	1
E 74260	1	6	2	33	.1	213	25	409	3.60	2	5	ND	1	11	1	2	2	53	.96	.002	2	367	4.22	1	.02	5	3.04	.02	.01	1	1
E 74261	1	19	2	9	.1	23	8	183	1.66	6	5	ND	1	18	1	2	2	27	1.59	.016	2	53	.99	2	.06	2	1.36	.03	.01	1	2
E 74262	1	30	2	40	.1	86	23	518	4.22	4	5	ND	1	36	1	2	3	87	1.75	.002	2	191	3.26	1	.03	2	3.01	.01	.01	1	1
E 74263	1	49	2	21	.1	79	15	284	2.40	6	5	ND	1	40	2	2	3	56	2.91	.002	2	114	1.69	4	.03	2	2.21	.02	.01	1	3
E 74264	1	138	2	24	.1	42	15	311	2.69	2	5	ND	1	23	1	2	2	60	1.64	.003	2	70	1.74	2	.03	2	1.91	.02	.01	1	1
E 74265	1	16	2	32	.1	126	22	620	4.33	2	5	ND	1	22	1	2	2	99	4.63	.010	2	244	3.60	2	.02	4	3.24	.03	.03	1	1
E 74266	1	10	3	38	.1	156	25	756	4.97	2	5	ND	1	28	2	2	2	120	4.97	.009	2	365	4.27	3	.01	6	3.66	.01	.04	1	1
E 74267	1	41	9	23	.1	73	16	594	3.80	4	5	ND	1	22	1	2	3	90	4.40	.013	2	171	2.93	2	.03	2	2.93	.02	.02	1	2
E 74268	1	24	7	39	.2	170	28	779	5.05	2	5	ND	1	31	1	2	4	115	3.96	.004	2	575	4.59	2	.01	3	2.91	.02	.01	1	1
E 74269	1	19	6	47	.1	98	25	917	5.11	20	5	ND	1	44	1	2	2	106	6.43	.002	2	329	4.40	2	.01	3	1.50	.01	.01	3	2
E 74270	1	44	2	39	.1	99	21	694	5.95	111	5	ND	1	57	1	5	2	59	6.65	.003	2	63	3.21	6	.01	7	.76	.01	.00	1	102
E 74271	1	40	2	40	.1	70	22	601	5.40	155	5	ND	1	39	1	2	3	50	4.31	.003	2	48	2.47	6	.01	6	1.05	.02	.09	1	71
E 74272	1	36	2	34	.1	113	26	593	4.75	257	5	ND	1	40	1	2	3	50	4.72	.002	2	69	2.65	6	.01	6	.95	.02	.09	2	13
E 74273	2	65	4	30	.2	93	21	586	5.04	131	5	ND	1	33	1	5	2	55	4.35	.002	2	70	2.61	4	.01	4	1.39	.02	.08	3	72
E 74274	2	54	2	33	.1	77	22	487	5.79	57	5	ND	1	29	1	4	2	70	3.07	.002	2	73	2.25	5	.01	5	2.28	.02	.07	1	64
E 74275	1	76	3	34	.4	48	18	845	5.18	51	5	ND	1	33	1	2	2	114	4.29	.016	2	70	3.29	11	.01	3	2.19	.02	.06	1	11
SAMPLE#	No	Cu	Pb	Zn	Ag	Ni	Co	Mn	Fe	As	U	Au	Tb	Sr	Cd	Sb	Bi	V	Ca	P	La	Cr	Mg	Ba	Ti	B	Al	Na	K	W	Am*
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	%	%	PPM	PPM	%	PPM	%	PPM	%	%	%	PPM	PPB
E 74276	1	90	22	39	2.5	131	26	871	5.15	585	5	ND	1	42	1	22	4	113	4.71	.006	2	167	4.53	7	.01	10	1.58	.02	.05	1	13
E 74277	1	40	2	33	.4	150	23	751	4.34	138	5	ND	2	61	1	6	3	62	10.60	.003	2	96	4.63	4	.01	11	.45	.01	.05	4	48
E 74278	1	26	3	35	.2	199	24	898	4.54	40	11	ND	1	82	1	6	2	49	15.53	.002	2	118	5.81	4	.01	7	.36	.01	.04	4	19
E 74279	1	1012	379	58	34.3	80	18	798	7.73	42351	5	ND	2	52	2	240	77	34	9.50	.001	2	51	3.14	5	.01	8	.34	.02	.05	4	270
E 74280	1	36	10	31	.9	176	28	716	4.97	1529	5	ND	1	52	1	20	2	114	4.94	.002	2	111	4.60	5	.01	6	.37	.02	.02	4	16
E 74281	1	16	4	19	.4	93	18	622	4.51	261	5	ND	1	41	1	6	2	135	9.51	.004	2	58	3.88	3	.01	7	.34	.02	.01	4	2
E 74282	1	7	5	34	.1	125	24	680	5.27	26	5	ND	1	31	1	3	2	153	4.26	.005	2	251	4.68	3	.01	9	1.39	.02	.01	2	1
E 74283	1	13	4	33	.2	72	19	600	4.60	26	5	ND	1	30	1	4	4	120	4.77	.003	2	188	4.21	2	.01	7	.44	.02	.01	4	1
E 74284	1	14	2	35	.3	197	27	852	4.88	10	5	ND	1	31	1	3	3	110	9.73	.003	2	314	5.41	4	.01	13	.73	.02	.02	4	4
E 74285	1	12	2	27	.3	114	23	603	4.82	16	5	ND	2	23	1	2	2	140	3.42	.004	2	154	3.38	3	.01	8	.41	.03	.01	1	1
E 74286	1	57	2	35	.1	75	20	684	4.50	24	5	ND	1	47	1	2	2	124	9.50	.003	2	104	3.79	3	.01	9	.45	.02	.01	5	1
E 74287	1	4	3	29	.1	128	23	631	3.88	18	5	ND	1	42	1	2	2	105	9.50	.003	2	149	3.75	2	.01	10	.41	.02	.01	3	1
E 74288	1	6	2	21	.2	75	22	627	4.13	3	5	ND	2	35	1	2	3	130	3.86	.005	2	125	3.55	3	.01	9	.98	.02	.01	2	4

0.002 oz/ton
3.3 feet

0.008 oz/ton
1.6 feet

SAMPLE#	Mo PPM	Cu PPM	Pb PPM	Zn PPM	Ag PPM	Ni PPM	Co PPM	Mn PPM	Fe %	As PPM	U PPM	Au PPM	Th PPM	Sr PPM	Cd PPM	Sb PPM	Bi PPM	V PPM	Ca %	P %	La PPM	Cr PPM	Mg %	Ba PPM	Yt %	B PPM	Al %	Na %	K %	W PPM	Au* PPM
X 74086	1	124	2	44	.1	70	21	694	5.33	5	5	ND	1	21	1	2	2	156	4.72	.010	2	139	3.05	2	.01	6	2.89	.02	.01	1	1
X 74087	1	21	5	31	.1	186	28	753	5.66	14	5	ND	1	37	1	2	3	131	5.96	.009	2	414	4.67	5	.01	4	3.29	.01	.04	2	1
X 74088	2	46	9	38	.5	173	26	914	5.59	246	5	ND	1	57	2	15	2	84	8.06	.002	2	271	4.41	8	.01	6	1.19	.01	.07	5	5
X 74089	1	1767	217	149	21.4	47	9	1391	12.90	50696	5	ND	2	36	6	338	149	30	6.52	.001	2	70	2.84	7	.01	5	.42	.02	.03	38	835
X 74090	1	3296	49	56	23.0	9	16	2347	15.52	50805	5	2	2	10	4	368	137	6	5.36	.001	2	19	3.10	4	.01	4	.09	.02	.01	146	2065
X 74091	1	2553	447	591	70.5	54	16	1295	16.17	46005	5	ND	2	32	21	319	411	23	4.47	.001	2	83	2.25	7	.01	6	.24	.01	.03	18	935
X 74092	1	247	2	39	1.3	210	28	985	6.81	2550	5	ND	1	47	2	11	5	95	5.39	.004	2	253	4.36	10	.01	5	2.26	.01	.07	4	30
X 74093	1	71	2	47	.5	265	33	930	5.87	831	5	ND	1	38	1	4	4	128	6.12	.010	2	291	4.86	4	.01	5	3.16	.01	.03	5	10
X 74094	1	46	2	53	.3	68	24	826	5.36	264	5	ND	1	27	1	2	2	152	6.61	.009	2	255	4.09	2	.01	9	3.52	.01	.01	1	4
X 74095	1	108	6	37	.1	53	20	528	4.19	38	5	ND	1	13	1	2	2	98	2.93	.008	2	188	2.96	3	.03	4	2.60	.03	.03	1	1
X 74096	1	44	5	36	.1	247	28	684	4.47	55	5	ND	1	17	1	2	2	95	3.84	.009	2	626	4.92	2	.02	2	3.62	.01	.02	2	1
X 74097	1	31	2	42	.2	239	25	799	4.56	447	5	ND	1	27	1	5	3	104	6.89	.012	2	578	4.19	2	.01	6	3.15	.02	.01	1	9
X 74098	1	9	3	30	.1	68	17	579	4.59	14	5	ND	1	11	1	2	2	126	3.30	.013	2	114	2.78	5	.02	3	2.60	.02	.06	1	1

0.025 oz/ton
6.6 feet

Sample ID	As	Cd	Cu	Pb	Mn	Ni	Co	Zn	Fe	Mo	Ag	Au	Hg	Cr	Se	Bi	V	Ca	P	La	Ce	Nb	Ba	Y	U	Th	U ²³⁵				
74401	1	38	5	17	.1	203	24	276	3.25	11	5	ND	1	13	1	5	2	47	.56	.001	2	357	4.48	9	.01	5	2.08	.03	.03	1	1
74402	1	693	2	30	.6	152	33	672	6.48	1624	5	ND	1	19	1	34	9	88	12.91	.004	2	314	2.95	2	.01	7	2.58	.01	.01	1	26
74403	2	67	8	17	.1	110	23	327	3.87	2	5	ND	1	44	3	4	2	64	2.03	.003	2	235	3.13	6	.02	7	4.00	.10	.02	1	2
74404	1	24	2	16	.1	87	14	449	2.64	43	5	ND	1	54	1	6	2	63	10.27	.004	2	131	2.54	5	.01	9	1.79	.05	.02	3	4
74405	1	246	3	17	.1	72	19	571	3.29	103	19	ND	1	20	1	7	2	101	20.01	.004	2	91	1.07	3	.01	4	1.39	.02	.02	3	3
74406	1	276	3	11	.2	40	29	243	3.50	6	5	ND	1	12	1	2	3	86	1.34	.007	2	76	1.82	3	.02	7	1.78	.06	.01	1	2
74407	1	101	2	11	.1	29	15	244	2.82	17	5	ND	1	9	1	2	2	75	1.35	.005	2	60	1.35	4	.01	5	1.10	.06	.02	1	3
74408	1	198	7	29	.2	66	27	502	5.82	130	5	ND	1	84	1	4	4	88	4.89	.002	2	71	3.53	5	.01	6	.41	.03	.03	1	2
74409	1	474	11	10	.4	174	47	490	10.76	776	5	ND	1	36	1	55	7	63	3.23	.002	2	67	2.30	5	.01	4	.45	.03	.04	3	7
74410	1	271	2	19	.8	46	24	337	5.96	93	5	ND	1	61	1	8	2	29	9.54	.002	2	21	2.57	6	.01	8	.01	.04	.03	4	2
74411	1	323	2	16	.5	20	27	330	3.42	154	5	ND	1	25	2	6	2	53	4.04	.002	2	24	1.73	6	.01	9	.30	.02	.02	2	1
74412	1	472	8	28	.9	111	35	510	6.68	195	5	ND	1	95	3	75	3	79	6.70	.002	2	77	2.84	13	.01	9	.01	.04	.06	4	7
74413	1	683	2	18	1.0	154	43	250	7.25	308	5	ND	2	29	2	30	2	41	1.78	.001	3	88	1.10	11	.01	10	.72	.04	.07	2	5
74414	1	436	2	25	.8	60	48	424	5.89	217	6	ND	1	36	1	6	2	78	9.63	.002	2	35	2.63	5	.01	8	.64	.03	.03	5	1
74415	1	142	4	43	.6	142	37	614	7.55	182	5	ND	3	19	1	4	2	142	1.64	.001	2	177	2.10	11	.01	10	1.15	.03	.06	2	1
74416	1	250	2	20	.3	92	37	340	6.24	51	5	ND	2	21	2	2	2	114	1.78	.002	2	90	1.87	14	.01	10	.85	.04	.06	1	2
74417	1	182	2	17	.1	60	24	342	4.81	22	5	ND	1	47	2	2	2	136	3.91	.002	2	56	2.63	17	.01	5	1.61	.10	.05	1	1
74418	1	42	3	20	.2	61	25	456	5.11	17	5	ND	2	40	1	2	2	138	3.86	.003	2	58	2.97	9	.01	9	1.48	.04	.04	1	1
74419	2	8	6	14	.2	50	22	394	3.81	10	5	ND	1	94	2	4	2	111	4.90	.004	2	65	2.49	27	.01	10	4.25	.25	.04	1	4
74420	1	95	4	19	.4	64	29	479	4.76	159	6	ND	1	67	2	12	5	105	4.84	.002	2	57	3.84	9	.01	7	.79	.04	.03	3	1
74421	2	464	21	49	3.4	67	13	568	4.68	7735	9	ND	1	72	4	68	28	75	11.27	.004	2	138	2.33	16	.01	9	.79	.03	.05	11	30
74422	11	354	114	115	4.1	36	5	350	2.51	5254	5	ND	1	35	4	243	56	26	3.13	.002	2	118	1.47	5	.01	8	.27	.01	.03	23	905
74423	1	209	2	28	.9	148	40	301	7.31	225	5	ND	1	14	1	5	2	83	2.01	.002	2	100	1.37	7	.01	10	.66	.03	.03	2	1
74424	1	181	10	21	.5	31	15	411	4.48	452	5	ND	1	52	1	7	2	94	4.87	.007	2	46	2.15	21	.01	6	1.38	.05	.07	11	3
74425	2	419	2	42	1.2	123	21	600	6.91	137	5	ND	1	52	1	22	12	87	4.87	.003	2	155	3.21	13	.01	10	.51	.03	.05	37	1
74426	1	43	11	17	.3	44	14	468	3.99	18	5	ND	1	21	3	2	3	118	3.19	.004	2	87	2.88	6	.01	9	1.72	.06	.02	1	1
74427	1	222	4	18	4.2	31	19	209	8.35	219	5	ND	1	4	1	1	13	26	1.32	.001	2	43	.82	1	.01	3	.55	.01	.01	2	2
74428	1	222	11	31	.7	106	17	572	7.82	43	5	ND	2	11	1	3	3	124	1.95	.004	2	257	3.74	5	.01	7	3.36	.03	.03	1	1
74429	2	31	2	13	.2	43	13	240	2.63	12	5	ND	2	6	1	2	2	56	1.22	.006	2	83	1.64	4	.02	7	1.47	.06	.02	1	1
74430	1	10	2	21	.3	159	21	357	4.57	22	5	ND	2	7	1	2	2	104	1.18	.006	2	317	4.87	3	.04	6	2.78	.03	.01	8	1
74431	1	488	4	24	3.4	65	19	635	6.83	315	7	ND	1	15	2	3	47	94	9.52	.004	2	184	2.49	5	.01	6	2.27	.05	.01	3	9
74432	1	333	6	21	1.4	28	16	482	4.93	20	5	ND	1	6	1	5	6	98	1.69	.017	2	185	2.86	4	.02	5	2.28	.03	.01	2	3
74433	3	123	3	15	.4	21	11	333	3.76	5	5	ND	1	4	1	4	2	115	.81	.017	2	22	1.95	5	.04	3	1.58	.04	.02	1	3
74434	1	3	6	24	.1	163	24	462	4.94	10	5	ND	1	8	1	2	2	88	2.44	.005	2	377	3.99	3	.01	7	3.74	.04	.01	1	1
74435	1	69	2	18	.1	48	15	574	4.16	8	8	ND	1	15	1	2	2	94	10.93	.003	2	85	2.88	16	.01	11	3.15	.01	.12	2	1
74436	1	6	2	12	.1	25	10	348	2.80	2	5	ND	1	7	1	3	2	95	1.93	.011	2	28	1.98	4	.02	5	1.55	.03	.02	1	1
74437	1	6	3	9	.1	33	9	252	2.14	4	5	ND	1	17	1	2	2	53	1.46	.005	2	87	1.51	10	.01	4	1.90	.10	.02	1	1
74438	1	134	7	24	1.5	98	34	432	8.32	19	5	ND	1	48	1	5	16	181	3.86	.005	2	185	2.62	27	.01	9	4.11	.12	.05	4	5
74439	1	68	2	25	.3	148	20	375	3.77	11	5	ND	1	81	1	2	2	67	1.28	.004	2	289	3.73	107	.02	4	3.82	.04	.02	1	1

0.017oz/ton
1.31 feet