

ECO-TECH LABORATORIES LTD.

ASSAYING - ENVIRONMENTAL TESTING

10041 East Trans Canada Hwy., Kamloops, B.C. V2C 2J5 (604) 573-5700 Fax 573-4557

CAM

001277

Placer Dome Inc.

OCTOBER 27, 1989

ET#	Description	Au (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	Mo (ppm)	As (ppm)
PROJECT IP - CAM (9607)								
813 - 70	8555	5	.1	12	8	37	<1	5
813 - 71	8556	10	<.1	17	13	104	4	5
813 - 72	8557	20	<.1	18	15	48	2	9
813 - 73	8558	10	<.1	13	13	57	2	6
813 - 74	8559	10	<.1	23	12	42	<1	11
813 - 75	8560	20	<.1	35	16	55	2	5
813 - 76	8561	25	<.1	17	18	64	1	9
813 - 77	8562	15	.1	25	20	80	2	14
813 - 78	8563	25	<.1	17	19	58	<1	7
813 - 79	8564	15	<.1	17	20	86	<1	11
813 - 80	8565	20	<.1	16	22	61	<1	11
813 - 81	8566	15	<.1	14	19	83	<1	7
813 - 82	8567	40	<.1	12	15	51	<1	4
813 - 83	8568	25	<.1	20	18	83	<1	8
813 - 84	8569	5	<.1	9	13	44	<1	4
813 - 85	8570	20	<.1	16	29	79	<1	10
813 - 86	8571	15	<.1	22	14	73	<1	5
813 - 87	8572	10	.1	14	24	85	2	7
813 - 88	8573	10	<.1	20	14	93	6	6
813 - 89	8574	25	<.1	19	15	52	3	8
813 - 90	8575	10	<.1	12	12	43	5	5
813 - 91	8576	15	<.1	15	20	60	1	7
813 - 92	8577	5	<.1	4	10	30	<1	4
813 - 93	8578	25	.1	23	23	91	2	11
813 - 94	8579	5	.1	26	31	90	2	12
813 - 95	8580	10	<.1	13	22	57	1	11
813 - 96	8581	15	<.1	30	39	89	1	15
813 - 97	8582	10	.1	11	21	48	<1	11
813 - 98	8583	5	.2	16	28	73	3	12
813 - 99	8586	15	.1	21	27	122	2	8
813 - 100	8587	5	.2	12	19	44	<1	4

PROJECT IP - ARMITAGE (9585)

813 - 101	1481	5	.1	15	11	57	<1	5
-----------	------	---	----	----	----	----	----	---


Frank Pezzotti
 ECO-TECH LABORATORIES LTD.
 FRANK PEZZOTTI, A.Sc.T.
 B.C. Certified Assayer

F A X - BOB MOWER @ VCR .
 SCB9/PLACER9

ECO-TECH KAMLOOPS

18.30.1989 17:37

P. 3



ECO-TECH LABORATORIES LTD.

ASSAYING - ENVIRONMENTAL TESTING

10041 East Trans Canada Hwy., Kamloops, B.C. V2C 2J8 (604) 573-5700 Fax 573-4557

OCTOBER 30, 1989

CERTIFICATE OF ANALYSIS ETK 89-817


Placer Dome Inc.
401, 1450 Pearson Place
KAMLOOPS, B.C.
VIS 1J9

DATE RECEIVED:	OCTOBER 23, 1989	REJECTS:	STORE
PROJECT:	IP - COOPER/CAM	PULPS:	STORE
LAB NUMBER:	9411/9412	NOTE:	> = MORE THAN
NUMBER SAMPLES:	16		** = INSUFFICIENT SAMPLE
TYPE SAMPLES:	BULK		

ET#	Description	Au (ppb)	Au (ppb)	Au (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	Mo (ppm)	As (ppm)
PROJECT COOPER LAB# 9411										
817 - 1	8976	35	20	400	.6	24	54	117	<1	26
817 - 2	8977	15	5	290	.4	16	25	76	3	15
817 - 3	8978	145	5	25	.6	19	45	103	4	20
817 - 4	8979	5	10	10	.2	12	44	97	5	8
817 - 5	8980	150	25	25	<.1	21	35	91	3	26
817 - 6	8981	10	15	20	.1	18	38	92	5	15
817 - 7	8982	5	5	670	<.1	16	27	76	<1	17
817 - 8	8983	5	5	5	<.1	25	41	101	3	18
817 - 9	8984	10	5	5	<.1	16	27	63	2	12
817 - 15	9032	135	165	410	<.1	116	33	82	3	15
817 - 16	9033	255	490	620	<.1	67	34	104	6	14
PROJECT CAM LAB# 9412										
817 - 10	8997	290	10	10	.1	14	17	52	6	7
817 - 11	8998	10	20	10	<.1	15	15	51	6	17
817 - 12	8999	10	**	**	<.1	10	10	41	4	7
817 - 13	9000	5	10	10	<.1	25	14	41	5	10
817 - 14	9022	15	10	10	<.1	12	11	40	2	8

Frank J. Pezzotti
ECO-TECH LABORATORIES LTD.
FRANK J. PEZZOTTI, A.Sc.T.
B.C. Certified Assayer

FAX - BOB MOWER @ VCR




ECO-TECH LABORATORIES LTD.

ASSAYING - ENVIRONMENTAL TESTING
 10041 East Trans Canada Hwy., Kamloops, B.C. V2C 2J3 (604) 573-5700 Fax 573-4557

Placer Dome Inc.

OCTOBER 27, 1989

ET#	Description	Al (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	Mo (ppm)	As (ppm)
PROJECT IP - COOPER (9410)								
813 - 29	8510	<5	<.1	12	29	58	3	20
813 - 30	8511	<5	<.1	61	27	70	1	15
813 - 31	8512	10	.2	18	36	76	1	18
813 - 32	8513	5	.1	16	26	49	<1	15
813 - 33	8514	10	.3	11	31	33	<1	7
813 - 34	8515	10	.1	15	22	79	<1	12
813 - 35	8516	15	2	16	25	57	<1	18
PROJECT IP - CAM (9607)								
813 - 36	8521	25	.1	17	28	75	<1	13
813 - 37	8522	<5	.2	15	43	56	1	17
813 - 38	8523	10	.1	12	19	49	<1	10
813 - 39	8524	15	<.1	14	20	74	2	11
813 - 40	8525	25	<.1	24	9	52	<1	6
813 - 41	8526	30	.2	23	26	54	2	14
813 - 42	8527	15	<.1	10	12	31	5	5
813 - 43	8528	10	<.1	15	9	37	2	5
813 - 44	8529	<5	<.1	10	5	24	2	4
813 - 45	8530	25	<.1	13	15	30	1	5
813 - 46	8531	15	<.1	11	10	37	1	4
813 - 47	8532	30	.1	14	20	56	3	8
813 - 48	8533	5	<.1	12	18	43	5	10
813 - 49	8534	5	.1	16	17	59	<1	7
813 - 50	8535	10	.1	12	14	34	<1	4
813 - 51	8536	25	<.1	11	8	32	<1	3
813 - 52	8537	10	<.1	13	17	59	<1	5
813 - 53	8538	10	<.1	12	10	35	2	4
813 - 54	8539	5	<.1	13	13	45	3	5
813 - 55	8540	10	.1	13	14	53	<1	6
813 - 56	8541	10	<.1	18	22	91	<1	14
813 - 57	8542	25	<.1	10	11	39	<1	7
813 - 58	8543	<5	<.1	13	10	44	1	5
813 - 59	8544	<5	.1	14	11	51	1	4
813 - 60	8545	10	<.1	7	7	35	2	5
813 - 61	8546	10	<.1	11	11	66	<1	4
813 - 62	8547	20	<.1	10	7	35	<1	5
813 - 63	8548	15	.1	18	20	53	2	6
813 - 64	8549	15	<.1	9	10	39	2	5
813 - 65	8550	20	.2	19	14	52	3	6
813 - 66	8551	10	<.1	10	10	34	<1	5
813 - 67	8552	5	<.1	17	13	88	1	6
813 - 68	8553	15	<.1	15	15	58	<1	7
813 - 69	8554	20	<.1	13	14	64	<1	5



ECO-TECH LABORATORIES LTD.

ASSAYING - ENVIRONMENTAL TESTING

10041 East Trans Canada Hwy., Kamloops, B.C. V2C 2J3 (604) 573-5700 Fax 573-4557

Placer Dome Inc.

OCTOBER 27, 1989

ET#	Description	Au (ppb)	Ag (ppm)	Cu. (ppm)	Pb (ppm)	Zn (ppm)	Mo (ppm)	As (ppm)
PROJECT IP - CAM (9607)								
813 - 70	8555	5	.1	12	8	37	<1	5
813 - 71	8556	10	<.1	17	13	104	4	5
813 - 72	8557	20	<.1	18	15	48	2	9
813 - 73	8558	10	<.1	13	13	57	2	6
813 - 74	8559	10	<.1	23	12	42	<1	11
813 - 75	8560	20	<.1	35	16	55	2	5
813 - 76	8561	25	<.1	17	18	64	1	9
813 - 77	8562	15	.1	25	20	80	2	14
813 - 78	8563	25	<.1	17	19	58	<1	7
813 - 79	8564	15	<.1	17	20	86	<1	11
813 - 80	8565	20	<.1	16	22	61	<1	11
813 - 81	8566	15	<.1	14	19	83	<1	7
813 - 82	8567	40	<.1	12	15	51	<1	4
813 - 83	8568	25	<.1	20	18	83	<1	8
813 - 84	8569	5	<.1	9	13	44	<1	4
813 - 85	8570	20	<.1	16	29	79	<1	10
813 - 86	8571	15	<.1	22	14	73	<1	5
813 - 87	8572	10	.1	14	24	85	2	7
813 - 88	8573	10	<.1	20	14	93	6	6
813 - 89	8574	25	<.1	19	15	52	3	8
813 - 90	8575	10	<.1	12	12	43	5	5
813 - 91	8576	15	<.1	15	20	60	1	7
813 - 92	8577	5	<.1	4	10	30	<1	4
813 - 93	8578	25	.1	23	23	91	2	11
813 - 94	8579	5	.1	26	31	90	2	12
813 - 95	8580	10	<.1	13	22	57	1	11
813 - 96	8581	15	<.1	30	39	89	1	15
813 - 97	8582	10	.1	11	21	48	<1	11
813 - 98	8583	5	.2	16	28	73	3	12
813 - 99	8586	15	.1	21	27	122	2	8
813 - 100	8587	5	.2	12	19	44	<1	4

PROJECT IP - ARMITAGE (9585)

813 - 101	1481	5	.1	15	11	57	<1	5
-----------	------	---	----	----	----	----	----	---

Frank Pezzotti
 ECO-TECH LABORATORIES LTD.
 FRANK PEZZOTTI, A.Sc.T.
 B.C. Certified Assayer

PDI lab data file: P9412
 AREA: CAM
 MAPSHEET NO: 82F8
 VENTURE: BC GEN 1P
 GEOLOGIST: M GAREAU
 LAB PROJECT NO: 9412

PLEASE DISTRIBUTE RESULTS TO: MG LR EK RH LAB

REMARKS:
 "AU WILL BE ANALYZED 3 TIMES IN PPB"

STANDARD ANALYSIS METHODS USED BY PDL GEOCHEM LAB ARE LISTED BELOW:
 ALL RESULTS EXPRESSED AS INDICATED IN UNITS COLUMN BELOW
 ANY EXCEPTIONS FOR THIS PROJECT ARE NOTED ABOVE

REMARKS: INTERNAL LAB STANDARDS HAVE BEEN INCLUDED FOR REFERENCE.
 SAMPLE NUMBERS FOLLOWED BY * ARE DUPLICATE ANALYSES.

	UNITS	WT.G	ATTACK USED	TIME	RANGE	METHOD
AG	PPM	0.5	HClO ₄ /HNO ₃	4HRS	0.2-20	A.A. BACKGROUND COR
AS	PPM	0.5	AQUA REGIA	3HRS	2-2000	DC PLASMA
AU1	PPB	10.0	AQUA REGIA	3HRS	5-4000	A.A. SOLVENT EXTRACT.
CU	PPM	0.5	HClO ₄ /HNO ₃	4HRS	2-4000	ATOMIC ABSORPTION
MO	PPM	0.5	HClO ₄ /HNO ₃	4HRS	1-1000	ATOMIC ABSORPTION
PB	PPM	0.5	HClO ₄ /HNO ₃	4HRS	2-3000	A.A. BACKGROUND COR.
ZN	PPM	0.5	HClO ₄ /HNO ₃	4HRS	2-3000	ATOMIC ABSORPTION

GRID	SAMPLE	PROJECT	Ag PPM	As PPM	Au1 PPB	Au-A PPB	Au-B PPB	Cu PPM	Mo PPM	Pb PPM	Zn PPM
82F8		A8997 9412	.1	7	290	10	10	14	6	17	52
82F8		A8998 9412	<.1	17	10	20	10	15	6	15	51
82F8		A8999 9412	<.1	7	10	NSS	NSS	10	4	10	41
82F8		A9000 9412	<.1	10	5	10	10	25	5	14	41
82F8		A9027 9412	<.1	8	15	10	10	12	2	11	40
82F8		A9027* 9412									

END OF LISTING - 6 RECORDS PRINTED Run on: 89:11:01 at 10:42:05

PLACER DOME INC: GEOCHEM ASSAY SYSTEM

Following elements needed some values adjusted:

ELEMENT	NSS	LOW	HI	%	BLNK	NVAL
AG	0	4	0	0	0	5
AU-A	1	0	0	0	0	4
AU-B	1	0	0	0	0	4

1 records skipped: tests, duplicate analyses

SUMMARY OF GEOCHEM DATA: BC GEN 1P CAM

ITEM	# VALUES	MISSING	MINIMUM	MAXIMUM	AVERAGE	STD. DEV.
GRID	5	0	82F8	82F8		
SAMP	0	5				
PROJ	5	0	9412	9412		
AG	5	0	0.05	0.10	0.06	0.02
AS	5	0	7.00	17.00	9.80	4.21
AU-A	4	1	10.00	20.00	12.50	5.00
AU-B	4	1	10.00	10.00	10.00	0.00
AU1	5	0	5.00	290.00	66.00	125.27
CU	5	0	10.00	25.00	15.20	5.81
MO	5	0	2.00	6.00	4.60	1.67
PB	5	0	10.00	17.00	13.40	2.88
ZN	5	0	40.00	52.00	45.00	5.96

END OF SCAN: DATE: 89:11:01 time: 10:42:05 5 RECORDS PROCESSED

PDI lab data file: P9607
 AREA: CAM
 MAPSHEET NO: 82F8
 VENTURE: BC GEN 1P
 GEOLOGIST: M GAREAU
 LAB PROJECT NO: 9607

PLEASE DISTRIBUTE RESULTS TO: MG LR EK RH LAB

STANDARD ANALYSIS METHODS USED BY PDL GEOCHEM LAB ARE LISTED BELOW:
 ALL RESULTS EXPRESSED AS INDICATED IN UNITS COLUMN BELOW
 ANY EXCEPTIONS FOR THIS PROJECT ARE NOTED ABOVE

REMARKS: INTERNAL LAB STANDARDS HAVE BEEN INCLUDED FOR REFERENCE.
 SAMPLE NUMBERS FOLLOWED BY * ARE DUPLICATE ANALYSES.

	UNITS	WT.G	ATTACK USED	TIME	RANGE	METHOD
AG	PPM	0.5	HClO ₄ /HNO ₃	4HRS	0.2-20	A.A. BACKGROUND COR
AS	PPM	0.5	AQUA REGIA	3HRS	2-2000	DC PLASMA
AU1	PPB	10.0	AQUA REGIA	3HRS	5-4000	A.A. SOLVENT EXTRACT.
CU	PPM	0.5	HClO ₄ /HNO ₃	4HRS	2-4000	ATOMIC ABSORPTION
MO	PPM	0.5	HClO ₄ /HNO ₃	4HRS	1-1000	ATOMIC ABSORPTION
PB	PPM	0.5	HClO ₄ /HNO ₃	4HRS	2-3000	A.A. BACKGROUND COR.
ZN	PPM	0.5	HClO ₄ /HNO ₃	4HRS	2-3000	ATOMIC ABSORPTION

GRID	SAMPLE	PROJECT	Ag PPM	As PPM	Au1 PPB	Cu PPM	Mo PPM	Pb PPM	Zn PPM
82F8	A8525	9607	<.1	6	25	24	<1	9	52
82F8	A8526	9607	.2	14	30	23	2	26	54
82F8	A8527	9607	<.1	5	15	10	5	12	31
82F8	A8528	9607	<.1	5	10	15	2	9	37
82F8	A8529	9607	<.1	4	<5	10	2	5	24
82F8	A8530	9607	<.1	5	25	13	1	15	30
82F8	A8531	9607	<.1	4	15	11	1	10	37
82F8	A8532	9607	.1	8	30	14	3	20	56
82F8	A8533	9607	<.1	10	5	12	5	18	43
82F8	A8533*	9607							
82F8	A8534	9607	.1	7	5	16	<1	17	59
82F8	A8535	9607	.1	4	10	12	<1	14	34
82F8	A8536	9607	<.1	3	25	11	<1	8	32
82F8	A8537	9607	<.1	5	10	13	<1	17	59
82F8	A8538	9607	<.1	4	10	12	2	10	35
82F8	A8539	9607	<.1	5	5	13	3	13	45
82F8	A8540	9607	.1	6	10	13	<1	14	53
82F8	A8541	9607	<.1	14	10	18	<1	22	91
82F8	A8542	9607	<.1	7	25	10	<1	11	39
82F8	A8542*	9607							
82F8	A8543	9607	<.1	5	<5	13	1	10	44
82F8	A8544	9607	.1	4	<2	14	1	11	51
82F8	A8545	9607	<.1	5	10	7	2	7	35
82F8	A8546	9607	<.1	4	10	11	<1	11	66
82F8	A8547	9607	<.1	5	20	10	<1	7	35
82F8	A8548	9607	.1	6	15	18	2	20	53
82F8	A8549	9607	<.1	5	15	9	2	10	39
82F8	A8550	9607	.2	6	20	19	3	14	52
82F8	A8551	9607	<.1	5	10	10	<1	10	34
82F8	A8551*	9607							
82F8	A8552	9607	<.1	6	5	17	1	13	88
82F8	A8553	9607	<.1	7	15	15	<1	15	58
82F8	A8554	9607	<.1	5	20	13	<1	14	64
82F8	A8555	9607	.1	5	5	12	<1	8	37
82F8	A8556	9607	<.1	5	10	17	4	13	104
82F8	A8557	9607	<.1	9	20	18	2	15	48
82F8	A8558	9607	<.1	6	10	13	2	13	57
82F8	A8559	9607	<.1	11	10	23	<1	12	42
82F8	A8560	9607	<.1	5	20	35	2	16	55
82F8	A8560*	9607							
82F8	A8561	9607	<.1	9	25	17	1	18	64
82F8	A8562	9607	.1	14	15	25	2	20	80
82F8	A8563	9607	<.1	7	25	17	<1	19	58
82F8	A8564	9607	<.1	11	15	17	<1	20	86
82F8	A8565	9607	<.1	11	20	16	<1	22	61
82F8	A8566	9607	<.1	7	15	14	<1	19	83
82F8	A8567	9607	<.1	4	40	12	<1	15	51
82F8	A8568	9607	<.1	8	25	20	<1	18	83
82F8	A8569	9607	<.1	4	5	9	<1	13	44
82F8	A8569*	9607							
82F8	A8570	9607	<.1	10	20	16	<1	29	79
82F8	A8571	9607	<.1	5	15	22	<1	14	73
82F8	A8572	9607	.1	7	10	14	2	24	85
82F8	A8573	9607	<.1	6	10	20	6	14	93
82F8	A8574	9607	<.1	8	25	19	3	15	52
82F8	A8575	9607	<.1	5	10	12	5	12	43
82F8	A8576	9607	<.1	7	15	15	1	20	60

GRID	SAMPLE	PROJECT	Ag PPM	As PPM	Au1 PPB	Cu PPM	Mo PPM	Pb PPM	Zn PPM
82F8	A8577	9607	<.1	4	5	4	<1	10	30
82F8	A8578	9607	.1	11	25	23	2	23	91
82F8	A8578*	9607							
82F8	A8579	9607	.1	12	5	26	2	31	90
82F8	A8580	9607	<.1	11	10	13	1	22	57
82F8	A8581	9607	<.1	15	15	30	1	39	89
82F8	A8582	9607	.1	11	10	11	<1	21	48
82F8	A8583	9607	.2	12	5	16	3	28	73
82F8	A8586	9607	.1	8	15	21	2	27	122
82F8	A8587	9607	.2	4	5	12	<1	19	44
82F8	A8587*	9607							

END OF LISTING - 68 RECORDS PRINTED Run on: 89:11:01 at 10:42:05

PLACER DOME INC: GEOCHEM ASSAY SYSTEM

Following elements needed some values adjusted:


ELEMENT	NSS	LOW	HI	%	BLNK	NVAL
AG	0	44	0	0	0	61
AU1	0	3	0	0	0	61
MO	0	27	0	0	0	61

7 records skipped: tests, duplicate analyses

SUMMARY OF GEOCHEM DATA: BC GEN 1P CAM

ITEM	# VALUES	MISSING	MINIMUM	MAXIMUM	AVERAGE	STD. DEV.
GRID	61	0	82F8	82F8		
SAMP	0	61				
PROJ	61	0	9607	9607		
AG	61	0	0.05	0.20	0.07	0.04
AS	61	0	3.00	15.00	7.07	3.07
AU1	61	0	1.00	40.00	14.28	8.22
CU	61	0	4.00	35.00	15.49	5.58
MO	61	0	0.50	6.00	1.52	1.34
PB	61	0	5.00	39.00	16.08	6.55
ZN	61	0	24.00	122.00	57.57	21.46

END OF SCAN: DATE: 89:11:01 time: 10:42:05 61 RECORDS PROCESSED



ECO-TECH LABORATORIES LTD.

ASSAYING • ENVIRONMENTAL TESTING
10041 East Trans Canada Hwy., Kamloops, B.C. V2C 2J3 (804) 673-5700 Fax 673-4557

DATE: Nov. 2/89


TO: MICHAEL GAREAU

FROM: JACKIE BLACK

NO. OF PAGES: ~~2~~ 3 (including this page)

MESSAGE:

Prop IP - CAN (9608)



ECO-TECH LABORATORIES LTD.

ASSAYING - ENVIRONMENTAL TESTING

10041 East Trans Canada Hwy., Kamloops, B.C. V2C 2J3 (604) 573-5700 Fax 573-4557

I N V O I C E

DATE: NOVEMBER 3, 1989

LACER DOME INC.
 .O. BOX 49330, BENTALL POSTAL STATION
 600, 1055 DUNSMUIR STREET
 ANCOUVER, B.C.
 7X 1P1
 TTENTION: MICHAEL GAREAU

INVOICE #: ETK 89-839

=====

A N A L Y S E S	P R I C E / S A M P L E	A M O U N T
-----------------	-------------------------	-------------

=====

PROJECT: IP - CAM (9608)
 =====


ULPS

14	AU GEOCHEM	6.75	94.50
14	SETS AG/PB/CU/ZN/MO GEOCHEM	6.00	84.00
14	AS GEOCHEM	4.00	56.00

SUB-TOTAL:	234.50
LESS 10% DISCOUNT:	23.45

TOTAL DUE & PAYABLE UPON RECEIPT:	211.05
-----------------------------------	--------

TERMS: NET 30 DAYS. INTEREST AT RATE OF 1-1/2% PER MONTH (18% PER ANNUM)
 WILL BE CHARGED ON OVERDUE ACCOUNTS.

**ECO-TECH LABORATORIES LTD.**

ASSAYING - ENVIRONMENTAL TESTING

10041 East Trans Canada Hwy., Kamloops, B.C. V2C 2J3 (804) 573-5700 Fax 573-4667

NOVEMBER 2, 1989

 =====
 CERTIFICATE OF ANALYSIS ETK 89-839
 =====


PLACER DONE INC.
 P.O. BOX 49330, BENTALL POSTAL STATION
 1600, 1055 DUNSMUIR STREET
 VANCOUVER, B.C. V7X 1P1
 ATTENTION: MICHAEL GAREAU

=====

DATE RECEIVED:	OCTOBER 25, 1989	REJECTS:	N/A
PROJECT:	IP - CAM (4608)	PULPS:	STORE
NUMBER SAMPLES:	13		
TYPE SAMPLES:	SOIL (PULPS)	NOTE:	< = LESS THAN

=====

ET#	Description	Au (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	As (ppm)	Mo (ppm)
839 - 1	A 8780	5	<.1	7	18	67	12	<1
839 - 2	A 8781	10	<.1	7	16	58	10	<1
839 - 3	A 8782	15	<.1	8	12	69	6	<1
839 - 4	A 8783	10	<.1	11	15	48	8	<1
839 - 5	A 8784	5	<.1	15	12	54	8	<1
839 - 6	A 8785	<5	<.1	22	20	68	9	<1
839 - 7	A 8786	10	<.1	11	15	46	9	<1
839 - 8	A 8787	10	<.1	18	16	48	11	<1
839 - 9	A 8788	<5	<.1	21	12	33	6	<1
839 - 10	A 8789	10	<.1	13	9	11	6	<1
839 - 11	A 8790	15	<.1	22	8	32	8	<1
839 - 12	A 8791	10	<.1	21	12	31	10	<1
839 - 13	A 8973	20	<.1	16	17	80	8	<1
839 - 14	Z UNDETERMINED	<5	<.1	15	21	57	19	<1



 ECO-TECH LABORATORIES LTD.
 Frank J. Pezzotti, A.Sc.I.
 B.C. Certified Assayer

FAX - MICHAEL GAREAU @ VCR
 cc: GAIL MARKLE
 SC89/PLACER10

P L A C E R D O M E I N C (V A N C O U V E R L A B O R A T O R Y)

GEOCHEMICAL DATA LISTING: BC GEN 1P CAM

DATE: 89:09:08

PDI lab data file: P9406
 AREA: CAM
 MAPSHEET NO: 82F8
 VENTURE: BC GEN 1P
 GEOLOGIST: M GAREAU
 LAB PROJECT NO: 9406

PLEASE DISTRIBUTE RESULTS TO: M GAREAU
 B. HODGSON M. GAREAU E. KIMURA L. REINERTSON

STANDARD ANALYSIS METHODS USED BY PDL GEOCHEM LAB ARE LISTED BELOW:
 ALL RESULTS EXPRESSED AS INDICATED IN UNITS COLUMN BELOW
 ANY EXCEPTIONS FOR THIS PROJECT ARE NOTED ABOVE

REMARKS: INTERNAL LAB STANDARDS HAVE BEEN INCLUDED FOR REFERENCE.
 SAMPLE NUMBERS FOLLOWED BY * ARE DUPLICATE ANALYSES.

	UNITS	WT.G	ATTACK USED	TIME	RANGE	METHOD
AG	PPM	0.5	HCL04/HNO3	4HRS	0.2-20	A.A. BACKGROUND COR
AS	PPM	0.5	AQUA REGIA	3HRS	2-2000	DC PLASMA
AU1	PPB	10.0	AQUA REGIA	3HRS	5-4000	A.A. SOLVENT EXTRACT.
CU	PPM	0.5	HCL04/HNO3	4HRS	2-4000	ATOMIC ABSORPTION
MO	PPM	0.5	HCL04/HNO3	4HRS	1-1000	ATOMIC ABSORPTION
PB	PPM	0.5	HCL04/HNO3	4HRS	2-3000	A.A. BACKGROUND COR.
ZN	PPM	0.5	HCL04/HNO3	4HRS	2-3000	ATOMIC ABSORPTION

GRID	SAMPLE	PROJECT	Aq PPM	As PPM	Au1 PPB	Cu PPM	Mo PPM	Pb PPM	Zn PPM
82F8	A	9026 9406	<0.2	20	<5	8	6	2	2
82F8	A	9028 9406	<0.2	16	<5	2	1	<2	3
82F8	A	9028* 9406	<0.2		<5	2	1	<2	3

END OF LISTING - 3 RECORDS PRINTED Run on: 89:09:08 at 16:51:26