

861477
Platinum Blonde

```
X      X      RRRRR      A      LL
XX     XX     RR  RR     AAA     LL
  XX  XX     RR  RR     AA  AA     LL
    XXX     RR  RR     AA  AA     LL
    XXX     RRRRR     AAAAAAA     LL
  XX  XX     RR  RR     AA  AA     LL
XX     XX     RR  RR     AA  AA     LLLLLLL
X      X      RR      R     AA  AA     LLLLLLL
```

XRF - WHOLE ROCK ANALYSIS

PLACER DEVELOPMENT LIMITED
Attn: NORM GANGNES
RESEARCH CENTRE
323 ALEXANDER STREET
VANCOUVER, BRITISH COLUMBIA V6A 1C4

CUSTOMER No. 898

DATE SUBMITTED
3-MAR-87

REPORT 31586

REF. FILE 27068

06-APR-87

XRF W. R. A. SUMS INCLUDE ALL ELEMENTS DETERMINED.
FOR SUMMATION ELEMENTS ARE CALCULATED AS OXIDES.

SAMPLE	SI02	AL2O3	CAO	MGO	NA2O	K2O	FE2O3	MNO	TIO2	P2O5	LOI	SUM
16350	47.7	16.2	6.88	4.02	3.40	3.01	9.32	0.15	0.71	0.32	6.70	98.7
16358	50.7	14.1	7.37	2.28	2.53	6.26	9.08	0.19	1.04	0.41	4.31	98.9
16386	52.6	17.5	6.04	1.65	3.72	5.39	7.09	0.14	0.59	0.29	3.23	98.7
26561	49.8	12.0	10.9	3.99	2.27	4.39	11.5	0.26	0.86	0.39	2.23	99.0
16391	47.4	11.9	9.10	2.60	1.70	5.30	11.4	0.23	1.31	0.50	6.70	98.8
16277	48.1	15.6	6.39	4.55	2.80	2.29	11.6	0.23	0.91	0.29	6.00	99.0
16285	43.9	9.83	10.5	3.99	1.60	3.62	12.5	0.31	1.19	0.61	6.70	95.1
26628	40.6	10.2	10.7	4.87	1.06	3.41	13.8	0.31	1.18	0.59	7.77	94.9
16737	53.4	15.3	3.30	1.21	2.03	8.24	7.79	0.19	0.80	0.32	5.47	98.5
16741	55.4	16.3	4.00	1.02	2.92	8.05	5.48	0.14	0.66	0.25	4.62	99.3
16742	51.7	17.0	5.82	2.58	5.07	2.96	7.12	0.18	0.58	0.35	5.00	98.7
16747	52.8	14.9	5.39	1.55	2.08	8.28	7.43	0.16	0.84	0.32	4.00	98.3
15564	52.6	15.8	4.01	0.89	2.08	8.43	8.06	0.18	0.90	0.37	4.85	98.7
15585	54.1	17.1	3.49	0.60	2.10	9.15	6.50	0.13	0.71	0.24	4.62	99.2
16294	51.8	15.0	5.93	1.91	2.59	7.28	7.74	0.18	0.80	0.33	4.31	98.4
16318	53.9	15.6	5.10	1.59	3.11	7.62	7.04	0.15	0.76	0.30	3.00	98.7
26646	50.1	15.8	12.5	3.66	3.42	1.90	7.21	0.23	0.73	0.31	2.23	98.3
16436	53.7	15.4	4.39	1.26	2.13	8.32	6.91	0.14	0.82	0.32	5.08	99.0
16448	53.7	15.9	4.38	0.99	2.57	8.27	6.77	0.14	0.76	0.28	4.00	98.2
16453	53.1	17.1	6.67	3.23	6.21	1.26	5.17	0.08	0.77	0.27	5.23	99.2
26555	59.7	16.7	0.52	1.30	3.73	6.87	5.79	0.05	0.69	0.20	2.47	98.3
26557	47.8	13.4	10.1	3.27	1.80	4.74	7.05	0.18	0.52	0.33	9.39	98.8
9415	49.3	16.5	6.70	3.87	3.50	2.48	7.55	0.17	0.67	0.24	7.62	98.8
26813	40.5	7.66	15.0	6.71	1.85	1.55	20.7	0.36	1.14	0.92	2.77	99.3
26817	52.0	14.5	7.26	2.38	2.64	6.68	8.67	0.21	1.07	0.41	2.85	99.2
15360	39.1	7.86	14.1	9.14	1.11	2.26	18.6	0.32	1.30	1.03	3.23	98.2
26822	46.7	10.2	14.1	4.84	2.39	2.96	12.6	0.34	0.71	1.04	2.54	98.6

SAMPLE	SI02	AL2O3	CAO	MGO	NA2O	K2O	FE2O3	MNO	TI02	P2O5	LOI	SUM
15365	54.6	16.4	5.10	1.27	3.17	7.74	5.89	0.15	0.70	0.25	2.77	98.6
15248	46.7	10.4	12.2	4.29	2.19	3.79	15.2	0.34	1.09	0.81	1.08	98.3
15252	53.7	14.4	6.44	2.10	1.85	8.38	8.43	0.17	0.93	0.39	1.54	99.1
15262	51.1	13.2	8.02	2.71	2.04	6.72	10.4	0.21	1.07	0.50	1.70	98.4
15270	43.8	9.79	11.7	9.26	1.50	3.76	14.0	0.28	0.97	0.75	2.62	98.6
15273	52.6	15.5	5.99	3.82	3.00	6.43	7.37	0.16	0.60	0.34	2.31	98.4
16365	56.0	16.5	4.39	0.83	4.04	6.97	5.59	0.18	0.53	0.13	3.47	98.9
16373	43.9	12.0	11.0	8.35	2.13	3.35	14.0	0.25	0.91	0.68	2.77	99.6
16382	52.2	15.2	6.25	2.52	3.15	6.24	8.79	0.20	0.88	0.39	2.54	98.8
16236	63.6	15.2	3.52	1.25	3.80	3.36	3.21	0.08	0.42	0.17	4.00	98.9
16241	52.0	15.2	6.74	1.62	3.42	5.98	8.51	0.25	0.96	0.28	3.16	98.5
15588	48.0	15.0	8.73	5.81	3.13	3.69	10.2	0.20	0.63	0.50	2.62	98.8
15592	58.1	17.7	3.22	0.76	4.70	7.29	3.53	0.12	0.40	0.10	2.93	99.2
9416	58.9	17.9	2.09	0.85	4.45	7.60	3.79	0.10	0.42	0.11	2.54	99.1
9420	43.8	10.5	10.8	3.44	1.71	4.44	13.4	0.26	1.22	0.70	5.62	96.4
9422	54.9	15.9	5.32	1.39	3.70	6.67	5.80	0.15	0.68	0.27	3.62	98.8
15235	49.9	13.4	6.97	2.70	1.52	6.89	9.37	0.20	0.94	0.44	6.23	99.0
15454	48.3	13.9	7.71	6.03	3.00	3.89	8.88	0.17	0.55	0.45	5.16	98.3
15445	35.8	4.52	17.8	6.70	0.57	0.18	25.8	0.44	1.58	1.46	4.70	99.7
9411	40.2	11.3	13.7	9.47	1.13	2.33	13.6	0.22	0.81	0.69	4.85	98.5
15244	48.9	12.2	8.40	1.81	2.61	4.71	11.0	0.27	1.26	0.33	7.23	99.0
15467	42.4	15.0	12.0	7.33	1.66	2.48	14.2	0.23	0.88	0.79	2.00	99.3
15470	38.8	8.98	13.7	9.53	1.21	2.33	19.6	0.33	1.21	1.17	1.70	98.7
15479	38.0	6.03	15.2	9.47	0.67	1.75	21.1	0.37	1.51	1.46	3.16	98.9
15484	37.8	4.39	17.7	6.99	0.97	0.45	23.3	0.43	1.41	1.43	4.08	99.0
15489	60.5	14.1	5.33	1.54	3.34	3.24	4.78	0.11	0.54	0.31	5.00	99.1
15497	53.1	14.9	5.69	1.57	2.22	7.73	6.96	0.17	0.77	0.31	4.70	98.7

SAMPLE	SI02	AL2O3	CAO	MGO	NA2O	K2O	FE2O3	MNO	TIO2	P2O5	LOI	SUM
16326	41.0	6.05	17.4	6.51	0.97	1.49	20.7	0.40	1.62	1.23	1.31	98.8
16336	40.0	4.34	19.3	7.49	0.98	0.26	23.3	0.44	1.57	1.30	0.77	99.8
16343	37.6	5.73	17.8	5.98	1.70	0.81	20.5	0.46	1.23	1.28	5.85	99.0
15500	63.7	15.6	3.81	1.54	3.16	3.30	3.71	0.08	0.52	0.21	4.31	100.2
15502	38.0	6.59	16.7	7.97	0.94	1.32	20.8	0.39	1.31	1.18	3.39	98.8
15514	63.2	15.1	4.26	1.35	3.60	3.34	3.52	0.09	0.48	0.21	4.62	100.1
15523	38.8	3.90	19.3	8.31	0.84	0.29	22.6	0.39	1.36	1.75	1.70	99.3
16242	38.6	8.86	14.1	3.38	1.13	1.66	16.0	0.45	2.13	0.86	12.8	100.2
16253	58.6	16.3	1.99	0.75	2.72	7.77	7.25	0.11	0.81	0.35	2.16	99.2
16270	54.6	15.1	5.03	1.19	2.59	7.05	7.27	0.18	0.79	0.37	5.23	99.9

SAMPLE	CR	RB	SR	Y	ZR	NB	BA
16350	80	<10	920	<10	100	10	1690
16358	80	120	2330	30	60	20	3090
16386	50	100	1830	10	20	10	1790
26561	100	70	1190	30	60	10	2050
16391	50	80	2220	20	30	30	3270
16277	50	80	700	20	10	20	760
16285	80	80	1110	30	80	40	1620
26628	100	<10	1440	10	70	30	2000
16737	50	150	1850	10	60	40	1860
16741	40	130	2010	20	40	20	2090
16742	40	70	1240	20	30	20	1150
16747	50	120	2550	20	<10	30	2220
15564	90	160	2270	10	50	40	2080
15585	60	170	1820	30	30	30	1950
16294	60	130	2130	40	40	30	1850
16318	70	150	2170	10	70	20	1780
26646	60	40	900	10	20	20	810
16436	60	140	2200	10	20	10	2050
16448	50	160	1900	30	50	20	1770
16453	60	40	700	30	60	20	400
26555	130	<10	660	<10	40	10	1470
26557	160	<10	1000	<10	70	10	920
9415	60	90	760	<10	<10	20	840
26813	100	<10	430	<10	150	20	320
26817	50	50	1700	20	170	40	2160
15360	170	<10	520	<10	40	30	830
26822	130	<10	730	<10	110	20	720

SAMPLE	CR	RB	SR	Y	ZR	NB	BA
15365	60	90	2450	10	60	20	2210
15248	110	<10	700	10	130	30	530
15252	90	<10	3260	<10	10	20	3260
15262	100	50	2980	10	30	30	3470
15270	250	<10	490	<10	20	10	850
15273	140	50	1290	<10	100	20	1090
16365	60	<10	1340	20	150	20	1010
16373	200	20	820	<10	30	30	710
16382	90	<10	1580	<10	80	30	1810
16236	80	120	750	10	120	20	1340
16241	50	<10	1440	<10	140	50	1360
15588	170	30	1200	10	<10	10	1170
15592	60	140	1430	50	100	20	1180
9416	80	70	1360	10	120	20	1200
9420	60	<10	1580	<10	80	30	3100
9422	70	110	1580	10	100	20	1920
15235	70	40	2030	10	10	30	1880
15454	220	110	800	<10	20	30	800
15445	90	<10	430	40	130	20	150
9411	220	80	770	<10	<10	10	810
15244	80	90	760	90	240	50	590
15467	90	10	1480	<10	<10	10	790
15470	100	<10	440	<10	60	30	630
15479	120	<10	380	20	50	20	520
15484	120	<10	460	<10	110	20	60
15489	120	120	750	10	100	20	1280
15497	50	160	2360	20	40	30	2090

SAMPLE	CR	RB	SR	Y	ZR	NB	BA
16326	120	50	610	30	80	30	450
16336	80	20	320	10	120	10	20
16343	90	40	510	30	130	30	50
15500	110	110	770	10	120	50	1360
15502	100	50	480	10	80	20	710
15514	90	120	720	10	110	30	1490
15523	120	10	350	30	60	30	20
16242	50	40	820	60	280	70	200
16253	90	50	1440	<10	50	30	2000
16270	70	160	1770	30	80	20	1820